

# Calculated Sputtering, Reflection and Range Values

W. Eckstein

June 24, 2002

## **Abstract**

The Monte Carlo program TRIM.SP was applied to calculate sputtering yields, reflection coefficients and mean ranges. Tables of these values are produced in the energy range from 10 eV to 300 keV and for several angles of incidence. Li, Be, B, C, Mg, Al, Si, P, Ti, Fe, Ni, Cu, Ga, Ge, Nb, Mo, Ag, In, Cs, Sm, Ta, W, Pt, Au, Hg and U are chosen as one-component target materials, BeO, B<sub>4</sub>C, B<sub>2</sub>O<sub>3</sub>, B(OH)<sub>3</sub>, SiO<sub>2</sub>, TiC, WO<sub>3</sub>, WO<sub>4</sub>, W<sub>x</sub>O<sub>y</sub> as more component targets. Some examples for layered structures are also given.  $\mu$ , H, D, T, <sup>3</sup>He, <sup>4</sup>He, C, N, O, Ne, Na, Mg, Al, P, Ar, K, Kr, Xe, Hg, Bi and Rn are selected as projectiles. Selfbombardment and an incident Maxwellian distribution is regarded for some cases, too.

## 0.1 Introduction

This report gives a collection of sputtering, reflection and range values calculated in the last decade (approximately). It is also an extension of an earlier report [1]. Whereas [1] only data for Be, C, and W targets are presented, this report gives data for other targets, too. In contrast to [1], the data in this report are given in exponential form to present more accurate values at low ion energies. Calculated sputtering yields from an earlier report are also included [2].

## 0.2 The model

The vectorized version of TRIM.SP [3, 4] and different versions of it were applied. The basis is a randomized target structure and the binary collision approximation. In most cases the KrC potential [5] is applied as interaction potential, but some examples are calculated with the Moliere [6], ZBL [8] and a special potential for Si [9]. The integration for getting the scattering angle is usually performed with the procedure 'magic' [7], but in a few cases also with the Gauss-Mehler procedure [10, 2]. For the inelastic energy loss an equipartition of the Lindhard-Scharff (LS) [11] and the Oen-Robinson (OR) [12] models is chosen mostly, but at high energies the Andersen-Ziegler (AZ) tables for H [13] and the Ziegler tables (Z) for He [14] are used. Further details can be found in [2]. As surface binding energy the heat of sublimation is used (see table 6.1 in [2]). For the hydrogen isotopes and nitrogen a binding energy  $e_{\text{sb}} = 1 \text{ eV}$  is chosen for these projectiles which leads to an acceleration of the incoming species and to a decrease in the angle of incidence; it has further an influence on the backscattered species (deceleration and increase in exit angle) in the same way as the surface binding energy effects the sputtered atoms. The statistical errors in the sputtering yields and reflection coefficients are usually smaller than 3% ( $1\sigma$ ) for values larger than  $10^{-5}$  and may reach 100% at the lowest values.

## 0.3 Data Representation

The calculated values are given in tables. The tables are arranged in such a way that lines give an angular dependence of sputtering yields at a fixed energy  $e_0$ , and columns give an energy dependence at a fixed angle of incidence,  $\alpha$ . In special cases this arrangement is changed. On top of the tables the input values are given:

z1	projectile (ion) atomic number
m1	projectile mass
z2	target atomic number
m2	target mass
c2	target atomic fraction
E <sub>0</sub>	projectile energy (eV)
alpha	angle of incidence
nh	number of histories (= number of projectiles)
sbe	surface binding energy (eV) for target atoms
rho	atomic target density (g/cm <sup>3</sup> )
ef	cutoff energy (eV), to stop calculation
esb	projectile binding energy (eV)
ca	correction factor to the screening length in the potential
kk0	number of ring cylinders for weak simultaneous collisions (proj.)
kk0r	number of ring cylinders for weak simultaneous collisions (recoils)
kdee1	inelastic loss model for projectiles (1: LS, 2: OR, 3: (LS+OR)/2, 4: AZ for H, 5: Z for He)
kdee2	inelastic loss model for target atoms (1: LS, 2: OR, 3: (LS+OR)/2)
ipot	interaction potential for projectiles (1: KrC, 2: Moliere, 3: ZBL, 4: Si potential)
ipotr	interaction potential for target atoms (1: KrC, 2: Moliere, 3: ZBL, 4: Si potential)
program	this gives the version used for the calculation
ne	number of projectile energies in the table
na	number of incident angles in the table
dx	depth interval (Å)

For most projectile - target combinations five tables are produced: sputtering yields, sputtered energies, particle reflection coefficients, energy reflection coefficients, and average depths of implanted atoms. The definitions are: the sputter yield,  $Y$ , is the number of sputtered atoms per projectile, the sputtered energy,  $Y_E$ , is the mean energy taken away by sputtered atoms per projectile energy, the particle reflection coefficient,  $R_N$ , is the fraction of backscattered projectiles (not implanted or transmitted), and the energy reflection coefficient,  $R_E$ , is the fraction of the incident energy carried by the reflected projectiles. In a few cases also transmission has been investigated.  $T_N$  and  $T_E$  are the particle and energy transmission coefficients.  $YT$  and  $YT_E$  are the forward sputtering yield and the forward sputtered energy, respectively.

Input values different from the usually chosen values are indicated by italic style. If the input values are the same, they are not repeated at the same page.

The data are stored at /afs/ipp/u/wge/reports/rep02. The data in the tables of the report are stored in the corresponding subdirectories; their names represent the target species. More data for other projectile-target combinations, but mostly for single energy and angle, can be found in /afs/ipp/m/wge/result/trim.

## 0.4 Data Use

The calculated values are valid for nearly flat surfaces.

The energy distribution of the sputtered atoms can be described in a first order approximation by a Thompson distribution:

$$f(E)dE = \frac{E}{(E + E_s)^3}dE \quad (0.1)$$

Applying this distribution an energy  $E$  can be determined by a pseudorandom number  $r$  due to the formula

$$\frac{E}{E_s} = \frac{1}{(1 + 1/a)\sqrt{1/r} - 1} \quad (0.2)$$

where  $E_s$  is the surface binding energy and  $a$  the maximum transferable energy divided by the surface binding energy

$$a = \frac{4m_1 m_2}{(m_1 + m_2)^2} \frac{E_0}{E_s} \quad (0.3)$$

The mean energy  $\langle E \rangle$  of sputtered atoms for a constant incident energy is given by

$$\langle E(E_0, \alpha) \rangle = E_0 \frac{Y_E(E_0, \alpha)}{Y(E_0, \alpha)} \quad (0.4)$$

For an incident Maxwellian distribution the mean energy is provided in the corresponding table.

The angular distribution of sputtered atoms can be approximated by a cosine distribution in a first approximation. An exit angle  $\theta$  can again be determined by a random number  $r$

$$\theta = \arcsin r \quad (0.5)$$

For backscattered atoms the situation is more difficult, because simple formulae for the energy and angular distributions do not exist. As for sputtered atoms the mean energy of reflected atoms can be determined for a constant incident energy by

$$\langle E(E_0, \alpha) \rangle = E_0 \frac{R_E(E_0, \alpha)}{R_N(E_0, \alpha)} \quad (0.6)$$

For rough surfaces the angular dependence of the sputtering yield and the reflection coefficients is less pronounced as given in the tables.

# Bibliography

- [1] W. Eckstein, Calculated Sputtering, Reflection and Range Values, IPP 9/117, 1998
- [2] W. Eckstein, C. García-Rosales, J. Roth, and W.Ottenberger, Sputtering Data, IPP 9/82, 1993
- [3] J. P. Biersack and W. Eckstein, Appl. Phys. **34** (1984) 73
- [4] W. Eckstein, Computer Simulation of Ion-Solid Interaction (Springer-Verlag, Berlin, Heidelberg, 1991)
- [5] W. D. Wilson, L. G. Haggmark, and J. P. Biersack, Phys. Rev. B **15** (1977) 2458
- [6] G. Molire, Z. Naturforsch. A **2** (1947) 133
- [7] J. P. Biersack, L. G. Haggmark, Nucl. Instrum. Meth. **174** (1980) 257
- [8] J. F. Ziegler, J. P. Biersack, U. Littmark, The Stopping and Range of Ions in Solids, The Stopping and Range of Ions in Matter, Vol.1, ed.by J. F. Ziegler, Pergamon, New York, 1985
- [9] W. Eckstein, S. Hackel, D. Heinemann, B. Fricke, Z. Phys. D **24** (1992) 171
- [10] M. T. Robinson, Tables of Classical Scattering Integrals, U.S. Atomic Energy Commission, ORNL-4556 (1970)
- [11] J. Lindhard and M. Scharff, Phys. Rev. **124** (1961) 128
- [12] D. Oen and M. T. Robinson, Nucl. Instrum. Meth. **132** (1976) 647
- [13] H. H. Andersen, J. F. Ziegler, Hydrogen Stopping Powers and Ranges in All Elements, The Stopping and Range of Ions in Matter, Vol.3, ed.by J. F. Ziegler, Pergamon, New York, 1977
- [14] J. F. Ziegler, Helium Stopping Powers and Ranges in All Elements, The Stopping and Range of Ions in Matter, Vol.4, ed.by J. F. Ziegler, Pergamon, New York, 1977

The numbers in the table are the page numbers at which the corresponding data are presented. The lines of the table give the data for the same projectile (in italic style), the rows for the same target atom.

### mono-atomic targets

	Li	Be	B	C	Al	Si	Ti	V	Fe	Ni	Cu	Ga	Ge	Zr	Nb
$\mu$															
<i>H</i>		14		41		82			114	119	120	138			
<i>D</i>	7	16	37	44	76	83	104	111	114	120	121	139			
<i>T</i>	10	20		47					115	121	122	152			165
<i><sup>3</sup>He</i>		22								121		154			
<i><sup>4</sup>He</i>	11	23		50	77	84	105		116	122	141				
<i>Li</i>	12		25		52										
<i>Be</i>				39		85									
<i>B</i>					53										
<i>C</i>					62										
<i>N</i>		30			65										
<i>O</i>		32	40		66	78	85	106							
<i>Ne</i>		33				86				124	143		160		
<i>Mg</i>						86							160		
<i>Al</i>						86							160		
<i>Si</i>						87							161		
<i>P</i>						100							161		
<i>Ar</i>		35		68	81	101	108	109			128	144		162	
<i>Ti</i>								112		118					
<i>V</i>										132		146			
<i>Fe</i>												156			
<i>Ni</i>															
<i>Cu</i>															
<i>Ga</i>															
<i>Kr</i>										134					
<i>Xe</i>						102				136	151		159		
<i>Hg</i>						103							163		
<i>Bi</i>						72									

	Mo	Pd	Ag	In	Cs	Sm	Ta	W	Pt	Au	Hg	U
$\mu$										242		
<i>H</i>	166				196			208				
<i>D</i>	167			190	197		207	211		243		257
<i>T</i>	170				199			214				
<i><sup>4</sup>He</i>	172	188	191					217	239	246		258
<i>C</i>	175							219				
<i>N</i>								221				
<i>O</i>	175							224	240	248		258
<i>Ne</i>	176							224		249		
<i>Na</i>				192					240	250		258
<i>Ar</i>	177			193						251		
<i>K</i>				194						255		259
<i>Kr</i>	180					205						
<i>Mo</i>	181											
<i>In</i>												
<i>Xe</i>	185	189	195	201		203		226	241	252		260
<i>Cs</i>												
<i>W</i>								229		253		
<i>Au</i>												
<i>Hg</i>	186										260	
<i>Rn</i>	187										261	
<i>U</i>												

### compound targets

	BeO	B <sub>4</sub> C	B <sub>2</sub> O <sub>3</sub>	B(OH) <sub>3</sub>	SiO <sub>2</sub>	TiC	WO <sub>3</sub>	WO <sub>4</sub>	W <sub>x</sub> O <sub>y</sub>
$\mu$									
<i>H</i>		266			280				
<i>D</i>		268			281				
<i><sup>4</sup>He</i>		271							
<i>C</i>		274							
<i>O</i>	263	276	278	279			282	287	288
<i>Ne</i>		277					285		
<i>Kr</i>							286		

### layered targets

	Li on Cu	Li on LiCu	B <sub>2</sub> O <sub>3</sub> on B	B <sub>2</sub> O <sub>3</sub> on B <sub>4</sub> C	B(OH) <sub>3</sub> on B	B(OH) <sub>3</sub> on B <sub>4</sub> C	O on WO <sub>3</sub>	WO <sub>3</sub> on W
<i>D</i>		295						
<i>O</i>			301		303		305	
<i>Ar</i>	291	299					307	

## Mono-atomic targets

# D → Li

Sputtering yield of Li by D  
 z1= 1, m1= 2.01, z2= 3, m2= 6.94, sbe=1.67 eV, rho=0.53 g/cm\*\*3  
 ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program : testvmcx, IPP 9/82  
 ne=14, na= 2

E <sub>0</sub> (eV)	0°	65°
10	3.81e-3	2.10e-2
15	9.88e-3	6.36e-2
20	1.58e-2	1.10e-1
30	2.38e-2	1.76e-1
50	3.30e-2	2.55e-1
70	3.87e-2	2.97e-1
100	4.22e-2	3.28e-1
200	4.45e-2	3.44e-1
300	4.10e-2	
500	3.41e-2	2.91e-1
1000	2.67e-2	2.06e-1
2000	1.81e-2	1.38e-1
5000	1.04e-2	7.08e-2
10000	6.93e-3	3.68e-2

Sputtered energy of Li by D  
 program : testvmcx  
 ne=13, na= 2

E <sub>0</sub> (eV)	0°	65°
10	2.98e-4	3.21e-3
15	7.92e-4	9.43e-3
20	1.21e-3	1.50e-2
30	1.65e-3	2.11e-2
50	1.81e-3	2.39e-2
70	1.88e-3	2.41e-2
100	1.78e-3	2.21e-2
200	1.26e-3	1.65e-2
500	4.66e-4	9.04e-3
1000	2.50e-4	4.77e-3
2000	9.72e-5	1.97e-3
5000	3.33e-5	6.75e-4
10000	1.48e-5	2.31e-4

# $D \rightarrow Li$

Particle reflection coefficient of D backscattered from Li  
 $z1 = 1$ ,  $m1 = 2.01$ ,  $z2 = 3$ ,  $m2 = 6.94$ ,  $sbe = 1.67$  eV,  $\rho = 0.53$  g/cm<sup>3</sup>  
 $ef = 0.98$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program : testvmcx  
ne=13, na= 2

$E_0$ (eV)	0°	65°
10	1.50e-1	5.48e-1
15	1.46e-1	5.31e-1
20	1.39e-1	5.09e-1
30	1.30e-1	4.70e-1
50	1.16e-1	4.24e-1
70	1.06e-1	4.02e-1
100	9.40e-2	3.80e-1
200	6.92e-2	3.36e-1
500	4.18e-2	2.83e-1
1000	2.28e-2	2.34e-1
2000	1.02e-2	1.86e-1
5000	3.28e-3	1.01e-1
10000	1.30e-3	4.92e-2

Energy reflection coefficient of D backscattered from Li  
program : testvmcx  
ne=13, na= 2

$E_0$ (eV)	0°	65°
10	3.76e-2	3.07e-1
15	3.74e-2	3.03e-1
20	3.58e-2	2.87e-1
30	3.33e-2	2.56e-1
50	2.93e-2	2.23e-1
70	2.65e-2	2.06e-1
100	2.37e-2	1.88e-1
200	1.68e-2	1.61e-1
500	9.56e-3	1.25e-1
1000	4.86e-3	9.16e-2
2000	1.94e-3	6.21e-2
5000	5.52e-4	2.27e-2
10000	1.77e-4	8.20e-3

Average depth (mean range) in Å of D implanted in Li  
program : testvmcx  
ne=13, na= 2

$E_0$ (eV)	0°	65°
10	1.25e+1	9.30e+0
15	1.70e+1	1.28e+1
20	2.13e+1	1.59e+1
30	2.94e+1	2.17e+1
50	4.49e+1	3.24e+1
70	6.01e+1	4.34e+1
100	8.24e+1	5.83e+1
200	1.58e+2	1.08e+2
500	3.90e+2	2.47e+2
1000	7.76e+2	4.61e+2
2000	1.52e+3	8.21e+2
5000	3.44e+3	1.66e+3
10000	5.99e+3	2.68e+3

## D → Li

Sputtering yield of Li by D  
 $z1 = 1$ ,  $m1 = 2.01$ ,  $z2 = 3$ ,  $m2 = 6.94$ ,  $sbe = \text{eV}$ ,  $\rho = 0.53 \text{ g/cm}^{**3}$   
 $ef = 0.98 \text{ eV}$ ,  $esb = 1.00 \text{ eV}$ ,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program : testvmcx  
 $ne = 3$ ,  $na = 2$ ,  $n(sbe) = 4$

sbe(eV)	1.60	1.90	2.20	2.50	2.20	2.50
E <sub>0</sub> (eV)	0°	0°	0°	0°	65°	65°
30			5.90e-4	1.05e-4		
50	2.18e-2	1.29e-2	7.81e-3	4.50e-3	6.09e-3	3.23e-3
100	4.92e-2	3.57e-2	2.65e-2	2.05e-2		

Sputtered energy of Li by D  
 $ne = 3$ ,  $na = 2$ ,  $n(sbe) = 4$

sbe(eV)	1.60	1.90	2.20	2.50	2.20	2.50
E <sub>0</sub> (eV)	0°	0°	0°	0°	65°	65°
30			6.92e-6	8.83e-7		
50	4.75e-4	2.75e-4	1.58e-4	8.55e-5	1.30e-4	6.51e-5
100	9.74e-4	7.40e-4	5.51e-4	4.45e-4		

## D → Li

D on Li, Maxwellian velocity distribution, sheath potential 0 kT  
 $z1 = 1$ ,  $m1 = 2.01$ ,  $z2 = 3$ ,  $m2 = 6.94$ ,  $sbe = 1.67 \text{ eV}$ ,  $\rho = 0.53 \text{ g/cm}^{**3}$   
 $ef = 0.98 \text{ eV}$ ,  $esb = 1.00 \text{ eV}$ ,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program : testvmcx  
 $ne = 11$

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
2	1.83e-3	6.58e-4	1.44e+0	2.04e-1	1.25e-1	2.45e+0	4.50e+0
5	1.89e-2	4.33e-3	2.29e+0	3.04e-1	1.63e-1	5.36e+0	9.90e+0
10	5.18e-2	8.25e-3	3.19e+0	3.24e-1	1.59e-1	9.84e+0	1.78e+1
20	9.83e-2	1.09e-2	4.42e+0	3.08e-1	1.44e-1	1.87e+1	3.22e+1
50	1.53e-1	9.92e-3	6.47e+0	2.70e-1	1.17e-1	4.33e+1	7.18e+1
100	1.74e-1	7.82e-3	8.93e+0	2.34e-1	9.77e-2	8.30e+1	1.34e+2
200	1.71e-1	4.95e-3	1.16e+1	2.00e-1	7.73e-2	1.54e+2	2.59e+2
500	1.39e-1	2.57e-3	1.84e+1	1.52e-1	5.27e-2	3.44e+2	6.03e+2
1000	1.05e-1	1.22e-3	2.32e+1	1.15e-1	3.40e-2	5.92e+2	1.12e+3
2000	7.19e-2	5.11e-4	2.83e+1	8.44e-2	2.12e-2	9.98e+2	1.97e+3
5000	3.93e-2	1.39e-4	3.54e+1	5.25e-2	1.00e-2	1.91e+3	3.95e+3

D on Li , Maxwellian velocity distribution , sheath potential 3 kT  
 $ne = 11$

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
2	7.84e-3	1.02e-3	1.30e+0	1.92e-1	6.17e-2	3.22e+0	1.17e+1
5	3.43e-2	3.09e-3	2.25e+0	1.74e-1	5.41e-2	7.75e+0	2.37e+1
10	5.58e-2	3.72e-3	3.34e+0	1.51e-1	4.62e-2	1.53e+1	4.21e+1
20	6.96e-2	3.28e-3	4.71e+0	1.25e-1	3.74e-2	2.99e+1	7.71e+1
50	7.10e-2	2.18e-3	7.67e+0	9.25e-2	2.66e-2	7.20e+1	1.81e+2
100	5.57e-2	1.13e-3	1.01e+1	6.27e-2	1.64e-2	1.31e+2	3.55e+2
200	4.40e-2	5.85e-4	1.33e+1	3.91e-2	9.19e-3	2.35e+2	7.05e+2
500	2.35e-2	1.70e-4	1.81e+1	1.52e-2	3.16e-3	5.19e+2	1.67e+3
1000	1.60e-2	6.89e-5	2.15e+1	5.85e-3	1.03e-3	8.85e+2	3.06e+3
2000	9.17e-3	2.53e-5	2.76e+1	2.19e-3	3.31e-4	1.51e+3	5.29e+3
5000	4.43e-3	7.99e-6	4.51e+1	4.73e-4	7.77e-5	4.10e+3	1.01e+4

# T → Li

Sputtering yield of Li by T  
 z1 = 1, m1 = 3.01, z2 = 3, m2 = 6.94, sbe = 1.68, 1.67 eV, rho = 0.53 g/cm\*\*3  
 ef = 0.90, esb = 1.00, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1 (KrC)  
 program: newtrim (Laszlo), IPP9/82  
 ne = 13, na = 13

E <sub>0</sub> (eV)	0°	20°	40°	50°	60°	65°	70°	75°	77°	80°	82°	85°	87°
10	2.52e-3					3.67e-2							
14	7.36e-3												
20	1.34e-2						1.50e-1						
30	2.04e-2							3.35e-1					
50	3.00e-2								4.30e-1				
100	4.20e-2	5.44e-2	1.50e-1	2.25e-1	3.48e-1		4.51e-1	5.00e-1	5.74e-1				
200	4.71e-2									5.31e-1			
300	4.52e-2	6.40e-2	1.37e-1	2.16e-1						7.33e-1			
500	4.40e-2							3.87e-1					
1000	3.66e-2							3.09e-1					
2000	2.67e-2							2.00e-1					
5000	1.64e-2							1.04e-1					
10000	1.10e-2							6.11e-2					

Sputtered energy of Li by T  
 program: newtrim (Laszlo)  
 ne = 10, na = 2

E <sub>0</sub> (eV)	0°	65°
10		6.99e-3
20		2.42e-2
50	1.58e-3	3.54e-2
100	1.53e-3	3.24e-2
200	1.20e-3	2.43e-2
500	6.44e-4	1.38e-2
1000	3.47e-4	8.36e-3
2000	1.51e-4	3.48e-3
5000	6.03e-5	1.31e-3
10000	1.74e-5	4.90e-4

Particle reflection coefficient of T backscattered from Li  
 z1 = 1, m1 = 3.01, z2 = 3, m2 = 6.94, Es = 1.68 eV, rho = 0.53 g/cm\*\*3  
 ef = 0.90, esb = 1.00, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1 (KrC)  
 program: newtrim (Laszlo)  
 ne = 10, na = 2

E <sub>0</sub> (eV)	0°	65°
10		4.75e-1
20		4.49e-1
50	6.62e-2	3.74e-1
100	5.39e-2	3.28e-1
200	3.96e-2	2.92e-1
500	2.29e-2	2.46e-1
1000	1.29e-2	2.04e-1
2000	5.75e-3	1.55e-1
5000	2.15e-3	9.41e-2
10000	7.45e-4	5.12e-2

Energy reflection coefficient of T backscattered from Li  
 ne = 10, na = 2

E <sub>0</sub> (eV)	0°	65°
10		2.41e-1
20		2.33e-1
50	1.18e-2	1.80e-1
100	9.65e-3	1.50e-1
200	7.05e-3	1.29e-1
500	3.91e-3	1.03e-1
1000	2.11e-3	7.95e-2
2000	8.73e-4	5.10e-2
5000	2.96e-4	2.24e-2
10000	1.00e-4	8.83e-3

Average depth (mean range) in Å of T implanted in Li  
 ne = 10, na = 2

E <sub>0</sub> (eV)	0°	65°
10		7.69e+0
20		1.35e+1
50	4.17e+1	2.79e+1
100	7.73e+1	5.08e+1
200	1.50e+2	9.47e+1
500	3.77e+2	2.28e+2
1000	7.77e+2	4.40e+2
2000	1.58e+3	8.34e+2
5000	3.76e+3	1.80e+3
10000	6.75e+3	3.03e+3

## He → Li

He on Li, Maxwellian velocity distribution, sheath potential 0 kT  
 z1= 2, m1= 4.00, z2= 3, m2= 6.94, sbe= 1.68 eV, rho= 0.53 g/cm\*\*3  
 ef=0.30 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: newtrim (Laszlo)  
 ne=11

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
2	2.16e-3	1.07e-3	1.99e+0	5.37e-1	2.58e-1	1.92e+0	3.23e+0
5	2.83e-2	8.70e-3	3.08e+0	4.65e-1	2.16e-1	4.64e+0	6.54e+0
10	9.00e-2	1.84e-2	4.09e+0	3.95e-1	1.76e-1	8.90e+0	1.08e+1
20	1.88e-1	2.59e-2	5.50e+0	3.25e-1	1.38e-1	1.70e+1	1.77e+1
50	3.46e-1	2.85e-2	8.24e+0	2.49e-1	9.86e-2	3.96e+1	3.57e+1
100	4.37e-1	2.46e-2	1.12e+1	2.04e-1	7.84e-2	7.68e+1	6.43e+1
200	4.88e-1	1.90e-2	1.56e+1	1.67e-1	6.31e-2	1.51e+2	1.21e+2
500	4.71e-1	1.17e-2	2.46e+1	1.33e-1	4.87e-2	3.64e+2	2.88e+2
1000	4.25e-1	7.48e-3	3.49e+1	1.12e-1	3.83e-2	6.75e+2	5.58e+2
2000	3.45e-1	4.19e-3	4.84e+1	8.69e-2	2.62e-2	1.20e+3	1.08e+3
5000	2.34e-1	1.91e-3	8.15e+1	5.93e-2	1.58e-2	2.65e+3	2.38e+3

He on Li, Maxwellian velocity distribution, sheath potential 2 kT  
 ne= 9

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
2	7.09e-3	1.78e-3	1.96e+0	2.30e-1	6.26e-2	2.13e+0	5.75e+0
5	5.41e-2	6.77e-3	2.50e+0	1.56e-1	3.60e-2	4.60e+0	1.12e+1
10	1.18e-1	1.09e-2	3.68e+0	1.18e-1	2.57e-2	8.69e+0	1.85e+1
20	1.78e-1	1.11e-2	4.95e+0	9.04e-2	2.00e-2	1.77e+1	3.20e+1
50	2.31e-1	9.16e-3	7.96e+0	6.56e-2	1.54e-2	4.69e+1	7.06e+1
100	2.41e-1	7.29e-3	1.21e+1	5.01e-2	1.12e-2	8.89e+1	1.31e+2
200	1.98e-1	3.90e-3	1.58e+1	3.51e-2	8.50e-3	1.94e+2	2.62e+2
500	1.54e-1	1.64e-3	2.12e+1	2.03e-2	4.53e-3	4.46e+2	6.51e+2
1000	1.03e-1	8.49e-4	3.31e+1	1.03e-2	2.04e-3	7.95e+2	1.29e+3

He on Li, Maxwellian velocity distribution, sheath potential 3 kT  
 ne=11

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
2	9.98e-3	1.76e-3	1.77e+0	1.89e-1	4.24e-2	2.25e+0	6.98e+0
5	5.89e-2	6.17e-3	2.62e+0	1.27e-1	2.52e-2	4.96e+0	1.35e+1
10	1.14e-1	8.36e-3	3.68e+0	9.61e-2	1.81e-2	9.43e+0	2.28e+1
20	1.65e-1	8.64e-3	5.24e+0	7.32e-2	1.39e-2	1.90e+1	3.96e+1
50	1.99e-1	6.63e-3	8.31e+0	5.04e-2	9.71e-3	4.81e+1	8.79e+1
100	1.96e-1	4.65e-3	1.19e+1	3.66e-2	6.95e-3	9.49e+1	1.69e+2
200	1.62e-1	2.68e-3	1.67e+1	2.43e-2	4.79e-3	1.97e+2	3.34e+2
500	1.19e-1	1.01e-3	2.13e+1	1.27e-2	2.24e-3	4.41e+2	8.42e+2
1000	8.36e-2	5.96e-4	3.57e+1	6.25e-3	8.84e-4	7.08e+2	1.66e+3
2000	5.46e-2	2.65e-4	4.83e+1	1.19e-3	1.91e-4	1.60e+3	3.09e+3
5000	1.78e-2		1.34e+2				6.45e+3

He on Li, Maxwellian velocity distribution, sheath potential 9 kT  
 ne=11

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
2	9.98e-3	1.76e-3	1.77e+0	1.89e-1	4.24e-2	2.25e+0	6.98e+0
5	5.89e-2	6.17e-3	2.62e+0	1.27e-1	2.52e-2	4.96e+0	1.35e+1
10	1.14e-1	8.36e-3	3.68e+0	9.61e-2	1.81e-2	9.43e+0	2.28e+1
20	1.65e-1	8.64e-3	5.24e+0	7.32e-2	1.39e-2	1.90e+1	3.96e+1
50	1.99e-1	6.63e-3	8.31e+0	5.04e-2	9.71e-3	4.81e+1	8.79e+1
100	1.96e-1	4.65e-3	1.19e+1	3.66e-2	6.95e-3	9.49e+1	1.69e+2
200	1.62e-1	2.68e-3	1.67e+1	2.43e-2	4.79e-3	1.97e+2	3.34e+2
500	1.19e-1	1.01e-3	2.13e+1	1.27e-2	2.24e-3	4.41e+2	8.42e+2
1000	8.36e-2	5.96e-4	3.57e+1	6.25e-3	8.84e-4	7.08e+2	1.66e+3
2000	5.46e-2	2.65e-4	4.83e+1	1.19e-3	1.91e-4	1.60e+3	3.09e+3
5000	1.78e-2		1.34e+2				6.45e+3

# Li → Li

Sputtering yield of Li by Li

$z1 = 3$ ,  $m1 = 6.94$ ,  $z2 = 3$ ,  $m2 = 6.94$ ,  $sbe = 1.68$  eV,  $\rho = 0.53$  g/cm<sup>3</sup>  
 $ef = 1.18$  eV,  $esb = 1.68$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: newtrim (Laszlo), IPP 9/82  
ne= 9, na=10

$E_0$ (eV)	0°	30°	45°	55°	60°	65°	70°	75°	80°	85°
20	5.42e-3							2.28e-1		
50	4.29e-2							5.96e-1		
100	9.48e-2	2.60e-1	5.19e-1		9.21e-1	1.05e-0	1.13e-0	1.07e-0	7.68e-1	3.21e-1
200	1.50e-1	3.43e-1	6.56e-1		1.18e-0	1.39e-0	1.58e-0	1.62e-0	1.36e-0	5.19e-1
500	1.91e-1							2.29e-0		
1000	2.07e-1	3.75e-1	6.57e-1	1.04e-0	1.33e-0		2.06e-0	2.49e-0	2.82e-0	
2000	1.87e-1							2.38e-0		
5000	1.44e-1							2.01e-0		
10000	1.19e-1							1.48e-0		

Sputtered energy of Li by Li

program: newtrim (Laszlo)  
ne= 9, na=10

$E_0$ (eV)	0°	30°	45°	55°	60°	65°	70°	75°	80°	85°
20	2.62e-4							5.67e-2		
50	1.62e-3							1.02e-1		
100	2.72e-3	1.27e-2	3.41e-2		7.85e-2	9.78e-2	1.15e-1	1.22e-1	9.97e-2	5.00e-2
200	3.17e-3	1.23e-2	3.12e-2		7.17e-2	8.94e-2	1.10e-1	1.25e-1	1.16e-1	5.40e-2
500	2.61e-3							1.09e-1		
1000	2.08e-3	6.76e-3	1.61e-2	3.06e-2	4.15e-2		7.17e-2	8.97e-2	1.02e-1	8.26e-2
2000	1.29e-3								6.53e-2	
5000	5.98e-4								3.85e-2	
10000	3.46e-4								2.08e-2	

Particle reflection coefficient of Li backscattered from Li

$z1 = 3$ ,  $m1 = 6.94$ ,  $z2 = 3$ ,  $m2 = 6.94$ ,  $sbe = 1.68$  eV,  $\rho = 0.53$  g/cm<sup>3</sup>  
 $ef = 1.18$  eV,  $esb = 1.68$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: newtrim (Laszlo)  
ne= 9, na=10

$E_0$ (eV)	0°	30°	45°	55°	60°	65°	70°	75°	80°	85°
20	9.31e-4							5.18e-1		
50	3.80e-3							5.96e-1		
100	5.39e-3	2.39e-2	6.99e-2		1.93e-1	2.69e-1	3.72e-1	5.18e-1	7.21e-1	9.05e-1
200	5.10e-3	2.09e-2	5.93e-2		1.64e-1	2.27e-1	3.14e-1	4.33e-1	6.28e-1	8.89e-1
500	3.56e-3							3.52e-1		
1000	2.42e-3	1.11e-2	3.39e-2	7.57e-2	1.12e-1		2.24e-1	3.10e-1	4.50e-1	6.98e-1
2000	1.79e-3							2.89e-1		
5000	6.04e-4							2.45e-1		
10000								2.08e-1		

Energy reflection coefficient of Li backscattered from Li

ne= 9, na=10

$E_0$ (eV)	0°	30°	45°	55°	60°	65°	70°	75°	80°	85°
20	5.99e-5							2.56e-1		
50	2.25e-4							3.43e-1		
100	3.04e-4	2.92e-3	1.33e-2		6.05e-2	1.02e-1	1.70e-1	2.91e-1	4.98e-1	7.32e-1
200	2.79e-4	2.45e-3	1.07e-2		4.74e-2	7.96e-2	1.32e-1	2.26e-1	4.20e-1	7.49e-1
500	1.91e-4							1.67e-1		
1000	1.27e-4	1.20e-3	6.34e-3	1.77e-2	3.03e-2		8.35e-2	1.41e-1	2.53e-1	5.40e-1
2000	1.18e-4							1.25e-1		
5000	2.66e-5							1.01e-1		
10000								7.16e-2		

Average depth (mean range) in Å of Li implanted in Li

ne= 9, na=10

$E_0$ (eV)	0°	30°	45°	55°	60°	65°	70°	75°	80°	85°
20	1.01e+1							3.62e+0		
50	1.94e+1							8.87e+0		
100	3.25e+1	2.85e+1	2.43e+1		1.95e+1	1.79e+1	1.66e+1	1.53e+1	1.40e+1	1.25e+1
200	5.63e+1	4.95e+1	4.17e+1		3.35e+1	3.09e+1	2.85e+1	2.62e+1	2.43e+1	2.22e+1
500	1.24e+2							5.60e+1		
1000	2.39e+2	2.09e+2	1.74e+2	1.50e+2	1.38e+2		1.13e+2	1.04e+2	9.58e+1	8.93e+1
2000	4.79e+2							2.00e+2		
5000	1.23e+3							4.69e+2		
10000	2.45e+3							8.63e+2		

## Li → Li

Li on Li, Maxwellian velocity distribution, sheath potential 0 kT  
 z1= 3, m1= 6.94, z2= 3, m2= 6.94, sbe=1.67 eV, rho= 0.53 g/cm\*\*3  
 ef=1.62 eV, esb=1.67 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx, newtrim(Laszlo)  
 ne=14

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
1.1	4.56e-4	3.04e-4	1.47e+0	1.10e-3	1.12e-3	2.24e+0	1.12e+0
1.4	1.24e-3	7.64e-4	1.73e+0	2.85e-3	2.74e-3	2.69e+0	1.36e+0
2	4.22e-3	2.37e-3	2.24e+0	9.29e-3	8.13e-3	3.50e+0	1.82e+0
3	1.41e-2	6.30e-3	2.68e+0	2.40e-2	1.80e-2	4.49e+0	2.51e+0
5	4.28e-2	1.44e-2	3.36e+0	5.70e-2	3.80e-2	6.67e+0	3.94e+0
10	1.26e-1	2.84e-2	4.53e+0	1.09e-1	6.07e-2	1.12e+1	6.83e+0
20	2.58e-1	3.90e-2	6.04e+0	1.43e-1	7.01e-2	1.96e+1	1.18e+1
50	4.88e-1	4.31e-2	8.87e+0	1.48e-1	6.39e-2	4.32e+1	2.43e+1
100	6.66e-1	4.10e-2	1.23e+1	1.34e-1	5.37e-2	8.01e+1	4.22e+1
200	7.95e-1	3.49e-2	1.74e+1	1.19e-1	4.60e-2	1.53e+2	7.64e+1
500	8.58e-1	2.39e-2	2.78e+1	9.74e-2	3.58e-2	3.66e+2	1.80e+2
1000	7.95e-1	1.62e-2	4.08e+1	7.90e-2	2.92e-2	7.39e+2	3.52e+2
2000	7.35e-1	1.12e-2	6.09e+1	7.05e-2	2.35e-2	1.33e+3	6.96e+2
5000				5.12e-2	1.82e-2	3.57e+3	1.69e+3

Li on Li, Maxwellian velocity distribution, sheath potential 3 kT  
 ne=14

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
1.1	1.43e-3	3.71e-4	1.43e+0	1.56e-3	5.76e-4	2.03e+0	3.34e+0
1.4	3.47e-3	7.95e-4	1.61e+0	3.05e-3	1.04e-3	2.37e+0	4.02e+0
2	1.07e-2	2.00e-3	1.87e+0	6.82e-3	2.07e-3	3.03e+0	5.29e+0
3	2.71e-2	4.10e-3	2.27e+0	1.19e-2	3.06e-3	3.86e+0	7.15e+0
5	6.41e-2	7.17e-3	2.79e+0	1.71e-2	3.68e-3	5.39e+0	1.05e+1
10	1.36e-1	1.05e-2	3.84e+0	2.04e-2	3.51e-3	8.59e+0	1.74e+1
20	2.14e-1	1.16e-2	5.41e+0	1.92e-2	2.94e-3	1.53e+1	2.92e+1
50	3.19e-1	1.09e-2	8.58e+0	1.73e-2	2.65e-3	3.82e+1	6.10e+1
100	3.45e-1	8.13e-3	1.21e+1	1.28e-2	1.88e-3	7.31e+1	1.12e+2
200	3.24e-1	5.68e-3	1.76e+1	9.05e-3	1.43e-3	1.58e+2	2.15e+2
500	2.40e-1	2.46e-3	2.57e+1	4.72e-3	6.67e-4	3.53e+2	5.38e+2
1000	2.16e-1	1.54e-3	3.57e+1	2.99e-3	4.51e-4	7.57e+2	1.10e+3
2000	1.46e-1	8.98e-4	6.14e+1	7.58e-4	1.36e-4	1.80e+3	2.19e+3
5000	9.47e-2	3.04e-4	8.04e+1			5.07e+3	

Li on Li, Maxwellian velocity distribution, sheath potential 9 kT  
 ne=14

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
1.1	5.18e-3	5.87e-4	1.37e+0	2.18e-3	3.64e-4	2.02e+0	6.58e+0
1.4	1.08e-2	1.04e-3	1.49e+0	3.38e-3	5.06e-4	2.31e+0	7.84e+0
2	2.37e-2	1.93e-3	1.79e+0	5.45e-3	7.29e-4	2.94e+0	1.01e+1
3	4.80e-2	3.25e-3	2.23e+0	7.61e-3	9.23e-4	4.00e+0	1.36e+1
5	8.93e-2	4.65e-3	2.86e+0	9.45e-3	9.90e-4	5.76e+0	1.99e+1
10	1.55e-1	6.03e-3	4.27e+0	1.01e-2	9.55e-4	1.04e+1	3.35e+1
20	2.15e-1	5.74e-3	5.87e+0	8.97e-3	8.33e-4	2.04e+1	5.84e+1
50	2.55e-1	4.50e-3	9.72e+0	6.58e-3	6.13e-4	5.12e+1	1.30e+2
100	2.49e-1	3.06e-3	1.35e+1	4.13e-3	3.27e-4	8.71e+1	2.52e+2
200	2.10e-1	1.82e-3	1.90e+1	2.23e-3	2.79e-4	2.75e+2	5.03e+2
500	1.43e-1	6.45e-4	2.49e+1	1.55e-3	1.37e-4	4.85e+2	1.29e+3
1000	1.20e-1	4.38e-4	4.01e+1	2.61e-4	1.90e-5	8.02e+2	2.57e+3
2000	8.47e-2	1.82e-4	4.71e+1	2.12e-4	8.83e-6	9.16e+2	4.88e+3
5000	4.98e-2	8.04e-5	8.89e+1			8.65e+3	

# H → Be

Sputtering yield of Be by H  
 z1= 1, m1= 1.01, z2= 4, m2= 9.01, sbe=3.38 eV, rho=1.80 g/cm\*\*3  
 ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program : trvmc  
 ne=17, na=10

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	60°	65°	75°	80°	85°
15	2.39e-5	2.63e-5	2.85e-5	2.14e-5	1.21e-5	8.09e-6	4.43e-6			
17	1.80e-4	1.95e-4	2.08e-4	1.66e-4	1.05e-4	7.32e-5	4.48e-5	9.26e-6	3.26e-6	3.82e-6
20	8.03e-4	8.49e-4	9.25e-4	8.35e-4	6.15e-4	4.64e-4	3.12e-4	8.45e-5	3.29e-5	1.31e-5
22	1.45e-3	1.50e-3	1.68e-3	1.65e-3	1.32e-3		7.44e-4	2.31e-4	9.69e-5	3.89e-5
25	2.57e-3	2.75e-3	3.17e-3	3.36e-3	2.89e-3	2.50e-3	1.92e-3	7.73e-4	3.29e-4	1.38e-4
27	3.50e-3									
30	4.68e-3	4.98e-3	5.82e-3	6.88e-3	6.92e-3	6.37e-3	5.53e-3	2.68e-3	1.26e-3	4.78e-4
40	8.46e-3	9.19e-3	1.13e-2	1.48e-2	1.76e-2	1.87e-2	1.83e-2	1.10e-2	4.97e-3	1.39e-3
50	1.15e-2	1.24e-2	1.55e-2	2.20e-2	2.89e-2	3.24e-2	3.40e-2	2.38e-2	1.05e-2	2.46e-3
70	1.54e-2	1.69e-2	2.19e-2	3.35e-2	4.76e-2	5.61e-2	6.40e-2	5.41e-2	2.57e-2	4.28e-3
100	1.85e-2	2.04e-2	2.70e-2	4.38e-2	6.49e-2	7.81e-2	9.48e-2	9.73e-2	5.15e-2	6.63e-3
140	1.98e-2	2.24e-2	3.07e-2	5.05e-2	7.71e-2		1.18e-1	1.39e-1	8.57e-2	1.02e-2
200	2.02e-2	2.28e-2	3.27e-2	5.57e-2	8.43e-2	1.05e-1	1.33e-1	1.78e-1	1.33e-1	1.70e-2
300	1.93e-2	2.23e-2	3.27e-2	5.64e-2	8.66e-2		1.37e-1	2.07e-1	1.91e-1	3.41e-2
500	1.69e-2	1.98e-2	2.99e-2	5.13e-2	8.02e-2	1.00e-1	1.30e-1	2.15e-1	2.43e-1	8.09e-2
1000	1.26e-2	1.49e-2	2.26e-2	4.00e-2	6.28e-2	8.37e-2	1.04e-1	1.88e-1	2.51e-1	1.93e-1
2000						5.55e-2				

Sputtered energy of Be by H  
 ne=17, na=10

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	60°	65°	75°	80°	85°
15	5.14e-7	6.20e-7	7.95e-7	6.37e-7	3.73e-7	2.51e-7	1.27e-7			
17	5.30e-6	6.12e-6	7.26e-6	6.29e-6	3.98e-6	2.79e-6	1.68e-6	3.59e-7	1.31e-7	2.07e-7
20	3.14e-5	3.45e-5	4.08e-5	3.99e-5	2.98e-5	2.25e-5	1.54e-5	4.24e-6	1.71e-6	7.12e-7
22	6.21e-5	6.65e-5	8.12e-5	8.74e-5	7.17e-5		4.08e-5	1.29e-5	5.50e-6	2.34e-6
25	1.22e-4	1.36e-4	1.68e-4	1.92e-4	1.73e-4		1.19e-4	4.71e-5	2.15e-5	9.17e-6
27	1.74e-4									
30	2.42e-4	2.67e-4	3.31e-4	4.23e-4	4.46e-4	4.20e-4	3.77e-4	1.94e-4	9.45e-5	3.69e-5
40	4.61e-4	5.09e-4	6.62e-4	9.35e-4	1.17e-3	1.29e-3	1.33e-3	8.94e-4	4.35e-4	1.28e-4
50	6.19e-4	6.74e-4	8.89e-4	1.34e-3	1.87e-3	2.21e-3	2.45e-3	2.01e-3	9.77e-4	2.47e-4
70	7.72e-4	8.60e-4	1.14e-3	1.88e-3	2.88e-3	3.56e-3	4.33e-3	4.44e-3	2.38e-3	4.33e-4
100	8.25e-4	9.19e-4	1.24e-3	2.11e-3	3.33e-3	4.37e-3	5.66e-3	7.00e-3	4.30e-3	6.46e-4
140	7.78e-4	8.76e-4	1.21e-3	2.11e-3	3.44e-3		6.00e-3	8.66e-3	6.13e-3	8.86e-4
200	6.59e-4	7.45e-4	1.08e-3	1.99e-3	3.22e-3	4.34e-3	5.77e-3	8.99e-3	7.80e-3	1.27e-3
300	5.02e-4	5.80e-4	8.63e-4	1.66e-3	2.77e-3		4.77e-3	8.11e-3	8.64e-3	2.00e-3
500	3.13e-4	3.77e-4	5.91e-4	1.11e-3	1.99e-3	2.42e-3	3.33e-3	6.22e-3	7.74e-3	3.29e-3
1000	1.39e-4	1.66e-4	2.92e-4	5.88e-4	1.00e-3	1.27e-3	1.88e-3	3.66e-3	5.11e-3	4.57e-3
2000						6.26e-4				

# H → Be

Particle reflection coefficient of H backscattered from Be  
 z1= 1, m1= 1.01, z2= 4, m2= 9.01, sbe=3.38 eV, rho=1.80 g/cm\*\*3  
 ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program : trvmc  
 ne=18, na=10

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	60°	65°	75°	80°	85°
10	4.27e-1	4.51e-1	5.21e-1	6.43e-1	7.48e-1	8.56e-1	9.38e-1	9.61e-1	9.74e-1	
15	3.79e-1	4.01e-1	4.65e-1	5.87e-1	7.02e-1	7.66e-1	8.32e-1	9.38e-1	9.69e-1	9.83e-1
17	3.66e-1	3.86e-1	4.48e-1	5.68e-1	6.85e-1	7.51e-1	8.20e-1	9.37e-1	9.70e-1	9.85e-1
20	3.49e-1	3.68e-1	4.28e-1	5.44e-1	6.61e-1	7.30e-1	8.04e-1	9.34e-1	9.71e-1	9.87e-1
22	3.40e-1	3.59e-1	4.16e-1	5.29e-1	6.46e-1	7.92e-1	9.31e-1	9.71e-1	9.88e-1	
25	3.28e-1	3.46e-1	4.02e-1	5.10e-1	6.26e-1	6.97e-1	7.76e-1	9.26e-1	9.71e-1	9.89e-1
27	3.22e-1									
30	3.11e-1	3.28e-1	3.81e-1	4.85e-1	5.97e-1	6.69e-1	7.50e-1	9.17e-1	9.70e-1	9.91e-1
40	3.87e-1	3.03e-1	3.53e-1	4.48e-1	5.52e-1	6.21e-1	7.05e-1	8.97e-1	9.66e-1	9.93e-1
50	2.69e-1	2.85e-1	3.32e-1	4.22e-1	5.20e-1	5.87e-1	6.68e-1	8.75e-1	9.60e-1	9.93e-1
70	2.44e-1	2.58e-1	3.03e-1	3.88e-1	4.76e-1	5.35e-1	6.13e-1	8.33e-1	9.46e-1	9.94e-1
100	2.18e-1	2.32e-1	2.74e-1	3.53e-1	4.36e-1	4.90e-1	5.60e-1	7.77e-1	9.20e-1	9.93e-1
140	1.94e-1	2.08e-1	2.47e-1	3.23e-1	4.02e-1	5.17e-1	7.17e-1	8.82e-1	9.92e-1	
200	1.68e-1	1.81e-1	2.19e-1	2.92e-1	3.69e-1	4.22e-1	4.77e-1	6.58e-1	8.28e-1	9.87e-1
300	1.39e-1	1.51e-1	1.87e-1	2.58e-1	3.31e-1		4.35e-1	6.00e-1	7.77e-1	9.74e-1
500	1.03e-1	1.14e-1	1.46e-1	2.13e-1	2.85e-1	3.36e-1	3.86e-1	5.39e-1	6.71e-1	9.37e-1
1000	5.91e-2	6.64e-2	9.28e-1	1.50e-1	2.17e-1	2.68e-1	3.18e-1	4.67e-1	5.80e-1	8.28e-1
2000						1.91e-1				

Energy reflection coefficient of H backscattered from Be  
 ne=18, na=10

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	60°	65°	75°	80°	85°
10	1.96e-1	2.15e-1	2.73e-1	3.88e-1	5.01e-1	6.34e-1	7.58e-1	7.99e-1	8.24e-1	
15	1.71e-1	1.87e-1	2.38e-1	3.50e-1	4.71e-1	5.45e-1	6.27e-1	7.85e-1	8.40e-1	8.70e-1
17	1.63e-1	1.78e-1	2.27e-1	3.35e-1	4.56e-1	5.33e-1	6.19e-1	7.89e-1	8.49e-1	8.81e-1
20	1.54e-1	1.68e-1	2.14e-1	3.16e-1	4.36e-1	5.14e-1	6.05e-1	7.92e-1	8.59e-1	8.93e-1
22	1.49e-1	1.62e-1	2.06e-1	3.04e-1	4.23e-1		5.95e-1	7.92e-1	8.63e-1	9.00e-1
25	1.42e-1	1.55e-1	1.96e-1	2.90e-1	4.04e-1	4.84e-1	5.79e-1	7.89e-1	8.68e-1	9.08e-1
27	1.39e-1									
30	1.33e-1	1.45e-1	1.83e-1	2.69e-1	3.78e-1	4.56e-1	5.54e-1	7.82e-1	8.73e-1	9.17e-1
40	1.20e-1	1.30e-1	1.65e-1	2.40e-1	3.37e-1	4.10e-1	5.06e-1	7.62e-1	8.74e-1	9.28e-1
50	1.11e-1	1.20e-1	1.52e-1	2.20e-1	3.08e-1	3.76e-1	4.68e-1	7.37e-1	8.70e-1	9.35e-1
70	9.79e-2	1.06e-1	1.34e-1	1.95e-1	2.70e-1	3.27e-1	4.10e-1	6.86e-1	8.54e-1	9.42e-1
100	8.46e-2	9.22e-2	1.17e-1	1.71e-1	2.36e-1	2.86e-1	3.56e-1	6.18e-1	8.21e-1	9.45e-1
140	7.29e-2	8.00e-2	1.02e-1	1.51e-1	2.09e-1		3.13e-1	5.45e-1	7.71e-1	9.45e-1
200	6.08e-2	6.72e-2	8.70e-2	1.31e-1	1.84e-1	2.25e-1	2.75e-1	4.73e-1	6.98e-1	9.40e-1
300	4.81e-2	5.30e-2	7.03e-2	1.09e-1	1.57e-1		2.37e-1	4.09e-1	6.03e-1	9.22e-1
500	3.29e-2	3.72e-2	5.11e-2	8.30e-2	1.24e-1	1.55e-1	1.94e-1	3.34e-1	4.90e-1	8.65e-1
1000	1.68e-2	1.92e-2	2.83e-2	5.06e-2	8.15e-2	1.07e-1	1.39e-1	2.55e-1	3.71e-1	7.02e-1
2000						6.27e-2				

Average depth (mean range) in Å of H implanted in Be  
 ne=18, na=10

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	60°	65°	75°	80°	85°
10	5.11e+0	5.06e+0	4.96e+0	4.79e+0	4.65e+0	4.49e+0	4.32e+0	4.24e+0	4.18e+0	
15	6.88e+0	6.81e+0	6.64e+0	6.39e+0	6.20e+0	6.09e+0	5.98e+0	5.74e+0	5.58e+0	5.58e+0
17	7.55e+0	7.47e+0	7.27e+0	6.99e+0	6.77e+0	6.65e+0	6.54e+0	6.29e+0	6.17e+0	6.05e+0
20	8.52e+0	8.43e+0	8.20e+0	7.86e+0	7.61e+0	7.47e+0	7.34e+0	7.07e+0	6.93e+0	6.80e+0
22	9.15e+0	9.05e+0	8.80e+0	8.43e+0	8.15e+0		7.86e+0	7.57e+0	7.41e+0	7.27e+0
25	1.01e+1	1.00e+1	9.69e+0	9.25e+0	8.95e+0	8.79e+0	8.63e+0	8.30e+0	8.14e+0	7.98e+0
27	1.07e+1									
30	1.16e+1	1.15e+1	1.11e+1	1.06e+1	1.02e+1	1.01e+1	9.86e+0	9.49e+0	9.30e+0	9.13e+0
40	1.45e+1	1.44e+1	1.39e+1	1.32e+1	1.27e+1	1.25e+1	1.22e+1	1.18e+1	1.16e+1	1.13e+1
50	1.74e+1	1.71e+1	1.65e+1	1.57e+1	1.51e+1	1.47e+1	1.45e+1	1.39e+1	1.37e+1	1.34e+1
70	2.28e+1	2.25e+1	2.17e+1	2.05e+1	1.95e+1	1.91e+1	1.87e+1	1.80e+1	1.77e+1	1.74e+1
100	3.07e+1	3.03e+1	2.91e+1	2.73e+1	2.60e+1	2.54e+1	2.48e+1	2.38e+1	2.34e+1	2.31e+1
140	4.09e+1	4.03e+1	3.85e+1	3.60e+1	3.42e+1		3.24e+1	3.10e+1	3.05e+1	3.00e+1
200	5.58e+1	5.48e+1	5.23e+1	4.86e+1	4.58e+1	4.44e+1	4.33e+1	4.11e+1	4.05e+1	4.06e+1
300	8.00e+1	7.84e+1	7.44e+1	6.86e+1	6.41e+1		6.03e+1	5.67e+1	5.57e+1	5.54e+1
500	1.26e+2	1.23e+2	1.17e+2	1.06e+2	9.82e+1	9.45e+1	9.10e+1	8.50e+1	8.28e+1	8.25e+1
1000	2.37e+2	2.31e+2	2.15e+1	1.91e+1	1.74e+2	1.65e+2	1.57e+2	1.43e+2	1.38e+2	1.36e+2
2000						2.80e+2				

# D → Be

Sputtering yield of Be by D  
 z1= 1, m1= 2.01, z2= 4, m2= 9.01, sbe=3.38 eV, rho=1.80 g/cm\*\*3  
 ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program : trvmc  
 ne=21, na=12

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	60°	65°	70°	75°	80°	85°	87°	
10	4.13e-6	4.30e-6	4.56e-6										
11	2.61e-5	3.05e-5	3.15e-5	2.69e-5	1.86e-5		1.00e-5		3.67e-6	8.00e-7	5.00e-7		
12	9.29e-5	1.07e-4	1.25e-4	1.14e-4	8.71e-5	6.81e-5	5.37e-5		2.31e-5	1.39e-5	9.62e-6		
13	2.32e-4	2.67e-4	3.47e-4	3.16e-4	2.61e-4	2.10e-4	1.62e-4		7.67e-5	4.78e-5	3.18e-5		
14	4.65e-4	5.50e-4	6.90e-4	6.91e-4	5.92e-4		3.92e-4		1.91e-4	1.20e-4	7.85e-5		
15	8.10e-4	9.42e-4	1.21e-3	1.29e-3	1.12e-3	9.82e-4	7.97e-4		4.11e-4	2.57e-4	1.65e-4		
17	1.73e-3	2.02e-3	2.60e-3	3.03e-3	2.92e-3		2.29e-3		1.25e-3	7.67e-4	4.62e-4		
20	3.64e-3	4.19e-3	5.46e-3	7.03e-3	7.46e-3	7.12e-3	6.59e-3		3.76e-3	2.14e-3	1.16e-3		
25	7.30e-3	8.25e-3	1.11e-2	1.57e-2	1.87e-2	1.94e-2	1.85e-2		1.08e-2	5.51e-3	2.51e-3		
30	1.08e-2	1.22e-2	1.69e-2	2.54e-2	3.25e-2	3.58e-2	3.46e-2		2.07e-2	1.02e-2	3.82e-3		
40	1.68e-2	1.90e-2	2.64e-2	4.34e-2	6.08e-2		7.17e-2		4.54e-2	2.12e-2	5.91e-3		
50	2.09e-2	2.40e-2	3.45e-2	5.78e-2	8.53e-2	9.88e-2	1.07e-1		7.40e-2	3.23e-2	7.37e-3		
70	2.63e-2	3.04e-2	4.43e-2	7.94e-2	1.19e-1		1.60e-1		1.28e-1	5.90e-2	9.51e-3		
100	3.10e-2	3.59e-2	5.42e-2	9.78e-2	1.49e-1	1.80e-1	2.13e-1		2.00e-1	1.01e-1	1.27e-2		
140	3.32e-2	3.94e-2	6.11e-2	1.08e-1	1.68e-1		2.48e-1		2.71e-1	1.60e-1	1.82e-2		
200	3.51e-2	4.03e-2	6.32e-2	1.14e-1	1.77e-1	2.20e-1	2.68e-1		3.42e-1	2.43e-1	2.93e-2		
300	3.44e-2	4.20e-2	6.34e-2	1.12e-1	1.75e-1	2.12e-1	2.72e-1		3.91e-1	3.42e-1	5.71e-2		
500	3.24e-2	3.85e-2	5.82e-2	1.04e-1	1.50e-1	1.98e-1	2.57e-1		4.08e-1	4.39e-1	1.38e-1		
1000	2.53e-2	2.96e-2	4.37e-2	7.80e-2	1.25e-1	1.54e-1	2.06e-1		3.65e-1	4.59e-1	3.34e-1		
2000	1.76e-2												
3000	1.25e-2		2.02e-2	3.43e-2		7.29e-2		1.29e-1		2.89e-1	4.59e-1	3.18e-1	

Sputtered energy of Be by D  
 ne=19, na=10

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	60°	65°	75°	80°	85°	
10	1.72e-7										
11	1.21e-6	1.56e-6	1.98e-6	1.99e-6	1.51e-6		9.34e-7	4.11e-7	1.24e-7	2.70e-8	
12	4.88e-6	6.11e-6	8.54e-6	8.82e-6	7.18e-6	5.83e-6	5.05e-6	2.39e-6	1.49e-6	1.10e-6	
13	1.30e-5	1.66e-5	2.54e-5	2.61e-5	2.35e-5	1.94e-5	1.55e-5	8.02e-6	5.16e-6	3.52e-6	
14	2.79e-5	3.57e-5	5.17e-5	5.93e-5	5.50e-5		3.98e-5	2.08e-5	1.33e-5	8.92e-6	
15	5.04e-5	6.24e-5	9.50e-5	1.14e-4	1.09e-4	9.93e-5	8.38e-5	4.72e-5	2.99e-5	1.98e-5	
17	1.13e-4	1.43e-4	2.13e-4	2.37e-4	3.05e-4		2.57e-4	1.49e-4	9.47e-5	5.87e-5	
20	2.51e-4	3.10e-4	4.62e-4	6.96e-4	8.14e-4	8.32e-4	7.90e-4	4.86e-4	2.91e-4	1.63e-4	
25	5.28e-4	6.36e-4	9.66e-4	1.56e-3	2.09e-3	2.26e-3	2.32e-3	1.53e-3	8.29e-4	3.96e-4	
30	7.87e-4	9.35e-4	1.44e-3	2.49e-3	3.56e-3	4.15e-3	4.36e-3	3.04e-3	1.59e-3	6.39e-4	
40	1.20e-3	1.42e-3	2.12e-3	3.97e-3	6.30e-3		8.66e-3	6.66e-3	3.39e-3	1.01e-3	
50	1.43e-3	1.68e-3	2.60e-3	4.94e-3	8.18e-3	1.02e-2	1.21e-2	1.04e-2	5.02e-3	1.26e-3	
70	1.60e-3	1.88e-3	2.95e-3	5.87e-3	1.00e-2		1.59e-2	1.58e-2	8.45e-3	1.53e-3	
100	1.63e-3	1.95e-3	3.04e-3	6.18e-3	1.07e-2	1.36e-2	1.78e-2	2.07e-2	1.22e-2	1.84e-3	
140	1.48e-3	1.82e-3	2.94e-3	5.89e-3	1.02e-2		1.72e-2	2.30e-2	1.58e-2	2.26e-3	
200	1.30e-3	1.48e-3	2.57e-3	5.21e-3	8.88e-3	1.21e-2	1.52e-2	2.31e-2	1.92e-2	3.03e-3	
300	1.01e-3	1.24e-3	2.07e-3	4.14e-3	7.29e-3		1.22e-2	2.06e-2	2.03e-2	4.56e-3	
500	6.64e-4	8.04e-4	1.42e-3	3.03e-3	4.99e-3	6.57e-3	8.91e-3	1.58e-2	1.85e-2	7.33e-3	
1000	3.22e-4	3.90e-4	7.24e-4	1.47e-3	2.71e-3	3.50e-3	4.93e-3	9.33e-3	1.25e-2	1.04e-2	

# D → Be

Particle reflection coefficient of D backscattered from Be  
 z1= 1, m1= 2.01, z2= 4, m2= 9.01, sbe=3.38 eV, rho=1.80 g/cm\*\*3  
 ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program : trvmc  
 ne=19, na=10

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	60°	65°	75°	80°	85°
10	3.05e-1									
11	2.97e-1	3.23e-1	4.00e-1	5.45e-1	6.74e-1		8.12e-1	9.21e-1	9.52e-1	9.68e-1
12	2.89e-1	3.14e-1	3.90e-1	5.34e-1	6.66e-1	7.37e-1	8.08e-1	9.23e-1	9.55e-1	9.72e-1
13	2.82e-1	3.06e-1	3.81e-1	5.23e-1	6.57e-1	7.30e-1	8.04e-1	9.24e-1	9.58e-1	9.74e-1
14	2.76e-1	2.99e-1	3.72e-1	5.13e-1	6.48e-1		7.99e-1	9.24e-1	9.60e-1	9.77e-1
15	2.70e-1	2.92e-1	3.63e-1	5.03e-1	6.39e-1	7.15e-1	7.94e-1	9.24e-1	9.61e-1	9.78e-1
17	2.58e-1	2.80e-1	3.48e-1	4.84e-1	6.21e-1		7.83e-1	9.23e-1	9.63e-1	9.81e-1
20	2.45e-1	2.66e-1	3.29e-1	4.60e-1	5.95e-1	6.76e-1	7.64e-1	9.20e-1	9.65e-1	9.84e-1
25	2.27e-1	2.46e-1	3.05e-1	4.26e-1	5.58e-1	6.41e-1	7.34e-1	9.12e-1	9.66e-1	9.87e-1
30	2.14e-1	2.32e-1	2.88e-1	4.01e-1	5.27e-1	6.11e-1	7.06e-1	9.02e-1	9.64e-1	9.89e-1
40	2.95e-1	2.10e-1	2.61e-1	3.64e-1	4.81e-1		6.56e-1	8.80e-1	9.60e-1	9.91e-1
50	1.81e-1	1.96e-1	2.44e-1	3.41e-1	4.49e-1	5.22e-1	6.17e-1	8.56e-1	9.53e-1	9.92e-1
70	1.63e-1	1.76e-1	2.19e-1	3.07e-1	4.05e-1		5.58e-1	8.09e-1	9.38e-1	9.93e-1
100	1.43e-1	1.58e-1	2.00e-1	2.77e-1	3.65e-1	4.24e-1	5.03e-1	7.48e-1	9.10e-1	9.93e-1
140	1.29e-1	1.41e-1	1.85e-1	2.53e-1	3.35e-1		4.61e-1	6.85e-1	8.68e-1	9.91e-1
200	1.12e-1	1.22e-1	1.59e-1	2.30e-1	3.09e-1	3.58e-1	4.24e-1	6.22e-1	8.10e-1	9.86e-1
300	9.35e-2	1.04e-1	1.37e-1	2.05e-1	2.81e-1		3.90e-1	5.64e-1	7.35e-1	9.72e-1
500	7.20e-2	8.05e-2	1.10e-1	1.72e-1	2.46e-1	2.87e-1	3.47e-1	5.09e-1	6.49e-1	9.32e-1
1000	4.38e-2	5.04e-2	7.37e-2	1.27e-1	1.92e-1	2.39e-1	2.94e-1	4.45e-1	5.66e-1	8.23e-1

Energy reflection coefficient of D backscattered from Be  
 ne=19, na=10

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	60°	65°	75°	80°	85°
10	9.79e-2									
11	9.60e-2	1.11e-1	1.62e-1	2.73e-1	3.92e-1		5.42e-1	6.93e-1	7.47e-1	7.79e-1
12	9.40e-2	1.09e-1	1.58e-1	2.69e-1	3.89e-1	4.63e-1	5.45e-1	7.04e-1	7.61e-1	7.95e-1
13	9.19e-2	1.06e-1	1.54e-1	2.63e-1	3.86e-1	4.61e-1	5.46e-1	7.13e-1	7.73e-1	8.08e-1
14	9.00e-2	1.04e-1	1.50e-1	2.58e-1	3.81e-1		5.46e-1	7.20e-1	7.84e-1	8.20e-1
15	8.80e-2	1.01e-1	1.47e-1	2.53e-1	3.76e-1	4.55e-1	5.45e-1	7.26e-1	7.92e-1	8.30e-1
17	8.43e-2	9.67e-2	1.40e-1	2.42e-1	3.65e-1		5.40e-1	7.34e-1	8.07e-1	8.47e-1
20	7.96e-2	9.11e-2	1.31e-1	2.27e-1	3.48e-1	4.30e-1	5.29e-1	7.41e-1	8.22e-1	8.66e-1
25	7.33e-2	8.34e-2	1.19e-1	2.06e-1	3.21e-1	4.04e-1	5.07e-1	7.44e-1	8.38e-1	8.88e-1
30	6.84e-2	7.79e-2	1.11e-1	1.90e-1	2.97e-1	3.79e-1	4.83e-1	7.40e-1	8.46e-1	9.03e-1
40	6.14e-2	6.94e-2	9.80e-2	1.67e-1	2.62e-1		4.39e-1	7.22e-1	8.52e-1	9.20e-1
50	5.66e-2	6.39e-2	8.97e-2	1.52e-1	2.38e-1	3.04e-1	4.02e-1	6.98e-1	8.51e-1	9.30e-1
70	5.01e-2	5.65e-2	7.90e-2	1.33e-1	2.06e-1		3.48e-1	6.47e-1	8.37e-1	9.41e-1
100	4.35e-2	4.94e-2	7.06e-2	1.16e-1	1.78e-1	2.27e-1	2.98e-1	5.78e-1	8.04e-1	9.47e-1
140	3.86e-2	4.35e-2	6.14e-2	1.04e-1	1.58e-1		2.62e-1	5.07e-1	7.52e-1	9.48e-1
200	3.27e-2	3.73e-2	5.42e-2	9.20e-2	1.41e-1	1.77e-1	2.31e-1	4.36e-1	6.78e-1	9.43e-1
300	2.66e-2	3.06e-2	4.47e-2	7.88e-2	1.24e-1		2.04e-1	3.75e-1	5.84e-1	9.24e-1
500	1.96e-2	2.28e-2	3.43e-2	6.32e-2	1.02e-1	1.31e-1	1.71e-1	3.15e-1	4.76e-1	8.67e-1
1000	1.10e-2	1.30e-2	2.10e-2	4.24e-2	7.19e-2	9.78e-2	1.31e-1	2.49e-1	3.71e-1	7.08e-1

Average depth (mean range) in Å of D implanted in Be  
 ne=19, na=10

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	60°	65°	75°	80°	85°
10	4.20e+0									
11	4.53e+0	4.47e+0	4.31e+0	4.06e+0	3.87e+0		3.63e+0	3.37e+0	3.24e+0	3.12e+0
12	4.85e+0	4.78e+0	4.61e+0	4.35e+0	4.14e+0	4.01e+0	3.89e+0	3.62e+0	3.48e+0	3.38e+0
13	5.16e+0	5.08e+0	4.90e+0	4.62e+0	4.40e+0	4.26e+0	4.14e+0	3.86e+0	3.72e+0	3.60e+0
14	5.47e+0	5.39e+0	5.19e+0	4.88e+0	4.66e+0		4.39e+0	4.09e+0	3.95e+0	3.82e+0
15	5.77e+0	5.68e+0	5.47e+0	5.15e+0	4.90e+0	4.75e+0	4.62e+0	4.32e+0	4.17e+0	4.04e+0
17	6.36e+0	6.26e+0	6.02e+0	5.66e+0	5.39e+0		5.08e+0	4.76e+0	4.59e+0	4.44e+0
20	7.21e+0	7.10e+0	6.82e+0	6.39e+0	6.08e+0	5.91e+0	5.74e+0	5.39e+0	5.21e+0	5.02e+0
25	8.61e+0	8.48e+0	8.11e+0	7.59e+0	7.20e+0	6.99e+0	6.79e+0	6.37e+0	6.17e+0	5.96e+0
30	9.95e+0	9.79e+0	9.36e+0	8.74e+0	8.29e+0	8.11e+0	7.81e+0	7.36e+0	7.09e+0	6.84e+0
40	1.26e+1	1.24e+1	1.18e+1	1.10e+1	1.04e+1		9.78e+0	9.19e+0	8.86e+0	8.59e+0
50	1.52e+1	1.49e+1	1.42e+1	1.31e+1	1.24e+1	1.20e+1	1.17e+1	1.10e+1	1.06e+1	1.02e+1
70	2.02e+1	1.98e+1	1.89e+1	1.74e+1	1.63e+1		1.54e+1	1.45e+1	1.41e+1	1.34e+1
100	2.76e+1	2.71e+1	2.57e+1	2.37e+1	2.21e+1	2.15e+1	2.07e+1	1.94e+1	1.88e+1	1.85e+1
140	3.75e+1	3.69e+1	3.47e+1	3.18e+1	2.97e+1		2.77e+1	2.60e+1	2.52e+1	2.42e+1
200	5.22e+1	5.12e+1	4.82e+1	4.41e+1	4.08e+1	3.91e+1	3.79e+1	3.52e+1	3.43e+1	3.33e+1
300	7.68e+1	7.51e+1	7.07e+1	6.40e+1	5.88e+1		5.44e+1	5.03e+1	4.90e+1	4.85e+1
500	1.26e+2	1.24e+2	1.15e+2	1.03e+2	9.47e+1	9.06e+1	8.66e+1	7.94e+1	7.69e+1	7.60e+1
1000	2.51e+2	2.45e+2	2.26e+2	1.99e+2	1.81e+2	1.69e+2	1.61e+2	1.45e+2	1.39e+2	1.37e+2

## D → Be

D on Be, Maxwellian velocity distribution, sheath potential 3 kT  
 z1= 1, m1= 2.01, z2= 4, m2= 9.01, sbe=3.38 eV, rho=1.80 g/cm \*\*3  
 ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program : testvmcx  
 ne=12

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
2	2.64e-4	4.14e-5	1.57e+0	3.82e-1	1.52e-1	3.98e+0	3.98e+0
2.5	1.00e-3	1.40e-4	1.75e+0	3.61e-1	1.44e-1	4.98e+0	4.75e+0
3	2.19e-3	2.74e-4	1.87e+0	3.42e-1	1.35e-1	5.94e+0	5.48e+0
4	6.45e-3	7.50e-4	2.32e+0	3.11e-1	1.21e-1	7.80e+0	6.87e+0
5	1.15e-2	1.22e-3	2.64e+0	2.87e-1	1.10e-1	9.60e+0	8.17e+0
7	2.10e-2	1.92e-3	3.21e+0	2.57e-1	9.63e-2	1.31e+1	1.07e+1
10	3.19e-2	2.47e-3	3.86e+0	2.32e-1	8.55e-2	1.84e+1	1.43e+1
20	4.78e-2	2.80e-3	5.86e+0	1.85e-1	6.44e-2	3.49e+1	2.60e+1
50	5.65e-2	1.96e-3	8.69e+0	1.35e-1	4.48e-2	8.29e+1	6.05e+1
100	5.14e-2	1.22e-3	1.19e+1	1.01e-1	3.11e-2	1.55e+2	1.18e+2
200	3.96e-2	6.26e-4	1.58e+1	6.67e-2	1.90e-2	2.85e+2	2.31e+2
500	2.35e-2	1.87e-4	1.98e+1	3.00e-2	6.91e-3	5.75e+2	5.48e+2
1000	1.45e-2	7.95e-5	2.74e+1	1.29e-2	2.69e-3	1.04e+3	1.03e+3
2000	8.34e-3	3.34e-5	4.00e+1	4.38e-3	8.29e-4	1.89e+3	1.82e+3

# D → Be

D on Be, Maxwellian energy distribution, sheath potential 0 kT,  $\alpha=0^\circ$   
 $z1=1$ ,  $m1=2.01$ ,  $z2=4$ ,  $m2=9.01$ ,  $sbe=3.38$  eV,  $\rho=1.80$  g/cm<sup>\*\*3</sup>  
 $ef=0.98$  eV,  $esb=1.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program : testvmcx  
ne=11

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
5	4.73e-4	1.10e-4	1.74e+0	2.29e-1	8.30e-2	2.72e+0	2.86e+0
7	1.36e-3	2.67e-4	2.06e+0	2.43e-1	8.13e-2	3.52e+0	3.93e+0
10	3.08e-3	5.18e-4	2.52e+0	2.45e-1	7.61e-2	4.66e+0	5.42e+0
20	9.32e-3	1.08e-3	3.45e+0	2.27e-1	6.28e-2	8.26e+0	9.86e+0
30	1.41e-2	1.29e-3	4.12e+0	2.07e-1	5.45e-2	1.19e+1	1.40e+1
40	1.81e-2	1.33e-3	4.41e+0	1.91e-1	4.85e-2	1.52e+1	1.80e+1
50	2.05e-2	1.34e-3	4.91e+0	1.81e-1	4.43e-2	1.84e+1	2.20e+1
100	2.73e-2	1.22e-3	6.69e+0	1.47e-1	3.31e-2	3.38e+1	4.12e+1
200	3.12e-2	8.30e-4	8.03e+0	1.15e-1	2.30e-2	6.04e+1	8.02e+1
500	2.75e-2	3.96e-4	1.08e+1	7.25e-2	1.21e-2	1.26e+2	1.94e+2
1000	2.37e-2	1.92e-4	1.22e+1	4.82e-2	6.35e-3	1.98e+2	3.75e+2

D on Be, Maxwellian energy distribution, sheath potential 0 kT,  $\alpha=60^\circ$   
ne=10

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
5	1.22e-3	5.06e-4	3.12e+0	5.78e-1	4.08e-1	5.29e+0	1.71e+0
7	4.08e-3	1.41e-3	3.62e+0	6.17e-1	4.11e-1	6.99e+0	2.67e+0
10	1.08e-2	2.94e-3	4.07e+0	6.31e-1	3.93e-1	9.32e+0	4.12e+0
20	4.07e-2	7.48e-3	5.50e+0	6.11e-1	3.34e-1	1.63e+1	8.45e+0
30	6.91e-2	1.00e-2	6.54e+0	5.66e-1	2.86e-1	2.28e+1	1.22e+1
50	1.13e-1	1.16e-2	7.74e+0	5.14e-1	2.39e-1	3.49e+1	1.86e+1
100	1.61e-1	1.03e-2	9.62e+0	4.36e-1	1.84e-1	6.35e+1	3.33e+1
200	1.89e-1	7.79e-3	1.23e+1	3.69e-1	1.47e-1	1.19e+2	5.98e+1
500	1.77e-1	3.94e-3	1.68e+1	2.94e-1	9.81e-2	2.52e+2	1.35e+2
1000	1.45e-1	2.23e-3	2.32e+1	2.36e-1	6.47e-2	4.14e+2	2.46e+2

D on Be, Maxwellian energy distribution, sheath potential 3 kT,  $\alpha=0^\circ$   
 $z1=1$ ,  $m1=2.01$ ,  $z2=4$ ,  $m2=9.01$ ,  $sbe=3.38$  eV,  $\rho=1.80$  g/cm<sup>\*\*3</sup>  
 $ef=0.98$  eV,  $esb=1.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program : testvmcx  
ne=10

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
5	5.49e-3	4.59e-4	1.88e+0	2.39e-1	7.59e-2	7.14e+0	7.92e+0
7	1.14e-2	9.23e-4	2.54e+0	2.14e-1	6.67e-2	9.82e+0	1.04e+1
10	1.85e-2	1.37e-3	3.34e+0	1.89e-1	5.86e-2	1.39e+1	1.39e+1
20	2.96e-2	1.60e-3	4.85e+0	1.52e-1	4.52e-2	2.67e+1	2.53e+1
30	3.21e-2	1.47e-3	6.19e+0	1.32e-1	3.87e-2	3.95e+1	3.64e+1
50	3.53e-2	1.18e-3	7.49e+0	1.09e-1	3.09e-2	6.38e+1	5.88e+1
100	3.31e-2	6.96e-4	9.46e+0	7.95e-2	2.13e-2	1.20e+2	1.14e+2
200	2.78e-2	3.69e-4	1.19e+1	4.87e-2	1.18e-2	2.18e+2	2.26e+2
500	1.70e-2	1.18e-4	1.57e+1	1.96e-2	4.12e-3	4.74e+2	5.52e+2
1000	1.14e-2	4.52e-5	1.79e+1	8.58e-3	1.65e-3	8.66e+2	1.04e+3

D on Be, Maxwellian energy distribution, sheath potential 3 kT,  $\alpha=60^\circ$   
ne=11

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
5	9.48e-3	1.07e-3	2.53e+0	3.11e-1	1.24e-1	9.01e+0	7.38e+0
7	1.84e-2	1.86e-3	3.17e+0	2.77e-1	1.08e-1	1.23e+1	9.67e+0
10	3.10e-2	2.61e-3	3.78e+0	2.47e-1	9.39e-2	1.71e+1	1.29e+1
15	4.26e-2	3.03e-3	4.80e+0	2.19e-1	8.08e-2	2.49e+1	1.82e+1
20	4.96e-2	3.09e-3	5.59e+0	2.01e-1	7.34e-2	3.28e+1	2.33e+1
30	6.06e-2	3.01e-3	6.73e+0	1.78e-1	6.33e-2	4.82e+1	3.33e+1
50	6.00e-2	2.29e-3	8.60e+0	1.49e-1	5.15e-2	7.79e+1	5.34e+1
100	5.74e-2	1.60e-3	1.26e+1	1.14e-1	3.70e-2	1.47e+2	1.03e+2
200	4.54e-2	7.30e-4	1.45e+1	7.68e-2	2.23e-2	2.62e+2	2.02e+2
500	2.74e-2	2.44e-4	2.01e+1	3.79e-2	9.15e-3	5.44e+2	4.86e+2
1000	1.66e-2	1.08e-4	2.92e+1	1.61e-2	3.47e-3	9.71e+2	9.08e+2

# $T \rightarrow Be$

Sputtering yield of Be by T  
 $z1 = 1$ ,  $m1 = 3.02$ ,  $z2 = 4$ ,  $m2 = 9.01$ ,  $sbe = 3.38$  eV,  $\rho = 1.80$  g/cm\*\*3  
 $ef = 0.98$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program : trvnc  
ne=15, na=10

$E_0$ (eV)	0°	15°	30°	45°	55°	60°	65°	75°	80°	85°
10	1.78e-5	2.56e-5	3.89e-5	4.74e-5	4.98e-5	4.92e-5	4.55e-5	3.43e-5	2.76e-5	2.12e-5
11	7.08e-5	1.00e-4	1.49e-4	1.81e-4	1.96e-4		1.82e-4	1.32e-4	1.05e-4	7.89e-5
12	1.77e-4	2.44e-4	3.77e-4	4.92e-4	5.30e-4	5.47e-4	5.05e-4	3.65e-4	2.66e-4	2.00e-4
13	3.49e-4	4.72e-4	7.42e-4	1.02e-3	1.15e-3		1.09e-3	7.68e-4	5.68e-4	4.10e-4
15	9.03e-4	1.20e-3	1.98e-3	2.92e-3	3.46e-3	3.58e-3	3.43e-3	2.37e-3	1.61e-3	1.07e-3
17	1.74e-3	2.28e-3	3.71e-3	6.05e-3	7.30e-3		7.59e-3	4.98e-3	3.16e-3	1.95e-3
20	3.43e-3	4.39e-3	7.28e-3	1.24e-2	1.60e-2	1.72e-2	1.70e-2	1.06e-2	6.07e-3	3.28e-3
25	6.83e-3	8.60e-3	1.42e-2	2.54e-2	3.52e-2	3.84e-2	3.87e-2	2.31e-2	1.19e-2	5.34e-3
30	1.03e-2	1.29e-2	2.12e-2	3.96e-2	5.62e-2		6.36e-2	3.85e-2	1.88e-2	7.22e-3
50	2.11e-2	2.56e-2	4.26e-2	8.41e-2	1.28e-1		1.61e-1	1.10e-1	4.78e-2	1.09e-2
100	3.27e-2	4.02e-2	6.88e-2	1.33e-1	2.10e-1		2.98e-1	2.73e-1	1.36e-1	1.72e-2
200	4.00e-2	4.94e-2	8.17e-2	1.55e-1	2.44e-1	3.25e-1	3.73e-1	4.63e-1	3.24e-1	3.82e-2
300	4.14e-2	5.06e-2	8.22e-2	1.55e-1	2.38e-1		3.78e-1	5.30e-1	4.67e-1	7.57e-2
500	4.05e-2	4.85e-2	7.70e-2	1.41e-1	2.22e-1	2.66e-1	3.56e-1	5.61e-1	5.99e-1	1.83e-1
1000	3.38e-2	3.94e-2	6.09e-2	1.12e-1	1.73e-1	2.13e-1	2.88e-1	5.01e-1	6.42e-1	4.52e-1

Sputtered energy of Be by T  
ne=15, na=10

$E_0$ (eV)	0°	15°	30°	45°	55°	60°	65°	75°	80°	85°
10	1.09e-6	1.86e-6	3.57e-6	5.18e-6	5.82e-6	6.06e-6	5.83e-6	4.72e-6	3.89e-6	3.07e-6
11	4.65e-6	7.58e-6	1.40e-5	2.04e-5	2.40e-5		2.44e-5	1.90e-5	1.52e-5	1.17e-5
12	1.22e-5	1.92e-5	3.63e-5	5.67e-5	6.75e-5	7.26e-5	7.05e-5	5.40e-5	4.03e-5	3.08e-5
13	2.51e-5	3.82e-5	7.37e-5	1.19e-4	1.53e-4		1.58e-4	1.17e-4	8.86e-5	6.52e-5
15	6.76e-5	1.01e-4	2.02e-4	3.59e-4	4.73e-4	5.17e-4	5.21e-4	3.86e-4	2.74e-4	1.82e-4
17	1.33e-4	1.93e-4	3.85e-4	7.52e-4	1.03e-3		1.19e-3	8.54e-4	5.66e-4	3.58e-4
20	2.64e-4	3.73e-4	7.46e-4	1.56e-3	2.29e-3	2.62e-3	2.75e-3	1.93e-3	1.16e-3	6.54e-4
25	5.19e-4	7.19e-4	1.40e-3	3.09e-3	4.93e-3	5.86e-3	6.30e-3	4.40e-3	2.45e-3	1.14e-3
30	7.78e-4	1.04e-3	2.03e-3	4.60e-3	7.58e-3		1.02e-2	7.44e-3	3.92e-3	1.58e-3
50	1.42e-3	1.84e-3	3.38e-3	8.04e-3	1.45e-2		2.20e-2	1.89e-2	9.22e-3	2.30e-3
100	1.69e-3	2.13e-3	4.07e-3	9.35e-3	1.69e-2		2.86e-2	3.29e-2	1.94e-2	2.88e-3
200	1.42e-3	1.83e-3	3.48e-3	7.97e-3	1.39e-2		2.42e-2	3.61e-2	2.93e-2	4.46e-3
300	1.16e-3	1.50e-3	2.84e-3	6.41e-3	1.10e-2		1.95e-2	3.19e-2	3.19e-2	6.81e-3
500	8.22e-4	1.04e-3	2.02e-3	4.49e-3	7.99e-3		1.41e-2	2.48e-2	2.93e-2	1.11e-2
1000	4.28e-4	5.57e-4	1.08e-3	2.42e-3	4.34e-3		8.14e-3	1.53e-2	2.05e-2	1.59e-2

# $T \rightarrow Be$

Particle reflection coefficient of T backscattered from Be  
 $z1 = 1$ ,  $m1 = 3.02$ ,  $z2 = 4$ ,  $m2 = 9.01$ ,  $sbe = 3.38$  eV,  $\rho = 1.80$  g/cm<sup>3</sup>  
 $ef = 0.98$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program : trvmc  
ne=15, na=10

$E_0$ (eV)	0°	15°	30°	45°	55°	60°	65°	75°	80°	85°
10	2.06e-1	2.33e-1	3.15e-1	4.70e-1	6.12e-1	6.89e-1	7.66e-1	8.90e-1	9.28e-1	9.48e-1
11	2.04e-1	2.30e-1	3.10e-1	4.65e-1	6.09e-1		7.67e-1	8.97e-1	9.36e-1	9.56e-1
12	2.01e-1	2.26e-1	3.04e-1	4.58e-1	6.04e-1	6.85e-1	7.67e-1	9.02e-1	9.42e-1	9.62e-1
13	1.98e-1	2.22e-1	2.98e-1	4.51e-1	5.98e-1		7.65e-1	9.05e-1	9.46e-1	9.66e-1
15	1.90e-1	2.12e-1	2.85e-1	4.34e-1	5.83e-1	6.68e-1	7.58e-1	9.08e-1	9.52e-1	9.73e-1
17	1.82e-1	2.04e-1	2.73e-1	4.17e-1	5.66e-1		7.47e-1	9.09e-1	9.56e-1	9.77e-1
20	1.72e-1	1.92e-1	2.57e-1	3.94e-1	5.42e-1	6.33e-1	7.31e-1	9.08e-1	9.59e-1	9.81e-1
25	1.59e-1	1.77e-1	2.37e-1	3.63e-1	5.05e-1	5.96e-1	7.01e-1	9.00e-1	9.60e-1	9.86e-1
30	1.49e-1	1.65e-1	2.20e-1	3.38e-1	4.74e-1		6.71e-1	8.90e-1	9.59e-1	9.88e-1
50	1.23e-1	1.37e-1	1.83e-1	2.79e-1	3.93e-1		5.76e-1	8.41e-1	9.49e-1	9.92e-1
100	9.57e-2	1.07e-1	1.44e-1	2.24e-1	3.12e-1		4.59e-1	7.26e-1	9.01e-1	9.92e-1
200	7.27e-2	8.20e-2	1.14e-1	1.83e-1	2.59e-1		3.78e-1	5.91e-1	7.96e-1	9.85e-1
300	6.04e-2	6.85e-2	9.85e-2	1.61e-1	2.35e-1		3.46e-1	5.32e-1	7.16e-1	9.71e-1
500	4.62e-2	5.27e-2	7.92e-2	1.36e-1	2.05e-1		3.09e-1	4.78e-1	6.27e-1	9.29e-1
1000	2.86e-2	3.39e-2	5.47e-2	1.03e-1	1.65e-1		2.63e-1	4.22e-1	5.45e-1	8.14e-1

Energy reflection coefficient of T backscattered from Be  
ne=15, na=10

$E_0$ (eV)	0°	15°	30°	45°	55°	60°	65°	75°	80°	85°
10	4.43e-2	5.68e-2	9.98e-2	1.99e-1	3.11e-1	3.80e-1	4.56e-1	6.08e-1	6.64e-1	6.98e-1
11	4.48e-2	5.69e-2	9.91e-2	1.99e-1	3.13e-1		4.65e-1	6.26e-1	6.87e-1	7.23e-1
12	4.49e-2	5.66e-2	9.77e-2	1.97e-1	3.13e-1	3.88e-1	4.71e-1	6.41e-1	7.06e-1	7.44e-1
13	4.47e-2	5.59e-2	9.58e-2	1.94e-1	3.12e-1		4.75e-1	6.54e-1	7.21e-1	7.62e-1
15	4.38e-2	5.41e-2	9.19e-2	1.87e-1	3.06e-1	3.86e-1	4.78e-1	6.72e-1	7.47e-1	7.90e-1
17	4.25e-2	5.22e-2	8.77e-2	1.80e-1	2.98e-1		4.76e-1	6.84e-1	7.65e-1	8.12e-1
20	4.05e-2	4.93e-2	8.21e-2	1.68e-1	2.85e-1	3.68e-1	4.69e-1	6.96e-1	7.86e-1	8.37e-1
25	3.75e-2	4.53e-2	7.45e-2	1.52e-1	2.62e-1	3.44e-1	4.50e-1	7.02e-1	7.07e-1	8.66e-1
30	3.51e-2	4.23e-2	6.86e-2	1.39e-1	2.42e-1		4.29e-1	7.01e-1	8.19e-1	8.85e-1
50	2.87e-2	3.43e-2	5.49e-2	1.08e-1	1.88e-1		3.52e-1	6.63e-1	8.30e-1	9.21e-1
100	2.21e-2	2.62e-2	4.15e-2	8.14e-2	1.37e-1		2.55e-1	5.44e-1	7.84e-1	9.43e-1
200	1.65e-2	1.98e-2	3.24e-2	6.42e-2	1.07e-1		1.93e-1	4.02e-1	6.57e-1	9.41e-1
300	1.37e-2	1.63e-2	2.75e-2	5.53e-2	9.51e-2		1.70e-1	3.42e-1	5.61e-1	9.23e-1
500	1.01e-2	1.23e-2	2.15e-2	4.52e-2	8.00e-2		1.45e-1	2.89e-1	4.55e-1	8.63e-1
1000	5.95e-3	7.51e-3	1.39e-2	3.18e-2	5.96e-2		1.14e-1	2.35e-1	3.58e-1	7.04e-1

Average depth (mean range) in Å of T implanted in Be  
ne=15, na=10

$E_0$ (eV)	0°	15°	30°	45°	55°	60°	65°	75°	80°	85°
10	3.73e+0	3.66e+0	3.47e+0	3.18e+0	2.94e+0	2.77e+0	2.64e+0	2.29e+0	2.12e+0	1.99e+0
11	4.04e+0	3.96e+0	3.77e+0	3.46e+0	3.21e+0		2.90e+0	2.54e+0	2.36e+0	2.22e+0
12	4.34e+0	4.26e+0	4.05e+0	3.72e+0	3.46e+0	3.29e+0	3.14e+0	2.77e+0	2.59e+0	2.44e+0
13	4.63e+0	4.54e+0	4.32e+0	3.97e+0	3.70e+0		3.37e+0	3.00e+0	2.81e+0	2.65e+0
15	5.19e+0	5.10e+0	4.84e+0	4.46e+0	4.16e+0	3.98e+0	3.81e+0	3.42e+0	3.21e+0	3.04e+0
17	5.74e+0	5.63e+0	5.34e+0	4.92e+0	4.60e+0		4.24e+0	3.82e+0	3.59e+0	3.40e+0
20	6.53e+0	6.41e+0	6.08e+0	5.59e+0	5.22e+0	5.01e+0	4.81e+0	4.38e+0	4.16e+0	3.93e+0
25	7.82e+0	7.66e+0	7.24e+0	6.65e+0	6.20e+0	5.98e+0	5.74e+0	5.24e+0	4.97e+0	4.73e+0
30	9.07e+0	8.88e+0	8.39e+0	7.68e+0	7.16e+0		6.63e+0	6.07e+0	5.75e+0	5.47e+0
50	1.39e+1	1.36e+1	1.28e+1	1.16e+1	1.08e+1		1.00e+1	9.15e+0	8.75e+0	8.26e+0
100	2.55e+1	2.50e+1	2.34e+1	2.11e+1	1.94e+1		1.78e+1	1.64e+1	1.57e+1	1.47e+1
200	4.88e+1	4.76e+1	4.44e+1	3.97e+1	3.63e+1		3.31e+1	3.03e+1	2.93e+1	2.83e+1
300	7.25e+1	7.07e+1	6.58e+1	5.86e+1	5.32e+1		4.82e+1	4.40e+1	4.23e+1	4.09e+1
500	1.22e+2	1.18e+2	1.10e+2	9.68e+1	8.74e+1		7.85e+1	7.10e+1	6.81e+1	6.59e+1
1000	2.49e+2	2.42e+2	2.22e+2	1.94e+2	1.73e+2		1.53e+2	1.36e+2	1.29e+2	1.25e+2

### $^3\text{He} \rightarrow \text{Be}$

Sputtering yield of Be by  $^3\text{He}$

$z1=2$ ,  $m1=3.02$ ,  $z2=4$ ,  $m2=9.01$ ,  $sbe=3.38$  eV,  $\rho=1.80$  g/cm $^{**3}$   
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program : trvmc  
ne= 7, na= 1

$E_0$ (eV)	$0^\circ$
20	3.29e-3
30	1.61e-2
50	4.07e-2
100	7.04e-2
200	9.38e-2
500	9.87e-2
1000	9.56e-2

Sputtered energy of Be by  $^3\text{He}$   
ne= 7, na= 1

$E_0$ (eV)	$0^\circ$
20	2.49e-4
30	1.19e-3
50	2.72e-3
100	3.71e-3
200	3.40e-3
500	2.07e-3
1000	1.29e-3

Particle reflection coefficient of  $^3\text{He}$  backscattered from Be

$z1=2$ ,  $m1=3.02$ ,  $z2=4$ ,  $m2=9.01$ ,  $sbe=3.38$  eV,  $\rho=1.80$  g/cm $^{**3}$   
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program : trvmc  
ne= 7, na= 1

$E_0$ (eV)	$0^\circ$
20	2.74e-1
30	2.20e-1
50	1.72e-1
100	1.26e-1
200	9.36e-2
500	6.55e-2
1000	4.21e-2

Energy reflection coefficient of  $^3\text{He}$  backscattered from Be  
ne= 7, na= 1

$E_0$ (eV)	$0^\circ$
20	6.57e-2
30	5.25e-2
50	4.00e-2
100	2.82e-2
200	2.02e-2
500	1.40e-2
1000	8.52e-3

Average depth (mean range) in Å of  $^3\text{He}$  implanted in Be  
ne= 7, na= 1

$E_0$ (eV)	$0^\circ$
20	4.25e+0
30	5.76e+0
50	8.52e+0
100	1.49e+1
200	2.70e+1
500	6.20e+1
1000	1.21e+2

# $^4\text{He} \rightarrow \text{Be}$

Sputtering yield of Be by  $^4\text{He}$   
 $z1 = 2$ ,  $m1 = 4.00$ ,  $z2 = 4$ ,  $m2 = 9.01$ ,  $sbe = 3.38$  eV,  $\rho = 1.80$  g/cm\*\*3  
 $ef = 0.50$  eV,  $esb = 0.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program : trvmc  
ne=23, na= 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	3.34e-6	8.39e-6	1.97e-5	2.03e-5	1.82e-5	1.92e-5	8.86e-6	2.04e-6	
11	1.59e-5	3.46e-5	6.56e-5	7.58e-5	8.52e-5	9.01e-5	3.65e-5	7.69e-6	
12	4.18e-5	7.72e-5	1.42e-4	1.95e-4	2.57e-4	2.88e-4	1.09e-4	2.18e-5	
13	8.92e-5	2.81e-4	4.58e-4	6.51e-4	6.89e-4	2.39e-4	4.23e-5	1.00e-6	
15	3.08e-4	4.80e-4	8.95e-4	1.70e-3	2.48e-3	2.44e-3	7.39e-4	1.27e-4	
17	8.21e-4	1.21e-3	2.32e-3	4.43e-3	6.16e-3	5.82e-3	1.64e-3	2.58e-4	2.33e-6
20	2.27e-3	3.25e-3	6.23e-3	1.20e-2	1.59e-2	1.40e-2	3.68e-3	5.39e-4	4.80e-6
25	6.28e-3	8.90e-3	1.68e-2	3.19e-2	4.16e-2	3.50e-2	8.72e-3	1.28e-3	8.40e-6
30	1.16e-2	1.57e-2	3.02e-2	5.75e-2	7.30e-2	6.24e-2	1.72e-2	2.35e-3	2.00e-5
40	2.35e-2	3.11e-2	5.76e-2	1.10e-1	1.41e-1	1.27e-1	3.68e-2	5.16e-3	3.31e-5
50	3.42e-2	4.47e-2	8.12e-2	1.56e-1	2.05e-1	1.94e-1	6.22e-2	9.25e-3	5.43e-5
70	5.03e-2	6.53e-2	1.17e-1	2.24e-1	3.04e-1	3.16e-1	1.25e-1	2.12e-2	1.05e-4
100	6.76e-2	8.77e-2	1.54e-1	2.90e-1	4.05e-1	4.66e-1	2.35e-1	4.84e-2	2.49e-4
140	8.31e-2	1.04e-1	1.82e-1	3.39e-1	4.85e-1	5.98e-1	3.88e-1	1.04e-1	5.83e-4
200	9.60e-2	1.20e-1	2.01e-1	3.71e-1	5.48e-1	7.23e-1	5.99e-1	2.11e-1	1.69e-3
300	1.06e-1	1.30e-1	2.14e-1	3.89e-1	5.83e-1	8.21e-1	8.40e-1	4.34e-1	6.74e-3
400	1.09e-1	1.34e-1	2.18e-1	3.93e-1	5.90e-1	8.56e-1	9.94e-1	6.39e-1	1.68e-2
500	1.10e-1	1.36e-1	2.12e-1	3.88e-1	5.86e-1	8.64e-1	1.09e-0	8.12e-1	3.60e-2
700	1.09e-1	1.30e-1	2.06e-1	3.66e-1	5.61e-1	8.49e-1	1.18e-0	1.06e-0	1.06e-1
1000	1.04e-1	1.25e-1	1.89e-1	3.37e-1	5.21e-1	8.18e-1	1.21e-0	1.24e-0	2.77e-1
2000	8.70e-2	1.00e-1	1.48e-1	2.62e-1	4.03e-1	6.67e-1	1.10e-0	1.36e-0	9.00e-1
5000	5.93e-2	6.60e-2	9.39e-2	1.58e-1	2.38e-1	4.08e-1	7.66e-1	1.09e-0	1.37e-0
10000	4.08e-2	4.52e-2	6.05e-2	9.41e-2	1.42e-1	2.38e-1	4.87e-1	7.53e-1	1.23e-0

Sputtered energy of Be by  $^4\text{He}$   
ne=23, na= 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	1.61e-7	4.95e-7	1.63e-6	2.12e-6	2.20e-6	2.72e-6	1.40e-6	3.30e-7	
11	8.90e-7	2.37e-6	5.87e-6	8.26e-6	1.09e-5	1.29e-5	5.78e-6	1.24e-6	
12	2.60e-6	5.76e-6	1.35e-5	2.27e-5	3.45e-5	4.23e-5	1.80e-5	3.81e-6	
13	5.89e-6	1.19e-5	2.78e-5	5.59e-5	9.05e-5	1.07e-4	4.26e-5	7.71e-6	1.57e-7
15	2.21e-5	4.04e-5	9.59e-5	2.24e-4	3.67e-4	4.05e-4	1.38e-4	2.48e-5	
17	6.21e-5	1.06e-4	2.57e-4	6.06e-4	9.63e-4	1.03e-3	3.28e-4	5.44e-5	4.45e-7
20	1.75e-4	2.92e-4	7.08e-4	1.69e-3	2.60e-3	2.62e-3	7.86e-4	1.21e-4	1.09e-6
25	4.72e-4	7.73e-4	1.87e-3	4.49e-3	6.94e-3	6.81e-3	1.98e-3	3.04e-4	1.70e-6
30	8.45e-4	1.31e-3	3.21e-3	7.87e-3	1.19e-2	1.22e-2	3.75e-3	5.73e-4	
40	1.60e-3	2.38e-3	5.46e-3	1.36e-2	2.14e-2	2.36e-2	8.37e-3	1.25e-3	6.64e-6
50	2.17e-3	3.11e-3	7.01e-3	1.75e-2	2.83e-2	3.34e-2	1.35e-2	2.12e-3	9.91e-6
70	2.82e-3	3.98e-3	8.65e-3	2.15e-2	3.57e-2	4.66e-2	2.38e-2	4.48e-3	1.91e-5
100	3.22e-3	4.52e-3	9.56e-3	2.30e-2	3.89e-2	5.54e-2	3.69e-2	8.80e-3	3.89e-5
140	3.39e-3	4.55e-3	9.58e-3	2.28e-2	3.84e-2	5.70e-2	4.90e-2	1.58e-2	8.24e-5
200	3.19e-3	4.41e-3	8.88e-3	2.07e-2	3.55e-2	5.53e-2	5.89e-2	2.55e-2	2.22e-4
300	2.83e-3	3.79e-3	7.67e-3	1.76e-2	3.03e-2	4.95e-2	6.25e-2	3.85e-2	7.26e-4
400	2.46e-3	3.43e-3	6.71e-3	1.55e-2	2.67e-2	4.40e-2	6.01e-2	4.58e-2	1.55e-3
500	2.27e-3	3.09e-3	5.95e-3	1.36e-2	2.35e-2	3.98e-2	5.82e-2	4.99e-2	2.90e-3
700	1.80e-3	2.41e-3	4.90e-3	1.10e-2	1.91e-2	3.25e-2	5.14e-2	5.13e-2	6.64e-3
1000	1.39e-3	1.94e-3	3.72e-3	8.61e-3	1.50e-2	2.67e-2	4.35e-2	4.75e-2	1.35e-2
2000	7.58e-4	1.02e-3	2.03e-3	4.74e-3	8.54e-3	1.61e-2	2.84e-2	3.53e-2	2.48e-2
5000	2.80e-4	3.74e-4	7.54e-4	1.79e-3	3.26e-3	6.47e-3	1.30e-2	1.88e-2	2.08e-2
10000	1.18e-4	1.59e-4	3.28e-4	7.12e-4	1.32e-3	2.53e-3	6.01e-3	9.39e-3	1.28e-2

# $^4\text{He} \rightarrow \text{Be}$

Particle reflection coefficient of  $^4\text{He}$  backscattered from Be  
 $z1=2$ ,  $m1=4.00$ ,  $z2=4$ ,  $m2=9.01$ ,  $sbe=3.38$  eV,  $\rho_{ee}=1.80$  g/cm\*\*3  
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program : trvmc  
ne=23, na= 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	3.15E-1	3.55E-1	4.62E-1	6.44E-1	7.88E-1	9.20E-1	9.90E-1	9.99E-1	1.00E+0
11	3.05E-1	3.44E-1	4.49E-1	6.32E-1	7.79E-1	9.16E-1	9.90E-1	9.99E-1	1.00E+0
12	2.94E-1	3.32E-1	4.36E-1	6.20E-1	7.70E-1	9.12E-1	9.89E-1	9.99E-1	1.00E+0
13	2.84E-1	3.20E-1	4.24E-1	6.08E-1	7.61E-1	9.08E-1	9.89E-1	9.99E-1	1.00E+0
15	2.64E-1	2.98E-1	3.99E-1	5.85E-1	7.42E-1	8.99E-1	9.88E-1	9.99E-1	1.00E+0
17	2.47E-1	2.79E-1	3.76E-1	5.61E-1	7.23E-1	8.90E-1	9.87E-1	9.99E-1	1.00E+0
20	2.25E-1	2.54E-1	3.47E-1	5.29E-1	6.96E-1	8.74E-1	9.85E-1	9.99E-1	1.00E+0
25	1.97E-1	2.28E-1	3.08E-1	4.82E-1	6.52E-1	8.47E-1	9.81E-1	9.98E-1	1.00E+0
30	1.77E-1	2.00E-1	2.77E-1	4.41E-1	6.12E-1	8.21E-1	9.76E-1	9.98E-1	1.00E+0
40	1.50E-1	1.69E-1	2.36E-1	3.81E-1	5.48E-1	7.69E-1	9.65E-1	9.97E-1	1.00E+0
50	1.32E-1	1.50E-1	2.08E-1	3.40E-1	4.98E-1	7.21E-1	9.52E-1	9.96E-1	1.00E+0
70	1.10E-1	1.25E-1	1.75E-1	2.85E-1	4.25E-1	6.42E-1	9.21E-1	9.92E-1	1.00E+0
100	9.22E-2	1.05E-1	1.48E-1	2.44E-1	3.59E-1	5.58E-1	8.68E-1	9.82E-1	1.00E+0
140	7.91E-2	8.69E-2	1.26E-1	2.10E-1	3.08E-1	4.87E-1	8.00E-1	9.64E-1	1.00E+0
200	6.61E-2	7.43E-2	1.09E-1	1.82E-1	2.74E-1	4.19E-1	7.13E-1	9.27E-1	1.00E+0
300	5.40E-2	6.34E-2	9.14E-2	1.58E-1	2.37E-1	3.68E-1	6.21E-1	8.57E-1	9.99E-1
400	4.63E-2	5.55E-2	8.12E-2	1.42E-1	2.18E-1	3.37E-1	5.62E-1	7.93E-1	9.97E-1
500	4.17E-2	4.99E-2	7.43E-2	1.34E-1	2.05E-1	3.20E-1	5.26E-1	7.41E-1	9.93E-1
700	3.43E-2	4.10E-2	6.39E-2	1.17E-1	1.85E-1	2.95E-1	4.81E-1	6.63E-1	9.79E-1
1000	2.79E-2	3.31E-2	5.39E-2	1.03E-1	1.68E-1	2.71E-1	4.43E-1	6.00E-1	9.42E-1
2000	1.67E-2	2.05E-2	3.54E-2	7.54E-2	1.31E-1	2.26E-1	3.86E-1	5.15E-1	8.05E-1
5000	6.59E-3	8.27E-3	1.62E-2	4.10E-2	8.21E-2	1.66E-1	3.20E-1	4.40E-1	6.43E-1
10000	2.86E-3	3.54E-3	6.96E-3	2.06E-2	4.80E-2	1.14E-1	2.63E-1	3.85E-1	5.69E-1

Energy reflection coefficient of  $^4\text{He}$  backscattered from Be  
ne=23, na= 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	4.87E-2	6.66E-2	1.24E-1	2.50E-1	3.91E-1	5.85E-1	7.99E-1	8.86E-1	9.48E-1
11	4.76E-2	6.47E-2	1.21E-1	2.47E-1	3.88E-1	5.86E-1	8.03E-1	8.90E-1	9.52E-1
12	4.64E-2	6.27E-2	1.17E-1	2.43E-1	3.85E-1	5.86E-1	8.06E-1	8.94E-1	9.55E-1
13	4.51E-2	6.08E-2	1.14E-1	2.39E-1	3.82E-1	5.85E-1	8.09E-1	8.98E-1	9.58E-1
15	4.26E-2	5.70E-2	1.08E-1	2.30E-1	3.74E-1	5.81E-1	8.13E-1	9.03E-1	9.62E-1
17	4.02E-2	5.34E-2	1.01E-1	2.21E-1	3.66E-1	5.76E-1	8.15E-1	9.07E-1	9.65E-1
20	3.70E-2	4.88E-2	9.29E-2	2.07E-1	3.51E-1	5.66E-1	8.17E-1	9.11E-1	9.68E-1
25	3.28E-2	4.28E-2	8.12E-2	1.86E-1	3.27E-1	5.48E-1	8.16E-1	9.16E-1	9.72E-1
30	2.97E-2	3.85E-2	7.21E-2	1.68E-1	3.04E-1	5.28E-1	8.12E-1	9.18E-1	9.78E-1
40	2.53E-2	3.21E-2	5.98E-2	1.40E-1	2.64E-1	4.88E-1	7.99E-1	9.20E-1	9.77E-1
50	2.21E-2	2.83E-2	5.18E-2	1.21E-1	2.33E-1	4.49E-1	7.83E-1	9.18E-1	9.78E-1
70	1.85E-2	2.33E-2	4.23E-2	9.73E-2	1.90E-1	3.85E-1	7.46E-1	9.11E-1	9.79E-1
100	1.55E-2	1.94E-2	3.47E-2	7.91E-2	1.51E-1	3.16E-1	6.85E-1	8.94E-1	9.79E-1
140	1.30E-2	1.60E-2	2.92E-2	6.62E-2	1.24E-1	2.60E-1	6.10E-1	8.64E-1	9.79E-1
200	1.10E-2	1.38E-2	2.50E-2	5.56E-2	1.05E-1	2.11E-1	5.16E-1	8.13E-1	9.77E-1
300	9.04E-3	1.16E-2	2.05E-2	4.75E-2	8.75E-2	1.75E-1	4.20E-1	7.22E-1	9.73E-1
400	7.68E-3	1.00E-2	1.85E-2	4.15E-2	7.82E-2	1.55E-1	3.62E-1	6.43E-1	9.67E-1
500	6.94E-3	9.10E-3	1.67E-2	3.86E-2	7.29E-2	1.43E-1	3.24E-1	5.79E-1	9.59E-1
700	5.67E-3	7.40E-3	1.43E-2	3.35E-2	6.45E-2	1.29E-1	2.81E-1	4.88E-1	9.34E-1
1000	4.58E-3	5.91E-3	1.17E-2	2.93E-2	5.70E-2	1.14E-1	2.48E-1	4.16E-1	8.78E-1
2000	2.62E-3	3.49E-3	7.42E-3	1.99E-2	4.14E-2	8.85E-2	2.00E-1	3.21E-1	6.84E-1
5000	9.27E-4	1.28E-3	2.96E-3	9.22E-3	2.20E-2	5.48E-2	1.41E-1	2.36E-1	4.60E-1
10000	3.74E-4	4.89E-4	1.13E-3	3.92E-3	1.03E-2	3.01E-2	9.46E-2	1.74E-1	3.50E-1

Average depth (mean range) in Å of  $^4\text{He}$  in Be  
ne=23, na= 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	2.40E+0	2.30E+0	2.20E+0	2.10E+0	1.90E+0	1.70E+0	1.30E+0	1.10E+0	6.00E-1
11	2.60E+0	2.50E+0	2.40E+0	2.20E+0	2.00E+0	1.80E+0	1.50E+0	1.20E+0	7.00E-1
12	2.80E+0	2.70E+0	2.60E+0	2.40E+0	2.20E+0	1.90E+0	1.60E+0	1.30E+0	8.00E-1
13	2.90E+0	2.90E+0	2.70E+0	2.50E+0	2.30E+0	2.10E+0	1.70E+0	1.40E+0	9.00E-1
15	3.30E+0	3.20E+0	3.10E+0	2.80E+0	2.60E+0	2.30E+0	1.90E+0	1.60E+0	1.10E+0
17	3.60E+0	3.50E+0	3.40E+0	3.10E+0	2.90E+0	2.50E+0	2.10E+0	1.80E+0	1.30E+0
20	4.10E+0	4.00E+0	3.80E+0	3.50E+0	3.20E+0	2.90E+0	2.40E+0	2.10E+0	1.60E+0
25	4.80E+0	4.70E+0	4.40E+0	4.10E+0	3.80E+0	3.40E+0	2.90E+0	2.60E+0	2.10E+0
30	5.50E+0	5.40E+0	5.10E+0	4.60E+0	4.30E+0	3.90E+0	3.40E+0	3.00E+0	2.50E+0
40	6.80E+0	6.70E+0	6.30E+0	5.70E+0	5.30E+0	4.80E+0	4.20E+0	3.80E+0	3.20E+0
50	8.10E+0	7.90E+0	7.50E+0	6.70E+0	6.20E+0	5.70E+0	5.00E+0	4.50E+0	3.90E+0
70	1.06E+1	1.04E+1	9.70E+0	8.70E+0	8.00E+0	7.30E+0	6.50E+0	6.00E+0	4.60E+0
100	1.42E+1	1.39E+1	1.29E+1	1.16E+1	1.06E+1	9.60E+0	8.70E+0	8.00E+0	6.50E+0
140	1.89E+1	1.84E+1	1.71E+1	1.53E+1	1.39E+1	1.26E+1	1.13E+1	1.06E+1	9.00E+0
200	2.58E+1	2.51E+1	2.33E+1	2.07E+1	1.88E+1	1.69E+1	1.52E+1	1.43E+1	1.18E+1
300	3.72E+1	3.61E+1	3.35E+1	2.95E+1	2.67E+1	2.39E+1	2.15E+1	2.04E+1	1.82E+1
400	4.84E+1	4.71E+1	4.38E+1	3.84E+1	3.46E+1	3.09E+1	2.77E+1	2.64E+1	2.39E+1
500	6.00E+1	5.82E+1	5.38E+1	4.71E+1	4.25E+1	3.77E+1	3.37E+1	3.23E+1	2.97E+1
700	8.29E+1	8.07E+1	7.41E+1	6.49E+1	5.81E+1	5.12E+1	4.56E+1	4.33E+1	4.19E+1
1000	1.18E+2	1.15E+2	1.05E+2	9.16E+1	8.12E+1	7.14E+1	6.33E+1	6.02E+1	5.84E+1
2000	2.38E+2	2.30E+2	2.10E+2	1.80E+2	1.58E+2	1.37E+2	1.19E+2	1.12E+2	1.08E+2
5000	5.97E+2	5.77E+2	5.22E+2	4.38E+2	3.75E+2	3.15E+2	2.63E+2	2.43E+2	2.30E+2
10000	1.15E+3	1.11E+3	1.00E+3	8.29E+2	6.95E+2	5.62E+2	5.00E+2	4.08E+2	3.78E+2

# Be → Be

Sputtering yield of Be by Be

```

z1= 4, m1= 9.01, z2= 4, m2= 9.01, sbe=3.38 eV, rho=1.80 g/cm**3
ef=3.33 eV, esb=3.38 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : trvrmc
ne=24, na=15

```

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
5				3.05e-6	7.10e-6	9.83e-6	1.05e-5	1.02e-5	1.03e-5
6			3.17e-6	2.32e-5	3.87e-5	4.62e-5	4.62e-5	4.64e-5	4.61e-5
7			1.36e-5	6.54e-5	9.76e-5	1.18e-4	1.30e-4	1.34e-4	1.38e-4
8		3.35e-6	3.53e-5	1.35e-4	1.96e-4	2.71e-4	3.47e-4	3.80e-4	4.01e-4
9		9.66e-6	7.48e-5	2.48e-4	3.92e-4	6.31e-4	8.84e-4	9.58e-4	1.01e-3
10		2.12e-5	1.33e-4	4.22e-4	7.84e-4	1.37e-3	1.89e-3	2.04e-3	2.17e-3
11	6.78e-6	4.03e-6	2.21e-4	7.39e-4	1.51e-3	2.62e-3	3.47e-3	3.77e-3	3.74e-3
12	1.26e-5	6.63e-5	3.47e-4	1.22e-3	2.74e-3	4.67e-3	5.88e-3	6.00e-3	6.04e-3
13	2.14e-5	1.01e-4	5.39e-4	2.07e-3	4.48e-3	7.29e-3	8.69e-3	8.73e-3	8.84e-3
15	5.23e-5	2.17e-4	1.22e-3	4.95e-3	9.90e-3	1.48e-2	1.61e-2	1.57e-2	1.51e-2
17	1.15e-4	4.40e-4	2.39e-3	9.79e-3	1.79e-2	2.48e-2	2.50e-2	2.35e-2	2.22e-2
20	3.05e-4	1.09e-3	5.63e-3	2.08e-2	3.47e-2	4.38e-2	4.04e-2	3.65e-2	3.33e-2
25	1.09e-3	3.32e-3	1.54e-2	4.77e-2	7.14e-2	8.21e-2	6.87e-2	5.85e-2	5.09e-2
30	2.68e-3	7.27e-3	2.95e-2	8.18e-2	1.16e-1	1.25e-1	9.74e-2	7.92e-2	6.58e-2
40	8.41e-3	1.93e-2	6.54e-2	1.58e-1	2.12e-1	2.15e-1	1.50e-1	1.12e-1	8.65e-2
50	1.68e-2	4.45e-2	1.03e-1	2.33e-1	3.06e-1	3.04e-1	1.99e-1	1.37e-1	9.65e-2
70	3.77e-2	6.72e-2	1.73e-1	3.59e-1	4.70e-1	4.71e-1	2.87e-1	1.73e-1	1.03e-1
100	7.00e-2	1.11e-1	2.49e-1	4.93e-1	6.63e-1	6.94e-1	4.21e-1	2.29e-1	1.06e-1
200	1.43e-1	1.98e-1	3.77e-1	7.18e-1	1.02e-0	1.21e-0	8.77e-1	4.38e-1	1.16e-1
300	1.86e-1	2.46e-1	4.37e-1	8.19e-1	1.19e-0	1.52e-0	1.30e-0	6.90e-1	1.37e-1
500	2.33e-1	2.93e-1	4.94e-1	9.03e-1	1.34e-0	1.85e-0	1.92e-0	1.23e-0	2.08e-1
700	2.57e-1	3.16e-1	5.11e-1	9.30e-1	1.40e-0	2.00e-0	2.31e-0	1.72e-0	3.09e-1
1000	2.74e-1	3.31e-1	5.19e-1	9.31e-1	1.41e-0	2.09e-0	2.65e-0	2.27e-0	5.10e-1
2000	2.53e-1								
3000	2.63e-1								
5000	2.27e-1						2.99e-0	3.38e-0	2.20e-0

$E_0$ (eV)	0°	20°	40°	50°	60°	70°	75°	77.5°	80°	85°
1000	2.65e-1	3.64e-1	7.25e-1	1.11e-0	1.67e-0	2.41e-0	2.63e-0		2.27e-0	5.02e-1
3000	2.63e-1	3.25e-1	6.02e-1	9.12e-1	1.46e-0	2.35e-0	2.99e-0	3.20e-0	3.38e-0	2.20e-0

Sputtered energy of Be by Be  
ne=24, na=15

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
5				3.14e-7	8.46e-7	1.38e-6	1.62e-6	1.63e-6	1.71e-6
6			2.59e-7	2.61e-6	5.18e-6	7.07e-6	7.93e-6	8.26e-6	8.46e-6
7			1.17e-6	7.76e-6	1.39e-5	1.96e-5	2.41e-5	2.56e-5	2.71e-5
8		2.115e-7	3.18e-6	1.64e-5	2.93e-5	4.74e-5	6.86e-5	7.69e-5	8.28e-5
9		6.65e-7	6.91e-6	3.11e-5	6.10e-5	1.16e-4	1.82e-4	2.02e-4	2.18e-4
10		1.56e-6	1.25e-5	5.47e-5	1.28e-4	2.62e-4	4.01e-4	4.50e-4	4.87e-4
11	3.57e-7	2.98e-6	2.14e-5	1.01e-4	2.58e-4	5.22e-4	7.69e-4	8.63e-4	8.62e-4
12	6.92e-7	4.94e-6	3.46e-5	1.73e-4	4.79e-4	9.61e-4	1.34e-3	1.42e-3	1.45e-3
13	1.18e-6	7.66e-6	5.51e-5	3.05e-4	8.07e-4	1.54e-3	2.03e-3	2.10e-3	2.18e-3
15	2.97e-6	1.66e-5	1.33e-4	7.60e-4	1.85e-3	3.22e-3	3.91e-3	3.94e-3	3.87e-3
17	6.75e-6	3.49e-5	2.70e-4	1.56e-3	3.44e-3	5.56e-3	6.23e-3	6.08e-3	5.87e-3
20	1.84e-5	8.91e-5	6.56e-4	3.39e-3	6.76e-3	1.01e-2	1.04e-2	9.68e-3	9.00e-3
25	6.59e-5	2.69e-4	1.77e-3	7.72e-3	1.40e-2	1.90e-2	1.79e-2	1.57e-2	1.39e-2
30	1.53e-4	5.54e-4	3.25e-3	1.29e-2	2.23e-2	2.87e-2	2.53e-2	2.12e-2	1.79e-2
40	4.26e-4	1.30e-3	6.53e-3	2.31e-2	3.80e-2	4.69e-2	3.79e-2	2.93e-2	2.27e-2
50	7.62e-4	2.09e-3	9.24e-3	3.09e-2	5.09e-2	6.20e-2	4.77e-2	3.43e-2	2.43e-2
70	1.47e-3	3.45e-3	1.33e-2	4.03e-2	6.67e-2	8.36e-2	6.18e-2	3.97e-2	2.37e-2
100	2.37e-3	4.85e-3	1.61e-2	4.58e-2	7.73e-2	1.01e-1	7.68e-2	4.54e-2	2.12e-2
200	3.69e-3	6.38e-3	1.73e-2	4.58e-2	7.90e-2	1.15e-1	1.07e-1	6.12e-2	1.66e-2
300	4.03e-3	6.49e-3	1.64e-2	4.21e-2	7.23e-2	1.12e-1	1.22e-1	7.56e-2	1.61e-2
500	3.96e-3	6.07e-3	1.44e-2	3.56e-2	6.24e-2	1.01e-1	1.28e-1	9.56e-2	1.84e-2
700	3.68e-3	5.51e-3	1.27e-2	3.11e-2	5.55e-2	9.18e-2	1.24e-1	1.07e-1	2.31e-2
1000	3.25e-3	4.82e-3	1.08e-2	2.64e-2	4.81e-2	8.10e-2	1.17e-1	1.12e-1	3.07e-2
3000	1.87e-3						7.86e-2	9.04e-2	5.93e-2

$E_0$ (eV)	0°	20°	40°	50°	60°	70°	75°	77.5°	80°	85°
1000	3.13e-3	5.83e-3	1.88e-2	3.42e-2	6.07e-2	9.75e-2	1.16e-1		1.12e-1	3.08e-2
3000	1.87e-3	3.02e-3	9.30e-3	1.90e-2	3.44e-2	6.14e-2	7.86e-2	8.59e-2	9.04e-2	5.93e-2

# Be → Be

Particle reflection coefficient of Be backscattered from Be  
 z1= 4, m1= 9.01, z2= 4, m2= 9.01, sbe=3.38 eV, rho=1.80 g/cm\*\*3  
 ef=3.33 eV, esb=3.38 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program : trvmc  
 ne=24, na=16

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
5							2.61e-8	1.04e-7	1.79e-7
6				1.86e-8	1.75e-7	5.41e-6	2.48e-5	4.10e-5	5.53e-5
7				3.86e-7	1.37e-5	1.13e-4	4.21e-4	6.15e-4	7.63e-4
8				7.09e-6	1.20e-4	7.28e-4	2.15e-3	2.93e-3	3.51e-3
9			4.43e-7	6.14e-5	5.57e-4	2.63e-3	6.71e-3	8.81e-3	1.04e-2
10			6.21e-6	2.91e-4	1.80e-3	6.80e-3	1.55e-2	1.97e-2	2.28e-2
11		1.23e-7	3.32e-5	8.97e-4	4.43e-3	1.40e-2	2.89e-2	3.59e-2	4.06e-2
12		8.83e-7	1.03e-4	2.15e-3	8.66e-3	2.46e-2	4.72e-2	5.72e-2	6.40e-2
13	3.54e-8	4.31e-6	2.64e-4	4.10e-3	1.49e-2	3.81e-2	6.91e-2	8.23e-2	9.10e-2
15	9.31e-7	3.54e-5	1.00e-3	1.07e-2	3.25e-2	7.24e-2	1.21e-1	1.41e-1	1.55e-1
17	7.28e-6	1.30e-4	2.37e-3	2.00e-2	5.47e-2	1.13e-1	1.81e-1	2.08e-1	2.26e-1
20	4.31e-5	4.34e-4	5.59e-3	3.70e-2	9.22e-2	1.77e-1	2.73e-1	3.11e-1	3.35e-1
25	1.90e-4	1.28e-3	1.19e-2	6.57e-2	1.52e-1	2.78e-1	4.17e-1	4.71e-1	5.05e-1
30	4.20e-4	2.31e-3	1.77e-2	8.98e-2	1.99e-1	3.58e-1	5.33e-1	6.01e-1	6.40e-1
40	1.02e-3	4.22e-3	2.65e-2	1.18e-1	2.54e-1	4.56e-1	6.79e-1	7.60e-1	8.07e-1
50	1.63e-3	5.73e-3	3.17e-2	1.28e-1	2.72e-1	4.95e-1	7.46e-1	8.35e-1	8.84e-1
70	2.72e-3	7.80e-3	3.48e-2	1.28e-1	2.70e-1	5.03e-1	7.82e-1	8.88e-1	9.41e-1
100	3.91e-3	9.09e-3	3.47e-2	1.17e-1	2.44e-1	4.68e-1	7.78e-1	9.03e-1	9.65e-1
200	5.32e-3	9.73e-3	2.92e-2	8.92e-2	1.81e-1	3.64e-1	6.94e-1	8.82e-1	9.79e-1
300	5.18e-3	8.94e-3	2.57e-2	7.52e-2	1.54e-1	3.05e-1	6.16e-1	8.41e-1	9.80e-1
500	4.65e-3	7.66e-3	2.12e-2	6.12e-2	1.26e-1	2.51e-1	5.09e-1	7.55e-1	9.74e-1
700	4.04e-3	6.53e-3	1.83e-2	5.58e-2	1.11e-1	2.23e-1	4.56e-1	6.84e-1	9.62e-1
1000	3.42e-3	5.54e-3	1.53e-2	4.69e-2	9.92e-2	2.00e-1	4.05e-1	6.12e-1	9.39e-1

$E_0$ (eV)	0°	20°	40°	50°	60°	70°	75°	77.5°	80°	82.5°	85°
1000	3.62e-3	6.70e-3	3.33e-2	6.57e-2	1.44e-1	2.79e-1	4.03e-1		6.07e-1		9.40e-1
3000	1.30e-3	3.30e-3	1.98e-2	4.40e-2	1.09e-1	2.13e-1	3.15e-1	3.75e-1	4.54e-1	5.66e-1	7.71e-1

Energy reflection coefficient of Be backscattered from Be  
 ne=24, na=16

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
5							3.22e-9	1.42e-8	2.48e-8
6				2.21e-9	2.12e-8	7.74e-7	3.92e-6	6.78e-6	9.38e-6
7				4.45e-8	2.09e-6	2.03e-5	8.56e-5	1.31e-4	1.67e-4
8				9.31e-7	2.10e-5	1.50e-4	5.03e-4	7.16e-4	8.79e-4
9			4.36e-8	8.72e-6	1.03e-4	5.90e-4	1.70e-3	2.35e-3	2.82e-3
10		6.66e-7	4.45e-5	3.51e-4	1.61e-3	4.19e-3	5.60e-3	6.62e-3	
11	9.90e-9	4.06e-6	1.47e-4	9.07e-4	3.48e-3	8.34e-3	1.08e-2	1.26e-2	
12	7.44e-8	1.34e-5	3.73e-4	1.85e-3	6.43e-3	1.44e-2	1.85e-2	2.11e-2	
13	2.07e-9	3.70e-7	3.49e-5	7.50e-4	3.35e-3	1.04e-2	2.21e-2	2.77e-2	3.15e-2
15	6.56e-8	3.40e-6	1.41e-4	2.11e-3	7.88e-3	2.14e-2	4.19e-2	5.17e-2	5.84e-2
17	5.27e-7	1.35e-5	3.50e-4	4.15e-3	1.41e-2	3.56e-2	6.66e-2	8.09e-2	9.08e-2
20	3.24e-6	4.71e-5	8.71e-4	8.23e-3	2.54e-2	5.96e-2	8.23e-2	1.30e-1	1.45e-1
25	1.44e-5	1.40e-4	1.90e-3	1.55e-2	4.51e-2	1.01e-1	1.81e-1	2.16e-1	2.40e-1
30	3.07e-5	2.49e-4	2.86e-3	2.18e-2	6.16e-2	1.39e-1	2.46e-1	2.96e-1	3.28e-1
40	7.07e-5	4.30e-4	4.24e-3	2.92e-2	8.29e-2	1.90e-1	3.47e-1	4.18e-1	4.65e-1
50	1.08e-4	5.54e-4	4.88e-3	3.15e-2	9.08e-2	2.16e-1	4.09e-1	5.00e-1	5.59e-1
70	1.67e-4	6.85e-4	5.10e-3	3.07e-2	9.04e-2	2.29e-1	4.68e-1	5.91e-1	6.70e-1
100	2.20e-4	7.46e-4	4.68e-3	2.67e-2	7.93e-2	2.15e-1	4.92e-1	6.48e-1	7.53e-1
200	2.83e-4	7.30e-4	3.60e-3	1.81e-2	5.23e-2	1.55e-1	4.46e-1	6.76e-1	8.49e-1
300	2.68e-4	6.46e-4	3.03e-3	1.43e-2	4.19e-2	1.21e-1	3.81e-1	6.45e-1	8.76e-1
500	2.50e-4	5.51e-4	2.43e-3	1.13e-2	3.20e-2	9.16e-2	2.94e-1	5.61e-1	8.85e-1
700	2.21e-4	4.76e-4	2.10e-3	9.68e-3	2.76e-2	7.79e-2	2.49e-1	4.88e-1	8.75e-1
1000	1.89e-4	4.12e-4	1.78e-3	8.41e-3	2.44e-2	6.79e-2	2.09e-1	4.15e-1	8.48e-1

$E_0$ (eV)	0°	20°	40°	50°	60°	70°	75°	77.5°	80°	82.5°	85°
1000	1.86e-4	5.43e-4	5.39e-3	1.40e-2	4.05e-2	1.14e-1	2.05e-1		4.10e-1		8.49e-1
3000	7.79e-5	3.43e-4	3.09e-3	9.18e-3	3.03e-2	8.05e-2	1.41e-1	1.91e-1	2.61e-1	3.79e-1	6.30e-1

# Be → Be

Average depth (mean range) in Å of Be implanted in Be  
 z1= 4, m1= 9.01, z2= 4, m2= 9.01, sbe=3.38 eV, rho=1.80 g/cm\*\*3  
 ef=3.33 eV, esb=3.38 eV, kk0=kk0r=2, kdeel=kdee2=3, ipot=ipotr=1 (KrC), ca=1.00  
 program : trvmc  
 ne=24, na=10

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
5	6.00E-1	5.00E-1	5.00E-1	4.00E-1	4.00E-1	3.00E-1	3.00E-1	3.00E-1	3.00E-1
6	8.00E-1	7.00E-1	6.00E-1	5.00E-1	4.00E-1	4.00E-1	3.00E-1	3.00E-1	3.00E-1
7	9.00E-1	9.00E-1	8.00E-1	6.00E-1	5.00E-1	4.00E-1	3.00E-1	3.00E-1	3.00E-1
8	1.10E+0	1.00E+0	9.00E-1	7.00E-1	5.00E-1	4.00E-1	3.00E-1	3.00E-1	3.00E-1
9	1.20E+0	1.10E+0	1.00E+0	7.00E-1	6.00E-1	4.00E-1	3.00E-1	3.00E-1	3.00E-1
10	1.30E+0	1.20E+0	1.00E+0	8.00E-1	6.00E-1	5.00E-1	3.00E-1	3.00E-1	3.00E-1
11	1.40E+0	1.30E+0	1.10E+0	9.00E-1	7.00E-1	5.00E-1	4.00E-1	3.00E-1	3.00E-1
12	1.50E+0	1.40E+0	1.20E+0	9.00E-1	7.00E-1	5.00E-1	4.00E-1	3.00E-1	3.00E-1
13	1.70E+0	1.60E+0	1.30E+0	1.00E+0	8.00E-1	5.00E-1	4.00E-1	3.00E-1	3.00E-1
15	1.90E+0	1.80E+0	1.50E+0	1.10E+0	8.00E-1	6.00E-1	4.00E-1	3.00E-1	3.00E-1
17	2.10E+0	2.00E+0	1.70E+0	1.30E+0	9.00E-1	7.00E-1	4.00E-1	4.00E-1	3.00E-1
20	2.40E+0	2.30E+0	2.00E+0	1.50E+0	1.10E+0	8.00E-1	5.00E-1	4.00E-1	4.00E-1
25	2.90E+0	2.80E+0	2.40E+0	1.80E+0	1.40E+0	1.00E+0	6.00E-1	5.00E-1	4.00E-1
30	3.40E+0	3.20E+0	2.80E+0	2.20E+0	1.70E+0	1.20E+0	8.00E-1	6.00E-1	5.00E-1
40	4.20E+0	4.10E+0	3.60E+0	2.90E+0	2.30E+0	1.80E+0	1.20E+0	9.00E-1	8.00E-1
50	5.00E+0	4.80E+0	4.30E+0	3.50E+0	3.00E+0	2.40E+0	1.70E+0	1.30E+0	1.10E+0
70	6.60E+0	6.40E+0	5.70E+0	4.80E+0	4.00E+0	3.30E+0	2.60E+0	2.10E+0	1.80E+0
100	8.70E+0	8.40E+0	7.50E+0	6.40E+0	5.50E+0	4.70E+0	3.70E+0	3.20E+0	2.70E+0
200	1.48E+1	1.43E+1	1.29E+1	1.10E+1	9.50E+0	8.10E+0	6.70E+0	6.00E+0	5.00E+0
300	2.06E+1	1.99E+1	1.80E+1	1.52E+1	1.31E+1	1.12E+1	9.40E+0	8.50E+0	7.40E+0
500	3.15E+1	3.05E+1	2.76E+1	2.33E+1	2.01E+1	1.70E+1	1.44E+1	1.32E+1	1.17E+1
700	4.23E+1	4.10E+1	3.70E+1	3.12E+1	2.69E+1	2.27E+1	1.91E+1	1.76E+1	1.58E+1
1000	5.84E+1	5.65E+1	5.11E+1	4.30E+1	3.68E+1	3.08E+1	2.59E+1	2.38E+1	2.18E+1

# Be → Be

Sputtering yield of Be by Be

```

z1= 4, m1= 9.01, z2= 4, m2= 9.01, sbe=2.00 eV, rho=1.85 g/cm***3
ef=1.98 eV, esb=2.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : trspv1cn
ne= 8, na= 5

```

E <sub>0</sub> (eV)	20°	35°	45°	60°	75°
20				8.10e-2	
50			5.25e-1	2.46e-1	
100			9.49e-1	5.30e-1	
200	5.38e-1	9.38e-1	1.32e-0	1.20e-0	
500	6.28e-1	1.06e-0	1.50e-0	1.85e-0	
1000	5.95e-1	9.84e-1	1.40e-0	3.94e-0	
2000	5.69e-1		1.23e-0	2.30e-0	
5000			9.30e-1	1.85e-0	3.89e-0

Sputtered energy of Be by Be  
ne= 8, na= 5

E <sub>0</sub> (eV)	20°	35°	45°	60°	75°
20				1.90e-2	
50			5.62e-2	4.66e-2	
100			6.65e-2	7.48e-2	
200	1.23e-2	3.24e-2	5.71e-2	1.12e-1	
500	9.13e-3	2.32e-2	3.97e-2	1.38e-1	
1000	6.40e-3	1.58e-2	2.69e-2	2.69e-2	1.19e-1
2000	4.15e-3		1.71e-2	4.31e-2	6.26e-2
5000			1.05e-2	2.64e-2	

Particle reflection coefficient of Be backscattered from Be  
z1= 4, m1= 9.01, z2= 4, m2= 9.01, sbe=2.00 eV, rho=1.85 g/cm\*\*\*3  
ef=1.98 eV, esb=2.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
program : trspv1cn  
ne=10, na= 6

E <sub>0</sub> (eV)	20°	35°	45°	60°	70°	75°
15				5.67e-2	1.38e-1	
20			3.98e-2	1.43e-1	6.58e-1	
30				2.90e-1		
50			1.70e-1	3.91e-1	8.70e-1	
100			1.36e-1	3.56e-1	8.46e-1	
200	1.22e-2	4.50e-2	9.23e-2	2.56e-1	5.16e-1	7.43e-1
500	9.40e-3	2.93e-2	5.46e-2	1.68e-1	3.53e-1	5.29e-1
1000	8.13e-3	2.20e-2	4.52e-2	1.34e-1	2.74e-1	4.03e-1
2000	5.10e-3	1.56e-2	3.10e-2	1.10e-1		
5000			2.29e-2	8.38e-2		2.83e-1

Energy reflection coefficient of Be backscattered from Be  
ne=10, na= 6

E <sub>0</sub> (eV)	20°	35°	45°	60°	70°	75°
15				1.47e-2	4.68e-2	
20			8.19e-3	4.25e-2	3.05e-1	
30				9.84e-2		
50			4.25e-2	1.49e-1	5.44e-1	
100			3.27e-2	1.39e-1	5.69e-1	
200	9.81e-4	6.34e-3	2.05e-2	9.31e-2	2.75e-1	4.93e-1
500	7.60e-4	4.28e-3	1.05e-2	5.20e-2	1.64e-1	3.12e-1
1000	6.91e-4	2.98e-3	8.41e-3	3.88e-2	1.13e-1	2.11e-1
2000	4.40e-4	2.26e-2	5.72e-3	3.15e-2		
5000			4.26e-3	2.27e-2		1.24e-1

Average depth (mean range) in Å of Be implanted in Be  
ne=10, na= 8

E <sub>0</sub> (eV)	20°	35°	45°	60°	70°	75°	80°	85°
15				5.70e-1	3.40e-1	2.90e-1		
20			1.12e+0	7.30e-1	4.05e-1	3.40e-1	3.10e-1	
30				1.16e+0	6.40e-1	5.10e-1	4.30e-1	
50			2.89e+0	2.14e+0	1.42e+0	1.08e+0	8.80e-1	
100			5.32e+0	4.16e+0	3.02e+0	2.53e+0	2.09e+0	
200	1.23e+1	1.07e+1	9.55e+0	7.51e+0	6.33e+0	5.67e+0	5.12e+0	4.39e+0
500	2.72e+1	2.38e+1	2.12e+1	1.66e+1	1.39e+1	1.27e+1	1.17e+1	9.81e+0
1000	5.11e+1	4.49e+1	4.00e+1	3.08e+1	2.60e+1	2.37e+1	2.18e+1	1.92e+1
2000	1.01e+2	8.81e+1	7.78e+1	6.09e+1	4.19e+2	4.51e+1	4.15e+1	3.77e+1
5000			1.95e+2	1.49e+2	1.08e+2	1.09e+2	9.89e+1	9.00e+1

## Be → Be

Be on Be, Maxwellian velocity distribution, sheath potential 0 kT  
 z1= 4, m1= 9.01, z2= 4, m2= 9.01, sbe=3.38 eV, rho=1.80 g/cm\*\*3  
 ef=3.33 eV, esb=3.38 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program : testvmcx  
 ne=14

kT(eV)	Y	$Y_E$	$E_{sp}$	$R_N$	$R_E$	$E_b$	range
2.4	4.40e-4	2.86e-4	3.12e+0	1.69e-3	1.69e-3	4.81e+0	2.40e-1
3	1.13e-3	6.80e-4	3.62e+0	4.20e-3	4.02e-3	5.73e+0	3.36e-1
4	3.24e-3	1.74e-3	4.30e+0	1.11e-2	9.65e-3	6.95e+0	4.89e-1
5	6.74e-3	3.25e-3	4.82e+0	2.11e-2	1.69e-2	8.04e+0	6.41e-1
7	1.79e-2	7.16e-3	5.61e+0	4.36e-2	3.23e-2	1.04e+1	9.20e-1
10	4.10e-2	1.39e-2	6.80e+0	7.92e-2	5.42e-2	1.38e+1	1.34e+0
20	1.33e-1	2.97e-2	8.94e+0	1.53e-1	9.01e-2	2.35e+1	2.69e+0
50	3.60e-1	4.57e-2	1.27e+1	1.99e-1	9.82e-2	4.94e+1	6.30e+0
100	5.82e-1	4.76e-2	1.64e+1	1.96e-1	8.89e-2	9.11e+1	1.13e+1
200	7.89e-1	4.38e-2	2.21e+1	1.70e-1	7.34e-2	1.72e+2	2.00e+1
500	1.00e-0	3.43e-2	3.41e+1	1.27e-1	4.82e-2	3.79e+2	4.40e+1
1000	1.05e-0	2.60e-2	4.98e+1	1.07e-1	4.12e-2	7.69e+2	8.57e+1
2000	9.84e-1	1.76e-2	7.06e+1	8.87e-2	3.19e-2	1.42e+3	1.66e+2
5000	7.67e-1	8.68e-3	1.14e+2	6.66e-2	2.27e-2	3.43e+3	4.14e+2

Be on Be, Maxwellian velocity distribution, sheath potential 3 kT  
 ne=12

kT(eV)	Y	$Y_E$	$E_{sp}$	$R_N$	$R_E$	$E_b$	range
1.4	1.43e-4	3.82e-5	1.87e+0	1.63e-4	7.18e-5	3.08e+0	6.63e-1
2	7.05e-4	1.82e-4	2.58e+0	1.10e-3	4.52e-4	4.12e+0	1.03e+0
3	4.10e-3	9.43e-4	3.45e+0	4.89e-3	1.75e-3	5.38e+0	1.54e+0
5	2.13e-2	3.83e-3	4.50e+0	1.51e-2	4.57e-3	7.59e+0	2.47e+0
10	9.07e-2	1.02e-2	5.64e+0	2.69e-2	6.22e-3	1.16e+1	4.43e+0
20	2.02e-1	1.45e-2	7.18e+0	2.76e-2	5.13e-3	1.86e+1	7.65e+0
50	3.39e-1	1.45e-2	1.07e+1	2.23e-2	3.43e-3	3.84e+1	1.59e+1
100	4.05e-1	1.22e-2	1.50e+1	1.72e-2	2.54e-3	7.37e+1	2.83e+1
200	4.38e-1	9.26e-3	2.12e+1	1.32e-2	1.94e-3	1.47e+2	5.27e+1
500	4.10e-1	5.46e-3	3.33e+1	8.17e-3	1.19e-3	3.65e+2	1.26e+2
1000	3.29e-1	3.12e-3	4.74e+1	4.71e-3	7.19e-4	7.64e+2	2.52e+2
2000	2.52e-1	1.59e-3	6.32e+1	2.67e-3	4.12e-4	1.54e+3	5.14e+2

Be on Be, Maxwellian velocity distribution, sheath potential 9 kT  
 ne=14

kT(eV)	Y	$Y_E$	$E_{sp}$	$R_N$	$R_E$	$E_b$	range
1.4	8.07e-4	1.11e-4	2.12e+0	6.22e-4	1.28e-4	3.18e+0	1.77e+0
1.5	1.15e-3	1.59e-4	2.27e+0	8.40e-4	1.72e-4	3.38e+0	1.88e+0
2	4.13e-3	5.16e-4	2.75e+0	2.47e-3	4.67e-4	4.16e+0	2.42e+0
3	1.67e-2	1.64e-3	3.25e+0	5.86e-3	9.56e-4	5.39e+0	3.41e+0
5	5.34e-2	3.86e-3	3.97e+0	1.01e-2	1.33e-3	7.27e+0	5.14e+0
10	1.36e-1	6.49e-3	5.24e+0	1.22e-2	1.31e-3	1.19e+1	8.83e+0
20	2.24e-1	7.71e-3	7.58e+0	1.23e-2	1.16e-3	2.07e+1	1.52e+1
50	3.18e-1	6.61e-3	1.14e+1	8.60e-3	7.35e-4	4.70e+1	3.26e+1
100	3.39e-1	5.06e-3	1.64e+1	6.57e-3	5.88e-4	9.84e+1	6.09e+1
200	3.28e-1	3.50e-3	2.35e+1	4.11e-3	3.91e-4	2.09e+2	1.18e+2
500	2.63e-1	1.78e-3	3.72e+1	2.01e-3	2.18e-4	5.97e+2	2.99e+2
1000	2.00e-1	9.36e-4	5.15e+1	6.76e-4	6.79e-5	1.11e+3	6.06e+2
2000	1.47e-1	4.98e-4	7.48e+1	6.57e-4	6.40e-5	2.14e+3	1.21e+3
5000	9.14e-2	1.67e-4	1.00e+2				2.80e+3

# N → Be

Sputtering yield of Be by N  
 z1= 7, m1= 14.01, z2= 4, m2= 9.01, sbe=3.38 eV, rho=1.80 g/cm\*\*3  
 ef=0.95 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program : trvmc  
 ne=16, na= 9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10		6.00E-6	4.36E-5	6.72E-5	1.22E-4	1.72E-4	1.65E-4	1.43E-4	
12		8.67E-7	3.97E-5	1.75E-4	4.81E-4	9.51E-4	1.04E-3	8.36E-4	6.57E-4
15	1.13E-6	1.16E-5	1.72E-4	1.26E-3	3.59E-3	5.69E-3	4.37E-3	3.01E-3	2.07E-3
20	1.30E-5	1.26E-4	1.42E-3	9.69E-3	2.04E-2	2.37E-2	1.36E-2	8.05E-3	4.73E-3
25	1.32E-4	6.48E-4	5.96E-3	2.95E-2	5.03E-2	5.10E-2	2.53E-2	1.33E-2	6.72E-3
27	2.23E-4	1.08E-3	9.07E-3	4.01E-2	6.49E-2	6.37E-2	3.04E-2	1.55E-2	7.40E-3
30	4.97E-4	2.10E-3	1.51E-2	5.89E-2	8.96E-2	8.43E-2	3.88E-2	1.84E-2	8.20E-3
40	2.72E-3	8.91E-3	4.55E-2	1.36E-1	1.84E-1	1.63E-1	6.78E-2	2.81E-2	9.70E-3
50	7.94E-3	2.07E-2	8.48E-2	2.20E-1	2.86E-1	2.48E-1	9.91E-2	3.73E-2	1.03E-2
70	2.53E-2	5.31E-2	1.66E-1	3.79E-1	4.82E-1	4.24E-1	1.67E-1	5.58E-2	1.06E-2
100	6.02E-2	1.05E-1	2.71E-1	5.69E-1	7.39E-1	6.80E-1	2.82E-1	8.75E-2	1.14E-2
140	1.08E-1	1.69E-1	3.79E-1	7.53E-1	1.00E+0	9.94E-1	4.54E-1	1.38E-1	1.23E-2
200	1.72E-1	2.45E-1	4.86E-1	9.37E-1	1.29E+0	1.40E+0	7.38E-1	2.33E-1	1.53E-2
300	2.47E-1	3.29E-1	5.97E-1	1.12E+0	1.59E+0	1.89E+0	1.23E+0	4.34E-1	2.22E-2
500	3.38E-1	4.27E-1	7.15E-1	1.31E+0	1.90E+0	2.49E+0	2.12E+0	9.55E-1	4.64E-2
1000	4.48E-1	5.36E-1	8.32E-1	1.46E+0	2.18E+0	3.11E+0	3.51E+0	2.38E+0	1.83E-1

Sputtered energy of Be by N  
 ne=16, na= 9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10		6.00E-6	4.36E-5	6.72E-5	1.22E-4	1.72E-4	1.65E-4	1.43E-4	
12		8.67E-7	3.97E-5	1.75E-4	4.81E-4	9.51E-4	1.04E-3	8.36E-4	6.57E-4
15	1.13E-6	1.16E-5	1.72E-4	1.26E-3	3.59E-3	5.69E-3	4.37E-3	3.01E-3	2.07E-3
20	1.30E-5	1.26E-4	1.42E-3	9.69E-3	2.04E-2	2.37E-2	1.36E-2	8.05E-3	4.73E-3
25	1.32E-4	6.48E-4	5.96E-3	2.95E-2	5.03E-2	5.10E-2	2.53E-2	1.33E-2	6.72E-3
27	2.23E-4	1.08E-3	9.07E-3	4.01E-2	6.49E-2	6.37E-2	3.04E-2	1.55E-2	7.40E-3
30	4.97E-4	2.10E-3	1.51E-2	5.89E-2	8.96E-2	8.43E-2	3.88E-2	1.84E-2	8.20E-3
40	2.72E-3	8.91E-3	4.55E-2	1.36E-1	1.84E-1	1.63E-1	6.78E-2	2.81E-2	9.70E-3
50	7.94E-3	2.07E-2	8.48E-2	2.20E-1	2.86E-1	2.48E-1	9.91E-2	3.73E-2	1.03E-2
70	2.53E-2	5.31E-2	1.66E-1	3.79E-1	4.82E-1	4.24E-1	1.67E-1	5.58E-2	1.06E-2
100	6.02E-2	1.05E-1	2.71E-1	5.69E-1	7.39E-1	6.80E-1	2.82E-1	8.75E-2	1.14E-2
140	1.08E-1	1.69E-1	3.79E-1	7.53E-1	1.00E+0	9.94E-1	4.54E-1	1.38E-1	1.23E-2
200	1.72E-1	2.45E-1	4.86E-1	9.37E-1	1.29E+0	1.40E+0	7.38E-1	2.33E-1	1.53E-2
300	2.47E-1	3.29E-1	5.97E-1	1.12E+0	1.59E+0	1.89E+0	1.23E+0	4.34E-1	2.22E-2
500	3.38E-1	4.27E-1	7.15E-1	1.31E+0	1.90E+0	2.49E+0	2.12E+0	9.55E-1	4.64E-2
1000	4.48E-1	5.36E-1	8.32E-1	1.46E+0	2.18E+0	3.11E+0	3.51E+0	2.38E+0	1.83E-1

# $N \rightarrow Be$

Particle reflection coefficient of N backscattered from Be  
 $z_1 = 7$ ,  $m_1 = 14.01$ ,  $z_2 = 4$ ,  $m_2 = 9.01$ ,  $sbe = 3.38$  eV,  $\rho = 1.80$  g/cm\*\*3  
 $ef = 0.95$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program : trvmc  
ne=16, na= 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	2.50E-7	1.77E-4	9.43E-3	5.26E-2	1.64E-1	3.19E-1	3.83E-1	4.23E-1	
12		3.87E-6	1.01E-3	2.36E-2	9.69E-2	2.58E-1	4.60E-1	5.38E-1	5.84E-1
15		4.59E-5	3.58E-3	5.11E-2	1.69E-1	3.84E-1	6.26E-1	7.13E-1	7.59E-1
20	8.00E-6	3.66E-4	9.76E-3	9.50E-2	2.63E-1	5.26E-1	7.87E-1	8.67E-1	9.07E-1
25	4.03E-5	8.48E-4	1.56E-2	1.25E-1	3.20E-1	6.00E-1	8.57E-1	9.30E-1	9.62E-1
27	5.88E-5	1.04E-3	1.73E-2	1.33E-1	3.33E-1	6.17E-1	8.74E-1	9.42E-1	9.72E-1
30	9.43E-5	1.28E-3	1.93E-2	1.42E-1	3.48E-1	6.35E-1	8.89E-1	9.55E-1	9.81E-1
40	1.76E-4	1.83E-3	2.28E-2	1.52E-1	3.64E-1	6.57E-1	9.12E-1	9.73E-1	9.93E-1
50	2.22E-4	2.05E-3	2.32E-2	1.48E-1	3.56E-1	6.53E-1	9.18E-1	9.78E-1	9.96E-1
70	2.92E-4	2.13E-3	2.10E-2	1.31E-1	3.24E-1	6.23E-1	9.15E-1	9.82E-1	9.98E-1
100	2.98E-4	2.00E-3	1.81E-2	1.07E-1	2.75E-1	5.67E-1	8.98E-1	9.81E-1	9.99E-1
140	3.75E-4	1.82E-3	1.50E-2	8.61E-2	2.26E-1	4.99E-1	8.67E-1	9.77E-1	9.99E-1
200	3.33E-4	1.52E-3	1.25E-2	6.77E-2	1.80E-1	4.20E-1	8.16E-1	9.66E-1	9.99E-1
300	4.12E-4	1.51E-3	9.97E-3	5.23E-2	1.39E-1	3.37E-1	7.32E-1	9.40E-1	9.99E-1
500	3.35E-4	1.29E-3	7.62E-3	3.89E-2	1.04E-1	2.54E-1	6.01E-1	8.72E-1	9.98E-1
1000	4.00E-4	9.30E-4	5.28E-3	2.71E-2	7.38E-2	1.85E-1	4.43E-1	7.11E-1	9.90E-1

Energy reflection coefficient of N backscattered from Be  
ne=16, na = 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	1.99E-8	1.71E-5	1.47E-3	1.15E-2	4.78E-2	1.16E-1	1.52E-1	1.76E-1	
12	2.77E-7	1.07E-4	3.83E-3	2.17E-2	7.87E-2	1.79E-1	2.29E-1	2.62E-1	
15	3.22E-6	4.04E-4	8.78E-3	3.95E-2	1.24E-1	2.65E-1	3.34E-1	3.78E-1	
20	2.63E-7	2.63E-5	1.10E-3	1.71E-2	6.54E-2	1.83E-1	3.73E-1	4.62E-1	5.19E-1
25	1.77E-6	6.02E-5	1.74E-3	2.29E-2	8.27E-2	2.21E-1	4.42E-1	5.45E-1	6.11E-1
27	2.53E-6	7.19E-5	1.93E-3	2.45E-2	8.74E-2	2.32E-1	4.62E-1	5.70E-1	6.39E-1
30	4.05E-6	8.60E-5	2.11E-3	2.61E-2	9.27E-2	2.44E-1	4.87E-1	6.01E-1	6.74E-1
40	6.55E-6	1.11E-4	2.38E-3	2.79E-2	9.95E-2	2.65E-1	5.37E-1	6.68E-1	7.52E-1
50	7.43E-6	1.12E-4	2.27E-3	2.66E-2	9.79E-2	2.70E-1	5.62E-1	7.07E-1	7.99E-1
70	7.99E-6	1.00E-4	1.86E-3	2.25E-2	8.80E-2	2.61E-1	5.81E-1	7.48E-1	8.52E-1
100	6.73E-6	7.96E-5	1.42E-3	1.72E-2	7.19E-2	2.36E-1	5.79E-1	7.71E-1	8.91E-1
140	7.97E-6	6.54E-5	1.08E-3	1.27E-2	5.58E-2	2.02E-1	5.58E-1	7.78E-1	9.15E-1
200	5.84E-6	4.99E-5	8.10E-4	9.22E-3	4.13E-2	1.62E-1	5.16E-1	7.70E-1	9.32E-1
300	8.36E-6	5.08E-5	6.00E-4	6.55E-3	2.91E-2	1.19E-1	4.47E-1	7.40E-1	9.42E-1
500	5.38E-6	4.18E-5	4.50E-4	4.47E-3	1.97E-2	8.04E-2	3.40E-1	6.62E-1	9.44E-1
1000	9.43E-6	3.43E-5	3.20E-4	3.03E-3	1.27E-2	5.16E-2	2.18E-1	4.93E-1	9.25E-1

Average depth (mean range) in Å of N implanted in Be  
ne=16, na = 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	9.00E-1	9.00E-1	7.00E-1	5.00E-1	4.00E-1	2.00E-1	1.00E-1	1.00E-1	1.00E-1
12	1.10E+0	1.00E+0	9.00E-1	6.00E-1	4.00E-1	3.00E-1	1.00E-1	1.00E-1	1.00E-1
15	1.40E+0	1.30E+0	1.10E+0	8.00E-1	6.00E-1	3.00E-1	2.00E-1	1.00E-1	1.00E-1
20	1.90E+0	1.80E+0	1.50E+0	1.10E+0	8.00E-1	5.00E-1	3.00E-1	2.00E-1	1.00E-1
25	2.30E+0	2.20E+0	1.80E+0	1.40E+0	1.10E+0	7.00E-1	4.00E-1	3.00E-1	2.00E-1
27	2.40E+0	2.30E+0	2.00E+0	1.50E+0	1.20E+0	8.00E-1	5.00E-1	3.00E-1	2.00E-1
30	2.70E+0	2.50E+0	2.20E+0	1.60E+0	1.30E+0	9.00E-1	6.00E-1	4.00E-1	3.00E-1
40	3.40E+0	3.20E+0	2.80E+0	2.20E+0	1.80E+0	1.30E+0	9.00E-1	6.00E-1	4.00E-1
50	4.10E+0	3.90E+0	3.40E+0	2.70E+0	2.20E+0	1.70E+0	1.20E+0	9.00E-1	6.00E-1
70	5.30E+0	5.00E+0	4.40E+0	3.50E+0	3.00E+0	2.40E+0	1.70E+0	1.30E+0	9.00E-1
100	6.90E+0	6.60E+0	5.80E+0	4.70E+0	4.00E+0	3.20E+0	2.40E+0	1.90E+0	1.30E+0
140	8.40E+0	9.00E+0	7.50E+0	6.10E+0	5.20E+0	4.20E+0	3.30E+0	2.70E+0	1.90E+0
200	1.14E+1	1.09E+1	9.70E+0	8.00E+0	6.70E+0	5.60E+0	4.40E+0	3.70E+0	2.80E+0
300	1.53E+1	1.47E+1	1.31E+1	1.08E+1	9.10E+0	7.60E+0	6.10E+0	5.30E+0	4.20E+0
500	2.25E+1	2.16E+1	1.94E+1	1.60E+1	1.35E+1	1.11E+1	9.10E+0	8.10E+0	6.50E+0
1000	3.89E+1	3.75E+1	3.36E+1	2.77E+1	2.35E+1	1.91E+1	1.54E+1	1.40E+1	1.17E+1

# O → Be

Sputtering yield of Be by O  
 $z1 = 8, m1 = 16.00, z2 = 4, m2 = 9.01, sbe = 3.38 \text{ eV}, rho = 1.80 \text{ g/cm}^{**3}$   
 $ef = 0.95 \text{ eV}, esb = 1.00 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1$  (KrC)  
 program : trvmc  
*only low fluence!*  
 $ne = 19, na = 1$

$E_0(\text{eV})$	$0^\circ$
18	4.89e-6
20	1.36e-5
22	3.03e-5
25	9.18e-5
30	3.71e-4
40	2.16e-3
45	4.03e-3
50	6.41e-3
60	1.34e-2
70	2.22e-2
100	6.06e-2
140	1.02e-1
200	1.65e-1
300	2.35e-1
500	3.50e-1
1000	4.97e-1
2000	5.81e-1
5000	6.10e-1
10000	5.24e-1

Sputtered energy of Be by O  
 $ne = 10, na = 1$

$E_0(\text{eV})$	$0^\circ$
18	1.71e-7
20	4.99e-7
22	1.19e-6
25	3.72e-6
30	1.54e-5
40	8.78e-5
45	1.60e-4
50	2.46e-4
60	4.80e-4
70	7.55e-4

Particle reflection coefficient of O backscattered from Be  
 $z1 = 8, m1 = 16.00, z2 = 4, m2 = 9.01, sbe = 3.38 \text{ eV}, rho = 1.80 \text{ g/cm}^{**3}$   
 $ef = 0.95 \text{ eV}, esb = 1.00 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1$  (KrC)  
*only low fluence!*  
 $ne = 10, na = 1$

$E_0(\text{eV})$	$0^\circ$
18	4.20e-8
20	2.24e-7
22	1.12e-6
25	3.40e-6
30	1.05e-5
40	2.57e-5
45	3.85e-5
50	5.60e-5
60	5.80e-5
70	3.00e-5

Energy reflection coefficient of O backscattered from Be  
 $ne = 10, na = 1$

$E_0(\text{eV})$	$0^\circ$
18	1.70e-9
20	8.69e-9
22	4.52e-8
25	1.34e-7
30	3.68e-7
40	9.16e-7
45	1.18e-6
50	1.64e-6
60	1.30e-6
70	1.41e-6

Average depth (mean range) in Å of O implanted in Be  
 $ne = 10, na = 1$

$E_0(\text{eV})$	$0^\circ$
18	1.62e+0
20	1.80e+0
22	1.97e+0
25	2.22e+0
30	2.60e+0
40	3.32e+0
45	3.65e+0
50	3.96e+0
60	4.57e+0
70	5.13e+0

# Ne → Be

Sputtering yield of Be by Ne  
 z1=10, m1= 20.18, z2= 4, m2= 9.01, sbe=3.38 eV, rho=1.80 g/cm\*\*3  
 ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program : trvmc  
 ne=26, na= 9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10		4.40e-7				9.78e-6	6.67e-6	2.08e-6	
11		3.38e-6	3.66e-5	4.64e-5	4.27e-5	2.45e-5	7.14e-6	1.33e-7	
12	5.59e-8	1.18e-5	8.78e-5	1.10e-4	1.26e-4	7.28e-5	2.15e-5	9.00e-7	
13	7.45e-7	3.13e-7	2.83e-5	1.62e-4	2.33e-4	3.24e-4	1.81e-4	4.81e-5	4.00e-7
14	3.91e-8	1.07e-6	5.68e-5	2.68e-4	4.62e-4	7.00e-4	3.57e-4	9.21e-5	2.50e-6
15	1.20e-7	2.14e-6	9.76e-5	4.38e-4	8.77e-4	1.36e-3	6.33e-4	1.56e-4	3.52e-6
17	8.18e-7	1.14e-5	2.38e-4	1.07e-3	2.61e-3	3.69e-3	1.47e-3	3.45e-4	9.40e-6
20	5.80e-6	4.91e-5	6.31e-4	3.59e-3	8.54e-3	1.04e-2	3.59e-3	8.33e-4	2.13e-5
22	1.54e-5	1.07e-4	1.14e-3	6.69e-3	1.49e-2	1.67e-2	5.51e-3	1.20e-3	3.43e-5
25	4.73e-5	2.66e-5	2.53e-3	1.41e-4	2.79e-2	2.88e-2	8.96e-3	1.99e-3	5.78e-5
30	1.99e-4	8.77e-4	7.12e-3	3.32e-2	5.81e-2	5.47e-2	1.63e-2	3.52e-3	1.03e-4
35	5.66e-4	2.16e-3	1.47e-2	6.01e-2	9.45e-2	8.59e-2	2.59e-2	5.42e-3	1.61e-4
40	1.28e-3	4.28e-3	2.55e-2	9.16e-2	1.38e-1	1.23e-1	3.64e-2	7.64e-3	2.23e-4
45	2.44e-3	7.47e-3	3.91e-2	1.28e-1	1.81e-1	1.62e-1	4.91e-2	1.00e-2	2.82e-4
50	4.08e-3	1.16e-2	5.44e-2	1.64e-1	2.32e-1	2.03e-1	6.09e-2	1.27e-2	3.49e-4
60	9.11e-3	2.24e-1	8.93e-2	2.44e-1	3.34e-1	2.90e-1	9.01e-2	1.85e-2	4.86e-4
70	1.63e-2	3.61e-2	1.26e-1	3.18e-1	4.35e-1	3.82e-1	1.23e-1	2.53e-2	6.19e-4
80	2.75e-2								
100	4.51e-2	8.23e-2	2.26e-1	5.12e-1	7.02e-1	6.51e-1	2.25e-1	4.84e-2	1.09e-3
150	9.80e-2	1.55e-1	3.57e-1	7.56e-1	1.06e-0	1.07e-0	4.41e-1	1.03e-1	2.13e-3
200	1.50e-1	2.20e-1	4.58e-1	9.36e-1	1.33e-0	1.43e-0	6.80e-1	1.71e-1	3.33e-3
300	2.40e-1	3.27e-1	6.10e-1	1.18e-0	1.71e-0	2.03e-0	1.19e-0	3.50e-1	7.10e-3
500	3.72e-1	4.72e-1	7.98e-1	1.47e-0	2.17e-0	2.83e-0	2.18e-0	8.37e-1	2.11e-2
700	4.58e-1	5.67e-1	9.13e-1	1.64e-0	2.44e-0	3.33e-0	3.04e-0	1.43e-0	4.59e-2
1000	5.44e-1	6.56e-1	1.02e-0	1.80e-0	2.68e-0	3.81e-0	4.00e-0	2.33e-0	1.12e-1
3000	7.00e-1								

Sputtered energy of Be by Ne  
 ne=24, na= 9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10		1.19e-8				1.10e-6	1.01e-6	3.08e-7	
11		1.27e-7	2.37e-6	4.08e-6	5.07e-6	3.67e-6	1.12e-6	1.96e-8	
12	1.52e-9	4.90e-7	6.11e-6	1.05e-5	1.58e-5	1.11e-5	3.49e-6	1.49e-7	
13	1.4e-10	8.29e-9	1.26e-6	2.12e-5	2.39e-5	4.26e-5	2.82e-5	7.95e-6	5.45e-8
14	9.3e-10	2.71e-8	2.73e-6	2.11e-5	4.96e-5	9.50e-5	5.78e-5	1.56e-5	4.46e-7
15	2.47e-9	7.18e-8	4.86e-6	3.64e-5	9.81e-5	1.91e-4	1.05e-4	2.73e-5	5.54e-7
17	2.32e-8	3.97e-7	1.30e-5	9.73e-5	3.19e-4	5.61e-4	2.64e-4	6.26e-5	1.46e-6
20	1.78e-7	1.89e-6	3.83e-5	3.67e-4	1.14e-3	1.73e-3	6.77e-4	1.58e-4	3.26e-6
22	4.86e-7	4.33e-6	7.41e-5	7.17e-4	2.08e-3	2.87e-3	1.08e-3	2.35e-4	5.25e-6
25	1.54e-6	1.17e-5	1.75e-4	1.59e-3	4.05e-3	5.11e-3	1.80e-3	3.99e-4	8.90e-6
30	7.04e-6	4.04e-5	5.35e-4	3.91e-3	8.69e-3	1.01e-2	3.37e-3	6.97e-4	1.52e-5
35	2.01e-5	1.04e-4	1.13e-3	7.13e-3	1.43e-2	1.60e-2	5.35e-3	1.06e-3	2.26e-5
40	4.63e-5	2.08e-4	1.96e-3	1.09e-2	2.09e-2	2.28e-2	7.57e-3	1.48e-3	2.96e-5
45	8.74e-5	3.61e-4	2.98e-3	1.51e-2	2.73e-2	3.00e-2	9.96e-3	1.87e-3	3.63e-5
50	1.44e-4	5.52e-4	4.08e-3	1.88e-2	3.43e-2	3.72e-2	1.22e-2	2.35e-3	4.27e-5
60	3.10e-4	1.03e-3	6.37e-3	2.69e-2	4.74e-2	5.10e-2	1.75e-2	3.30e-3	5.48e-5
70	5.29e-4	1.58e-3	8.64e-3	3.35e-2	5.88e-2	6.47e-2	2.30e-2	4.29e-3	6.36e-5
100	1.32e-3	3.17e-3	1.35e-2	4.65e-2	8.23e-2	9.57e-2	3.81e-2	7.22e-3	9.03e-5
150	2.53e-3	5.16e-3	1.78e-2	5.56e-2	9.96e-2	1.28e-1	6.43e-2	1.35e-2	1.34e-4
200	3.47e-3	6.48e-3	1.97e-2	5.86e-2	1.04e-1	1.44e-1	8.68e-2	2.04e-2	1.86e-4
300	4.67e-3	7.95e-3	2.15e-2	5.88e-2	1.05e-1	1.58e-1	1.23e-1	3.66e-2	3.37e-4
500	5.69e-3	8.89e-3	2.18e-2	5.56e-2	9.89e-2	1.60e-1	1.63e-1	7.05e-2	9.18e-4
700	5.96e-3	9.06e-3	2.11e-2	5.23e-2	9.31e-2	1.53e-1	1.82e-1	9.99e-2	1.96e-3
1000	5.97e-3	8.85e-3	2.00e-2	4.86e-2	8.65e-2	1.45e-1	1.90e-1	1.33e-1	4.85e-3

# Ne → Be

Particle reflection coefficient of Ne backscattered from Be  
 z1=10, m1= 20.18, z2= 4, m2= 9.01, sbe=3.38 eV, rho=1.80 g/cm\*\*3  
 ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program : trvmc  
 ne=24, na= 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	2.81E-3	1.01E-2	5.76E-2	2.62E-1	5.23E-1	8.09E-1	9.74E-1	9.97E-1	1.00E+0
11	2.16E-3	8.46E-3	5.28E-2	2.55E-1	5.18E-1	8.08E-1	9.74E-1	9.97E-1	1.00E+0
12	1.64E-3	7.08E-3	4.88E-2	2.48E-1	5.12E-1	8.07E-1	9.74E-1	9.97E-1	1.00E+0
13	1.28E-3	5.97E-3	4.54E-2	2.41E-1	5.08E-1	8.05E-1	9.75E-1	9.97E-1	1.00E+0
14	1.00E-3	5.11E-3	4.25E-2	2.36E-1	5.03E-1	8.04E-1	9.75E-1	9.97E-1	1.00E+0
15	7.95E-4	4.38E-3	4.01E-2	2.31E-1	4.99E-1	8.02E-1	9.75E-1	9.97E-1	1.00E+0
17	5.15E-4	3.38E-3	3.62E-2	2.22E-1	4.91E-1	7.99E-1	9.75E-1	9.97E-1	1.00E+0
20	2.90E-4	2.48E-3	3.20E-2	2.11E-1	4.80E-1	7.94E-1	9.76E-1	9.97E-1	1.00E+0
22	2.09E-4	2.08E-3	2.99E-2	2.05E-1	4.74E-1	7.91E-1	9.75E-1	9.98E-1	1.00E+0
25	1.37E-4	1.69E-3	2.71E-2	1.96E-1	4.64E-1	7.85E-1	9.75E-1	9.98E-1	1.00E+0
30	8.62E-5	1.34E-3	2.37E-2	1.84E-1	4.48E-1	7.75E-1	9.75E-1	9.98E-1	1.00E+0
35	7.06E-5	1.14E-3	2.10E-2	1.71E-1	4.32E-1	7.64E-1	9.73E-1	9.98E-1	1.00E+0
40	6.03E-5	1.03E-3	1.90E-2	1.62E-1	4.15E-1	7.52E-1	9.72E-1	9.98E-1	1.00E+0
45	5.62E-5	8.75E-4	1.71E-2	1.50E-1	4.03E-1	7.41E-1	9.70E-1	9.98E-1	1.00E+0
50	5.09E-5	8.22E-4	1.57E-2	1.41E-1	3.87E-1	7.29E-1	9.69E-1	9.97E-1	1.00E+0
60	4.43E-5	6.54E-4	1.32E-2	1.25E-1	3.59E-1	7.05E-1	9.64E-1	9.97E-1	1.00E+0
70	3.79E-5	5.71E-4	1.13E-2	1.11E-1	3.33E-1	6.81E-1	9.59E-1	9.97E-1	1.00E+0
100	2.43E-5	3.80E-4	7.60E-3	8.29E-2	2.71E-1	6.11E-1	9.42E-1	9.96E-1	1.00E+0
150	2.08E-5	2.71E-4	5.22E-3	5.69E-2	2.02E-1	5.17E-1	9.07E-1	9.92E-1	1.00E+0
200	1.58E-5	2.22E-4	3.79E-3	4.35E-2	1.60E-1	4.45E-1	8.68E-1	9.86E-1	1.00E+0
300	1.46E-5	1.76E-4	2.97E-3	3.13E-2	1.14E-1	3.45E-1	7.86E-1	9.69E-1	1.00E+0
500	1.75E-5	1.47E-4	2.17E-3	2.19E-2	7.81E-2	2.43E-1	6.53E-1	9.18E-1	1.00E+0
700	1.95E-5	1.34E-4	1.81E-3	1.74E-2	6.32E-2	2.00E-1	5.55E-1	8.59E-1	9.99E-1
1000	1.33E-5	1.29E-4	1.52E-3	1.38E-2	5.13E-2	1.61E-1	4.64E-1	7.69E-1	9.97E-1

Energy reflection coefficient of Ne backscattered from Be  
 ne=24, na= 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	1.04E-7	1.43E-5	8.08E-4	1.46E-2	6.57E-2	2.11E-1	4.82E-1	6.48E-1	7.99E-1
11	1.17E-7	1.60E-5	8.64E-4	1.53E-2	6.81E-2	2.16E-1	4.91E-1	6.57E-1	8.09E-1
12	1.33E-7	1.78E-5	9.09E-4	1.59E-2	7.10E-2	2.21E-1	5.00E-1	6.65E-1	8.17E-1
13	1.62E-7	1.93E-5	9.46E-4	1.65E-2	7.19E-2	2.25E-1	5.07E-1	6.73E-1	8.25E-1
14	2.18E-7	2.09E-5	9.76E-4	1.69E-2	7.35E-2	2.29E-1	5.14E-1	6.80E-1	8.31E-1
15	2.96E-7	2.25E-5	1.00E-3	1.73E-2	7.48E-2	2.32E-1	5.20E-1	6.86E-1	8.37E-1
17	4.76E-7	2.57E-5	1.04E-3	1.78E-2	7.71E-2	2.38E-1	5.31E-1	6.98E-1	8.48E-1
20	6.38E-7	2.86E-5	1.07E-3	1.83E-2	7.93E-2	2.45E-1	5.45E-1	7.13E-1	8.61E-1
22	7.13E-7	2.90E-5	1.08E-3	1.84E-2	8.01E-2	2.48E-1	5.52E-1	7.21E-1	8.68E-1
25	6.66E-7	2.83E-5	1.07E-3	1.84E-2	8.11E-2	2.52E-1	5.61E-1	7.31E-1	8.77E-1
30	7.03E-7	2.62E-5	1.01E-3	1.81E-2	8.11E-2	2.55E-1	5.73E-1	7.46E-1	8.89E-1
35	7.21E-7	2.38E-5	9.43E-4	1.74E-2	7.99E-2	2.57E-1	5.81E-1	7.56E-1	8.97E-1
40	6.93E-7	2.18E-5	8.68E-4	1.66E-2	7.82E-2	2.55E-1	5.87E-1	7.65E-1	9.04E-1
45	6.30E-7	1.84E-5	7.71E-4	1.57E-2	7.67E-2	2.54E-1	5.91E-1	7.72E-1	9.10E-1
50	5.49E-7	1.69E-5	7.06E-4	1.49E-2	7.43E-2	2.52E-1	5.94E-1	7.77E-1	9.15E-1
60	4.51B-7	1.25E-5	5.78E-4	1.31E-2	6.92E-2	2.46E-1	5.97E-1	7.85E-1	9.23E-1
70	3.56E-7	1.03E-5	4.82E-4	1.16E-2	6.41E-2	2.38E-1	5.95E-1	7.90E-1	9.29E-1
100	2.39E-7	6.24E-6	2.94E-4	8.20E-3	5.14E-2	2.12E-1	5.87E-1	7.99E-1	9.39E-1
150	1.60E-7	4.06E-6	1.70E-4	5.11E-3	3.51E-2	1.75E-1	5.57E-1	7.96E-1	9.48E-1
200	9.92E-8	2.85E-6	1.17E-4	3.53E-3	2.66E-2	1.45E-1	5.23E-1	7.87E-1	9.52E-1
300	8.47E-8	2.27E-6	8.25E-5	2.27E-3	1.70E-2	1.04E-1	4.55E-1	7.58E-1	9.55E-1
500	1.10E-7	1.96E-6	5.83E-5	1.44E-3	1.01E-2	6.35E-2	3.50E-1	6.89E-1	9.53E-1
700	1.29E-7	1.91E-6	4.95E-5	1.10E-3	7.62E-3	4.85E-2	2.78E-1	6.19E-1	9.49E-1
1000	1.29E-7	2.03E-6	4.40E-5	8.63E-4	5.85E-3	3.62E-2	2.16E-1	5.28E-1	9.39E-1

Average depth (mean range) in Å of Ne implanted in Be  
 ne=24, na= 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	9.62E-1	8.78E-1	7.76E-1	7.00E-1	6.00E-1	5.00E-1	4.00E-1	3.00E-1	2.00E-1
11	1.03E+0	9.55E-1	8.42E-1	7.00E-1	6.00E-1	5.00E-1	4.00E-1	3.00E-1	1.00E-1
12	1.11E+0	1.03E+0	9.08E-1	8.00E-1	7.00E-1	6.00E-1	4.00E-1	3.00E-1	1.00E-1
13	1.19E+0	1.11E+0	9.76E-1	8.00E-1	7.00E-1	6.00E-1	4.00E-1	3.00E-1	2.00E-1
14	1.27E+0	1.19E+0	1.05E+0	9.00E-1	8.00E-1	6.00E-1	5.00E-1	3.00E-1	2.00E-1
15	1.36E+0	1.28E+0	1.12E+0	9.00E-1	8.00E-1	7.00E-1	5.00E-1	4.00E-1	2.00E-1
17	1.54E+0	1.46E+0	1.26E+0	1.00E+0	9.00E-1	7.00E-1	5.00E-1	4.00E-1	2.00E-1
20	1.82E+0	1.72E+0	1.48E+0	1.20E+0	1.00E+0	8.00E-1	6.00E-1	4.00E-1	2.00E-1
22	1.99E+0	1.88E+0	1.62E+0	1.30E+0	1.10E+0	9.00E-1	6.00E-1	5.00E-1	2.00E-1
25	2.23E+0	2.12E+0	1.82E+0	1.40E+0	1.20E+0	1.00E+0	7.00E-1	5.00E-1	3.00E-1
30	2.62E+0	2.49E+0	2.14E+0	1.70E+0	1.40E+0	1.10E+0	8.00E-1	6.00E-1	4.00E-1
35	3.00E+0	2.85E+0	2.45E+0	1.90E+0	1.60E+0	1.30E+0	9.00E-1	7.00E-1	4.00E-1
40	3.34E+0	3.18E+0	2.74E+0	2.20E+0	1.80E+0	1.40E+0	1.00E+0	8.00E-1	6.00E-1
45	3.68E+0	3.50E+0	3.02E+0	2.40E+0	2.00E+0	1.60E+0	1.10E+0	9.00E-1	5.00E-1
50	3.99E+0	3.81E+0	3.29E+0	2.60E+0	2.10E+0	1.70E+0	1.30E+0	1.00E+0	5.00E-1
60	4.59E+0	4.38E+0	3.80E+0	3.00E+0	2.50E+0	2.00E+0	1.50E+0	1.20E+0	8.00E-1
70	5.15E+0	4.92E+0	4.28E+0	3.40E+0	2.80E+0	2.20E+0	1.70E+0	1.30E+0	9.00E-1
100	6.65E+0	6.37E+0	5.57E+0	4.40E+0	3.60E+0	2.90E+0	2.30E+0	1.80E+0	1.30E+0
150	8.81E+0	8.46E+0	7.43E+0	5.90E+0	4.90E+0	4.00E+0	3.10E+0	2.60E+0	1.80E+0
200	1.07E+1	1.03E+1	9.08E+0	7.30E+0	6.00E+0	4.90E+0	3.90E+0	3.20E+0	2.30E+0
300	1.41E+1	1.36E+1	1.20E+1	9.70E+0	8.00E+0	6.40E+0	5.10E+0	4.40E+0	3.50E+0
500	2.01E+1	1.94E+1	1.72E+1	1.40E+1	1.15E+1	9.30E+0	7.40E+0	6.60E+0	5.10E+0
700	2.55E+1	2.46E+1	2.19E+1	1.78E+1	1.47E+1	1.18E+1	9.30E+0	8.30E+0	7.00E+0
1000	3.31E+1	3.20E+1	2.85E+1	2.32E+1	1.92E+1	1.53E+1	1.21E+1	9.00E+0	

# Ar → Be

Sputtering yield of Be by Ar  
 z1=18, m1= 39.95, z2= 4, m2= 9.01, sbe=3.38 eV, rho=1.80 g/cm\*\*3  
 ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program : trvmc  
 ne=25, na= 9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
13				2.60e-7	8.90e-7	8.35e-7	1.07e-6	4.80e-7	
14				2.39e-6	4.69e-6	4.33e-6	5.37e-6	1.91e-6	
15			7.83e-7	2.25e-5	3.14e-5	2.60e-5	1.66e-5	4.82e-6	
16				3.14e-6	4.89e-5	6.85e-5	6.80e-5	4.39e-5	1.23e-5
17				8.57e-6	8.55e-5	1.25e-4	1.48e-4	9.74e-5	2.85e-5
18				1.71e-5	1.36e-4	2.12e-4	2.87e-4	1.93e-4	5.23e-5
20		1.14e-6	4.85e-5	2.93e-5	5.25e-4	8.85e-5	5.55e-4	1.40e-4	3.98e-6
22		4.14e-6	1.15e-4	5.51e-4	1.23e-3	2.25e-3	1.21e-3	3.03e-4	8.70e-6
25	9.80e-7	1.64e-5	2.73e-4	1.40e-3	3.45e-3	6.31e-3	3.02e-3	6.97e-4	2.05e-5
30	1.18e-5	7.63e-5	8.35e-4	5.09e-3	1.25e-2	1.91e-2	8.09e-3	1.84e-3	5.23e-5
35	5.22e-5	2.46e-4	2.24e-3	1.26e-2	2.91e-2	3.99e-2	1.59e-2	3.50e-3	1.05e-4
40	1.48e-4	6.29e-4	4.94e-3	2.48e-2	5.33e-2	6.71e-2	2.63e-2	5.89e-3	1.76e-4
45	3.43e-4	1.30e-3	8.96e-3	4.12e-2	8.22e-2	1.01e-1	3.83e-2	8.57e-3	2.66e-4
50	6.98e-4	2.36e-3	1.44e-2	6.12e-2	1.18e-1	1.38e-1	5.28e-2	1.18e-2	3.50e-4
60	2.02e-3	5.80e-3	2.99e-2	1.10e-1	1.95e-1	2.25e-1	8.65e-2	1.90e-2	5.71e-4
70	4.36e-3	1.13e-2	4.99e-2	1.64e-1	2.82e-1	3.22e-1	1.24e-1	2.82e-2	8.30e-4
100	1.83e-2	3.79e-2	1.24e-1	3.29e-1	5.44e-1	6.30e-1	2.59e-1	5.83e-2	1.72e-3
150	5.72e-2	9.76e-2	2.45e-1	5.65e-1	9.13e-1	1.12e-0	5.23e-1	1.28e-1	3.62e-3
200	1.01e-1	1.59e-1	3.51e-1	7.56e-1	1.20e-0	1.54e-0	8.81e-1	2.15e-1	6.01e-3
300	1.91e-1	2.69e-1	5.28e-1	1.05e-0	1.64e-0	2.22e-0	1.40e-0	4.23e-1	1.23e-2
500	3.49e-1	4.49e-1	7.86e-1	1.46e-0	2.24e-0	3.21e-0	2.58e-0	9.51e-1	3.31e-2
700	4.71e-1	5.87e-1	9.68e-1	1.74e-0	2.65e-0	3.93e-0	3.65e-0	1.60e-0	6.52e-2
1000	6.07e-1	7.36e-1	1.16e-0	2.03e-0	3.07e-0	4.65e-0	5.01e-0	2.64e-0	1.36e-1
3000	9.00e-1								
5000	1.06e-0								

Sputtered energy of Be by Ar  
 ne=23, na= 9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
13				9.75e-9	4.49e-8	6.19e-8	9.51e-8	4.58e-8	
14				8.70e-8	2.38e-7	3.27e-7	4.68e-7	1.76e-7	
15			1.72e-8	9.43e-7	1.76e-6	2.05e-6	1.67e-6	5.09e-7	
16			8.72e-8	2.17e-6	4.05e-6	5.52e-6	4.45e-6	1.34e-6	
17			2.28e-7	3.98e-6	7.77e-6	1.24e-5	1.00e-5	3.19e-6	
18			4.90e-7	6.61e-6	1.41e-5	2.48e-5	2.03e-5	5.75e-6	1.56e-7
20		2.53e-8	1.55e-6	1.54e-5	3.70e-5	8.09e-5	6.12e-5	1.61e-5	3.80e-7
22		9.68e-8	3.93e-6	3.07e-5	9.34e-5	2.17e-4	1.39e-4	3.60e-5	8.76e-7
25	1.89e-8	4.14e-7	1.03e-5	8.67e-5	3.03e-4	6.52e-4	3.69e-4	8.62e-5	2.10e-6
30	2.75e-7	2.11e-6	3.58e-5	3.56e-4	1.14e-3	2.12e-3	1.06e-3	2.38e-4	5.40e-6
35	1.23e-6	7.52e-6	1.05e-4	9.40e-4	2.76e-3	4.66e-3	2.13e-3	4.62e-4	1.07e-5
40	3.64e-6	2.02e-5	2.45e-4	1.93e-3	5.18e-3	8.02e-3	3.60e-3	7.69e-4	1.76e-5
45	8.67e-6	4.36e-5	4.61e-4	3.23e-3	8.07e-3	1.22e-2	5.21e-3	1.12e-3	2.58e-5
50	1.78e-5	7.94e-5	7.52e-4	4.83e-3	1.15e-2	1.67e-2	7.21e-3	1.51e-3	3.31e-5
60	5.17e-5	1.99e-4	1.56e-3	8.63e-3	1.90e-2	2.71e-2	1.17e-2	2.42e-3	5.04e-5
70	1.11e-4	3.83e-4	2.55e-3	1.25e-2	2.69e-2	3.81e-2	1.65e-2	3.47e-3	6.78e-5
100	4.26e-4	1.17e-3	5.80e-3	2.29e-2	4.74e-2	6.89e-2	3.24e-2	6.58e-3	1.15e-4
150	1.19e-3	2.68e-3	1.00e-2	3.38e-2	6.83e-2	1.05e-1	5.84e-2	1.27e-2	1.88e-4
200	1.92e-3	3.91e-3	1.28e-2	3.96e-2	7.79e-2	1.27e-1	8.12e-2	1.96e-2	2.62e-4
300	3.09e-3	5.49e-3	1.59e-2	4.48e-2	8.48e-2	1.46e-1	1.18e-1	3.42e-2	4.24e-4
500	4.48e-3	7.27e-3	1.82e-2	4.71e-2	8.64e-2	1.54e-1	1.67e-1	6.55e-2	9.72e-4
700	5.21e-3	7.94e-3	1.90e-2	4.71e-2	8.50e-2	1.53e-1	1.92e-1	9.60e-2	1.80e-3
1000	5.58e-3	8.31e-3	1.91e-2	4.61e-2	8.24e-2	1.48e-1	2.09e-1	1.31e-1	3.89e-3

# Ar → Be

Particle reflection coefficient of Ar backscattered from Be  
 z1=18, m1= 39.95, z2= 4, m2= 9.01, sbe=3.38 eV, rho=1.80 g/cm\*\*3  
 ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program : trvmc  
 ne=24, na= 8

E <sub>0</sub> (eV)	15°	30°	45°	55°	65°	75°	80°	85°
10	4.00e-7	1.00e-3	4.73e-2	2.55e-1	6.78e-1	9.67e-1	9.97e-1	1.00e-0
13			4.86e-2	2.69e-1	9.72e-1	9.98e-1		
14			4.77e-2	2.68e-1	6.99e-1	9.72e-1	9.98e-1	
15			5.69e-4	4.21e-2	2.53e-1	6.85e-1	9.70e-1	9.98e-1 1.00e-0
16			5.24e-4	4.15e-2	2.52e-1	6.86e-1	9.71e-1	9.98e-1 1.00e-0
17			5.01e-4	4.10e-2	2.51e-1	6.87e-1	9.71e-1	9.98e-1 1.00e-0
18			4.81e-4	4.06e-2	2.51e-1	6.87e-1	9.72e-1	9.98e-1 1.00e-0
20	4.00e-8	4.58e-4	3.99e-2	2.49e-1	6.87e-1	9.72e-1	9.98e-1	1.00e-0
22	2.20e-7	4.57e-4	3.91e-2	2.48e-1	6.86e-1	9.73e-1	9.98e-1	1.00e-0
25	4.00e-7	4.45e-4	3.81e-2	2.44e-1	6.83e-1	9.73e-1	9.98e-1	1.00e-0
30	5.00e-7	4.34e-4	3.62e-2	2.38e-1	6.77e-1	9.73e-1	9.98e-1	1.00e-0
35	4.50e-7	3.98e-4	3.39e-2	2.29e-1	6.68e-1	9.72e-1	9.98e-1	1.00e-0
40	4.67e-7	3.66e-4	3.19e-2	2.20e-1	6.59e-1	9.71e-1	9.98e-1	1.00e-0
45	1.00e-7	3.57e-4	2.99e-2	2.12e-1	6.48e-1	9.70e-1	9.98e-1	1.00e-0
50	3.50e-7	3.11e-4	2.78e-2	2.02e-1	6.37e-1	9.68e-1	9.98e-1	1.00e-0
60	1.00e-6	2.54e-4	2.37e-2	1.85e-1	6.14e-1	9.64e-1	9.98e-1	1.00e-0
70	3.33e-7	2.08e-4	2.05e-2	1.68e-1	5.93e-1	9.61e-1	9.98e-1	1.00e-0
100	1.00e-7	1.32e-4	1.36e-2	1.29e-1	5.27e-1	9.46e-1	9.97e-1	1.00e-0
150		8.09e-6	8.10e-3	8.63e-2	4.30e-1	9.16e-1	9.94e-1	1.00e-0
200		5.63e-5	5.64e-3	6.25e-2	3.58e-1	8.81e-1	9.90e-1	1.00e-0
300		4.07e-5	3.56e-3	3.99e-2	2.61e-1	8.11e-1	9.80e-1	1.00e-0
500		2.90e-5	2.39e-3	2.39e-2	1.67e-1	6.73e-1	9.45e-1	1.00e-0
700		2.05e-5	1.88e-3	1.83e-2	1.24e-1	5.71e-1	8.98e-1	1.00e-0
1000		2.20e-5	1.48e-3	1.40e-2	9.57e-2	4.65e-1	8.23e-1	9.99e-1

Energy reflection coefficient of Ar backscattered from Be  
 ne=24, na= 8

E <sub>0</sub> (eV)	15°	30°	45°	55°	65°	75°	80°	85°
10		2.36e-6	9.15e-4	1.44e-2	1.03e-1	3.73e-1	5.64e-1	7.65e-1
13		1.01e-3	1.58e-2	1.11e-1	3.93e-1	5.88e-1		
14		1.05e-3	1.62e-2	1.14e-1	3.99e-1	5.94e-1		
15	4.53e-6	1.18e-3	1.71e-2	1.17e-1	4.04e-1	6.01e-1	7.96e-1	
16	4.75e-6	1.21e-3	1.74e-2	1.18e-1	4.09e-1	6.06e-1	8.00e-1	
17	5.10e-6	1.24e-3	1.77e-2	1.20e-1	4.14e-1	6.12e-1	8.05e-1	
18	5.34e-6	1.26e-3	1.80e-2	1.22e-1	4.18e-1	6.16e-1	8.09e-1	
20	5.68e-6	1.30e-3	1.84e-2	1.24e-1	4.25e-1	6.25e-1	8.16e-1	
22	1.93e-9	6.03e-6	1.31e-3	1.87e-2	1.26e-1	4.32e-1	6.33e-1	8.22e-1
25	2.96e-9	6.22e-6	1.33e-3	1.90e-2	1.29e-1	4.41e-1	6.44e-1	8.30e-1
30	3.21e-9	6.22e-6	1.30e-3	1.90e-2	1.31e-1	4.52e-1	6.58e-1	8.41e-1
35	2.57e-9	5.74e-6	1.25e-3	1.88e-2	1.33e-1	4.61e-1	6.69e-1	8.51e-1
40	3.75e-9	5.30e-6	1.19e-3	1.83e-2	1.33e-1	4.67e-1	6.78e-1	8.59e-1
45	1.12e-9	5.04e-6	1.13e-3	1.77e-2	1.33e-1	4.72e-1	6.86e-1	8.66e-1
50	1.66e-9	4.12e-6	1.04e-3	1.72e-2	1.31e-1	4.76e-1	6.93e-1	8.72e-1
60	7.99e-9	3.38e-6	8.71e-4	1.57e-2	1.28e-1	4.81e-1	7.03e-1	8.82e-1
70	1.90e-9	2.59e-6	7.43e-4	1.44e-2	1.25e-1	4.84e-1	7.10e-1	8.89e-1
100	1.29e-6	4.59e-4	1.09e-2	1.12e-1	4.81e-1	7.24e-1	9.04e-1	
150	6.60e-7	2.31e-4	6.83e-3	8.95e-2	4.65e-1	7.30e-1	9.18e-1	
200	4.45e-7	1.38e-4	4.53e-3	7.18e-2	4.40e-1	7.26e-1	9.25e-1	
300	2.72e-7	6.98e-5	2.38e-3	4.84e-2	3.93e-1	7.10e-1	9.31e-1	
500	1.92e-7	3.88e-5	1.10e-3	2.59e-2	3.02e-1	6.59e-1	9.34e-1	
700	8.85e-8	2.92e-5	7.54e-4	1.64e-2	2.41e-1	6.02e-1	9.32e-1	
1000	7.30e-8	2.16e-5	5.30e-4	1.14e-2	1.80e-1	5.25e-1	9.25e-1	

Average depth (mean range) in Å of Ar implanted in Be  
 ne=22, na= 9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	1.30E+0	1.30E+0	1.20E+0	1.00E+0	8.00E-1	6.00E-1	5.00E-1	4.00E-1	2.00E-1
15	2.10E+0	2.00E+0	1.80E+0	1.30E+0	1.10E+0	8.00E-1	6.00E-1	5.00E-1	4.00E-1
16	2.30E+0	1.90E+0	1.80E+0	1.40E+0	1.10E+0	9.00E-1	7.00E-1	5.00E-1	2.00E-1
17	2.40E+0	2.00E+0	2.00E+0	1.50E+0	1.20E+0	9.00E-1	7.00E-1	5.00E-1	2.00E-1
18	2.50E+0	2.40E+0	2.10E+0	1.60E+0	1.20E+0	9.00E-1	7.00E-1	6.00E-1	3.00E-1
20	2.70E+0	2.60E+0	2.20E+0	1.70E+0	1.30E+0	1.00E+0	8.00E-1	6.00E-1	4.00E-1
22	2.90E+0	2.80E+0	2.40E+0	1.80E+0	1.40E+0	1.10E+0	8.00E-1	6.00E-1	4.00E-1
25	3.30E+0	3.10E+0	2.70E+0	2.00E+0	1.50E+0	1.20E+0	9.00E-1	7.00E-1	6.00E-1
30	3.70E+0	3.60E+0	3.10E+0	2.30E+0	1.80E+0	1.30E+0	1.00E+0	8.00E-1	6.00E-1
35	4.20E+0	4.00E+0	3.50E+0	2.60E+0	2.00E+0	1.50E+0	1.10E+0	1.00E+0	6.00E-1
40	4.60E+0	4.40E+0	3.80E+0	2.80E+0	2.20E+0	1.60E+0	1.20E+0	1.10E+0	8.00E-1
45	5.00E+0	4.80E+0	4.10E+0	3.10E+0	2.40E+0	1.80E+0	1.30E+0	1.10E+0	7.00E-1
50	5.30E+0	5.10E+0	4.40E+0	3.30E+0	2.50E+0	1.90E+0	1.50E+0	1.20E+0	1.10E+0
60	6.00E+0	5.70E+0	5.00E+0	3.70E+0	2.90E+0	2.20E+0	1.70E+0	1.40E+0	1.00E+0
70	6.60E+0	6.30E+0	5.50E+0	4.20E+0	3.20E+0	2.40E+0	1.80E+0	1.60E+0	1.10E+0
100	8.20E+0	7.90E+0	6.90E+0	5.30E+0	4.00E+0	3.10E+0	2.30E+0	1.90E+0	1.40E+0
150	1.04E+1	1.00E+1	8.80E+0	6.80E+0	5.30E+0	4.00E+0	3.00E+0	2.60E+0	1.40E+0
200	1.23E+1	1.19E+1	1.04E+1	8.10E+0	6.30E+0	4.70E+0	3.60E+0	3.10E+0	2.80E+0
300	1.56E+1	1.50E+1	1.33E+1	1.05E+1	8.20E+0	6.10E+0	4.70E+0	4.00E+0	4.20E+0
500	2.11E+1	2.03E+1	1.80E+1	1.43E+1	1.13E+1	8.40E+0	6.40E+0	5.60E+0	4.40E+0
700	2.57E+1	2.48E+1	2.20E+1	1.76E+1	1.40E+1	1.04E+1	7.70E+0	6.80E+0	6.00E+0
1000	3.19E+1	3.07E+1	2.74E+1	2.20E+1	1.76E+1	1.31E+1	9.70E+0	8.50E+0	7.10E+0

# D → B

Sputtering yield of B by D

$z1 = 1$ ,  $m1 = 2.01$ ,  $z2 = 5$ ,  $m2 = 10.81$ ,  $sbe = 5.73$  eV,  $\rho = 2.35$  g/cm\*\*3  
 $ef = 0.95$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program : testvmcx, trspv1cn, IPP 9/82  
ne=10, na=14

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$	$82^\circ$	$85^\circ$	$88^\circ$
30	1.17e-3	1.25e-3	1.47e-3	1.81e-3	2.23e-3	2.29e-3	1.97e-3	1.62e-3	1.15e-3	7.05e-4	3.21e-4			
50	6.66e-3	6.78e-3	7.80e-3	1.00e-2	1.32e-2	1.78e-2	2.22e-2	2.23e-2	2.03e-2	1.40e-2	5.85e-3		1.17e-3	
100	1.46e-2	1.57e-2	1.78e-2	2.24e-2	3.23e-2	5.10e-2	7.69e-2	8.90e-2	9.82e-2	8.32e-2	3.79e-2		3.69e-3	
200	1.95e-2													
400	2.05e-2			2.60e-2	3.67e-2	5.24e-2	7.93e-2	1.29e-1		2.08e-1	2.53e-1	2.41e-1		3.82e-2
500	1.87e-2			2.16e-2	2.57e-2	3.52e-2	5.18e-2	7.86e-2	1.28e-1		2.06e-1	2.55e-1	2.68e-1	6.09e-2
1000	1.66e-2												2.20e-1	
5000	6.97e-3													
8000	5.43e-3				6.36e-3			1.19e-2	1.77e-2	2.88e-2		5.79e-2	8.04e-2	1.30e-1
100000											1.34e-2			2.41e-1
												3.90e-2		1.73e-1
													8.93e-2	

Sputtered energy of B by D  
program : testvmcx, trspv1cn  
ne=10, na=14

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$	$82^\circ$	$85^\circ$	$88^\circ$
30	6.71e-5	7.42e-5	8.99e-5	1.28e-4	1.68e-4	1.90e-4	1.78e-4	1.54e-4	1.09e-4	7.02e-5	3.26e-5			
50	4.48e-4	4.76e-4	5.76e-4	7.99e-4	1.11e-3	1.62e-3	2.29e-3	2.41e-3	2.35e-3	1.75e-3	8.24e-4		1.72e-4	
100	9.26e-4	9.78e-4	1.13e-3	1.50e-3	2.22e-3	3.88e-3	6.45e-3	8.21e-3	1.02e-2	9.74e-3	5.10e-3		5.83e-4	
200	9.17e-4													
400	6.45e-4			8.92e-4	1.33e-3	1.96e-3	3.29e-3	5.80e-3		1.06e-2	1.38e-2	1.51e-2		3.22e-3
500	4.95e-4			6.28e-4	7.28e-4	1.08e-3	1.66e-3	2.90e-3	5.37e-3		9.45e-3	1.22e-2	1.43e-2	4.39e-3
1000	3.05e-4											1.26e-2		
5000	3.68e-5													
8000	1.91e-5				2.87e-5			8.94e-5	1.40e-4	2.56e-4		6.29e-4	8.34e-4	1.50e-3
100000											1.59e-4		2.52e-3	2.72e-4
												1.61e-3		

Particle reflection coefficient of D backscattered from B

$z1 = 1$ ,  $m1 = 2.01$ ,  $z2 = 5$ ,  $m2 = 10.81$ ,  $sbe = 5.73$  eV,  $\rho = 2.35$  g/cm\*\*3  
 $ef = 0.95$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program : testvmcx, trspv1cn  
ne=10, na=14

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$	$82^\circ$	$85^\circ$	$88^\circ$
30	2.68e-1	2.76e-1	3.02e-1	3.48e-1	4.17e-1	5.25e-1	6.75e-1	7.63e-1	8.54e-1	9.29e-1	9.76e-1			
50	2.27e-1	2.35e-1	2.58e-1	2.96e-1	3.54e-1	4.47e-1	5.84e-1	6.79e-1	7.87e-1	8.96e-1	9.69e-1		9.95e-1	
100	1.86e-1	1.90e-1	2.09e-1	2.42e-1	2.91e-1	3.67e-1	4.79e-1	5.59e-1	6.63e-1	8.04e-1	9.39e-1		9.96e-1	
200	1.48e-1													
400	1.11e-1			1.29e-1	1.54e-1	1.96e-1	2.59e-1	3.43e-1		4.76e-1	5.73e-1	7.33e-1		9.74e-1
500	9.68e-2			1.05e-1	1.13e-1	1.39e-1	1.86e-1	2.43e-1	3.30e-1		4.56e-1	5.46e-1	6.95e-1	9.59e-1
1000	6.40e-2										7.93e-1			
5000	1.14e-2													
8000	5.96e-3				8.01e-3			2.04e-2	4.26e-2	9.04e-2		1.96e-1	2.85e-1	4.03e-1
100000											7.82e-2		5.83e-1	8.74e-1
												2.71e-1	5.28e-1	

Energy reflection coefficient of D backscattered from B  
ne=10, na=14

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$	$82^\circ$	$85^\circ$	$88^\circ$
30	9.67e-2	1.02e-1	1.18e-1	1.48e-1	2.00e-1	2.93e-1	4.46e-1	5.48e-1	6.67e-1	7.82e-1	8.71e-1			
50	7.97e-2	8.37e-2	9.74e-2	1.20e-2	1.61e-2	2.34e-2	3.66e-2	4.70e-2	6.02e-2	7.53e-2	8.79e-2		9.40e-1	
100	6.30e-2	6.50e-2	7.53e-2	9.33e-2	1.25e-1	1.77e-1	2.73e-1	3.54e-1	4.70e-1	6.49e-1	8.48e-1		9.56e-1	
200	4.83e-2													
400	3.43e-2			4.21e-2	5.37e-2	7.54e-2	1.11e-1	1.69e-1		2.81e-1	3.83e-1	5.83e-1		9.29e-1
500	2.95e-2			3.19e-2	3.58e-2	4.75e-2	6.95e-2	1.02e-1	1.59e-1		2.61e-1	3.55e-1	6.66e-1	9.07e-1
1000	1.78e-2													
5000	2.57e-3													
8000	1.29e-3				1.78e-3			4.20e-3	9.06e-3	2.11e-2		5.59e-2	9.68e-2	1.72e-1
100000											6.80e-3		3.41e-1	7.63e-1
												3.98e-2	1.78e-1	

Average depth (mean range) of D implanted in B  
ne=10, na=14

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$	$82^\circ$	$85^\circ$	$88^\circ$
30	8.57e+0	8.52e+0	8.37e+0	8.13e+0	7.85e+0	7.51e+0	7.18e+0	7.03e+0	6.79e+0	6.62e+0	6.41e+0			
50	1.29e+1	1.28e+1	1.26e+1	1.22e+1	1.17e+1	1.11e+1	1.06e+1	1.03e+1	1.00e+1	9.79e+0	9.43e+0		9.11e+0	
100	2.31e+1	2.29e+1	2.25e+1	2.17e+1	2.07e+1	1.96e+1	1.85e+1	1.80e+1	1.74e+1	1.71e+1	1.67e+1		1.64e+1	
200	4.28e+1													
400	8.17e+1			7.87e+1	7.55e+1	7.11e+1	6.64e+1	6.18e+1		5.73e+1	5.58e+1	5.44e+1		5.27e+1
500	1.01e+2	1.00e+2		9.76e+1	9.33e+1	8.75e+1	8.16e+1	7.54e+1		7.00e+1	6.73e+1	6.60e+1		6.57e+1
1000	1.98e+2													
5000	9.16e+2													
8000	1.38e+3				1.30e+3			1.07e+3	9.25e+2	7.68e+2		6.27e+2	5.65e+2	5.17e+2
100000											1.49e+3		4.86e+2	4.80e+2
												1.07e+3	9.25e+2	

## D → B

```
D on B, Maxwellian velocity distribution, sheath potential 3 kT
z1= 1, m1= 2.00, z2= 5, m2= 10.81, sbe=5.73 eV, rho=2.35 g/cm**3 eff=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2,
kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : testvrmcx
ne=12
```

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
3	6.34e-5	8.86e-6	2.10e+0	4.15e-1	1.82e-1	6.58e+0	4.85e+0
4	3.81e-4	4.76e-5	2.50e+0	3.78e-1	1.64e-1	8.64e+0	6.02e+0
5	1.21e-3	1.36e-4	2.81e+0	3.51e-1	1.49e-1	1.06e+1	7.14e+0
10	9.12e-3	8.30e-4	4.55e+0	2.82e-1	1.13e-1	2.01e+1	1.23e+1
20	2.14e-2	1.47e-3	6.86e+0	2.27e-1	8.70e-2	3.83e+1	2.19e+1
30	2.64e-2	1.58e-3	8.98e+0	2.05e-1	7.69e-2	5.64e+1	3.14e+1
50	3.10e-2	1.44e-3	1.16e+1	1.74e-1	6.30e-2	9.04e+1	4.95e+1
100	3.12e-2	9.72e-4	1.56e+1	1.34e-1	4.52e-2	1.69e+2	9.48e+1
200	2.63e-2	5.84e-4	2.22e+1	9.36e-2	2.88e-2	3.08e+2	1.83e+2
500	1.64e-2	1.69e-4	2.57e+1	4.44e-2	1.15e-2	6.50e+2	4.36e+2
1000	1.10e-2	7.26e-5	3.31e+1	2.09e-2	4.67e-3	1.12e+3	8.19e+2
2000	6.35e-3	3.02e-5	4.75e+1	7.85e-3	1.61e-3	2.05e+3	1.47e+3

## B → B

Sputtering yield of B by B  
 $z1 = 5, m1 = 10.81, z2 = 5, m2 = 10.81, sbe = 5.73 \text{ eV}, rho = 2.35 \text{ g/cm}^{**3}$   
 $ef = 5.68, esb = 5.73, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1$  (KrC)  
 program: testvmcx, trspvmc, IPP 9/82  
 $n_{\text{e}} = 9, n_{\text{a}} = 13$

$E_0 (\text{eV})$	$0^\circ$	$15^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$45^\circ$	$50^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$	$85^\circ$
50	2.56e-3												
70	7.84e-3												
100	2.10e-2												
200	7.44e-2												
500	1.52e-1												
1000	2.12e-1	2.80e-1		3.44e-1	4.56e-1	6.75e-1	8.27e-1	1.02e-0	1.50e-0	1.79e-0	2.04e-0	2.29e-0	2.09e-0
2000	2.50e-1												
5000	2.13e-1												
10000	2.10e-1												

Sputtered energy of B by B  
 program: testvmcx, trspvmc  
 $n_{\text{e}} = 9, n_{\text{a}} = 13$

$E_0 (\text{eV})$	$0^\circ$	$15^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$45^\circ$	$50^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$	$85^\circ$
50	1.29e-4												
70	3.74e-4												
100	8.40e-4												
200	2.40e-3												
500	3.39e-3												
1000	3.51e-3	5.56e-3		1.28e-2		1.70e-2	3.14e-2	3.04e-2	7.18e-2	9.02e-2	1.11e-1	1.26e-1	1.09e-1
2000	2.82e-3		5.23e-3						5.34e-2	8.90e-2		1.11e-1	4.47e-2
5000	1.53e-3												
10000	9.83e-4												

Particle reflection coefficient of B backscattered from B  
 $z1 = 5, m1 = 10.81, z2 = 5, m2 = 10.81, sbe = 5.73 \text{ eV}, rho = 2.35 \text{ g/cm}^{**3}$   
 $ef = 5.68, esb = 5.73, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1$  (KrC)  
 program: testvmcx, trspvmc  
 $n_{\text{e}} = 9, n_{\text{a}} = 13$

$E_0 (\text{eV})$	$0^\circ$	$15^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$45^\circ$	$50^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$	$85^\circ$
50	4.45e-4												
70	8.65e-4												
100	1.88e-3												
200	3.90e-3												
500	5.17e-3												
1000	4.45e-3	7.30e-3		6.20e-3	2.41e-2	3.03e-2	5.72e-2	6.48e-2	1.59e-1	2.20e-1	3.17e-1	4.54e-1	6.82e-1
2000	2.85e-3								3.52e-2	2.64e-1	1.06e-1	3.56e-1	9.51e-1
5000	2.00e-3												8.93e-1
10000	7.00e-4												

Energy reflection coefficient of B backscattered from B  
 $n_{\text{e}} = 9, n_{\text{a}} = 13$

$E_0 (\text{eV})$	$0^\circ$	$15^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$45^\circ$	$50^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$	$85^\circ$
50	3.05e-5												
70	5.38e-5												
100	1.23e-4												
200	1.98e-4												
500	2.55e-4												
1000	2.60e-4	5.38e-4		5.40e-4	2.61e-3	4.16e-3	1.04e-2	1.29e-2	4.49e-2	7.82e-2	1.34e-1	2.43e-1	4.82e-1
2000	1.57e-4								3.52e-2	1.06e-1			3.56e-1
5000	1.07e-4												7.85e-1
10000	5.68e-5												

Average depth (mean range) in Å of B implanted in B  
 $n_{\text{e}} = 9, n_{\text{a}} = 13$

$E_0 (\text{eV})$	$0^\circ$	$15^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$45^\circ$	$50^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$	$85^\circ$
50	3.67e+0												
70	4.77e+0												
100	6.25e+0												
200	1.05e+1												
500	2.33e+1												
1000	4.13e+1	3.76e+1		6.84e+1	3.38e+1	5.69e+1	2.88e+1	4.97e+1	2.29e+1	4.21e+1	2.09e+1	1.92e+1	1.76e+1
2000	7.26e+1												
5000	1.76e+2												
10000	3.56e+2												

## B → B

B on B, Maxwellian velocity distribution, sheath potential 0 kT  
 $z1 = 5, m1 = 10.81, z2 = 5, m2 = 10.81, sbe = 5.73 \text{ eV}, rho = 2.35 \text{ g/cm}^{**3}$   
 $ef = 5.68 \text{ eV}, esb = 5.73 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1 \text{ (KrC)}$   
program: testvmcx  
ne=12

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
4	4.51e-4	2.92e-4	5.18e+0	1.58e-3	1.61e-3	8.15e+0	3.29e-1
5	1.12e-3	6.88e-4	6.11e+0	3.89e-3	3.67e-3	9.41e+0	4.34e-1
7	4.07e-3	2.16e-3	7.31e+0	1.19e-2	1.04e-2	1.22e+1	6.35e-1
10	1.18e-2	5.21e-3	8.87e+0	2.93e-2	2.30e-2	1.57e+1	9.17e-1
20	5.67e-2	1.74e-2	1.23e+1	9.08e-2	5.91e-2	2.60e+1	1.80e-0
50	2.12e-1	3.70e-2	1.74e+1	1.70e-1	9.17e-2	5.38e+1	4.27e+0
100	3.90e-1	4.50e-2	2.31e+1	1.87e-1	8.90e-2	9.57e+1	7.76e+0
200	6.02e-1	4.67e-2	3.10e+1	1.75e-1	7.72e-2	1.76e+2	1.37e+1
500	8.52e-1	3.84e-2	4.55e+1	1.42e-1	5.74e-2	4.09e+2	2.98e+1
1000	9.66e-1	3.25e-2	6.66e+1	1.15e-1	4.44e-2	7.64e+2	5.45e+1
2000	9.76e-1	2.35e-2	9.68e+1	1.03e-1	3.80e-2	1.48e+3	1.06e+2
5000	8.49e-1	1.30e-2	1.52e+2	7.89e-2	2.69e-2	3.40e+3	2.55e+2

B on B, Maxwellian velocity distribution, sheath potential 3 kT  
 $z1 = 5, m1 = 10.81, z2 = 5, m2 = 10.81, sbe = 5.73 \text{ eV}, rho = 2.35 \text{ g/cm}^{**3}$   
 $ef = 5.68 \text{ eV}, esb = 5.73 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1 \text{ (KrC)}$   
program: testvmcx  
ne=10

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
3	4.69e-4	1.32e-4	4.21e+0	6.34e-4	2.63e-4	6.22e+0	1.07e+0
5	3.97e-3	9.51e-4	5.99e+0	4.59e-3	1.60e-3	8.69e+0	1.74e+0
10	2.99e-2	4.70e-3	7.85e+0	1.71e-2	4.81e-3	1.41e+1	3.17e+0
20	1.03e-1	1.04e-2	1.01e+1	2.50e-2	5.30e-3	2.12e+1	5.51e+0
50	2.38e-1	1.35e-2	1.42e+1	2.24e-2	3.72e-3	4.16e+1	1.13e+1
100	3.30e-1	1.32e-2	2.00e+1	2.30e-2	3.47e-3	7.52e+1	1.96e+1
200	3.81e-1	1.07e-2	2.81e+1	1.29e-2	1.97e-3	1.52e+2	3.50e+1
500	4.03e-1	7.22e-3	4.48e+1	1.11e-2	1.60e-3	3.60e+2	8.04e+1
1000	3.55e-1	4.50e-3	6.32e+1	7.18e-3	9.66e-4	6.73e+2	1.58e+2
2000	2.88e-1	2.58e-3	8.98e+1	3.99e-3	5.72e-4	1.44e+3	3.17e+2

B on B, Maxwellian velocity distribution, sheath potential 9 kT  
 $z1 = 5, m1 = 10.81, z2 = 5, m2 = 10.81, sbe = 5.73 \text{ eV}, rho = 2.35 \text{ g/cm}^{**3}$   
 $ef = 5.68 \text{ eV}, esb = 5.73 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1 \text{ (KrC)}$   
program: testvmcx  
ne=11

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
2	2.89e-4	4.40e-5	3.35e+0	2.33e-4	5.28e-5	4.99e+0	1.75e+0
5	1.36e-2	1.37e-3	5.54e+0	4.57e-3	7.31e-4	8.80e+0	3.74e+0
10	5.97e-2	3.95e-3	7.28e+0	9.30e-3	1.20e-3	1.42e+1	6.39e+0
20	1.33e-1	6.10e-3	1.01e+1	1.16e-2	1.16e-3	2.21e+1	1.09e+1
50	2.34e-1	6.89e-3	1.62e+1	9.38e-3	8.83e-4	5.18e+1	2.25e+1
100	2.85e-1	6.06e-3	2.34e+1	7.68e-3	6.51e-4	9.33e+1	4.04e+1
200	2.99e-1	4.34e-3	3.19e+1	5.60e-3	5.22e-4	2.05e+2	7.59e+1
500	3.06e-1	5.15e-3	3.71e+1	7.50e-3	8.96e-4	2.64e+2	7.58e+1
1000	2.33e-1	1.50e-3	7.07e+1	8.38e-4	1.03e-4	1.35e+3	3.73e+2
2000	1.78e-1	8.35e-4	1.03e+2	5.54e-4	2.77e-5	1.10e+3	7.52e+2
5000	1.13e-1	3.04e-4	1.48e+2				1.80e+3

## O → B

Sputtering yield of B by O  
 $z1 = 8, m1 = 16.00, z2 = 5, m2 = 10.81, sbe = 5.90 \text{ eV}, rho = 2.35 \text{ g/cm}^{**3}$   
 $ef = 0.95 \text{ eV}, esb = 1.00 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1 \text{ (KrC)}$   
program: IPP 9/82  
only low fluence!  
ne= 5, na=1

E <sub>0</sub> (eV)	0°
150	3.75e-2
300	1.14e-1
1000	2.77e-1
3000	3.87e-1
6000	4.16e-1

# H → C

Sputtering yield of C by H

$z1 = 1$ ,  $m1 = 1.01$ ,  $z2 = 6$ ,  $m2 = 12.01$ ,  $sbe = 7.41$  eV,  $\rho = 1.85$  g/cm<sup>3</sup>  
 $ef = 0.98$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program : trvmc  
ne = 9, na = 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
40	9.00E-6	1.33E-5	2.19E-5	2.97E-5	2.98E-5	1.67E-5	1.20E-6		
50	1.75E-4	2.80E-4	3.08E-4	3.91E-4	3.76E-4	2.15E-4	1.13E-4	2.00E-5	3.33E-6
70	1.23E-3	1.35E-3	1.66E-3	2.10E-3	2.39E-3	2.36E-3	1.32E-3	5.17E-4	8.66E-5
100	2.92E-3	2.98E-3	3.92E-3	5.19E-3	6.96E-3	9.20E-3	8.58E-3	4.74E-3	6.72E-4
140	4.42E-3	4.88E-3	6.40E-3	8.76E-3	1.36E-2	1.98E-2	2.47E-2	1.68E-2	2.41E-3
200	5.84E-3	6.35E-3	8.34E-3	1.31E-2	1.93E-2	3.04E-2	4.66E-2	3.87E-2	6.34E-3
300	7.05E-3	7.58E-3	1.04E-2	1.66E-2	2.58E-2	4.31E-2	6.95E-2	6.98E-2	1.52E-2
500	6.76E-3	7.54E-3	1.08E-2	1.89E-2	2.91E-2	4.94E-2	8.73E-2	1.03E-1	3.86E-2
1000	5.68E-3	6.50E-3	1.00E-2	1.88E-2	2.93E-2	4.87E-2	9.06E-2	1.20E-1	9.05E-2

Sputtered energy of C by H

ne = 9, na = 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
40	1.26E-7	2.04E-7	4.00E-7	6.52E-7	6.78E-7	3.46E-7	1.73E-8		
50	6.48E-6	8.13E-6	9.31E-6	1.37E-5	1.37E-5	9.00E-6	3.89E-6	5.62E-7	1.19E-7
70	5.02E-5	5.57E-5	7.25E-5	9.81E-5	1.17E-4	1.20E-4	6.79E-5	2.77E-5	4.79E-6
100	1.27E-4	1.34E-4	1.86E-4	2.60E-4	3.59E-4	5.14E-4	5.21E-4	3.24E-4	5.08E-5
140	1.94E-4	2.16E-4	2.86E-4	4.10E-4	6.72E-4	1.07E-3	1.51E-3	1.20E-3	1.94E-4
200	2.35E-4	2.68E-4	3.51E-4	5.70E-4	9.01E-4	1.50E-3	2.73E-3	2.56E-3	4.96E-4
300	2.55E-4	2.67E-4	3.95E-4	6.47E-4	1.03E-3	1.86E-3	3.46E-3	3.91E-3	1.08E-3
500	1.79E-4	2.10E-4	3.03E-4	5.70E-4	9.38E-4	1.72E-3	3.34E-3	4.48E-3	2.04E-3
1000	1.00E-4	1.15E-4	1.91E-4	3.94E-4	6.74E-4	1.18E-3	2.43E-3	3.45E-3	3.18E-3

Particle reflection coefficient of H backscattered from C

$z1 = 1$ ,  $m1 = 1.01$ ,  $z2 = 6$ ,  $m2 = 12.01$ ,  $sbe = 7.41$  eV,  $\rho = 1.85$  g/cm<sup>3</sup>  
 $ef = 0.98$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC) program : trvmc  
ne=11, na = 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	4.79E-1	5.02E-1	5.62E-1	6.71E-1	7.65E-1	8.61E-1	9.40E-1	9.62E-1	9.74E-1
20	4.07E-1	4.27E-1	4.82E-1	5.85E-1	6.88E-1	8.14E-1	9.34E-1	9.70E-1	9.86E-1
40	3.58E-1	3.74E-1	4.11E-1	4.99E-1	5.93E-1	7.61E-1	8.99E-1	9.63E-1	9.92E-1
50	3.39E-1	3.54E-1	4.02E-1	4.76E-1	5.64E-1	7.27E-1	9.06E-1	9.72E-1	9.96E-1
70	3.05E-1	3.20E-1	3.63E-1	4.42E-1	5.25E-1	6.47E-1	8.41E-1	9.44E-1	9.93E-1
100	2.79E-1	2.92E-1	3.33E-1	4.12E-1	4.86E-1	6.02E-1	7.92E-1	9.20E-1	9.92E-1
140	2.53E-1	2.66E-1	3.08E-1	3.82E-1	4.56E-1	5.59E-1	7.42E-1	8.86E-1	9.90E-1
200	2.26E-1	2.38E-1	2.78E-1	3.50E-1	4.24E-1	5.25E-1	6.88E-1	8.38E-1	9.85E-1
300	1.94E-1	2.05E-1	2.44E-1	3.17E-1	3.88E-1	4.83E-1	6.34E-1	7.75E-1	9.73E-1
500	1.53E-1	1.63E-1	2.01E-1	2.71E-1	3.43E-1	4.36E-1	5.73E-1	6.97E-1	9.35E-1
1000	9.81E-2	1.08E-1	1.39E-1	2.03E-1	2.75E-1	3.72E-1	5.10E-1	6.17E-1	8.41E-1

Energy reflection coefficient of H backscattered from C

ne=11, na = 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	2.44E-1	2.64E-1	3.19E-1	4.29E-1	5.35E-1	6.59E-1	7.77E-1	8.16E-1	8.40E-1
20	1.98E-1	2.13E-1	2.59E-1	3.58E-1	4.70E-1	6.26E-1	8.01E-1	8.65E-1	8.99E-1
40	1.67E-1	1.79E-1	2.08E-1	2.84E-1	3.77E-1	5.73E-1	7.69E-1	8.75E-1	9.30E-1
50	1.55E-1	1.66E-1	2.02E-1	2.64E-1	3.50E-1	5.35E-1	7.82E-1	8.92E-1	9.43E-1
70	1.35E-1	1.44E-1	1.74E-1	2.37E-1	3.13E-1	4.46E-1	6.98E-1	8.54E-1	9.42E-1
100	1.20E-1	1.28E-1	1.55E-1	2.13E-1	2.78E-1	3.96E-1	6.36E-1	8.22E-1	9.44E-1
140	1.05E-1	1.13E-1	1.39E-1	1.92E-1	2.52E-1	3.53E-1	5.72E-1	7.76E-1	9.44E-1
200	9.07E-2	9.75E-2	1.21E-1	1.69E-1	2.25E-1	3.18E-1	5.06E-1	7.12E-1	9.38E-1
300	7.42E-2	8.02E-2	1.02E-1	1.45E-1	1.97E-1	2.78E-1	4.42E-1	6.26E-1	9.19E-1
500	5.48E-2	5.95E-2	7.77E-2	1.16E-1	1.63E-1	2.34E-1	3.71E-1	5.24E-1	8.64E-1
1000	3.14E-2	3.54E-2	4.77E-2	7.69E-2	1.15E-1	1.79E-1	3.00E-1	4.14E-1	7.21E-1

Average depth (mean range) in Å of H implanted in C  
ne=11, na = 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	6.30E+0	6.30E+0	6.10E+0	6.00E+0	5.90E+0	5.70E+0	5.50E+0	5.50E+0	5.40E+0
20	1.02E+1	1.01E+1	9.90E+0	9.50E+0	9.30E+0	9.10E+0	8.80E+0	8.70E+0	8.60E+0
40	1.68E+1	1.66E+1	1.61E+1	1.55E+1	1.50E+1	1.46E+1	1.42E+1	1.41E+1	1.38E+1
50	1.98E+1	1.96E+1	1.90E+1	1.82E+1	1.76E+1	1.71E+1	1.66E+1	1.62E+1	1.61E+1
70	2.55E+1	2.52E+1	2.44E+1	2.34E+1	2.26E+1	2.18E+1	2.11E+1	2.09E+1	2.05E+1
100	3.37E+1	3.32E+1	3.21E+1	3.06E+1	2.95E+1	2.83E+1	2.73E+1	2.72E+1	2.65E+1
140	4.39E+1	4.34E+1	4.18E+1	3.96E+1	3.79E+1	3.65E+1	3.53E+1	3.49E+1	3.45E+1
200	5.89E+1	5.80E+1	5.59E+1	5.24E+1	5.03E+1	4.81E+1	4.62E+1	4.55E+1	4.55E+1
300	8.23E+1	8.11E+1	7.78E+1	7.30E+1	6.90E+1	6.57E+1	6.30E+1	6.20E+1	6.12E+1
500	1.27E+2	1.25E+2	1.19E+2	1.10E+2	1.04E+2	9.78E+1	9.23E+1	9.06E+1	9.09E+1
1000	2.34E+2	2.28E+2	2.15E+2	1.95E+2	1.81E+2	1.67E+2	1.56E+2	1.50E+2	1.50E+2

# H → C

Sputtering yield of C by H  
 $z1 = 1$ ,  $m1 = 1.00$ ,  $z2 = 6$ ,  $m2 = 12.01$ ,  $sbe = 7.41$  eV,  $\rho = 2.20$  g/cm $^3$   
 $ef = 1.80$  eV,  $esb = 2.26$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
 $\alpha = 0.00$   
program : trspvmc  
 $n_e = 5$ ,  $n_a = 1$ ,  $n(dx) = 8$

$E_0$ (eV)	$dx = 10$ Å	50 Å	100 Å	300 Å	500 Å	1000 Å	2000 Å	5000 Å
1000	1.45e-3	3.12e-3	5.49e-3	5.31e-3	5.34e-3	6.50e-3		6.50e-3
5000	1.65e-3	2.16e-3	1.80e-3		2.66e-3	2.19e-3	2.55e-3	
10000	1.20e-3	1.51e-3	1.33e-3		1.61e-3	1.72e-3		
20000	8.75e-4	8.44e-4	1.16e-3		1.16e-3	1.38e-3		
40000	5.17e-4	6.99e-4	5.91e-4					

Sputtered energy of C by H  
 $n_e = 5$ ,  $n_a = 1$ ,  $n(dx) = 8$

$E_0$ (eV)	$dx = 10$ Å	50 Å	100 Å	300 Å	500 Å	1000 Å	2000 Å	5000 Å
1000	1.87e-5	5.34e-5	1.11e-4	8.97e-5	1.09e-4	1.18e-4		1.18e-4
5000	6.15e-6	8.11e-6	5.89e-6		1.01e-5	1.07e-5	1.18e-5	
10000	3.22e-6	3.30e-6	4.36e-6		6.17e-6	4.24e-6		
20000	1.34e-6	1.14e-6	1.46e-6		1.80e-6	2.84e-6		
40000	4.71e-7	7.37e-7	5.02e-7					

Particle reflection coefficient of H backscattered from C  
 $n_e = 5$ ,  $n_a = 1$ ,  $n(dx) = 8$

$E_0$ (eV)	$dx = 10$ Å	50 Å	100 Å	300 Å	500 Å	1000 Å	2000 Å	5000 Å
1000	4.21e-3	3.31e-2	7.32e-2	1.03e-1	1.01e-1	9.80e-2		9.80e-2
5000	2.64e-4	1.24e-3	3.05e-3		1.66e-2	1.74e-2	1.66e-2	
10000	5.96e-5	3.68e-4	6.52e-4		4.99e-3	6.33e-3		
20000	1.67e-5	9.27e-5	1.48e-4		1.09e-3	2.28e-3		
40000	4.38e-6	1.50e-5	4.85e-5					

Energy reflection coefficient of H backscattered from C  
 $n_e = 5$ ,  $n_a = 1$ ,  $n(dx) = 8$

$E_0$ (eV)	$dx = 10$ Å	50 Å	100 Å	300 Å	500 Å	1000 Å	2000 Å	5000 Å
1000	3.05e-3	1.70e-2	2.72e-2	3.33e-2	3.27e-2	3.20e-2		3.20e-2
5000	2.02e-4	7.71e-4	1.67e-3		4.10e-3	4.47e-3	4.24e-3	
10000	4.55e-5	2.51e-4	3.75e-4		1.44e-3	1.58e-3		
20000	1.32e-5	6.74e-5	9.98e-5		3.89e-4	5.85e-4		
40000	3.48e-6	1.14e-5	2.84e-5					

Average depth (mean range) in Å of H implanted in C  
 $n_e = 4$ ,  $n_a = 1$ ,  $n(dx) = 7$

$E_0$ (eV)	$dx = 50$ Å	100 Å	300 Å	500 Å	1000 Å	2000 Å	5000 Å
1000	6.88e+0	4.49e+1	1.68e+2	1.98e+2	1.96e+2		1.96e+2
5000		6.85e-1		2.62e+2	6.99e+2		
10000				1.93e+2	6.24e+2		
20000				4.54e+1	4.27e+2		

## H → C

Transmission sputtering yield of C by H  
 $z1 = 1$ ,  $m1 = 1.00$ ,  $z2 = 6$ ,  $m2 = 12.01$ ,  $sbe = 7.41$  eV,  $\rho = 2.20$  g/cm<sup>3</sup>  
 $ef = 1.80$  eV,  $esb = 2.26$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
 $\alpha = 0.00$   
program : trspvmc  
nem = 5, na = 1, n(dx)=6

E <sub>0</sub> (eV)	dx=10 Å	50 Å	100 Å	300 Å	500 Å	1000 Å
1000	2.20e-2	2.99e-2	3.38e-2	6.03e-3	3.38e-2	
5000	6.40e-3	1.02e-2	1.20e-2		1.94e-2	1.19e-2
10000	3.39e-3	5.46e-3	6.55e-3		9.93e-3	1.64e-2
20000	1.78e-3	2.71e-3	3.35e-3		4.20e-3	7.07e-3
40000	8.79e-4	1.36e-3	1.71e-3			

Transmission sputtered energy of C by H  
nem = 5, na = 1, n(dx)=6

E <sub>0</sub> (eV)	dx=10 Å	50 Å	100 Å	300 Å	500 Å	1000 Å
1000	1.07e-3	1.22e-3	1.18e-3	9.09e-5	1.18e-3	
5000	1.37e-4	2.16e-4	2.66e-4		2.47e-4	5.16e-5
10000	4.83e-5	1.02e-4	9.98e-5		1.47e-4	1.23e-4
20000	1.53e-5	3.49e-5	4.81e-5		6.22e-5	6.25e-5
40000	4.76e-6	1.07e-5	2.23e-5			

Particle transmission coefficient of H transmitted through C  
nem = 5, na = 1, n(dx)=6

E <sub>0</sub> (eV)	dx=10 Å	50 Å	100 Å	300 Å	500 Å	1000 Å
1000	9.95e-1	9.64e-1	8.91e-1	1.65e-1	5.04e-5	
5000	9.99e-1	9.98e-1	9.96e-1		9.27e-1	2.70e-1
10000	1.00e-0	9.99e-1	9.99e-1		9.91e-1	9.29e-1
20000	1.00e-0	1.00e-0	9.99e-1		9.98e-1	9.93e-1
40000	1.00e-0	1.00e-0	1.00e-0			

Energy transmission coefficient of H transmitted through C  
nem = 5, na = 1, n(dx)=6

E <sub>0</sub> (eV)	dx=10 Å	50 Å	100 Å	300 Å	500 Å	1000 Å
1000	9.66e-1	8.14e-1	6.01e-1	3.05e-2	1.93e-6	
5000	9.88e-1	9.40e-1	8.81e-1		4.23e-1	2.60e-2
10000	9.92e-1	9.59e-1	9.19e-1		6.20e-1	2.92e-1
20000	9.94e-1	9.72e-1	9.44e-1		7.33e-1	5.01e-1
40000	9.96e-1	9.80e-1	9.60e-1			

# D → C

Sputtering yield of C by D  
 $z1 = 1$ ,  $m1 = 2.01$ ,  $z2 = 6$ ,  $m2 = 12.01$ ,  $sbe = 7.41$  eV,  $\rho = 1.85$  g/cm $^3$   
 $ef = 0.98$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC) program : trvmc  
 $ne = 12$ ,  $na = 9$

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
30	8.58E-5	1.12E-4	1.78E-4	2.30E-4	2.08E-4	1.12E-4	2.55E-5	8.60E-6	2.56E-6
33	2.16E-4					3.29E-4			
40	7.35E-4	9.15E-4	1.26E-3	1.72E-3	2.21E-3	1.80E-3	7.60E-4	3.12E-4	9.35E-5
50	1.96E-3	2.33E-3	3.09E-3	4.58E-3	5.87E-3	5.95E-3	4.15E-3	1.76E-3	4.45E-4
70	4.79E-3	5.19E-3	7.01E-3	1.13E-2	1.57E-2	2.14E-2	1.78E-2	8.60E-3	1.57E-3
100	8.18E-3	8.77E-3	1.21E-2	1.96E-2	3.08E-2	4.59E-2	4.78E-2	2.72E-2	4.04E-3
140	1.10E-2	1.21E-2	1.68E-2	2.88E-2	4.40E-2	7.03E-2	8.63E-2	5.73E-2	8.17E-3
200	1.32E-2	1.48E-2	2.41E-2	3.56E-2	5.93E-2	9.10E-2	1.21E-1	9.76E-2	1.41E-2
300	1.47E-2	1.66E-2	2.40E-2	4.33E-2	6.81E-2	1.13E-1	1.63E-1	1.51E-1	2.94E-2
500	1.44E-2	1.72E-2	2.72E-2	4.58E-2	7.39E-2	1.20E-1	1.89E-1	2.12E-1	7.29E-2
1000	1.30E-2	1.49E-2	2.36E-2	4.18E-2	6.49E-2	1.08E-1	1.90E-1	2.35E-1	1.72E-1
2000	1.02E-2			3.45E-2			1.88E-1	2.22E-1	2.45E-1

Sputtered energy of C by D  
 $ne = 12$ ,  $na = 9$

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
30	3.32E-6	4.76E-6	8.71E-6	1.27E-5	1.21E-5	6.80E-6	1.71E-6	6.29E-7	2.24E-7
33	9.15E-6					2.31E-5			
40	3.58E-5	5.17E-5	8.06E-5	1.26E-4	1.81E-4	1.54E-4	6.87E-5	2.90E-5	8.69E-6
50	1.18E-4	1.50E-4	2.19E-4	3.60E-4	5.08E-4	5.70E-4	4.41E-4	1.95E-4	5.31E-5
70	3.26E-4	3.50E-4	5.33E-4	9.23E-4	1.38E-3	2.05E-3	2.04E-3	1.10E-3	2.26E-4
100	5.27E-4	5.96E-4	8.80E-4	1.50E-3	2.56E-3	4.29E-3	5.49E-3	3.55E-3	5.71E-4
140	6.77E-4	7.50E-4	1.09E-3	2.03E-3	3.31E-3	5.93E-3	8.75E-3	6.73E-3	1.14E-3
200	7.12E-4	8.00E-4	1.18E-3	2.19E-3	3.99E-3	6.60E-3	1.04E-2	9.95E-3	1.73E-3
300	6.56E-4	7.50E-4	1.12E-3	2.23E-3	3.84E-3	7.15E-3	1.15E-2	1.19E-2	3.08E-3
500	5.02E-4	5.80E-4	1.03E-3	1.87E-3	3.19E-3	5.90E-3	1.01E-2	1.26E-2	5.40E-3
1000	2.94E-4	3.70E-4	5.70E-4	1.17E-3	2.01E-3	3.61E-3	6.82E-3	9.28E-3	7.69E-3
2000	1.39E-4			6.56E-4			4.66E-3	5.72E-3	6.93E-3

# D → C

Particle reflection coefficient of D backscattered from C  
 z1 = 1, m1 = 2.01, z2 = 6, m2 = 12.01, sbe = 7.41 eV, rho = 1.85 g/cm\*\*3  
 ef = 0.98 eV, esb = 1.00 eV, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1 (KrC)  
 program : trvmc  
 ne = 14, na = 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	3.74E-1	3.99E-1	4.70E-1	6.00E-1	7.09E-1	8.29E-1	9.23E-1	9.51E-1	9.66E-1
20	3.13E-1	3.32E-1	3.92E-1	5.10E-1	6.29E-1	7.79E-1	9.21E-1	9.64E-1	9.84E-1
30	2.81E-1	2.99E-1	3.52E-1	4.57E-1	5.70E-1	7.27E-1	9.03E-1	9.63E-1	9.89E-1
33	2.75E-1					7.13E-1			
40	2.62E-1	2.77E-1	3.28E-1	4.23E-1	5.29E-1	6.83E-1	8.82E-1	9.59E-1	9.91E-1
50	2.48E-1	2.62E-1	3.09E-1	4.01E-1	4.99E-1	6.49E-1	8.60E-1	9.52E-1	9.92E-1
70	2.27E-1	2.41E-1	2.86E-1	3.71E-1	4.59E-1	5.99E-1	8.20E-1	9.37E-1	9.92E-1
100	2.07E-1	2.19E-1	2.62E-1	3.39E-1	4.26E-1	5.48E-1	7.65E-1	9.10E-1	9.91E-1
140	1.88E-1	2.00E-1	2.41E-1	3.17E-1	3.97E-1	5.11E-1	7.10E-1	8.69E-1	9.90E-1
200	1.69E-1	1.80E-1	2.19E-1	2.96E-1	3.66E-1	4.75E-1	6.56E-1	8.24E-1	9.84E-1
300	1.48E-1	1.57E-1	1.95E-1	2.64E-1	3.40E-1	4.38E-1	6.04E-1	7.53E-1	9.71E-1
500	1.20E-1	1.28E-1	1.63E-1	2.27E-1	3.01E-1	3.98E-1	5.48E-1	6.79E-1	9.32E-1
1000	8.00E-2	8.85E-2	1.20E-1	1.82E-1	2.51E-1	3.52E-1	4.96E-1	6.03E-1	8.31E-1
2000	4.53E-2			1.31E-1			4.19E-1	5.59E-1	7.53E-1

Energy reflection coefficient of D backscattered from C  
 ne = 14, na = 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	1.47E-1	1.64E-1	2.18E-1	3.29E-1	4.39E-1	5.76E-1	7.11E-1	7.60E-1	7.89E-1
20	1.21E-1	1.34E-1	1.76E-1	2.73E-1	3.89E-1	5.59E-1	7.58E-1	8.34E-1	8.78E-1
30	1.06E-1	1.17E-1	1.53E-1	2.35E-1	3.40E-1	5.13E-1	7.51E-1	8.53E-1	9.08E-1
33	1.03E-1					5.00E-1			
40	9.73E-2	1.07E-1	1.39E-1	2.11E-1	3.06E-1	4.72E-1	7.32E-1	8.56E-1	9.23E-1
50	9.10E-2	9.92E-2	1.29E-1	1.96E-1	2.81E-1	4.38E-1	7.09E-1	8.53E-1	9.32E-1
70	8.20E-2	8.97E-2	1.17E-1	1.76E-1	2.49E-1	3.89E-1	6.62E-1	8.38E-1	9.41E-1
100	7.33E-2	8.02E-2	1.04E-1	1.56E-1	2.22E-1	3.40E-1	5.99E-1	8.06E-1	9.46E-1
140	6.55E-2	7.18E-2	9.43E-2	1.43E-1	2.01E-1	3.04E-1	5.35E-1	7.54E-1	9.47E-1
200	5.73E-2	6.34E-2	8.42E-2	1.30E-1	1.81E-1	2.74E-1	4.75E-1	6.93E-1	9.41E-1
300	4.95E-2	5.36E-2	7.22E-2	1.13E-1	1.63E-1	2.43E-1	4.15E-1	6.05E-1	9.22E-1
500	3.83E-2	4.22E-2	5.79E-2	9.24E-2	1.37E-1	2.10E-1	3.54E-1	5.10E-1	8.67E-1
1000	2.37E-2	2.70E-2	3.95E-2	6.77E-2	1.06E-1	1.71E-1	2.96E-1	4.18E-1	7.23E-1
2000	1.22E-2			4.29E-2			2.26E-1	3.53E-1	6.08E-1

Average depth (mean range) in Å of D implanted in C  
 ne = 13, na = 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	5.20E+0	5.20E+0	5.00E+0	4.80E+0	4.60E+0	4.40E+0	4.20E+0	4.10E+0	4.00E+0
20	8.60E+0	8.50E+0	8.20E+0	7.90E+0	7.60E+0	7.30E+0	6.90E+0	6.70E+0	6.60E+0
33	1.25E+1				1.03E+1				
40	1.45E+1	1.43E+1	1.38E+1	1.30E+1	1.25E+1	1.19E+1	1.14E+1	1.10E+1	1.07E+1
50	1.72E+1	1.70E+1	1.64E+1	1.54E+1	1.48E+1	1.41E+1	1.34E+1	1.30E+1	1.27E+1
70	2.26E+1	2.22E+1	2.14E+1	2.01E+1	1.90E+1	1.82E+1	1.73E+1	1.69E+1	1.63E+1
100	3.02E+1	2.97E+1	2.84E+1	2.67E+1	2.53E+1	2.39E+1	2.30E+1	2.24E+1	2.16E+1
140	4.01E+1	3.95E+1	3.77E+1	3.52E+1	3.33E+1	3.16E+1	3.01E+1	2.96E+1	2.88E+1
200	5.48E+1	5.39E+1	5.13E+1	4.76E+1	4.49E+1	4.26E+1	4.04E+1	3.94E+1	3.87E+1
300	7.88E+1	7.74E+1	7.36E+1	6.79E+1	6.38E+1	5.95E+1	5.65E+1	5.55E+1	5.47E+1
500	1.26E+2	1.24E+2	1.16E+2	1.07E+2	1.00E+2	9.34E+1	8.72E+1	8.55E+1	8.28E+1
1000	2.45E+2	2.39E+2	2.24E+2	2.02E+2	1.86E+2	1.70E+2	1.57E+2	1.52E+2	1.51E+2
2000	3.91E+2			3.11E+2			2.13E+2	2.20E+2	2.14E+2

# D → C

D on C, Maxwellian velocity distribution, sheath potential 0 kT  
 $z1 = 1$ ,  $m1 = 2.01$ ,  $z2 = 6$ ,  $m2 = 12.01$ ,  $sbe = 7.42$  eV,  $\rho = 2.26$  g/cm $^{**3}$   
 $ef = 0.98$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$ (KrC)  
program: testvmcx  
ne=10

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
8	2.22e-4	5.85e-5	4.23e+0	5.92e-1	3.53e-1	9.53e+0	5.31e+0
10	5.87e-4	1.45e-4	4.95e+0	5.82e-1	3.41e-1	1.17e+0	6.45e+0
14	1.81e-3	3.82e-4	5.90e+0	5.61e-1	3.19e-1	1.60e+1	8.52e+0
20	4.43e-3	8.30e-4	7.48e+0	5.31e-1	2.94e-1	2.21e+1	1.12e+1
30	1.07e-2	1.66e-3	9.28e+0	4.93e-1	2.63e-1	3.21e+1	1.56e+1
50	2.18e-2	2.68e-3	1.23e+1	4.44e-1	2.28e-1	5.14e+1	2.34e+1
100	3.99e-2	3.04e-3	1.52e+1	3.81e-1	1.85e-1	9.72e+1	4.15e+1
200	5.32e-2	2.88e-3	2.16e+1	3.23e-1	1.48e-1	1.82e+2	7.62e+1
500	5.86e-2	1.79e-3	3.07e+1	2.52e-1	1.04e-1	4.14e+2	1.73e+2
1000	5.40e-2	1.05e-3	3.92e+1	2.02e-1	7.32e-2	7.30e+2	3.22e+2

D on C, Maxwellian velocity distribution, sheath potential 3 kT  
 $z1 = 1$ ,  $m1 = 2.01$ ,  $z2 = 6$ ,  $m2 = 12.01$ ,  $sbe = 7.42$  eV,  $\rho = 2.26$  g/cm $^{**3}$   
 $ef = 0.98$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$ (KrC)  
program: testvmcx  
ne=16

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
5	2.27e-4	2.70e-5	2.97e-0	3.72e-1	1.64e-1	1.10e+1	7.91e+0
5	2.36e-4	2.79e-5	2.96e-0	3.71e-1	1.64e-1	1.10e+1	7.92e+0
7	1.17e-3	1.19e-4	3.56e-0	3.37e-1	1.45e-1	1.51e+1	1.09e+1
10	3.67e-3	3.61e-4	4.91e-0	3.06e-1	1.28e-1	2.10e+1	1.34e+1
10	3.72e-3	3.47e-4	4.66e-0	3.05e-1	1.28e-1	2.09e+1	1.34e+1
14	7.36e-3	6.46e-4	6.15e-0	2.78e-1	1.14e-1	2.87e+1	1.75e+1
20	1.19e-2	8.93e-4	7.50e-0	2.54e-1	1.01e-1	4.00e+1	2.35e+1
20	1.25e-2	9.47e-4	7.59e-0	2.54e-1	1.02e-1	4.00e+1	2.35e+1
30	1.70e-2	1.11e-3	9.66e-0	2.26e-1	8.80e-2	5.83e+1	3.30e+1
40	2.15e-2	1.27e-3	1.18e+1	2.08e-1	7.97e-2	7.65e+1	4.25e+1
50	1.99e-2	1.01e-3	1.27e+1	1.95e-1	7.74e-2	9.43e+1	5.16e+1
50	2.23e-2	1.18e-3	1.32e+1	1.95e-1	7.32e-2	9.41e+1	5.19e+1
100	2.35e-2	8.68e-4	1.85e+1	1.56e-1	5.53e-2	1.78e+2	9.78e+1
200	2.17e-2	4.91e-4	2.27e+1	1.12e-1	3.65e-2	3.26e+2	1.87e+2
500	1.48e-2	2.10e-4	3.54e+1	5.76e-2	1.55e-2	6.73e+2	4.42e+2
1000	9.49e-3	7.33e-5	3.86e+1	2.81e-2	6.54e-3	1.17e+3	8.31e+2

D on C, Maxwellian velocity distribution, sheath potential 3 kT  
 $z1 = 1$ ,  $m1 = 2.01$ ,  $z2 = 6$ ,  $m2 = 12.01$ ,  $sbe = 4.40$  eV,  $\rho = 1.85$  g/cm $^{**3}$   
 $ef = 0.98$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$ (KrC)  
program: trspvmc  
ne=12

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
2	1.77e-5		1.20e+0	4.46e-1		4.56e+0	4.37e+0
3	3.38e-4		1.71e+0	4.01e-1		6.77e+0	5.96e+0
4	1.33e-3		2.16e+0	3.69e-1		8.88e+0	7.42e+0
5	2.95e-3		2.55e+0	3.46e-1		1.09e+1	8.81e+0
7	7.69e-3		3.26e+0	3.15e-1		1.50e+1	1.15e+1
10	1.48e-2		4.15e+0	2.87e-1		2.06e+1	1.53e+1
14	2.26e-2		5.13e+0	2.64e-1		2.87e+1	2.02e+1
20	2.98e-2		6.30e+0	2.42e-1		4.02e+1	2.73e+1
50	4.03e-2		1.00e+1	1.89e-1		9.49e+1	6.15e+1
100	3.96e-2		1.36e+1	1.49e-1		1.79e+2	1.17e+2
200	3.30e-2		1.77e+1	1.09e-1		3.27e+2	2.25e+2
500	2.20e-2		2.44e+1	5.66e-2		6.83e+2	5.34e+2

D on C, Maxwellian velocity distribution, sheath potential 3 kT  
 $z1 = 1$ ,  $m1 = 2.01$ ,  $z2 = 6$ ,  $m2 = 12.01$ ,  $sbe = 7.40$  eV,  $\rho = 2.00$  g/cm $^{**3}$   
 $ef = 0.95$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$ (KrC)  
program: testvmcx  
ne= 2

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
1000	8.85e-3	7.47e-5	4.22e+1	2.80e-2	6.63e-3	1.19e+3	9.32e+2
2000	5.54e-3	3.08e-5	5.57e+1	1.12e-2	2.34e-3	2.08e+3	1.69e+3

# $T \rightarrow C$

Sputtering yield of C by T

```

z1= 1, m1= 2.01, z2= 6, m2= 12.01, sbe=7.41 eV, rho=1.85 g/cm**3
ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : trvmc
ne=12, na= 9

```

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
20			6.00E-6	7.80E-6					
25	4.70E-5	7.40E-5	1.43E-4	2.15E-4	1.82E-4	1.25E-4	4.14E-5	1.80E-5	7.00E-6
30	2.44E-4	3.25E-4	6.09E-4	9.78E-4	1.06E-3	9.45E-4	4.38E-4	2.30E-4	9.49E-5
40	1.23E-3	1.50E-3	2.56E-3	4.41E-3	6.15E-3	6.65E-3	4.37E-3	2.14E-3	6.37E-4
50	2.76E-3	3.50E-3	5.36E-3	9.16E-3	1.36E-2	1.77E-2	1.32E-2	6.16E-3	1.48E-3
70	6.05E-3	6.87E-3	1.03E-2	1.97E-2	3.02E-2	4.49E-2	3.92E-2	1.98E-2	3.57E-3
100	9.44E-3	1.14E-2	1.71E-2	3.20E-2	5.24E-2	7.87E-2	8.63E-2	4.77E-2	6.94E-3
140	1.28E-2	1.39E-2	2.25E-2	4.44E-2	6.92E-2	1.11E-1	1.38E-1	8.51E-2	1.17E-2
200	1.54E-2	1.76E-2	2.96E-2	5.58E-2	8.79E-2	1.41E-1	1.91E-1	1.45E-1	2.02E-2
300	1.75E-2	2.06E-2	3.29E-2	6.32E-2	1.02E-1	1.67E-1	2.35E-1	2.16E-1	4.29E-2
500	1.87E-2	2.23E-2	3.60E-2	6.58E-2	1.05E-1	1.73E-1	2.64E-1	2.92E-1	9.97E-2
1000	1.68E-2	2.02E-2	3.32E-2	5.98E-2	9.56E-2	1.61E-1	2.70E-1	3.40E-1	2.36E-1

Sputtered energy of C by T  
ne=12, na= 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
20			2.08E-7	5.59E-7					
25	2.26E-6	4.13E-6	9.81E-6	1.69E-5	1.57E-5	1.19E-5	4.67E-6	1.98E-6	9.39E-7
30	1.41E-5	2.14E-5	4.68E-5	8.94E-5	1.07E-4	1.03E-4	5.25E-5	2.85E-5	1.22E-5
40	8.27E-5	1.10E-4	2.18E-4	4.34E-4	6.94E-4	8.32E-4	6.24E-4	3.26E-4	1.02E-4
50	1.96E-4	2.70E-4	4.72E-4	9.44E-4	1.57E-3	2.29E-3	2.02E-3	1.07E-3	2.71E-4
70	4.54E-4	5.56E-4	8.91E-4	1.93E-3	3.24E-3	5.71E-3	6.29E-3	3.55E-3	6.91E-4
100	6.68E-4	8.18E-4	1.39E-3	2.88E-3	5.26E-3	9.12E-3	1.24E-2	7.74E-3	1.36E-3
140	8.37E-4	9.27E-4	1.58E-3	3.49E-3	6.22E-3	1.14E-2	1.72E-2	1.25E-2	2.16E-3
200	8.51E-4	1.07E-3	1.83E-3	3.86E-3	6.77E-3	1.27E-2	2.00E-2	1.75E-2	3.16E-3
300	8.36E-4	1.02E-3	1.73E-3	3.66E-3	6.79E-3	1.21E-2	1.98E-2	2.09E-2	5.34E-3
500	6.78E-4	8.14E-4	1.42E-3	3.03E-3	5.23E-3	9.51E-3	1.69E-2	2.09E-2	8.60E-3
1000	3.92E-4	5.01E-4	9.10E-4	1.98E-3	3.55E-3	6.45E-3	1.18E-2	1.52E-2	1.25E-2

# $T \rightarrow C$

Particle reflection coefficient of T backscattered from C  
 $z1 = 1$ ,  $m1 = 2.01$ ,  $z2 = 6$ ,  $m2 = 12.01$ ,  $sbe = 7.41$  eV,  $\rho = 1.85$  g/cm $^3$   
 $ef = 0.98$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program : trvmc  
ne=13, na= 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	2.89E-1	3.13E-1	3.90E-1	5.32E-1	6.58E-1	7.92E-1	9.04E-1	9.38E-1	9.56E-1
20	2.41E-1	2.61E-1	3.24E-1	4.50E-1	5.82E-1	7.49E-1	9.10E-1	9.59E-1	9.81E-1
25	2.26E-1	2.44E-1	3.03E-1	4.20E-1	5.48E-1	7.21E-1	9.01E-1	9.59E-1	9.85E-1
30	2.14E-1	2.32E-1	2.86E-1	3.98E-1	5.20E-1	6.94E-1	8.91E-1	9.58E-1	9.87E-1
40	1.97E-1	2.13E-1	2.63E-1	3.66E-1	4.78E-1	6.49E-1	8.69E-1	9.53E-1	9.89E-1
50	1.85E-1	1.99E-1	2.47E-1	3.42E-1	4.48E-1	6.10E-1	8.46E-1	9.47E-1	9.91E-1
70	1.67E-1	1.82E-1	2.25E-1	3.11E-1	4.08E-1	5.60E-1	8.01E-1	9.30E-1	9.91E-1
100	1.52E-1	1.62E-1	2.05E-1	2.85E-1	3.73E-1	5.09E-1	7.43E-1	9.03E-1	9.90E-1
140	1.37E-1	1.49E-1	1.87E-1	2.64E-1	3.44E-1	4.69E-1	6.86E-1	8.60E-1	9.88E-1
200	1.21E-1	1.32E-1	1.68E-1	2.44E-1	3.19E-1	4.36E-1	6.27E-1	8.07E-1	9.83E-1
300	1.05E-1	1.16E-1	1.52E-1	2.22E-1	2.95E-1	4.04E-1	5.74E-1	7.35E-1	9.67E-1
500	8.46E-2	9.52E-2	1.27E-1	1.93E-1	2.63E-1	3.63E-1	5.21E-1	6.60E-1	9.27E-1
1000	5.77E-2	6.59E-2	9.38E-2	1.55E-1	2.20E-1	3.18E-1	4.69E-1	5.83E-1	8.24E-1

Energy reflection coefficient of T backscattered from C  
ne=13, na = 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	8.56E-2	9.98E-2	1.48E-1	2.53E-1	3.64E-1	5.05E-1	6.50E-1	7.05E-1	7.38E-1
20	7.31E-2	8.38E-2	1.21E-1	2.12E-1	3.27E-1	5.02E-1	7.17E-1	8.03E-1	8.53E-1
25	6.81E-2	7.77E-2	1.12E-1	1.94E-1	3.04E-1	4.82E-1	7.19E-1	8.20E-1	8.77E-1
30	6.42E-2	7.31E-2	1.04E-1	1.80E-1	2.83E-1	4.61E-1	7.15E-1	8.29E-1	8.93E-1
40	5.83E-2	6.62E-2	9.40E-2	1.61E-1	2.52E-1	4.22E-1	6.98E-1	8.35E-1	9.22E-1
50	5.41E-2	6.14E-2	8.68E-2	1.47E-1	2.30E-1	3.87E-1	6.77E-1	8.34E-1	9.24E-1
70	4.87E-2	5.53E-2	7.74E-2	1.30E-1	2.01E-1	3.42E-1	6.27E-1	8.19E-1	9.36E-1
100	4.37E-2	4.85E-2	6.92E-2	1.16E-1	1.78E-1	2.97E-1	5.64E-1	7.88E-1	9.42E-1
140	3.87E-2	4.40E-2	6.23E-2	1.05E-1	1.61E-1	2.63E-1	5.02E-1	7.37E-1	9.44E-1
200	3.42E-2	3.86E-2	5.56E-2	9.60E-2	1.44E-1	2.36E-1	4.38E-1	6.70E-1	9.38E-1
300	2.90E-2	3.39E-2	4.96E-2	8.59E-2	1.31E-1	2.12E-1	3.84E-1	5.83E-1	9.18E-1
500	2.30E-2	2.68E-2	4.05E-2	7.19E-2	1.14E-1	1.82E-1	3.30E-1	4.91E-1	8.61E-1
1000	1.46E-2	1.78E-2	2.81E-2	5.47E-2	8.88E-2	1.52E-1	2.78E-1	3.99E-1	7.20E-1

Average depth (mean range) in Å of T implanted in C  
ne=13, na = 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	4.60E+0	4.50E+0	4.40E+0	4.10E+0	3.90E+0	3.60E+0	3.30E+0	3.20E+0	3.00E+0
20	7.70E+0	7.60E+0	7.30E+0	6.80E+0	6.50E+0	6.10E+0	5.70E+0	5.50E+0	5.30E+0
25	9.20E+0	9.00E+0	8.60E+0	8.10E+0	7.60E+0	7.20E+0	6.70E+0	6.50E+0	6.20E+0
30	1.05E+1	1.04E+1	9.90E+0	9.20E+0	8.70E+0	8.20E+0	7.70E+0	7.40E+0	7.10E+0
40	1.32E+1	1.29E+1	1.23E+1	1.15E+1	1.08E+1	1.02E+1	9.50E+0	9.20E+0	8.80E+0
50	1.57E+1	1.54E+1	1.47E+1	1.36E+1	1.28E+1	1.21E+1	1.13E+1	1.09E+1	1.05E+1
70	2.06E+1	2.02E+1	1.92E+1	1.77E+1	1.66E+1	1.57E+1	1.47E+1	1.42E+1	1.34E+1
100	2.77E+1	2.72E+1	2.58E+1	2.38E+1	2.22E+1	2.09E+1	1.95E+1	1.89E+1	1.79E+1
140	3.71E+1	3.63E+1	3.44E+1	3.16E+1	2.96E+1	2.74E+1	2.59E+1	2.50E+1	2.43E+1
200	5.08E+1	5.02E+1	4.72E+1	4.31E+1	4.01E+1	3.73E+1	3.47E+1	3.43E+1	3.28E+1
300	7.41E+1	7.26E+1	6.83E+1	6.24E+1	5.75E+1	5.27E+1	4.96E+1	4.81E+1	4.60E+1
500	1.21E+2	1.18E+2	1.11E+2	1.00E+2	9.22E+1	8.47E+1	7.82E+1	7.66E+1	7.44E+1
1000	2.42E+2	2.35E+2	2.19E+2	1.95E+2	1.76E+2	1.62E+2	1.47E+2	1.43E+2	1.39E+2

$T \rightarrow C$

T on C, Maxwellian velocity distribution, sheath potential 3 kT  
 $z1 = 1$ ,  $m1 = 3.02$ ,  $z2 = 6$ ,  $m2 = 12.01$ ,  $sbe = 7.42$  eV,  $\rho = 2.26$  g/cm $^{**3}$   
 $ef = 0.98$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$ (KrC)  
program: testvmcx  
ne = 9

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
7	2.13e-3	2.79e-4	4.51e+0	2.72e-1	9.87e-2	1.27e+1	9.11e+0
10	6.00e-3	6.80e-4	5.66e+0	2.42e-1	8.51e-2	1.76e+1	1.20e+1
14	1.15e-2	1.12e-3	6.79e+0	2.19e-1	7.62e-2	2.43e+1	1.58e+1
20	1.76e-2	1.46e-3	8.32e+0	1.98e-1	6.67e-2	3.37e+1	2.13e+1
30	2.33e-2	1.69e-3	1.08e+1	1.75e-1	5.88e-2	5.03e+1	3.03e+1
50	2.95e-2	1.73e-3	1.47e+1	1.50e-1	4.97e-2	8.28e+1	4.80e+1
100	3.23e-2	1.34e-3	2.07e+1	1.19e-1	3.77e-2	1.58e+2	9.29e+1
200	3.05e-2	7.91e-4	2.60e+1	8.55e-2	2.60e-2	3.04e+2	1.84e+2
500	1.96e-2	3.21e-4	4.10e+1	4.71e-2	1.20e-2	6.36e+2	4.57e+2

T on C, Maxwellian velocity distribution, sheath potential 3 kT  
 $z1 = 1$ ,  $m1 = 3.02$ ,  $z2 = 6$ ,  $m2 = 12.01$ ,  $sbe = 4.40$  eV,  $\rho = 1.85$  g/cm $^{**3}$   
 $ef = 0.98$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$ (KrC)  
program: trspvmc  
ne = 9

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
2	7.83e-5		1.75e+0	3.63e-1		3.77e+0	3.74e+0
3	7.40e-4		2.27e+0	3.29e-1		5.65e+0	5.22e+0
5	5.04e-3		3.12e+0	2.79e-1		9.22e+0	7.81e+0
7	1.19e-2		3.81e+0	2.51e-1		1.26e+1	1.02e+1
10	2.13e-2		4.68e+0	2.24e-1		1.77e+1	1.37e+1
15	3.27e-2		5.88e+0	2.00e-1		2.61e+1	1.93e+1
20	3.98e-2		6.90e+0	1.84e-1		3.44e+1	2.48e+1
30	4.76e-2		8.37e+0	1.65e-1		5.08e+1	3.55e+1
50	5.28e-2		1.07e+1	1.43e-1		8.31e+1	5.71e+1

# He → C

Sputtering yield of C by He

```

z1= 2, m1= 4.00, z2= 6, m2= 12.01, sbe=7.41 eV, rho=1.85 g/cm**3
ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : trvmc
ne=22, na= 9

```

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
20	2.42E-6	7.10E-6	2.05E-5	2.04E-5	1.09E-5	3.84E-6	8.64E-7	4.00E-7	
25	4.20E-5	7.14E-5	1.51E-4	1.95E-4	1.68E-4	1.23E-4	3.83E-5	6.98E-6	
27	1.00E-4	1.51E-4	2.98E-4	4.29E-4	4.34E-4	3.45E-4	1.18E-4	1.97E-5	
30	2.40E-4	3.68E-4	7.02E-4	1.10E-3	1.25E-3	1.12E-3	3.84E-4	6.08E-5	
35	7.20E-4	9.99E-4	1.97E-3	3.33E-3	4.17E-3	4.04E-3	1.39E-3	2.13E-4	
40	1.50E-3	2.03E-3	3.86E-3	7.20E-3	9.33E-3	9.26E-3	3.22E-3	4.72E-4	2.18E-6
50	3.83E-3	5.03E-3	9.12E-3	1.75E-2	2.45E-2	2.59E-2	9.71E-3	1.53E-3	6.43E-6
60	6.84E-3	8.61E-3	1.50E-2	2.94E-2	4.31E-2	4.73E-2	1.95E-2	3.40E-3	1.38E-5
70	1.01E-2	1.22E-2	2.07E-2	4.13E-2	6.23E-2	7.14E-2	3.30E-2	6.27E-3	2.35E-5
100	1.83E-2	2.23E-2	3.70E-2	7.36E-2	1.13E-1	1.44E-1	8.37E-2	2.02E-2	8.40E-5
140	2.63E-2	3.22E-2	5.31E-2	1.02E-1	1.61E-1	2.19E-1	1.58E-1	4.81E-2	2.64E-4
200	3.45E-2	4.23E-2	7.04E-2	1.35E-1	2.07E-1	2.95E-1	2.65E-1	1.04E-1	9.49E-4
300	4.28E-2	5.36E-2	8.65E-2	1.64E-1	2.50E-1	3.68E-1	3.90E-1	2.13E-1	4.03E-3
400	4.75E-2	5.80E-2	9.45E-2	1.76E-1	2.71E-1	4.05E-1	4.79E-1	3.19E-1	1.09E-2
500	5.05E-2	6.12E-2	9.96E-2	1.83E-1	2.81E-1	4.24E-1	5.33E-1	4.12E-1	2.25E-2
700	5.17E-2	6.30E-2	1.03E-1	1.87E-1	2.90E-1	4.38E-1	5.99E-1	5.41E-1	6.42E-2
1000	5.19E-2	6.28E-2	1.00E-1	1.86E-1	2.84E-1	4.36E-1	6.38E-1	6.58E-1	1.59E-1
2000	4.69E-2	5.63E-2	8.84E-2	1.56E-1	2.44E-1	3.93E-1	6.38E-1	7.58E-1	4.93E-1
3000	4.24E-2	4.91E-2	7.56E-2	1.36E-1	2.11E-1	3.45E-1	5.91E-1	7.49E-1	6.73E-1
5000	3.40E-2	4.00E-2	5.79E-2	1.07E-1	1.66E-1	2.74E-1	4.98E-1	6.83E-1	7.92E-1
10000	2.43E-2	2.76E-2	4.04E-2	6.84E-2	1.05E-1	1.81E-1	3.50E-1	5.23E-1	7.67E-1
20000	1.66E-2	1.85E-2	2.65E-2	4.13E-2	6.32E-2	1.07E-1	2.23E-1	3.48E-1	6.10E-1

Sputtered energy of C by He

```

ne=22, na= 9

```

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
20	1.01e-7	3.72e-7	1.39e-6	1.79e-6	1.08e-6	4.62e-7	1.30e-7	6.71e-8	
25	2.34E-6	4.64E-6	1.26E-5	1.96E-5	1.95E-5	1.55E-5	5.29E-6	1.01E-6	
27	1.00E-5	1.03E-5	2.54E-5	4.41E-5	5.02E-5	4.51E-5	1.68E-5	2.93E-6	
30	2.00E-5	2.64E-5	6.29E-5	1.20E-4	1.55E-4	1.20E-4	5.88E-5	9.52E-6	
35	5.00E-5	7.71E-5	1.87E-4	3.85E-4	5.51E-4	6.02E-4	2.40E-4	3.96E-5	
40	1.10E-4	1.62E-4	3.78E-4	8.55E-4	1.27E-3	1.49E-3	6.06E-4	9.43E-5	4.38E-7
50	2.80E-4	4.09E-4	8.88E-4	2.11E-3	3.44E-3	4.31E-3	1.96E-3	3.36E-4	1.43E-6
60	5.00E-4	7.04E-4	1.46E-3	3.44E-3	5.95E-3	7.81E-3	4.01E-3	7.58E-4	3.12E-6
70	7.40E-4	9.74E-4	1.92E-3	4.71E-3	8.36E-3	1.15E-2	6.75E-3	1.41E-3	5.35E-6
100	1.29E-3	1.66E-3	3.09E-3	7.41E-3	1.35E-2	2.11E-2	1.56E-2	4.41E-3	1.85E-5
140	1.68E-3	2.14E-3	4.10E-3	9.20E-3	1.68E-2	2.77E-2	2.57E-2	9.23E-3	5.45E-5
200	1.95E-3	2.48E-3	4.58E-3	1.05E-2	1.85E-2	3.12E-2	3.55E-2	1.67E-2	1.74E-4
300	2.01E-3	2.61E-3	4.74E-3	1.04E-2	1.86E-2	3.12E-2	4.04E-2	2.64E-2	6.41E-4
400	1.93E-3	2.46E-3	4.69E-3	9.93E-3	1.74E-2	2.97E-2	4.17E-2	3.26E-2	1.49E-3
500	1.85E-3	2.24E-3	4.24E-3	9.43E-3	1.63E-2	2.77E-2	4.09E-2	3.61E-2	2.66E-3
700	1.55E-3	2.00E-3	3.72E-3	8.13E-3	1.41E-2	2.44E-2	3.74E-2	3.82E-2	6.07E-3
1000	1.26E-3	1.65E-3	3.16E-3	6.94E-3	1.22E-2	1.99E-2	3.29E-2	3.68E-2	1.11E-2
2000	7.40E-4	9.80E-4	1.89E-3	4.03E-3	7.17E-3	1.29E-2	2.30E-2	2.88E-2	2.07E-2
3000	5.30E-4	6.60E-4	1.28E-3	2.96E-3	5.17E-3	9.62E-3	1.77E-2	2.27E-2	2.10E-2
5000	2.90E-4	3.90E-4	7.30E-4	1.72E-3	3.14E-3	6.01E-3	1.18E-2	1.62E-2	1.81E-2
10000	1.20E-4	1.70E-4	3.30E-4	7.60E-4	1.36E-3	2.80E-3	6.03E-3	9.09E-3	1.19E-2
20000	5.00E-5	8.00E-5	1.60E-4	3.10E-4	5.90E-4	1.10E-3	2.77E-3	4.37E-3	6.88E-3

# He → C

Particle reflection coefficient of He backscattered from C  
 z1= 2, m1= 4.00, z2= 6, m2= 12.01, sbe=7.41 eV, rho=1.85 g/cm\*\*3  
 ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC) program : trvmc  
 ne=24, na= 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	4.09E-1	4.44E-1	5.37E-1	6.93E-1	8.16E-1	9.31E-1	9.92E-1	9.99E-1	1.00E+0
15	3.40E-1	3.72E-1	4.64E-1	6.29E-1	7.66E-1	9.08E-1	9.89E-1	9.99E-1	1.00E+0
20	2.96E-1	3.24E-1	4.10E-1	5.73E-1	7.21E-1	8.82E-1	9.86E-1	9.99E-1	1.00E+0
25	2.66E-1	2.91E-1	3.70E-1	5.27E-1	6.80E-1	8.56E-1	9.81E-1	9.98E-1	1.00E+0
27	2.56E-1	2.80E-1	3.57E-1	5.12E-1	6.64E-1	8.45E-1	9.79E-1	9.98E-1	1.00E+0
30	2.44E-1	2.67E-1	3.40E-1	4.90E-1	6.43E-1	8.30E-1	9.76E-1	9.98E-1	1.00E+0
35	2.27E-1	2.48E-1	3.18E-1	4.60E-1	6.12E-1	8.05E-1	9.71E-1	9.97E-1	1.00E+0
40	2.14E-1	2.34E-1	2.99E-1	4.35E-1	5.83E-1	7.82E-1	9.64E-1	9.97E-1	1.00E+0
50	1.94E-1	2.13E-1	2.75E-1	3.96E-1	5.37E-1	7.39E-1	9.50E-1	9.95E-1	1.00E+0
60	1.80E-1	1.98E-1	2.54E-1	3.68E-1	5.02E-1	7.00E-1	9.36E-1	9.93E-1	1.00E+0
70	1.69E-1	1.86E-1	2.38E-1	3.47E-1	4.72E-1	6.68E-1	9.19E-1	9.91E-1	1.00E+0
100	1.47E-1	1.61E-1	2.07E-1	3.04E-1	4.14E-1	5.91E-1	8.71E-1	9.80E-1	1.00E+0
140	1.30E-1	1.44E-1	1.85E-1	2.72E-1	3.70E-1	5.30E-1	8.09E-1	9.61E-1	1.00E+0
200	1.13E-1	1.25E-1	1.64E-1	2.43E-1	3.30E-1	4.70E-1	7.33E-1	9.25E-1	1.00E+0
300	9.74E-2	1.08E-1	1.42E-1	2.16E-1	2.99E-1	4.24E-1	6.50E-1	8.61E-1	9.99E-1
400	8.73E-2	9.60E-2	1.31E-1	2.00E-1	2.76E-1	3.90E-1	5.98E-1	8.04E-1	9.96E-1
500	7.99E-2	8.84E-2	1.19E-1	1.86E-1	2.61E-1	3.74E-1	5.64E-1	7.58E-1	9.92E-1
700	6.87E-2	7.68E-2	1.07E-1	1.71E-1	2.40E-1	3.48E-1	5.24E-1	6.91E-1	9.78E-1
1000	5.75E-2	6.43E-2	9.36E-2	1.53E-1	2.20E-1	3.24E-1	4.90E-1	6.33E-1	9.42E-1
2000	3.79E-2	4.37E-2	6.71E-2	1.19E-1	1.82E-1	2.81E-1	4.33E-1	5.54E-1	8.17E-1
3000	2.78E-2	3.36E-2	5.18E-2	9.82E-2	1.58E-1	2.56E-1	4.07E-1	5.21E-1	7.44E-1
5000	1.74E-2	2.07E-2	3.56E-2	7.22E-2	1.26E-1	2.19E-1	3.69E-1	4.79E-1	6.69E-1
10000	7.81E-3	9.70E-3	1.72E-2	4.20E-2	8.14E-2	1.64E-1	3.12E-1	4.27E-1	6.01E-1
20000	3.21E-3	3.99E-3	7.13E-3	1.83E-2	4.27E-2	1.05E-1	2.48E-1	3.66E-1	5.47E-1

Energy reflection coefficient of He backscattered from C  
 ne=24, na= 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	9.49E-2	1.16E-1	1.79E-1	3.20E-1	4.49E-1	6.35E-1	8.31E-1	9.08E-1	9.61E-1
15	8.05E-2	9.76E-2	1.55E-1	2.82E-1	4.24E-1	6.23E-1	8.38E-1	9.20E-1	9.70E-1
20	7.02E-2	8.46E-2	1.35E-1	2.55E-1	3.97E-1	6.03E-1	8.38E-1	9.25E-1	9.74E-1
25	6.28E-2	7.53E-2	1.20E-1	2.30E-1	3.70E-1	5.82E-1	8.34E-1	9.27E-1	9.77E-1
27	6.05E-2	7.23E-2	1.15E-1	2.22E-1	3.60E-1	5.73E-1	8.32E-1	9.27E-1	9.78E-1
30	5.74E-2	6.84E-2	1.08E-1	2.10E-1	3.45E-1	5.60E-1	8.28E-1	9.28E-1	9.78E-1
35	5.32E-2	6.31E-2	9.94E-2	1.94E-1	3.24E-1	5.38E-1	8.21E-1	9.28E-1	9.79E-1
40	4.99E-2	5.91E-2	9.27E-2	1.80E-1	3.04E-1	5.18E-1	8.12E-1	9.27E-1	9.80E-1
50	4.48E-2	5.29E-2	8.26E-2	1.59E-1	2.71E-1	4.80E-1	7.94E-1	9.24E-1	9.81E-1
60	4.13E-2	4.84E-2	7.56E-2	1.45E-1	2.47E-1	4.45E-1	7.75E-1	9.19E-1	9.81E-1
70	3.86E-2	4.53E-2	7.02E-2	1.33E-1	2.27E-1	4.17E-1	7.54E-1	9.14E-1	9.81E-1
100	3.31E-2	3.87E-2	5.93E-2	1.12E-1	1.90E-1	3.50E-1	6.97E-1	8.95E-1	9.81E-1
140	2.88E-2	3.41E-2	5.16E-2	9.72E-2	1.61E-1	2.98E-1	6.25E-1	8.65E-1	9.80E-1
200	2.50E-2	2.94E-2	4.54E-2	8.41E-2	1.38E-1	2.51E-1	5.38E-1	8.13E-1	9.77E-1
300	2.14E-2	2.50E-2	3.86E-2	7.32E-2	1.21E-1	2.15E-1	4.50E-1	7.29E-1	9.72E-1
400	1.91E-2	2.21E-2	3.57E-2	6.78E-2	1.10E-1	1.91E-1	3.95E-1	6.57E-1	9.66E-1
500	1.72E-2	2.02E-2	3.19E-2	6.20E-2	1.02E-1	1.80E-1	3.61E-1	5.97E-1	9.57E-1
700	1.49E-2	1.76E-2	2.83E-2	5.55E-2	9.19E-2	1.64E-1	3.21E-1	5.18E-1	9.31E-1
1000	1.22E-2	1.46E-2	2.46E-2	4.95E-2	8.28E-2	1.48E-1	2.89E-1	4.50E-1	8.77E-1
2000	7.71E-3	9.44E-3	1.68E-2	3.58E-2	6.46E-2	1.22E-1	2.38E-1	3.60E-1	7.01E-1
3000	5.47E-3	6.99E-3	1.24E-2	2.84E-2	5.36E-2	1.05E-1	2.13E-1	3.21E-1	5.99E-1
5000	3.22E-3	4.06E-3	7.89E-3	1.91E-2	3.89E-2	8.18E-2	1.78E-1	2.75E-1	4.95E-1
10000	1.33E-3	1.71E-3	3.39E-3	9.35E-3	2.08E-2	5.09E-2	1.29E-1	2.15E-1	3.95E-1
20000	5.10E-4	6.26E-4	1.23E-3	3.49E-3	8.71E-3	2.53E-2	8.03E-2	1.49E-1	3.09E-1

Average depth (mean range) in Å of He implanted in C  
 ne=24, na= 9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	3.10E+0	3.00E+0	2.90E+0	2.70E+0	2.60E+0	2.40E+0	2.10E+0	1.80E+0	1.40E+0
15	4.00E+0	4.00E+0	3.80E+0	3.60E+0	3.40E+0	3.10E+0	2.80E+0	2.50E+0	1.90E+0
20	4.90E+0	4.80E+0	4.60E+0	4.30E+0	4.10E+0	3.80E+0	3.40E+0	3.10E+0	2.60E+0
25	5.70E+0	5.60E+0	5.40E+0	5.00E+0	4.70E+0	4.40E+0	3.90E+0	3.60E+0	3.20E+0
27	6.00E+0	5.90E+0	5.70E+0	5.30E+0	5.00E+0	4.60E+0	4.10E+0	3.80E+0	3.20E+0
30	6.50E+0	6.40E+0	6.10E+0	5.70E+0	5.40E+0	5.00E+0	4.50E+0	4.10E+0	3.70E+0
35	7.20E+0	7.10E+0	6.80E+0	6.30E+0	5.90E+0	5.50E+0	5.00E+0	4.60E+0	4.30E+0
40	8.00E+0	7.80E+0	7.50E+0	6.90E+0	6.50E+0	6.00E+0	5.40E+0	5.00E+0	4.40E+0
50	9.40E+0	9.20E+0	8.70E+0	8.10E+0	7.60E+0	7.10E+0	6.40E+0	5.90E+0	4.90E+0
60	1.07E+1	1.05E+1	1.00E+1	9.20E+0	8.60E+0	8.00E+0	7.30E+0	6.80E+0	5.90E+0
70	1.20E+1	1.18E+1	1.12E+1	1.03E+1	9.60E+0	8.90E+0	8.10E+0	7.60E+0	6.70E+0
100	1.58E+1	1.55E+1	1.47E+1	1.34E+1	1.24E+1	1.15E+1	1.07E+1	1.00E+1	9.30E+0
140	2.07E+1	2.02E+1	1.90E+1	1.73E+1	1.61E+1	1.49E+1	1.37E+1	1.30E+1	1.14E+1
200	2.76E+1	2.70E+1	2.54E+1	2.30E+1	2.12E+1	1.95E+1	1.81E+1	1.71E+1	1.55E+1
300	3.89E+1	3.80E+1	3.56E+1	3.22E+1	2.94E+1	2.70E+1	2.49E+1	2.42E+1	2.23E+1
400	5.01E+1	4.90E+1	4.56E+1	4.13E+1	3.77E+1	3.45E+1	3.17E+1	3.04E+1	2.85E+1
500	6.12E+1	5.98E+1	5.58E+1	5.03E+1	4.60E+1	4.16E+1	3.83E+1	3.70E+1	3.50E+1
700	8.35E+1	8.13E+1	7.56E+1	6.75E+1	6.18E+1	5.58E+1	5.08E+1	4.89E+1	4.73E+1
1000	1.17E+2	1.14E+2	1.05E+2	9.39E+1	8.51E+1	7.66E+1	6.99E+1	6.65E+1	6.47E+1
2000	2.29E+2	2.23E+2	2.05E+2	1.80E+2	1.62E+2	1.44E+2	1.29E+2	1.23E+2	1.19E+2
3000	3.42E+2	3.32E+2	3.05E+2	2.64E+2	2.36E+2	2.07E+2	1.83E+2	1.75E+2	1.68E+2
5000	5.66E+2	5.48E+2	4.99E+2	4.29E+2	3.76E+2	3.26E+2	2.82E+2	2.66E+2	2.54E+2
10000	1.10E+3	1.06E+3	9.61E+2	8.08E+2	6.94E+2	5.81E+2	4.87E+2	4.50E+2	4.26E+2
20000	2.04E+3	1.97E+3	1.77E+3	1.47E+3	1.23E+3	9.88E+2	7.84E+2	7.06E+2	6.55E+2

## Be → C

Sputtering yield of C by Be  
 $z1 = 4$ ,  $m1 = 9.01$ ,  $z2 = 6$ ,  $m2 = 12.01$ ,  $sbe = 7.41$  eV,  $\rho = 2.26$  g/cm $^{**3}$   
 $ef = 7.35$  eV,  $esb = 0.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program : trvmc95  
*only low fluence!*  
 $ne = 8$ ,  $na = 1$

$E_0$ (eV)	$0^\circ$
30	1.20e-5
40	2.11e-4
50	9.28e-4
70	4.48e-3
100	1.25e-2
200	4.42e-2
500	1.07e-1
1000	1.40e-1

Sputtered energy of C by Be  
 $ne = 8$ ,  $na = 1$

$E_0$ (eV)	$0^\circ$
30	6.72e-7
40	1.41e-5
50	6.08e-5
70	2.65e-4
100	6.41e-4
200	1.74e-3
500	2.83e-3
1000	2.64e-3

Particle reflection coefficient of Be backscattered from C  
 $z1 = 4$ ,  $m1 = 9.01$ ,  $z2 = 6$ ,  $m2 = 12.01$ ,  $sbe = 7.41$  eV,  $\rho = 2.26$  g/cm $^{**3}$   
 $ef = 7.35$  eV,  $esb = 0.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program : trvmc95  
*only low fluence!*  
 $ne = 8$ ,  $na = 1$

$E_0$ (eV)	$0^\circ$
30	2.86e-2
40	2.48e-2
50	2.46e-2
70	2.64e-2
100	2.68e-2
200	2.60e-2
500	2.02e-2
1000	1.39e-2

Energy reflection coefficient of Be backscattered from C  
 $ne = 8$ ,  $na = 1$

$E_0$ (eV)	$0^\circ$
30	1.92e-3
40	2.44e-3
50	2.85e-3
70	3.27e-3
100	3.01e-3
200	2.56e-3
500	1.76e-3
1000	1.23e-3

Average depth (mean range) in Å Be implanted in C  
 $ne = 8$ ,  $na = 1$

$E_0$ (eV)	$0^\circ$
30	2.58e+0
40	3.40e+0
50	4.16e+0
70	5.53e+0
100	7.28e+0
200	1.26e+1
500	2.64e+1
1000	4.77e+1

# C → C

Sputtering yield of C by C  
 z1= 6, m1= 12.01, z2= 6, m2= 12.01, sbe=7.41 eV, rho=1.85 g/cm\*\*3  
 ef=7.35 eV, esb=7.41 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program : trvmc, testvmcx  
 ne=19, na= 9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
8									
10			5.00e-7	6.50e-6	2.07e-5	5.00e-6	7.69e-6	8.99e-6	9.65e-6
12			3.21e-6	2.36e-5	5.03e-5	7.39e-5	8.42e-5	8.64e-5	8.58e-5
15			1.10e-5	8.90e-5	1.47e-4	2.00e-4	2.36e-4	2.60e-4	2.64e-4
17						3.95e-4			
20		1.00e-5	8.10e-5	3.60e-4	6.74e-4	1.18e-3	1.73e-3	1.95e-3	2.05e-3
25	5.00e-6	3.10e-5	2.76e-4	1.28e-3	2.90e-3	5.02e-3	6.61e-3	7.13e-3	7.12e-3
30	1.83e-5	1.00e-4	8.15e-4	3.95e-3	8.02e-3	1.31e-2	1.55e-2	1.55e-2	1.60e-2
40	1.35e-4	5.96e-4	3.73e-3	1.56e-2	2.85e-2	4.06e-2	4.16e-2	3.40e-2	3.85e-2
45	2.74e-4								
50	5.21e-4	1.89e-3	1.04e-2	3.58e-2	5.81e-2	7.50e-2	7.57e-2	7.03e-2	6.37e-2
70	2.57e-3	7.31e-3	3.01e-2	8.40e-2	1.34e-1	1.63e-1	1.51e-1	1.28e-1	1.10e-1
100	8.84e-3	1.96e-2	6.53e-2	1.66e-1	2.45e-1	2.89e-1	2.45e-1	1.99e-1	1.54e-1
140	2.13e-2	3.95e-2	1.11e-1	2.52e-1	3.74e-1	4.43e-1	3.65e-1	2.60e-1	1.83e-1
200	4.14e-2	6.76e-2	1.63e-1	3.49e-1	5.16e-1	6.33e-1	5.14e-1	3.53e-1	2.11e-1
300	7.16e-2	1.06e-1	2.27e-1	4.60e-1	6.83e-1	8.63e-1	7.42e-1	4.94e-1	2.42e-1
500	1.16e-1	1.61e-1	3.05e-1	5.98e-1	8.91e-1	1.18e-0	1.15e-0	7.92e-1	3.01e-1
1000	1.78e-1	2.28e-1	3.93e-1	7.38e-1	1.10e-0	1.55e-0	1.77e-0	1.45e-0	4.92e-1
1200	2.13E-1								

Sputtered energy of C by C  
 ne=19, na= 9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
8						6.25e-7	1.04e-6	1.27e-6	1.37e-6
10				5.76E-7	2.69E-6	3.92E-6	5.96E-6	6.31E-6	6.45E-6
12			2.79E-7	2.62E-6	6.69E-6	1.14E-5	1.47E-5	1.55E-5	1.59E-5
15			1.05E-6	1.07E-5	2.19E-5	3.46E-5	4.39E-5	5.10E-5	5.40E-5
17					7.13e-5				
20		7.29E-7	6.84E-6	4.83E-5	1.10E-4	2.30E-4	3.77E-4	4.42E-4	4.79E-4
25	2.49E-7	2.49E-6	2.94E-5	1.92E-4	5.19E-4	1.06E-3	1.61E-3	1.74E-3	1.80E-3
30	1.09E-6	7.99E-6	9.28E-5	6.15E-4	1.57E-3	2.94E-3	3.89E-3	4.07B-3	4.32E-3
40	8.28E-6	4.85E-5	4.35E-4	2.52E-3	5.71E-3	9.61E-3	1.12E-2	1.12E-2	1.10E-2
45	1.63e-5								
50	2.98E-5	1.49E-4	1.17E-3	5.77E-3	1.15E-2	1.80E-2	2.08E-2	2.00E-2	1.81E-2
70	1.32E-4	5.06E-4	3.08E-3	1.26E-2	2.47E-2	3.68E-2	4.01E-2	3.52B-2	3.10E-2
100	4.06E-4	1.21E-3	6.00E-3	2.19E-2	4.06E-2	5.90E-2	6.04E-2	5.14E-2	4.06E-2
140	8.92B-4	2.16E-3	8.86E-3	2.89E-2	5.32E-2	7.71E-2	7.89E-2	6.06B-2	4.48E-2
200	1.57E-3	3.26E-3	1.13E-2	3.40E-2	6.18E-2	9.29E-2	9.35E-2	7.18E-2	4.66E-2
300	2.35E-3	4.40E-3	1.32E-2	3.67E-2	6.56E-2	1.01E-1	1.09E-1	8.23E-2	4.48E-2
500	3.12B-3	5.29E-3	1.39E-2	3.70E-2	6.52E-2	1.02E-1	1.25E-1	1.00E-1	4.32E-2
1000	3.48E-3	5.41E-3	1.30E-2	3.27E-2	5.68E-2	9.42E-2	1.26E-1	1.18E-1	4.88E-2
1200	3.72E-3								

# C → C

Particle reflection coefficient of C backscattered from C  
 z1= 6, m1= 12.01, z2= 6, m2= 12.01, sbe=7.41 eV, rho=1.85 g/cm\*\*3  
 ef=7.35 eV, esb=7.41 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program : trvmc, testvmcx  
 ne=18, na= 9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10					4.00E-8	6.67E-7		8.00E-8	1.20E-7
12					1.69E-5	7.91E-7	5.67E-6	9.98E-6	1.30E-5
15				5.00E-6	1.07E-4	3.66E-4	5.13E-4	6.53E-4	
17					6.76E-4				
20			7.00E-6	2.20E-4	1.14E-3	3.69E-3	8.11E-3	1.02E-2	1.17E-2
25		4.00E-6	1.38E-4	1.99E-3	7.19E-3	1.78E-2	3.26E-2	3.94E-2	4.35E-2
30	2.02E-6	3.46E-5	6.64E-4	6.27E-3	1.98E-2	4.43E-2	7.30E-2	8.64E-2	9.39E-2
40	2.82E-5	2.58E-4	3.16E-3	2.16E-2	5.60E-2	1.12E-1	1.75E-1	2.03E-1	2.20E-1
45	6.23E-5								
50	1.11E-4	7.41E-4	6.47E-3	3.74E-2	9.15E-2	1.81E-1	2.82E-1	3.25E-1	3.56E-1
70	4.23E-4	1.97E-3	1.30E-2	6.25E-2	1.43E-1	2.80E-1	4.51E-1	5.30E-1	5.76E-1
100	1.11E-3	3.76E-3	1.96E-2	7.98E-2	1.78E-1	3.51E-1	5.88E-1	6.89E-1	7.58E-1
140	2.14E-3	5.52E-3	2.34E-2	8.52E-2	1.83E-1	3.70E-1	6.34E-1	7.67E-1	8.53E-1
200	3.38E-3	7.28E-3	2.61E-2	8.48E-2	1.77E-1	3.50E-1	6.39E-1	7.91E-1	8.92E-1
300	4.36E-3	8.44E-3	2.53E-2	8.10E-2	1.62E-1	3.23E-1	6.08E-1	7.88E-1	9.18E-1
500	5.32E-3	8.91E-3	2.45E-2	7.09E-2	1.39E-1	2.73E-1	5.36E-1	7.40E-1	9.28E-1
1000	4.84E-3	7.34E-3	2.05E-2	5.91E-2	1.17E-1	2.24E-1	4.46E-1	6.36E-1	9.09E-1
1200	3.70E-3								

Energy reflection coefficient of C backscattered from C  
 ne=18, na= 9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10					6.97E-9	1.03E-7		1.50E-8	1.89E-8
12					2.73E-6	1.37E-7	1.11E-6	1.99E-6	2.57E-6
15				8.57E-7	1.95E-5	7.67E-5		1.11E-4	1.45E-4
17					1.36E-4				
20			8.15E-7	3.51E-5	2.19E-4	8.51E-4	2.11E-3	2.78E-3	3.29E-3
25		1.95E-7	1.86E-5	3.63E-4	1.61E-3	4.77E-3	9.99E-3	1.28E-2	1.45E-2
30	1.34E-6	3.44E-6	9.73E-5	1.25E-3	4.93E-3	1.32E-2	2.49E-2	3.12E-2	3.48E-2
40	1.93E-6	2.59E-5	4.84E-4	4.83E-3	1.56E-2	3.79E-2	6.82E-2	8.34E-2	9.36E-2
45	1.08E-5								
50	7.52E-6	7.29E-5	9.88E-4	8.69E-3	2.69E-2	6.52E-2	1.18E-1	1.45E-1	1.64E-1
70	2.79E-5	1.89E-4	1.99E-3	1.46E-2	4.45E-2	1.09E-1	2.10E-1	2.62E-1	2.97E-1
100	6.78E-5	3.37E-4	2.82E-3	1.84E-2	5.61E-2	1.44E-1	3.00E-1	3.81E-1	4.43E-1
140	1.26E-4	4.75E-4	3.19E-3	1.91E-2	5.63E-2	1.55E-1	3.49E-1	4.70E-1	5.57E-1
200	1.98E-4	5.92E-4	3.44E-3	1.81E-2	5.19E-2	1.46E-1	3.69E-1	5.19E-1	6.41E-1
300	2.55E-4	6.40E-4	3.11E-3	1.60E-2	4.60E-2	1.31E-1	3.56E-1	5.43E-1	7.12E-1
500	2.94E-4	6.46E-4	2.90E-3	1.32E-2	3.58E-2	1.03E-1	3.02E-1	5.16E-1	7.63E-1
1000	2.72E-4	5.21E-4	2.30E-3	1.05E-2	2.84E-2	7.58E-2	2.33E-1	4.27E-1	7.75E-1
1200	1.98E-4								

Average depth (mean range) in Å of C implanted in C  
 ne=19, na= 9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
8					5.02E-1	4.24E-1	3.97E-1	3.79E-1	
10	1.28E+0	1.23E+0	1.10E+0	9.28E-1	8.03E-1	6.90E-1	6.03E-1	5.72E-1	5.54E-1
12			1.23E+0	9.95E-1	8.08E-1	6.28E-1	4.83E-1	4.33E-1	4.02E-1
15	1.81E+0	1.73E+0	1.54E+0	1.24E+0	9.36E-1	6.99E-1	5.13E-1	4.51E-1	4.11E-1
17					7.46E-1				
20	2.31E+0	2.21E+0	1.95E+0	1.48E+0	1.14E+0	8.16E-1	5.71E-1	4.89E-1	4.38E-1
25	2.77E+0	2.65E+0	2.30E+0	1.75E+0	1.33E+0	9.44E-1	6.36E-1	5.36E-1	4.74E-1
30	3.19E+0	3.05E+0	2.66E+0	2.03E+0	1.50E+0	1.10E+0	7.00E-1	6.00E-1	5.00E-1
40	3.97E+0	3.80E+0	3.32E+0	2.60E+0	2.00E+0	1.40E+0	9.00E-1	8.00E-1	6.00E-1
45	4.34E+0								
50	4.69E+0	4.49E+0	3.90E+0	3.10E+0	2.40E+0	1.80E+0	1.10E+0	9.00E-1	8.00E-1
70	5.99E+0	5.75E+0	5.10E+0	4.10E+0	3.30E+0	2.50E+0	1.70E+0	1.40E+0	1.20E+0
100	7.74E+0	7.40E+0	6.70E+0	5.50E+0	4.60E+0	3.80E+0	2.80E+0	2.30E+0	1.90E+0
140	9.84E+0	9.50E+0	8.50E+0	7.20E+0	6.20E+0	5.20E+0	4.00E+0	3.50E+0	3.00E+0
200	1.27E+1	1.23E+1	1.11E+1	9.40E+0	8.20E+0	6.90E+0	5.70E+0	5.00E+0	4.20E+0
300	1.71E+1	1.65E+1	1.50E+1	1.27E+1	1.10E+1	9.40E+0	7.90E+0	7.10E+0	6.00E+0
500	2.51E+1	2.43E+1	2.20E+1	1.87E+1	1.63E+1	1.38E+1	1.17E+1	1.07E+1	9.50E+0
1000	4.34E+1	4.20E+1	3.80E+1	3.22E+1	2.78E+1	2.38E+1	2.03E+1	1.85E+1	1.71E+1
1200	4.14E+1								

# $C \rightarrow C$

Sputtering yield of C by C  
 $z1 = 6, m1 = 12.01, z2 = 6, m2 = 12.01, sbe = 7.42 \text{ eV}, rho = 2.26 \text{ g/cm}^{**3}$   
 $ef = 7.37 \text{ eV}, esb = 7.42 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1$  (KrC)  
 program : testvmcx, trspv1cn, trvmc95, trvmc  
 $n_{\text{e}} = 36, n_{\text{a}} = 7$

$E_0 (\text{eV})$	$0^\circ$	$30^\circ$	$45^\circ$	$50^\circ$	$70^\circ$	$75^\circ$	$85^\circ$
8					2.63e-6		
10					1.83e-5		
12					5.49e-5		
14					1.14e-4		
15					1.72e-4		
20					1.32e-3		
25	5.72e-6				5.72e-3		
28	1.15e-5						
30	1.94E-5				1.40e-2		
35	5.53e-5						
40	1.44e-4				4.16e-2		
45	2.97e-4						
50	5.33E-4				7.77e-2		
50	5.75e-4						
70	2.72E-3						
100	9.31B-3				1.55e-1		
100	1.01e-2				2.64e-1		
150	2.65e-2						
200	4.51e-2				5.98e-1		
200	4.60e-2						
500	1.27E-1						
500	1.30e-1				1.27e-0		
1000	1.92E-1				1.81e-0		
1000	1.85e-1						
1200	2.13e-1						
2000	2.26e-1				2.16e-0		
2000	2.24e-1						
3000		4.59e-1	8.23e-1	1.03e-0	2.68e-0	1.23e-0	
3000			8.27e-1				
5000	2.54e-1				2.35e-0		
5000	2.34e-1						
10000	2.25E-1				2.06e-0		
10000	2.12e-1						
30000	1.60E-1				1.13e-0		
30000	1.56e-1						
100000	8.58e-2				4.39e-1		

Sputtered energy of C by C  
 $n_{\text{e}} = 36, n_{\text{a}} = 7$

$E_0 (\text{eV})$	$0^\circ$	$30^\circ$	$45^\circ$	$50^\circ$	$70^\circ$	$75^\circ$	$85^\circ$
8					3.50e-7		
10					2.67e-6		
12					8.99e-6		
14					2.04e-5		
15					3.07e-5		
20					2.69e-4		
25	6.76e-7				1.27e-3		
28	7.46e-7						
30	1.23E-6				3.30e-3		
35	3.69e-6						
40	8.84e-6				1.04e-2		
45	1.88e-5						
50	3.16E-5				1.97e-2		
50	3.43e-5						
70	1.42E-4				3.82e-2		
100	4.30E-4				6.00e-2		
100	4.89e-4						
150	1.04e-3						
200	1.62e-3				9.82e-2		
200	1.60e-3						
500	3.26E-3				1.22e-1		
500	3.19e-3						
1000	3.56E-3				1.13e-1		
1000	3.27e-3						
1200	3.73e-3						
2000	3.07e-3				9.71e-2		
2000	2.86e-3						
3000		9.06e-3	2.27e-2	2.92e-2	1.07e-1	6.04e-2	
3000			2.15e-2				
5000	2.15e-3				7.36e-2		
5000	1.96e-3						
10000	1.32E-3				5.13e-2		
10000	1.24e-3						
30000	4.66E-4				1.68e-2		
30000	5.03e-4						
100000	1.08e-4				2.34e-3		

# C → C

Particle reflection coefficient of C backscattered from C  
 z1= 6, m1= 12.01, z2= 6, m2= 12.01, sbe=7.42 eV, rho=2.26 g/cm\*\*3  
 ei=7.37 eV, esb=7.42 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program : testvmcx, trspv1cn, trvmc95, trvmc  
 ne=34, na= 7

E <sub>0</sub> (eV)	0°	30°	45°	50°	70°	75°	85°
12					2.82e-6		
14					5.91e-5		
15					1.86e-4		
20					5.44e-3		
25	1.41e-7				2.61e-2		
28	4.65e-7				6.32e-2		
30	1.45E-6						
35	8.15e-6						
40	2.88e-5						
45	6.58e-5						
50	1.14E-4						
50	1.10e-4						
70	5.03E-4						
100	1.25E-3						
100	1.33e-3						
150	2.46e-3						
200	3.45e-3						
200	3.03e-3						
500	5.29E-3						
500	3.84e-3						
1000	5.04E-3						
1000	4.04e-3						
1200	3.70e-3						
2000	3.95e-3						
2000	3.56e-3						
3000		1.30e-2	4.01e-2	6.01e-2		3.56e-1	8.28e-1
3000			4.19e-2				
5000	1.60e-3						
5000	1.82e-3						
10000	1.10E-3						
10000	1.16e-3						
30000	4.67E-4						
30000	4.20e-4						
100000	5.79e-5						

Energy reflection coefficient of C backscattered from C  
 ne=34, na= 7

E <sub>0</sub> (eV)	0°	30°	45°	50°	70°	75°	85°
12					1.47e-6		
14					1.16e-5		
15					3.82e-5		
20					1.31e-3		
25	3.63e-7				7.34e-3		
28	2.09e-7						
30	1.02E-7						
35	6.11e-7						
40	2.05e-6						
45	4.74e-6						
50	8.44E-6						
50	1.22e-5						
70	3.40E-5						
100	7.89E-5						
100	8.64e-5						
150	1.51e-4						
200	2.08e-4						
200	1.83e-4						
500	2.88E-4						
500	2.02e-4						
1000	2.99E-4						
1000	2.29e-4						
1200	1.09e-4						
2000	2.28e-4						
2000	2.20e-4						
3000		1.44e-3	6.86e-3	1.22e-2		1.63e-1	7.05e-1
3000			7.31e-3				
5000	8.71e-5						
5000	1.08e-4						
10000	6.68E-5						
10000	5.59e-5						
30000	1.27E-5						
30000	2.22e-5						
100000	2.47e-6						

# C → C

Average depth (mean range) in Å of C implanted in C  
 z1= 6, m1= 12.01, z2= 6, m2= 12.01, sbe=7.42 eV, rho=2.26 g/cm\*\*3  
 ef=7.37 eV, esb=7.42 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program : testvmcx, trspv1cn, trvmc95, trvmc  
 ne=37, na= 7

E <sub>0</sub> (eV)	0°	30°	45°	50°	70°	75°	85°
8					2.59e-1		
10					3.16e-1		
12					3.46e-1		
14					3.67e-1		
15					3.76e-1		
20	1.46e+0				4.33e-1		
25	2.10e+0				4.98e-1		
28	2.31e+0						
30	2.45E+0				5.74e-1		
30	2.03e+0						
35	2.78e+0						
40	3.09e+0				7.59e-1		
45	3.39e+0						
50	3.68E+0				9.81e-1		
50	3.07e+0						
70	4.74E+0				1.53e+0		
100	6.17E+0				2.48e+0		
100	5.30e+0						
150	8.30e+0						
200	1.02e+1				4.95e+0		
200	9.08e+0						
500	2.04E+1				1.02e+1		
500	1.89e+1						
1000	3.54E+1				1.81e+1		
1000	3.37e+1						
1200	4.11e+1						
2000	6.41e+1				3.14e+1		
2000	6.18e+1						
3000		8.05e+1	6.74e+1	6.29e+1		4.08e+1	3.49e+1
3000			6.76e+1		6.97e+1		
5000	1.49e+2						
5000	1.46e+2						
10000	2.94E+2				1.34e+2		
10000	2.91e+2						
30000	8.82E+2				3.69e+2		
30000	8.77e+2						
100000	2.72e+3				1.02e+3		

# $C \rightarrow C$

Sputtering yield of C by C  
 $z1 = 6, m1 = 12.01, z2 = 6, m2 = 12.01, sbe = 7.40 \text{ eV}, rho = 2.00 \text{ g/cm}^{**3}$   
 $ef = 7.35, 6.90 \text{ eV}, esb = 7.40 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1$  (KrC)  
 program : testvmcx, newtrim (Laszlo), trspvmc  
 $ne = 22, na = 7$

$E_0 (\text{eV})$	$0^\circ$	$30^\circ$	$45^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$80^\circ$
17					3.83e-4		
18					5.37e-4		
18					3.06e-4		
19					8.09e-4		
19					5.21e-4		
20					1.23e-3		
20					8.65e-4		
25					5.22e-3		
25					4.62e-3		
30					1.26e-2		
45	2.59e-4						
50	5.05E-4						
53	7.48e-4						
55	8.66e-4						
70	2.62E-3						
100	9.49E-3				1.73e-1		
150					3.12e-1		
300	7.36e-2				8.97e-1		
300	8.05e-2	2.33e-1	4.85e-1	8.16e-1	8.49e-1	4.66e-1	
1000	1.79e-1	4.23e-1	7.37e-1	1.38e-0	1.73e-0	1.39e-0	
3000	2.49e-1			1.50e-0	2.25e-0	2.68e-0	
6000					2.26e-0		

Sputtered energy of C by C

$E_0 (\text{eV})$	$0^\circ$	$30^\circ$	$45^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$80^\circ$
17					6.68e-5		
18					9.62e-5		
18					5.66e-5		
19					1.53e-4		
19					9.95e-5		
20					2.35e-4		
20					1.71e-4		
25					1.10e-3		
25					1.01e-3		
30					2.89e-3		
45	1.63e-5						
50	3.05B-5						
53	4.28e-5						
55	5.05e-5						
70	1.37B-4						
100	4.36E-4						
150							
300	2.24e-3						
300	2.41e-3	1.30e-2	3.85e-2	8.21e-2	9.96e-2	1.08e-1	7.84e-2
1000	3.54e-3	1.36e-2	2.99e-2	7.40e-2	4.91e-2	1.14e-1	1.11e-1
3000	2.80e-3					9.20e-2	1.12e-1
6000						6.34e-2	

# $C \rightarrow C$

Particle reflection coefficient of C backscattered from C  
 $z1 = 6, m1 = 12.01, z2 = 6, m2 = 12.01, sbe = 7.40 \text{ eV}, rho = 2.00 \text{ g/cm}^{**3}$   
 $ef = 7.35, 6.90 \text{ eV}, esb = 7.40 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1$  (KrC)  
 program : testvmcx, newtrim (Laszlo), trspvmc  
 $ne = 22, na = 7$

$E_0 (\text{eV})$	$0^\circ$	$30^\circ$	$45^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$80^\circ$
17					6.42e-4		
18					1.30e-3		
18					1.27e-3		
19					2.24e-3		
19					2.21e-3		
20					3.77e-3		
20					3.60e-3		
25					1.87e-2		
25					1.86e-2		
30					4.49e-2		
45	6.93e-5						
50	1.13E-4						
53	1.53e-4						
55	1.79e-4						
70	3.98E-4						
100	1.30E-3				2.96e-1		
150					3.68e-1	4.84e-1	
300	4.27e-3					5.19e-1	
300	4.47e-3	2.54e-2	8.19e-2	2.47e-1			
1000	4.46e-3	1.76e-2	5.98e-2	1.54e-1			
3000	3.98e-3			1.34e-1			
6000						2.42e-1	4.93e-1

Energy reflection coefficient of C backscattered from C  
 $ne = 22, na = 7$

$E_0 (\text{eV})$	$0^\circ$	$30^\circ$	$45^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$80^\circ$
17					1.37e-4		
18					2.75e-4		
18					2.65e-4		
19					4.90e-4		
19					4.81e-4		
20					8.47e-4		
20					8.15e-4		
25					4.94e-3		
25					4.81e-3		
30					1.32e-2		
45	4.84e-6						
50	7.50E-6				6.87e-2		
53	9.82e-6						
55	1.13e-5						
70	2.73E-5						
100	8.89E-5				1.16e-1		
150					1.52e-1	2.25e-1	
300	2.31e-4					2.55e-1	
300	2.54e-4	3.23e-3	1.66e-2	8.64e-2			
1000	2.13e-4	1.70e-3	1.03e-2	4.55e-2			
3000	1.31e-4			3.69e-2			
6000						8.17e-2	

Average depth (mean range) in Å of C implanted in C  
 $ne = 22, na = 7$

$E_0 (\text{eV})$	$0^\circ$	$30^\circ$	$45^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$80^\circ$
17					6.36e-1		
18					6.57e-1		
18					3.12e-1		
19					6.77e-1		
19					5.73e-1		
20					6.97e-1		
20					6.87e-1		
25					8.07e-1		
25					8.05e-1		
30					9.36e-1		
45	3.51e+0						
50	3.86E+0				1.53e+0		
53	4.08e+0						
55	4.21e+0						
70	5.12E+0						
100	7.09E+0				2.33e+0		
150					3.40e+0	2.94e-0	
300	1.57e+1					4.49e-0	
300	1.57e+1	1.39e+1	1.18e+1	9.29e-0			
1000	4.00e+1	3.50e+1	3.09e+1	2.39e+1			
3000	1.03e+2			5.99e+1			
6000						9.50e+1	

# C → C

C on C, Maxwellian velocity distribution, sheath potential 0 kT  
 z1= 6, m1= 12.01, z2=6, m2= 12.01, sbe=7.42 eV, rho=2.26 g/cm\*\*3  
 ef=7.37), esb=7.42 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1(KrC)  
 program: testvmcx  
 ne=11

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
5	4.24e-4	2.85e-4	6.71e+0	1.27e-3	1.28e-3	1.01e+1	4.95e-1
7	1.63e-3	9.62e-4	8.23e+0	4.78e-3	4.51e-3	1.32e+1	6.95e-1
10	5.88e-3	3.00e-3	1.02e+1	1.44e-2	1.19e-2	1.66e+1	9.77e-1
20	3.35e-2	1.22e-2	1.46e+1	5.89e-2	4.11e-2	2.80e+1	1.82e+0
50	1.54e-1	3.22e-2	2.09e+1	1.40e-1	7.71e-2	5.54e+1	4.10e+0
100	3.15e-1	4.28e-2	2.78e+1	1.70e-1	8.35e+2	9.85e+1	7.39e+0
200	5.06e-1	4.60e-2	3.64e+1	1.72e-1	7.55e+2	1.75e+2	1.27e+1
500	7.67e-1	4.21e-2	5.49e+1	1.46e-1	5.87e+2	4.02e+2	2.67e+1
1000	9.08e-1	3.54e-2	7.75e+1	1.22e-1	4.77e-2	7.75e+2	4.79e+1
2000	9.94e-1	2.72e-2	1.09e+2	1.02e-1	3.72e-2	1.46e+3	9.01e+1
5000	9.16e-1	1.58e-2	1.73e+2	8.36e-2	2.93e-2	3.52e+3	2.16e+2

C on C, Maxwellian velocity distribution, sheath potential 3 kT  
 ne=13

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
3.5	2.87e-4	7.74e-5	4.72e+0	3.71e-4	1.61e-4	7.58e+0	1.29e+0
5	1.45e-3	3.68e-4	6.36e+0	1.75e-3	6.70e-4	9.57e+0	1.78e+0
7	5.25e-3	1.19e-3	7.91e+0	5.15e-3	1.76e-3	1.19e+1	2.37e+0
10	1.58e-2	2.81e-3	8.92e+0	1.03e-2	3.12e-3	1.51e+1	3.17e+0
14	3.44e-2	5.08e-3	1.03e+1	1.52e-2	3.99e-3	1.84e+1	4.14e+0
20	6.52e-2	7.68e-3	1.18e+1	2.02e-2	4.53e-3	2.25e+1	5.44e+0
30	1.14e-1	1.05e-2	1.37e+1	2.22e-2	4.58e-3	3.09e+1	7.36e+0
50	1.82e-1	1.25e-2	1.72e+1	2.33e-2	4.04e-3	4.34e+1	1.08e+1
100	2.77e-1	1.31e-2	2.36e+1	2.14e-2	3.33e-3	7.78e+1	1.84e+1
200	3.56e-1	1.18e-2	3.31e+1	1.79e-2	2.54e-3	1.42e+2	3.19e+1
500	4.05e-1	8.48e-3	5.24e+1	1.25e-2	1.76e-3	3.52e+2	7.03e+1
1000	3.86e-1	5.88e-3	7.62e+1	9.26e-3	1.35e-3	7.30e+2	1.33e+2
2000	3.37e-1	3.70e-3	1.09e+2	4.60e-3	6.80e-4	1.46e+3	2.61e+2

C on C, Maxwellian velocity distribution, sheath potential 9 kT  
 ne=15

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
2	8.57e-5	1.32e-5	3.39e+0	6.90e-5	1.48e-5	4.72e+0	2.13e+0
3	7.70e-4	1.05e-4	4.52e+0	5.20e-4	1.10e-4	6.82e+0	2.48e+0
5	6.07e-3	6.76e-4	6.13e+0	2.78e-3	4.83e-4	9.55e+0	3.72e+0
7	1.68e-2	1.55e-3	7.09e+0	4.92e-3	7.25e-4	1.13e+1	4.80e+0
10	3.69e-2	2.82e-3	8.41e+0	7.52e-3	1.01e-3	1.48e+1	6.28e+0
14	6.35e-2	4.00e-3	9.71e+0	9.15e-3	1.09e-3	1.83e+1	8.04e+0
20	9.93e-2	5.22e-3	1.16e+1	1.07e-2	1.20e-3	2.47e+1	1.05e+1
30	1.47e-1	6.34e-3	1.43e+1	1.09e-2	1.12e-3	3.39e+1	1.42e+1
50	2.02e-1	6.84e-3	1.87e+1	1.06e-2	9.51e-4	4.95e+1	2.09e+1
100	2.68e-1	6.39e-3	2.63e+1	9.12e-3	8.05e-4	9.70e+1	3.66e+1
200	3.06e-1	5.17e-3	3.71e+1	6.74e-3	6.01e-4	1.96e+2	6.66e+1
500	3.01e-1	3.28e-3	6.01e+1	4.43e-3	4.39e-4	5.45e+2	1.55e+2
1000	2.52e-1	1.97e-3	8.60e+1	2.65e-3	1.81e-4	7.51e+2	3.50e+2
2000	2.01e-1	1.19e-3	1.30e+2	7.32e-4	3.52e-5	1.06e+3	6.93e+2
5000	1.33e-1	3.78e-4	1.57e+2				1.70e+3

# $^{13}\text{C} \rightarrow ^{12}\text{C}$

Particle reflection coefficient of  $^{13}\text{C}$  backscattered from  $^{12}\text{C}$   
 $z1=6$ ,  $m1=13.00$ ,  $z2=6$ ,  $m2=12.00$ ,  $sbe=7.41$  eV,  $\rho=2.26$  g/cm $^{**3}$   
 $ef=0.50$  eV,  $esb=7.41$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
 $\alpha=0.00$   
program : trvmc95  
ne=10, na= 1

$E_0$ (eV)	$0^\circ$	comment
22	3.03e-2	$ef=7.35$ eV, $esb=0.00$ eV
22	4.51e-2	$esb=0.00$ eV
47	2.00e-5	
72	1.50e-4	
92	3.30e-4	
122	6.60e-4	
222	1.95e-3	
472	3.33e-3	
692	3.34e-3	
1000	3.32e-3	

Particle reflection coefficient of  $^{13}\text{C}$  backscattered from  $^{12}\text{C}$   
ne=10, na= 1

$E_0$ (eV)	$0^\circ$	comment
22	7.19e-5	$ef=7.35$ eV, $esb=0.00$ eV
22	8.57e-4	$esb=0.00$ eV
47	1.53e-6	
72	8.01e-6	
92	1.97e-5	
122	3.07e-5	
222	9.47e-5	
472	1.58e-4	
692	1.64e-4	
1000	1.48e-4	

Moments of depth distribution in Å of  $^{13}\text{C}$  implanted in  $^{12}\text{C}$   
 $z1=6$ ,  $m1=13.00$ ,  $z2=6$ ,  $m2=12.00$ ,  $sbe=7.41$  eV,  $\rho=2.26$  g/cm $^{**3}$   
 $ef=0.50$  eV,  $esb=7.41$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
 $\alpha=0.00$   
program : trvmc95  
ne=10, na= 1

$E_0$ (eV)	range	$\sigma$	skewness	kurtosis	comment
10	1.46e+0	9.74e-1	3.61e-1	2.51e+0	
22	1.39e+0	8.18e-1	2.98e-1	2.28e+0	$ef=7.35$ eV, $esb=0.00$ eV
22	1.88e+0	1.16e+0	2.88e-1	2.50e+0	$ef=7.35$ eV, $esb=7.41$ eV
22	2.38e+0	1.34e+0	2.18e-1	2.53e+0	
22	2.40e+0	1.37e+0	2.27e-1	2.54e+0	
22	2.32e+0	1.30e+0	2.05e-1	2.54e+0	$kdee1=kdee2=2$
22	2.55e+0	1.44e+0	2.48e-1	2.59e+0	$kdee1=kdee2=1$
22	2.29e+0	1.30e+0	2.09e-1	2.53e+0	$kk0=kk0r=1$
22	2.59e+0	1.47e+0	2.64e-1	2.59e+0	$kk0=kk0r=3$
22	2.39e+0	1.36e+0	2.26e-1	2.54e+0	$ipot=ipotr=3$
22	2.42e+0	1.39e+0	2.33e-1	2.54e+0	$ck=0.00$
22	3.41e+0	1.95e+0	3.04e-1	2.67e+0	
22	1.91e+0	1.05e+0	3.15e-1	2.52e+0	$kk0=kk0r=0$
32	3.00e+0	1.61e+0	2.03e-1	2.58e+0	$esb=0.00$ eV
47	3.87e+0	1.99e+0	2.11e-1	2.62e+0	
72	5.15e+0	2.59e+0	2.53e-1	2.68e+0	
92	6.08e+0	3.04e+0	2.82e-1	2.69e+0	
122	7.39e+0	3.67e+0	3.11e-1	2.73e+0	
222	1.13e+1	5.56e+0	3.88e-1	2.86e+0	
472	1.95e+1	9.62e+0	4.35e-1	2.94e+0	
692	2.63e+1	1.28e+1	4.29e-1	2.91e+0	
1000	3.54e+1	1.70e+1	4.06e-1	2.88e+0	

# $N \rightarrow C$

Sputtering yield of C by N

```

z1= 7, m1= 14.01, z2= 6, m2= 12.01, sbe=7.41 eV, rho=1.85 g/cm**3
ef=0.95 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program: trvmc
ne=14, na=10

```

$E_0$ (eV)	0°	15°	30°	45°	55°	60°	65°	75°	80°	85°
15										
20										
25										
30	3.60E-6	1.31E-5	7.67E-5	3.70E-4	8.16E-4					
40	1.12E-6	1.78E-5	2.39E-4	1.40E-3	3.41E-3					
50	1.81E-5	1.55E-4	1.70E-3	9.34E-3	1.85E-2					
70	1.23E-4	7.40E-4	6.03E-3	2.68E-2	4.57E-2					
100	1.11E-3	4.30E-3	2.38E-2	7.85E-2	1.19E-1					
140	1.63E-2	3.47E-2	1.08E-1	2.62E-1	3.84E-1					
200	3.68E-2	6.42E-2	1.67E-1	3.75E-1	5.52E-1					
300	6.94E-2	1.06E-1	2.39E-1	5.06E-1	7.46E-1					
500	1.21E-1	1.68E-1	3.30E-1	6.55E-1	9.78E-1					
1000	1.96E-1	2.53E-1	4.40E-1	8.31E-1	1.24E+0					
15000						1.15e-0				

Sputtered energy of C by N

```
ne=14, na=10
```

$E_0$ (eV)	0°	15°	30°	45°	55°	60°	65°	75°	80°	85°
15										
20										
25										
30	4.60e-8	1.79e-7	9.61e-7	2.01E-5	1.77E-4	5.65E-4				
40	7.69e-7	9.64E-6	1.65E-4	1.38E-3	3.42E-3					
50	5.63E-6	4.88E-5	6.15E-4	4.11E-3	8.78E-3					
70	5.03E-5	2.78E-4	2.33E-3	1.16E-2	2.25E-2					
100	2.35E-4	8.73E-4	5.28E-3	2.18E-2	4.11E-2					
140	6.37E-4	1.81E-3	8.44E-3	3.02E-2	5.63E-2					
200	1.31E-3	2.97E-3	1.13E-2	3.64E-2	6.76E-2					
300	2.20E-3	4.21E-3	1.36E-2	4.02E-2	7.26E-2					
500	3.13E-3	5.39E-3	1.49E-2	4.05E-2	7.23E-2					
1000	3.74E-3	5.89E-3	1.44E-2	3.67E-2	6.45E-2					
15000						2.18e-2				

# N → C

Particle reflection coefficient of N backscattered from C  
 z1= 7, m1= 14.01, z2= 6, m2= 12.01, sbe=7.41 eV, rho=1.85 g/cm\*\*3  
 ef=0.95 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trvmc  
 ne=16, na=10

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	60°	65°	75°	80°	85°
10	2.78E-6	3.02E-4	7.13E-3	5.63E-2	1.54E-1		3.21E-1	5.10E-1	5.80E-1	6.20E-1
12	3.84E-5	9.46E-4	1.48E-2	9.34E-2	2.23E-1		4.28E-1	6.38E-1	7.12E-1	7.55E-1
15	2.85E-4	2.71E-3	2.76E-2	1.43E-1	3.07E-1		5.40E-1	7.65E-1	8.37E-1	8.76E-1
20	1.06E-3	6.20E-3	4.57E-2	1.98E-1	3.90E-1		6.40E-1	8.61E-1	9.23E-1	9.54E-1
25	1.91E-3	8.99E-3	5.65E-2	2.24E-1	4.28E-1		6.83E-1	8.96E-1	9.53E-1	9.78E-1
30	2.62E-3	1.08E-2	6.18E-2	2.34E-1	4.41E-1		6.97E-1	9.11E-1	9.65E-1	9.87E-1
40	3.62E-3	1.27E-2	6.46E-2	2.34E-1	4.39E-1		7.00E-1	9.21E-1	9.75E-1	9.94E-1
50	4.27E-3	1.34E-2	6.31E-2	2.23E-1	4.24E-1		6.87E-1	9.23E-1	9.79E-1	9.96E-1
70	4.93E-3	1.36E-2	5.76E-2	1.97E-1	3.85E-1		6.53E-1	9.16E-1	9.81E-1	9.98E-1
100	5.57E-3	1.32E-2	5.01E-2	1.66E-1	3.32E-1		5.98E-1	8.96E-1	9.79E-1	9.99E-1
140	5.53E-3	1.23E-2	4.25E-2	1.38E-1	2.81E-1		5.32E-1	8.65E-1	9.73E-1	9.99E-1
200	5.43E-3	1.11E-2	3.66E-2	1.14E-1	2.36E-1		4.59E-1	8.15E-1	9.61E-1	9.99E-1
300	4.94E-3	9.64E-3	3.00E-2	9.41E-2	1.92E-1		3.82E-1	7.38E-1	9.34E-1	9.99E-1
500	4.45E-3	7.91E-3	2.36E-2	7.36E-2	1.50E-1		3.04E-1	6.20E-1	8.68E-1	9.98E-1
1000	3.28E-3	5.77E-3	1.70E-2	5.49E-2	1.16E-1		2.34E-1	4.79E-1	7.23E-1	9.87E-1
15000						6.88E-2				

Energy reflection coefficient of N backscattered from C  
 ne=16, na=10

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	60°	65°	75°	80°	85°
10	1.53E-7	2.59E-5	9.18E-4	1.06E-2	3.86E-2		1.05E-1	2.06E-1	2.52E-1	2.82E-1
12	2.25E-6	8.41E-5	2.00E-3	1.85E-2	5.82E-2		1.47E-1	2.76E-1	3.34E-1	3.73E-1
15	1.78E-5	2.40E-4	3.86E-3	2.96E-2	8.44E-2		1.98E-1	3.61E-1	4.34E-1	4.81E-1
20	6.53E-5	5.58E-4	6.39E-3	4.29E-2	1.14E-1		2.54E-1	4.54E-1	5.42E-1	6.00E-1
25	1.12E-4	7.84E-4	7.82E-3	4.97E-2	1.30E-1		2.85E-1	5.08E-1	6.09E-1	6.74E-1
30	1.44E-4	9.01E-4	8.39E-3	5.24E-2	1.38E-1		3.02E-1	5.42E-1	6.53E-1	7.24E-1
40	1.79E-4	9.73E-4	8.37E-3	5.21E-2	1.41E-1		3.15E-1	5.80E-1	7.07E-1	7.88E-1
50	1.93E-4	9.53E-4	7.79E-3	4.89E-2	1.36E-1		3.18E-1	5.98E-1	7.38E-1	8.27E-1
70	2.00E-4	8.59E-4	6.55E-3	4.14E-2	1.22E-1		3.01E-1	6.09E-1	7.69E-1	8.71E-1
100	1.97E-4	7.55E-4	5.20E-3	3.30E-2	1.01E-1		2.72E-1	6.01E-1	7.86E-1	9.03E-1
140	1.82E-4	6.53E-4	4.11E-3	2.55E-2	8.07E-2		2.35E-1	5.77E-1	7.88E-1	9.23E-1
200	1.73E-4	5.49E-4	3.34E-3	1.98E-2	6.29E-2		1.92E-1	5.33E-1	7.76E-1	9.36E-1
300	1.52E-4	4.60E-4	2.59E-3	1.52E-2	4.73E-2		1.49E-1	4.65E-1	7.43E-1	9.44E-1
500	1.44E-4	3.77E-4	1.95E-3	1.11E-2	3.39E-2		1.07E-1	3.65E-1	6.66E-1	9.44E-1
1000	1.15E-4	2.80E-4	1.43E-3	7.86E-3	2.43E-2		7.36E-2	2.49E-1	5.10E-1	9.21E-1
15000						1.60E-2				

Average depth (mean range) in Å of N implanted in C  
 ne=16, na=10

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	60°	65°	75°	80°	85°
10	1.20E+0	1.10E+0	9.00E-1	6.00E-1	5.00E-1		3.00E-1	2.00E-1	1.00E-1	1.00E-1
12	1.40E+0	1.30E+0	1.10E+0	8.00E-1	6.00E-1		4.00E-1	2.00E-1	2.00E-1	1.00E-1
15	1.70E+0	1.60E+0	1.30E+0	1.00E+0	8.00E-1		5.00E-1	3.00E-1	2.00E-1	2.00E-1
20	2.20E+0	2.00E+0	1.80E+0	1.40E+0	1.10E+0		8.00E-1	5.00E-1	4.00E-1	3.00E-1
25	2.60E+0	2.50E+0	2.20E+0	1.70E+0	1.30E+0		1.00E+0	5.00E-1	3.00E-1	2.00E-1
30	3.10E+0	2.90E+0	2.50E+0	2.10E+0	1.70E+0		1.20E+0	8.00E-1	7.00E-1	5.00E-1
40	3.80E+0	3.60E+0	3.20E+0	2.60E+0	2.30E+0		1.80E+0	1.20E+0	9.00E-1	6.00E-1
50	4.50E+0	4.30E+0	3.60E+0	3.20E+0	2.70E+0		2.20E+0	1.50E+0	1.10E+0	9.00E-1
70	5.70E+0	5.50E+0	4.60E+0	4.20E+0	3.60E+0		3.00E+0	2.10E+0	1.60E+0	1.10E+0
100	7.40E+0	7.10E+0	6.00E+0	5.40E+0	4.70E+0		4.00E+0	3.00E+0	2.40E+0	1.60E+0
140	9.40E+0	9.00E+0	8.20E+0	6.90E+0	6.00E+0		5.10E+0	4.00E+0	3.30E+0	2.20E+0
200	1.20E+1	1.16E+1	1.05E+1	8.90E+0	7.70E+0		6.60E+0	5.40E+0	4.60E+0	3.20E+0
300	1.60E+1	1.55E+1	1.40E+1	1.18E+1	1.02E+1		8.70E+0	7.30E+0	6.40E+0	4.80E+0
500	2.32E+1	2.24E+1	2.02E+1	1.71E+1	1.48E+1		1.26E+1	1.06E+1	9.50E+0	7.60E+0
1000	3.94E+1	3.80E+1	3.44E+1	2.89E+1	2.50E+1		2.10E+1	1.76E+1	1.62E+1	1.39E+1
15000						2.48E+2				

# N → C

Sputtering yield of C by N  
 $z1 = 7$ ,  $m1 = 14.01$ ,  $z2 = 6$ ,  $m2 = 12.01$ ,  $sbe = 7.41$  eV,  $\rho = 2.26$  g/cm<sup>3</sup>  
 $ef = 0.95$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: trvmc  
 $ne = 2$ ,  $na = 12$

$E_0$ (eV)	0°	10°	20°	30°	40°	50°	60°	70°	75°	80°	85°	87°
15000	2.64e-1	2.79e-1	3.25e-1	4.11e-1	5.54e-1	8.02e-1	1.28e-0	2.24e-0	2.99e-0	3.87e-0	4.04e-0	2.05e-0
30000	2.15e-1	2.23e-1	2.54e-1	3.07e-1	3.95e-1	5.43e-1	8.37e-1	1.53e-0	2.21e-0	3.22e-0	4.29e-0	

Sputtered energy of C by N  
 $ne = 2$ ,  $na = 12$

$E_0$ (eV)	0°	10°	20°	30°	40°	50°	60°	70°	75°	80°	85°	87°
15000	1.21e-3	1.44e-3	2.15e-3	3.74e-3	6.70e-3	1.23e-2	2.40e-2	4.68e-2	6.32e-2	7.90e-2	7.72e-2	4.05e-2
30000	6.40e-4	7.57e-4	1.14e-3	1.92e-3	3.34e-3	5.90e-3	1.10e-2	2.30e-2	3.47e-2	4.93e-2	5.72e-2	

Particle reflection coefficient of N backscattered from C  
 $z1 = 7$ ,  $m1 = 14.01$ ,  $z2 = 6$ ,  $m2 = 12.01$ ,  $sbe = 7.41$  eV,  $\rho = 2.26$  g/cm<sup>3</sup>  
 $ef = 0.95$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: trvmc  
 $ne = 2$ ,  $na = 12$

$E_0$ (eV)	0°	10°	20°	30°	40°	50°	60°	70°	75°	80°	85°	87°
15000	3.93e-4	5.85e-4	1.27e-3	3.41e-3	9.43e-3	2.65e-2	7.02e-2	1.70e-1	2.60e-1	3.85e-1	6.07e-1	8.38e-1
30000	1.50e-4	2.68e-4	5.20e-4	1.69e-3	5.19e-3	1.63e-2	4.96e-2	1.39e-1	2.22e-1	3.44e-1	5.43e-1	

Energy reflection coefficient of N backscattered from C  
 $ne = 2$ ,  $na = 12$

$E_0$ (eV)	0°	10°	20°	30°	40°	50°	60°	70°	75°	80°	85°	87°
15000	1.80e-5	3.33e-5	9.01e-5	3.36e-4	1.21e-3	4.58e-3	1.63e-2	5.61e-2	1.05e-1	1.96e-1	4.27e-1	7.34e-1
30000	6.75e-6	1.28e-5	3.71e-5	1.57e-4	6.28e-4	2.62e-3	1.08e-2	4.23e-2	8.25e-2	1.62e-1	3.48e-1	

Average depth (mean range) in Å of N implanted in C  
 $ne = 2$ ,  $na = 12$

$E_0$ (eV)	0°	10°	20°	30°	40°	50°	60°	70°	75°	80°	85°	87°
15000	3.76e+2	3.70e+2	3.54e+2	3.26e+2	2.90e+2	2.48e+2	2.04e+2	1.62e+2	1.45e+2	1.30e+2	1.20e+2	1.18e+2
30000	7.52e+2	7.43e+2	7.08e+2	6.53e+2	5.80e+2	4.92e+2	3.98e+2	3.11e+2	2.73e+2	2.43e+2	2.20e+2	

# O → C

Sputtering yield of C by O  
 $z1 = 8, m1 = 16.00, z2 = 6, m2 = 12.01, sbe = 7.41 \text{ eV}, rho = 1.85, 2.00 \text{ g/cm}^{**3}$   
 $ef = 0.95, 2.10 \text{ eV}, esb = 1.00, 2.60 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1$  (KrC)  
 program: trvmc95, newtrim  
*only low fluence!*  
 $ne = 11, na = 1$

$E_0(\text{eV})$	$0^\circ$
38	4.60e-6
40	7.98e-6
42	1.30e-5
45	2.56e-5
50	6.56e-5
60	2.87e-4
70	7.79e-4
100	4.59e-3
150	1.80e-2
300	6.85e-2
1000	2.15e-1
3000	3.23e-1
6000	3.40e-1

Sputtered energy of C by O  
*only low fluence!*  
 $ne = 7, na = 1$

$E_0(\text{eV})$	$0^\circ$
38	1.78e-7
40	3.17e-7
42	5.33e-7
45	1.09e-6
150	6.75e-4
300	2.06e-3
1000	4.15e-3
3000	3.34e-3
6000	2.67e-3

Particle reflection coefficient of O backscattered from C  
 $z1 = 8, m1 = 16.00, z2 = 6, m2 = 12.01, sbe = 7.40 \text{ eV}, 1.85, 2.00 \text{ g/cm}^{**3}$   
 $ef = 2.10 \text{ eV}, esb = 2.60 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1$  (KrC)  
 program: newtrim, trvmc95  
*only low fluence!*  
 $ne = 7, na = 1$

$E_0(\text{eV})$	$0^\circ$
38	9.90e-4
40	1.06e-3
42	1.12e-3
45	1.21e-3
150	9.89e-4
300	1.44e-3
1000	6.39e-4
3000	3.21e-4
6000	4.18e-4

Energy reflection coefficient of O backscattered from C  
*only low fluence!*  
 $ne = 7, na = 1$

$E_0(\text{eV})$	$0^\circ$
38	4.34e-5
40	4.53e-5
42	4.70e-5
45	4.92e-5
150	2.78e-5
300	3.60e-5
1000	2.42e-5
3000	1.60e-6
6000	5.00e-6

Average depth (mean range) in Å of O implanted in C  
*only low fluence!*  
 $ne = 7, na = 1$

$E_0(\text{eV})$	$0^\circ$
38	3.54e+0
40	3.68e+0
42	3.82e+0
45	4.02e+0
150	8.68e+0
300	1.40e+1
1000	3.37e+1
3000	8.34e+1
6000	1.55e+2

# Ne → C

Sputtering yield of C by Ne  
 z1=10, m1= 20.18, z2= 6, m2= 12.01, sbe=7.41, rho=1.85 g/cm\*\*\*  
 ef=0.05 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program : trvmc  
 ne=24, na= 9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
15					9.51e-7	7.55e-7			
16					3.45e-6	2.15e-6			
17					3.60e-6	7.68e-6	5.34e-6	1.38e-6	
18					8.20e-6	1.40e-5	1.04e-5	3.60e-6	1.09e-6
20				1.23e-6	4.15e-5	6.95e-5	5.65e-5	2.28e-5	5.44e-6
22				2.86e-6	4.71e-5	7.73e-5	1.05e-4	6.48e-5	1.67e-5
25		1.20e-7	2.32e-5	2.03e-4	3.48e-4	5.24e-4	2.64e-4	5.71e-5	1.05e-6
30		2.76e-6	1.03e-4	6.70e-4	1.64e-3	2.63e-3	1.09e-3	2.27e-4	3.53e-6
35	6.40e-7	9.52e-6	2.02e-4	1.86e-3	5.55e-3	7.95e-3	2.89e-3	5.45e-4	8.66e-6
40	3.74e-6	4.61e-5	6.93e-4	5.10e-3	1.19e-2	1.53e-2	5.10e-3	9.67e-4	1.62e-5
45	1.07e-5	9.47e-5	1.38e-3	1.03e-2	2.26e-2	2.68e-2	8.92e-3	1.64e-3	2.29e-5
50	3.41e-5	2.53e-4	2.99e-3	1.72e-2	3.35e-2	3.65e-2	1.21e-2	2.38e-3	3.57e-5
60	1.48e-4	8.44e-4	7.70e-3	3.81e-2	6.81e-2	7.16e-2	2.40e-2	4.43e-3	6.18e-5
70	4.59e-4	2.12e-3	1.47e-2	6.09e-2	9.95e-2	1.05e-1	3.80e-2	6.73e-3	9.62e-5
100	3.25e-3	9.87e-3	4.63e-2	1.47e-1	2.27e-1	2.36e-1	8.83e-2	1.75e-2	2.20e-4
140	1.18e-2	2.69e-2	9.44e-2	2.56e-1	3.93e-1	4.21e-1	3.81e-2	4.74e-4	
200	3.03e-2	5.61e-2	1.60e-1	3.87e-1	5.91e-1	6.63e-1	3.26e-1	8.21e-2	1.04e-3
300	6.50e-2	1.03e-1	2.46e-1	5.46e-1	8.32e-1	9.92e-1	6.04e-1	1.80e-1	2.72e-3
500	1.26e-1	1.80e-1	3.61e-1	7.43e-1	1.13e-0	1.47e-0	1.15e-0	4.59e-1	9.91e-3
1000	2.32e-1	2.99e-1	5.24e-1	9.98e-1	1.51e-0	2.09e-0	2.17e-0	1.31e-0	6.38e-2
2000	3.36e-1	4.09e-1	6.49e-1	1.18e-0	1.79e-0	2.63e-0	3.25e-0	2.69e-0	3.79e-1
5000	4.16e-1	4.90e-1	7.30e-1	1.25e-0	1.92e-0	2.99e-0	4.28e-0	4.54e-0	2.19e-0
10000	4.21e-1	4.84e-1	6.88e-1	1.13e-0	1.73e-0	2.82e-0	4.55e-0	5.31e-0	4.28e-0
20000	3.81e-1	4.28e-1	5.76e-1	8.83e-1	1.31e-0	2.19e-0	4.09e-0	5.32e-0	5.70e-0

Sputtered energy of C by Ne  
 ne=24, na= 9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
15					5.96e-8	7.77e-8			
16					2.46e-7	2.17e-7			
17					1.87e-7	6.08e-7	6.25e-7	2.08e-7	
18					4.97e-7	1.25e-6	1.25e-6	5.86e-7	1.75e-7
20				4.97e-8	3.04e-6	7.13e-6	8.10e-6	3.80e-6	8.81e-7
22				1.36e-7	3.67e-6	8.39e-6	1.46e-5	1.06e-5	2.93e-6
25		4.47e-9	1.20e-6	1.80e-5	4.22e-5	8.02e-5	4.83e-5	1.08e-5	1.99e-7
30		9.65e-8	6.20e-6	6.60e-5	2.29e-4	4.54e-4	2.21e-4	4.91e-5	6.28e-7
35	1.87e-8	4.36e-7	1.39e-5	2.16e-4	8.56e-4	1.55e-3	6.66e-4	1.28e-4	1.88e-6
40	1.31e-7	2.13e-6	5.38e-5	6.38e-4	1.96e-3	3.13e-3	1.18e-3	2.30e-4	3.31e-6
45	4.11e-7	4.81e-7	1.14e-4	1.36e-3	3.86e-3	5.73e-3	2.24e-3	4.11e-4	4.64e-6
50	1.29e-6	1.34e-5	2.59e-4	2.30e-3	5.81e-3	7.89e-3	3.05e-3	5.99e-4	6.96e-6
60	6.14e-6	4.69e-5	6.79e-4	5.26e-3	1.20e-2	1.60e-2	6.23e-3	1.13e-3	1.20e-5
70	1.90e-5	1.16e-4	1.30e-3	8.34e-3	1.74e-2	2.32e-2	9.82e-3	1.72e-3	1.76e-5
100	1.27e-4	5.28e-4	3.81e-3	1.85e-2	3.70e-2	4.85e-2	2.19e-2	4.25e-3	3.61e-5
140	4.34e-4	1.34e-3	6.98e-3	2.84e-2	5.59e-2	7.65e-2	4.02e-2	8.49e-3	6.73e-5
200	1.02e-3	2.46e-3	1.04e-2	3.66e-2	7.11e-2	1.01e-1	6.45e-2	1.66e-2	1.32e-4
300	1.95e-3	3.96e-3	1.35e-2	4.23e-2	7.96e-2	1.20e-1	9.74e-2	3.13e-2	2.86e-4
500	3.12e-3	5.51e-3	1.58e-2	4.54e-2	8.23e-2	1.31e-1	1.35e-1	6.33e-2	9.19e-4
1000	4.24e-3	6.71e-3	1.66e-2	4.33e-2	7.79e-2	1.27e-1	1.64e-1	1.18e-1	5.53e-3
2000	4.41e-3	6.52e-3	1.48e-2	3.66e-2	6.56e-2	1.12e-1	1.62e-1	1.55e-1	2.62e-2
5000	3.53e-3	5.13e-3	1.11e-2	2.76e-2	4.98e-2	8.85e-2	1.40e-1	1.54e-1	8.59e-2
10000	2.53e-3	3.62e-3	7.82e-3	1.92e-2	3.63e-2	6.70e-2	1.14e-1	1.34e-1	1.11e-1
20000	1.56e-3	2.21e-3	4.71e-3	1.14e-2	2.11e-2	4.12e-2	8.11e-2	1.03e-1	1.04e-1

# Ne → C

Particle reflection coefficient of Ne backscattered from C  
 z1=10, m1= 20.18, z2= 6, m2= 12.01, sbe=7.41, rho=1.85 g/cm\*\*3  
 ef=0.05 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program : trvrmc  
 ne=22, na= 9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	1.31e-2	3.12e-2	1.15e-1	3.53e-1	5.94e-1	8.37e-1	9.77e-1	9.97e-1	1.00e-0
15	5.45e-3	1.78e-2	8.99e-2	3.22e-1	5.70e-1	8.29e-1	9.77e-1	9.97e-1	1.00e-0
20	3.10e-3	1.28e-2	7.66e-2	3.01e-1	5.51e-1	8.19e-1	9.77e-1	9.97e-1	1.00e-0
22	2.91e-3	1.27e-2	7.59e-2	2.98e-1	5.48e-1	8.18e-1	9.77e-1	9.98e-1	1.00e-0
25	2.17e-3	1.11e-2	6.79e-2	2.82e-1	5.32e-1	8.08e-1	9.76e-1	9.98e-1	1.00e-0
30	1.72e-3	8.69e-3	6.10e-2	2.65e-1	5.14e-1	7.97e-1	9.75e-1	9.98e-1	1.00e-0
35	1.67e-3	8.22e-3	5.75e-2	2.54e-1	5.00e-1	7.87e-1	9.74e-1	9.98e-1	1.00e-0
40	1.31e-3	6.86e-3	5.09e-2	2.36e-1	4.79e-1	7.72e-1	9.71e-1	9.97e-1	1.00e-0
45	1.34e-3	6.67e-3	4.83e-2	2.26e-1	4.67e-1	7.62e-1	9.70e-1	9.97e-1	1.00e-0
50	1.11e-3	5.73e-3	4.39e-2	2.12e-1	4.48e-1	7.48e-1	9.67e-1	9.97e-1	1.00e-0
60	1.08e-3	5.32e-3	3.92e-2	1.93e-1	4.22e-1	7.25e-1	9.63e-1	9.97e-1	1.00e-0
70	8.56e-4	4.53e-3	3.50e-2	1.75e-1	3.95e-1	6.99e-1	9.57e-1	9.96e-1	1.00e-0
100	7.17e-4	3.48e-4	2.59e-2	1.39e-1	3.29e-1	6.35e-1	9.38e-1	9.94e-1	1.00e-0
140	6.46e-4	2.74e-3	1.99e-2	1.09e-1	2.69e-1	5.63e-1	9.08e-1	9.91e-1	1.00e-0
200	5.97e-4	2.27e-3	1.57e-2	8.32e-2	2.17e-1	4.82e-1	8.63e-1	9.83e-1	1.00e-0
300	5.03e-4	1.98e-3	1.26e-2	6.43e-2	1.68e-1	3.92e-1	7.88e-1	9.64e-1	1.00e-0
500	4.63e-4	1.58e-3	9.35e-3	4.74e-2	1.26e-1	2.98e-1	6.66e-1	9.11e-1	1.00e-0
1000	3.72e-4	1.27e-3	7.09e-3	3.38e-2	9.08e-2	2.14e-1	5.01e-1	7.74e-1	9.96e-1
2000	2.97e-4	6.768e-4	4.57e-3	2.45e-2	6.36e-2	1.64e-1	3.82e-1	6.06e-1	9.67e-1
5000	1.48e-4	4.47e-4	2.84e-3	1.57e-2	4.42e-2	1.22e-1	2.96e-1	4.54e-1	8.07e-1
10000	1.01e-4	2.86e-4	1.81e-3	1.08e-2	3.43e-2	9.79e-2	2.56e-1	3.95e-1	6.60e-1
20000	4.80e-5	1.31e-4	9.10e-4	6.80e-3	2.45e-2	7.98e-2	2.24e-1	3.49e-1	5.66e-1

Energy reflection coefficient of Ne backscattered from C  
 ne=22, na= 9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	1.15e-5	2.37e-4	3.97e-3	3.40e-2	1.08e-1	2.73e-1	5.43e-1	6.98e-1	8.33e-1
15	2.23e-5	2.88e-4	4.42e-3	3.78e-2	1.17e-1	2.92e-1	5.76e-1	7.32e-1	8.67e-1
20	2.68e-5	3.07e-4	4.43e-3	3.88e-2	1.21e-1	3.02e-1	5.96e-1	7.54e-1	8.87e-1
22	2.38e-5	2.86e-4	4.20e-3	3.82e-2	1.21e-1	3.04e-1	6.02e-1	7.61e-1	8.93e-1
25	2.66e-5	2.72e-4	4.27e-3	3.83e-2	1.22e-1	3.07e-1	6.09e-1	7.69e-1	9.01e-1
30	2.63e-5	2.72e-4	4.01e-3	3.72e-2	1.21e-1	3.08e-1	6.17e-1	7.81e-1	9.10e-1
35	2.16e-5	2.27e-4	3.57e-3	3.51e-2	1.18e-1	3.07e-1	6.23e-1	7.89e-1	9.17e-1
40	2.26e-5	2.22e-4	3.43e-3	3.39e-2	1.16e-1	3.04e-1	6.27e-1	7.95e-1	9.23e-1
45	1.81e-5	1.87e-4	3.04e-3	3.17e-2	1.12e-1	3.01e-1	6.28e-1	8.00e-1	9.27e-1
50	1.89e-5	1.83e-4	2.91e-3	3.05e-2	1.09e-1	2.98e-1	6.29e-1	8.04e-1	9.31e-1
60	1.41e-5	1.43e-4	2.40e-3	2.71e-2	1.01e-1	2.89e-1	6.28e-1	8.09e-1	9.37e-1
70	1.38e-5	1.28e-4	2.21e-3	2.46e-2	9.58e-2	2.80e-1	6.25e-1	8.12e-1	9.41e-1
100	9.64e-6	9.05e-5	1.50e-3	1.88e-2	7.66e-2	2.50e-1	6.09e-1	8.14e-1	9.49e-1
140	8.10e-6	6.58e-5	1.04e-3	1.34e-2	5.97e-2	2.16e-1	5.83e-1	8.09e-1	9.54e-1
200	6.83e-6	5.27e-5	7.61e-4	9.66e-3	4.46e-2	1.77e-1	5.40e-1	7.94e-1	9.57e-1
300	5.87e-6	4.28e-5	5.89e-4	6.77e-3	3.15e-2	1.33e-1	4.73e-1	7.62e-1	9.58e-1
500	5.88e-6	3.51e-5	4.02e-4	4.48e-3	2.08e-2	9.00e-2	3.72e-1	6.90e-1	9.55e-1
1000	5.62e-6	2.98e-5	3.21e-4	3.08e-3	1.36e-2	5.68e-2	2.44e-1	5.36e-1	9.37e-1
2000	5.58e-6	2.05e-5	2.17e-4	2.31e-3	9.09e-3	3.92e-2	1.64e-1	3.72e-1	8.76e-1
5000	3.19e-6	1.39e-5	1.60e-4	1.56e-3	6.43e-3	2.81e-2	1.15e-1	2.39e-1	6.59e-1
10000	2.38e-6	1.10e-5	1.20e-4	1.16e-3	5.30e-3	2.27e-2	9.47e-2	1.95e-1	4.83e-1
20000	1.40e-6	4.71e-6	6.56e-5	7.49e-4	3.92e-3	1.84e-2	7.99e-2	1.63e-1	3.76e-1

Average depth (mean range) in Å of Ne implanted in C  
 ne=22, na= 9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	1.10E+0	1.00E+0	9.00E-1	8.00E-1	7.00E-1	6.00E-1	4.00E-1	3.00E-1	2.00E-1
15	1.60E+0	1.50E+0	1.30E+0	1.10E+0	1.00E+0	8.00E-1	6.00E-1	4.00E-1	2.00E-1
20	2.10E+0	2.00E+0	1.70E+0	1.40E+0	1.20E+0	1.00E+0	7.00E-1	5.00E-1	3.00E-1
22	2.30E+0	2.10E+0	1.90E+0	1.60E+0	1.30E+0	1.00E+0	8.00E-1	6.00E-1	2.00E-1
25	2.50E+0	2.40E+0	2.10E+0	1.70E+0	1.50E+0	1.20E+0	8.00E-1	6.00E-1	3.00E-1
30	2.90E+0	2.80E+0	2.40E+0	2.00E+0	1.70E+0	1.40E+0	1.00E+0	7.00E-1	3.00E-1
35	3.30E+0	3.10E+0	2.70E+0	2.30E+0	1.90E+0	1.60E+0	1.10E+0	8.00E-1	5.00E-1
40	3.60E+0	3.50E+0	3.00E+0	2.50E+0	2.10E+0	1.70E+0	1.20E+0	9.00E-1	5.00E-1
45	4.00E+0	3.80E+0	3.30E+0	2.70E+0	2.30E+0	1.90E+0	1.40E+0	1.10E+0	6.00E-1
50	4.30E+0	4.10E+0	3.60E+0	3.00E+0	2.50E+0	2.10E+0	1.50E+0	1.20E+0	7.00E-1
60	4.90E+0	4.70E+0	4.10E+0	3.40E+0	2.90E+0	2.40E+0	1.80E+0	1.40E+0	9.00E-1
70	5.50E+0	5.30E+0	4.60E+0	3.80E+0	3.20E+0	2.70E+0	2.00E+0	1.50E+0	1.00E+0
100	7.00E+0	6.70E+0	6.00E+0	4.90E+0	4.20E+0	3.50E+0	2.70E+0	2.30E+0	1.50E+0
140	8.80E+0	8.50E+0	7.50E+0	6.20E+0	5.30E+0	4.40E+0	3.50E+0	2.80E+0	2.10E+0
200	1.12E+1	1.07E+1	9.60E+0	7.90E+0	6.70E+0	5.60E+0	4.50E+0	3.80E+0	2.80E+0
300	1.46E+1	1.40E+1	1.25E+1	1.03E+1	8.90E+0	7.40E+0	6.00E+0	5.20E+0	3.90E+0
500	2.06E+1	1.98E+1	1.78E+1	1.47E+1	1.24E+1	1.03E+1	8.50E+0	7.70E+0	6.00E+0
1000	3.34E+1	3.23E+1	2.89E+1	2.39E+1	2.03E+1	1.67E+1	1.38E+1	1.22E+1	1.04E+1
2000	5.60E+1	5.40E+1	4.84E+1	4.01E+1	3.39E+1	2.76E+1	2.24E+1	2.03E+1	1.80E+1
5000	1.19E+2	1.15E+2	1.03E+2	8.47E+1	7.08E+1	5.73E+1	4.57E+1	4.11E+1	3.74E+1
10000	2.21E+2	2.14E+2	1.92E+2	1.58E+2	1.31E+2	1.05E+2	8.17E+1	7.34E+1	6.72E+1
20000	4.29E+2	4.14E+2	3.71E+2	3.04E+2	2.52E+2	2.00E+2	1.52E+2	1.36E+2	1.23E+2

# $\text{Ar} \rightarrow \text{C}$

Sputtering yield of C by Ar  
 $z1=18$ ,  $m1=39.95$ ,  $z2=6$ ,  $m2=12.01$ ,  $sbe=7.41$  eV,  $\rho=1.85$  g/cm $^{**3}$   
 $ef=0.05$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: trvmc  
ne=11, na=9

$E_0$ (eV)	$0^\circ$	$15^\circ$	$30^\circ$	$45^\circ$	$55^\circ$	$65^\circ$	$75^\circ$	$80^\circ$	$85^\circ$
25		1.60e-7	1.88e-5	4.80e-5	4.12e-5	1.62e-5	4.00e-6	9.00e-8	
30		4.44e-6	9.87e-5	1.94e-4	2.29e-4	1.32e-4	3.73e-5	7.10e-7	
40	1.80e-7	2.52e-6	7.96e-5	6.71e-4	1.75e-3	3.40e-3	1.77e-3	3.74e-4	7.38e-6
50	2.46e-6	2.31e-5	4.18e-4	3.20e-3	8.55e-3	1.47e-2	6.49e-3	1.33e-3	2.33e-5
70	6.64e-5	3.67e-4	3.54e-3	2.00e-2	4.57e-2	6.11e-2	2.65e-2	5.31e-3	9.35e-5
100	8.27e-4	2.98e-3	1.76e-2	7.25e-2	1.40e-1	1.78e-1	7.67e-2	1.60e-2	2.73e-4
140	4.62e-3	1.18e-2	4.90e-2	1.63e-1	2.99e-1	3.76e-1	1.72e-1	3.94e-2	6.61e-4
200	1.66e-2	3.34e-2	1.05e-1	2.94e-1	5.21e-1	6.75e-1	3.46e-1	8.68e-2	1.53e-3
300	4.54e-2	7.57e-2	1.93e-1	4.70e-1	8.13e-1	1.10e-0	6.73e-1	1.96e-1	3.94e-3
500	1.09e-1	1.60e-1	3.34e-1	7.22e-1	1.19e-0	1.73e-0	1.34e-0	4.96e-1	1.31e-2
1000	2.47e-1	3.21e-1	5.68e-1	1.09e-0	1.72e-0	2.62e-0	2.75e-0	1.46e-0	6.94e-2

Sputtered energy of C by Ar  
ne=11, na=9

$E_0$ (eV)	$0^\circ$	$15^\circ$	$30^\circ$	$45^\circ$	$55^\circ$	$65^\circ$	$75^\circ$	$80^\circ$	$85^\circ$
25			4.77e-9	8.41e-7	3.12e-6	3.78e-6	1.94e-6	5.16e-7	1.06e-8
30			1.33e-7	5.68E-6	1.51E-5	2.36E-5	1.71E-5	5.05E-6	8.74E-8
40	3.51e-9	8.05e-8	3.44e-6	4.90E-5	1.74E-4	4.25E-4	2.68E-4	5.91E-5	9.55E-7
50	6.13e-8	7.95e-7	2.21E-5	2.75E-4	9.65E-4	2.08E-3	1.11E-3	2.30E-4	3.24E-6
70	1.97e-6	1.49E-5	2.21E-4	1.95E-3	5.58E-3	9.49E-3	4.83E-3	9.66E-4	1.27E-5
100	2.58E-5	1.26E-4	1.13E-3	6.98E-3	1.69E-2	2.73E-2	1.42E-2	2.86E-3	3.44E-5
140	1.37E-4	4.83E-4	2.99E-3	1.44E-2	3.33E-2	5.37E-2	3.01E-2	6.72B-3	7.14E-5
200	4.66E-4	1.25E-3	5.80E-3	2.30E-2	5.05E-2	8.38E-2	5.51E-2	1.38E-2	1.45E-4
300	1.15E-3	2.49E-3	9.21E-3	3.11E-2	6.54E-2	1.12E-1	9.01E-2	2.77E-2	3.09E-4
500	2.32E-3	4.28E-3	1.28E-2	3.77E-2	7.42E-2	1.31E-1	1.36E-1	5.75E-2	8.75E-4
1000	3.91E-3	6.30E-3	1.57E-2	4.13E-2	7.60E-2	1.35E-1	1.83E-1	1.17E-1	4.28E-3

# Ar → C

Particle reflection coefficient of Ar backscattered from C  
 z1=18, m1= 39.95, z2= 6, m2= 12.01, sbe=7.41 eV, rho=1.85 g/cm\*\*3  
 ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trvmc  
 ne=14, na=8

E <sub>0</sub> (eV)	15°	30°	45°	55°	65°	75°	80°	85°
10	2.76E-4	8.67E-3	1.14E-1	3.69E-1	7.42E-1	9.70E-1	9.97E-1	1.00E+0
15	5.26E-5	5.43E-3	1.01E-1	3.56E-1	7.40E-1	9.73E-1	9.98E-1	1.00E+0
20	3.00E-5	4.27E-3	9.36E-2	3.48E-1	7.37E-1	9.73E-1	9.98E-1	1.00E+0
25	3.15E-5	3.75E-3	8.82E-2	3.38E-1	7.30E-1	9.74E-1	9.98E-1	1.00E+0
30	3.22E-5	3.41E-3	8.30E-2	3.27E-1	7.22E-1	9.73E-1	9.98E-1	1.00E+0
40	2.76E-5	2.84E-3	7.32E-2	3.05E-1	7.01E-1	9.71E-1	9.98E-1	1.00E+0
50	2.49E-5	2.35E-3	6.44E-2	2.82E-1	6.79E-1	9.67E-1	9.98E-1	1.00E+0
70	1.94E-5	1.66E-3	5.01E-2	2.42E-1	6.34E-1	9.58E-1	9.97E-1	1.00E+0
100	1.46E-5	1.11E-3	3.61E-2	1.94E-1	5.71E-1	9.43E-1	9.96E-1	1.00E+0
140	9.93E-6	8.47E-4	2.56E-2	1.49E-1	5.00E-1	9.19E-1	9.93E-1	1.00E+0
200	5.95E-6	5.96E-4	1.78E-2	1.09E-1	4.13E-1	8.77E-1	9.88E-1	1.00E+0
300	5.98E-6	4.49E-4	1.28E-2	7.68E-2	3.21E-1	8.09E-1	9.76E-1	1.00E+0
500	5.20E-6	3.45E-4	8.91E-3	5.10E-2	2.24E-1	6.88E-1	9.38E-1	1.00E+0
1000	2.61E-4	5.86E-3	3.15E-2	1.42E-1	4.97E-1	8.22E-1	9.98E-1	

Energy reflection coefficient of Ar backscattered from C  
 ne=14, na=8

E <sub>0</sub> (eV)	15°	30°	45°	55°	65°	75°	80°	85°
10	8.53E-8	5.74E-5	4.06E-3	3.25E-2	1.52E-1	4.33E-1	6.15E-1	7.95E-1
15	2.32E-7	7.96E-5	4.74E-3	3.65E-2	1.67E-1	4.64E-1	6.49E-1	8.25E-1
20	3.17E-7	8.79E-5	4.97E-3	3.85E-2	1.75E-1	4.83E-1	6.72E-1	8.45E-1
25	3.71E-7	8.70E-5	4.99E-3	3.90E-2	1.79E-1	4.97E-1	6.88E-1	8.58E-1
30	3.86E-7	8.21E-5	4.85E-3	3.88E-2	1.81E-1	5.06E-1	7.01E-1	8.68E-1
40	3.01E-7	6.83E-5	4.39E-3	3.73E-2	1.80E-1	5.17E-1	7.18E-1	8.83E-1
50	2.51E-7	5.46E-5	3.87E-3	3.50E-2	1.78E-1	5.23E-1	7.29E-1	8.94E-1
70	1.69E-7	3.51E-5	2.94E-3	3.00E-2	1.68E-1	5.25E-1	7.42E-1	9.08E-1
100	1.01E-7	2.01E-5	1.97E-3	2.35E-2	1.50E-1	5.18E-1	7.49E-1	9.20E-1
140	6.53E-8	1.27E-5	1.26E-3	1.71E-2	1.30E-1	5.01E-1	7.49E-1	9.28E-1
200	2.95E-8	7.88E-6	7.44E-4	1.17E-2	1.03E-1	4.69E-1	7.42E-1	9.34E-1
300	2.92E-8	5.17E-6	4.61E-4	7.09E-3	7.39E-2	4.18E-1	7.19E-1	9.38E-1
500	1.39E-8	3.60E-6	2.78E-4	3.86E-3	4.49E-2	3.32E-1	6.64E-1	9.37E-1
1000	2.68E-6	1.59E-4	1.91E-3	2.25E-2	2.08E-1	5.35E-1	9.25E-1	

Average depth (mean range of Ar implanted in C  
 ne=14, na=9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	1.30E+0	1.30E+0	1.10E+0	9.00E-1	8.00E-1	6.00E-1	5.00E-1	4.00E-1	2.00E-1
15	2.00E+0	1.90E+0	1.70E+0	1.30E+0	1.10E+0	8.00E-1	6.00E-1	5.00E-1	3.00E-1
20	2.60E+0	2.50E+0	2.10E+0	1.60E+0	1.30E+0	1.00E+0	8.00E-1	6.00E-1	5.00E-1
25	3.10E+0	3.00E+0	2.60E+0	2.00E+0	1.60E+0	1.20E+0	9.00E-1	7.00E-1	5.00E-1
30	3.60E+0	3.50E+0	3.00E+0	2.20E+0	1.80E+0	1.40E+0	1.10E+0	9.00E-1	6.00E-1
40	4.50E+0	4.30E+0	3.70E+0	2.80E+0	2.20E+0	1.70E+0	1.30E+0	1.10E+0	8.00E-1
50	5.20E+0	5.00E+0	4.30E+0	3.30E+0	2.60E+0	2.00E+0	1.60E+0	1.30E+0	9.00E-1
70	6.50E+0	6.20E+0	5.40E+0	4.10E+0	3.30E+0	2.60E+0	2.00E+0	1.70E+0	1.10E+0
100	8.10E+0	7.80E+0	6.80E+0	5.20E+0	4.20E+0	3.30E+0	2.50E+0	2.20E+0	1.70E+0
140	1.00E+1	9.60E+0	8.40E+0	6.50E+0	5.20E+0	4.10E+0	3.20E+0	2.70E+0	2.30E+0
200	1.23E+1	1.18E+1	1.04E+1	8.20E+0	6.50E+0	5.10E+0	4.00E+0	3.40E+0	2.80E+0
300	1.56E+1	1.50E+1	1.32E+1	1.05E+1	8.40E+0	6.60E+0	5.20E+0	4.50E+0	3.50E+0
500	2.10E+1	2.02E+1	1.79E+1	1.43E+1	1.15E+1	9.00E+0	7.00E+0	6.20E+0	5.40E+0
1000	3.16E+1	3.05E+1	2.72E+1	2.19E+1	1.78E+1	1.38E+1	1.06E+1	9.40E+0	7.20E+0

## Ar → C

Sputtering yield of C by Ar  
 $z1=18$ ,  $m1=39.95$ ,  $z2=6$ ,  $m2=12.01$ ,  $sbe=7.40, 7.42$  eV,  $\rho=2.26$  g/cm $^{**3}$   
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program : trspvmcx  
ne = 9, na = 1

$E_0$ (eV)	0°
100	8.51E-4
100	8.60E-4
200	1.80E-2
300	4.96E-2
500	1.23E-1
500	1.20E-1
1000	2.64E-1
1000	2.67E-1
4000	6.32E-1

Sputtered energy of C by Ar  
ne = 9, na = 1

$E_0$ (eV)	0°
100	2.65E-5
100	2.67E-5
200	4.92E-4
300	1.24E-3
500	2.55E-3
500	2.49E-3
1000	4.09E-3
1000	4.07E-3
4000	4.95E-3

Average depth (mean range) in Å of Ar implanted in C  
 $z1=18$ ,  $m1=39.95$ ,  $z2=6$ ,  $m2=12.01$ ,  $sbe=7.40, 7.42$  eV,  $\rho=2.26$  g/cm $^{**3}$   
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program : trspvmcx  
ne = 7, na = 1

$E_0$ (eV)	0°
50	3.82e+0
100	6.20E+0
200	9.61e+0
300	1.23E+1
500	1.67E+1
1000	2.55E+1
4000	6.28E+1

## Ar → C

Sputtering yield of C by Ar  
 $z1=18$ ,  $m1=39.95$ ,  $z2=6$ ,  $m2=12.01$ ,  $sbe=7.40$ ,  $\rho=2.26 \text{ g/cm}^{**3}$   
 $ef=0.50 \text{ eV}$ ,  $esb=0.00 \text{ eV}$ ,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr$   
 $\alpha=0.00$   
program : trspvmcx  
 $nem=4$ ,  $n(ipot)=3$

$E_0(\text{eV})$	KrC	Moliere	ZBL	comment
5000	6.83E-1	7.58e-1	6.70e-1	
5000	1.12e-0			$sbe=4.40 \text{ eV}$
5000	1.04e-0			$sbe=4.40 \text{ eV}, \rho=1.85 \text{ g/cm}^{**3}$
5000	6.24e-1			$\rho=1.85 \text{ g/cm}^{**3}$

Sputtered energy of C by Ar  
 $nem=4$ ,  $n(ipot)=3$

$E_0(\text{eV})$	KrC	Moliere	ZBL	comment
5000	4.98E-3	4.57e-3	5.26e-3	
5000	5.68e-3			$sbe=4.40 \text{ eV}$
5000	5.69e-3			$sbe=4.40 \text{ eV}, \rho=1.85 \text{ g/cm}^{**3}$
5000	4.66e-3			$\rho=1.85 \text{ g/cm}^{**3}$

Average depth (mean range) in Å of Ar implanted in C  
 $nem=4$ ,  $n(ipot)=3$

$E_0(\text{eV})$	KrC	Moliere	ZBL	comment
5000	7.41E+1	6.00e+1	7.51e+1	
5000	7.37e+1			$sbe=4.40 \text{ eV}$
5000	9.05e+1			$sbe=4.40 \text{ eV}, \rho=1.85 \text{ g/cm}^{**3}$
5000	9.10e+1			$\rho=1.85 \text{ g/cm}^{**3}$

# Xe → C

Sputtering yield of C by Xe  
 z1=54, m1=131.30, z2= 6, m2= 12.01, sbe=7.42, 7.40 eV, rho=2.26 g/cm\*\*3  
 ef=0.50, esb=0.00, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx, trspvmcx  
 ne=45, na=11

E <sub>0</sub> (eV)	0°	15°	30°	45°	60°	65°	70°	75°	77.5°	80°	85°
53				4.38e-6				2.97e-6			
55								1.01e-5		2.34e-6	
56					1.71e-5					1.00e-5	
59											1.60e-5
60								4.08e-5			2.72e-5
61											1.60e-5
63											4.49e-5
65								1.25e-4			1.23e-4
70			3.19e-6	8.01e-5				3.65e-4			2.85e-4
75			7.66e-6	1.48e-4				8.80e-4			
77								1.24e-3			
80			1.60e-5	2.18e-4				1.84e-3			5.67e-4
85			3.35e-5								
90		2.12e-6	5.10e-5	5.44e-4				5.63e-3			1.61e-3
95			7.92e-5								
100		6.33e-6	1.29e-4	1.15e-3					1.22e-2		3.42e-3
105		1.00e-5									
110	1.86e-6	1.76e-5	2.68e-4								6.16e-3
120	5.62e-6	3.88e-5	5.37e-4	4.26e-3	2.20e-2	3.47e-2	4.57e-2	3.70e-2			1.07e-2
130	1.22e-5	7.48e-5	8.54e-4								1.52e-2
135			1.19e-3								
140	2.22e-5	1.36e-4	1.49e-3	1.06e-2							
150	4.50e-5	2.33e-4	2.40e-3	1.55e-2	6.74e-2	1.04e-1	1.29e-1	1.02e-1			2.86e-2
160		3.82e-4									
170	1.24e-4		5.04e-3	2.79e-2				1.62e-1			4.69e-2
180	1.89e-4	8.74e-4									
190		1.20e-3									
200	4.15e-4	1.62e-3	1.04e-2	5.21e-2	1.89e-1	2.66e-1	3.33e-1	2.74e-1	1.80e-1		8.12e-2
220	8.08e-4	2.64e-3									
230	1.11e-3										
250	1.70e-3	5.30e-3	2.60e-2	1.06e-1				5.02e-1			1.54e-1
300	4.24e-3	1.07e-2	4.56e-2	1.63e-1				7.67e-1			2.46e-1
300	3.89e-3										
500	2.76e-2	5.31e-2	1.52e-1	3.99e-1	1.00e-0			1.83e-0	1.82e-0		6.97e-1
500	3.00e-2										
700	6.71e-2										
1000	1.27e-1	1.86e-1	3.93e-1	8.39e-1	1.79e-0			3.23e-0	3.82e-0		2.07e-0
1000	1.28e-1										
2000	3.25e-1										
3000	4.66e-1	6.00e-1	9.81e-1	1.77e-0	3.43e-0			5.92e-0	7.98e-0		7.42e-0
4000	5.99e-1										
7000	8.50e-1										
10000	1.02e-0	1.19e-0	1.80e-0	3.04e-0	5.47e-0				1.25e+1		1.62e+1
30000	1.46e-0	1.73e-0	2.43e-0	3.88e-0					1.60e+1		2.28e+1
100000	1.69e-0	1.89e-0	2.53e-0	3.73e-0					1.50e+1		2.45e+1

# Xe → C

Sputtered energy of C by Xe  
 z1=54, m1=131.30, z2= 6, m2= 12.01, sbe=7.42 eV, rho=2.26 g/cm\*\*3  
 ef=0.50, esb=0.00, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx  
 ne=44, na=11

$E_0$ (eV)	0°	15°	30°	45°	60°	65°	70°	75°	77.5°	80°	85°
53				8.12e-8				1.43e-7			
55								4.88e-7		1.30e-7	
56										5.64e-7	
59											9.02e-7
60				3.33e-7				1.93e-6			1.41e-6
61											2.32e-6
63											6.69e-6
65								6.25e-6			
70			1.40e-7	8.63e-7	1.80e-6			1.78e-5			
75			2.22e-7	3.52e-6				4.68e-5			
77								6.66e-5			
80			2.76e-7	6.47e-6				9.94e-5			
85			6.40e-7								
90		1.05e-7	9.27e-7	1.54e-5				3.22e-4			
95			1.47e-6								
100		2.68e-7	2.47e-6	3.43e-5				7.82e-4			
105		5.28e-7									
110	1.50e-7	3.33e-7	5.54e-6								
120	2.12e-7	9.82e-7	1.18e-5	1.62e-4	1.09e-3	1.84e-3	2.67e-3	2.40e-3			
130	2.48e-7	1.80e-6	1.94e-5								
135			2.61e-5								
140	6.15e-7	2.29e-6	3.58e-5	3.88e-4							
150	1.27e-6	4.03e-6	5.97e-5	5.73e-4	3.42e-3	5.73e-3	7.81e-3	6.91e-3			
160		6.92e-6									
170	1.72e-6		1.29e-4	1.06e-3				1.10e-2			
180	2.80e-6	1.55e-5									
190		2.09e-5									
200	5.65e-6	2.88e-5	2.76e-4	1.98e-3	9.74e-3	1.48e-2	2.03e-2	1.89e-2	1.30e-2	5.84e-3	
220	1.09e-5	4.56e-5									
230	1.50e-5										
250	2.28e-5	9.45e-5	6.93e-4	3.95e-3				3.36e-2		1.11e-2	
300	5.51e-5	1.88e-4	1.15e-3	5.90e-3				5.07e-2		1.72e-2	
300	5.21e-5										
500	3.36e-4	8.22e-4	3.40e-3	1.23e-2	4.01e-2			8.76e-2	1.01e-1		
500	3.47e-4										
700	7.23e-4										
1000	1.20e-3	2.23e-3	6.86e-3	2.00e-2	5.48e-2			1.13e-1	1.54e-1		
2000	2.36e-3										
3000	2.91e-3	4.22e-3	1.02e-2	2.58e-2	6.31e-2			1.22e-1	1.77e-1		
4000	3.10e-3										
7000	3.48e-3										
10000	3.43e-3	5.09e-3	1.14e-2	2.75e-2	6.44e-2				1.67e-1		
30000	3.05e-3	4.94e-3	1.04e-2	2.54e-2					1.56e-1		
100000	2.19e-3	2.99e-3	7.14e-3	1.71e-2					1.21e-1	1.82e-1	

# Xe → C

Particle reflection coefficient of Xe backscattered from C  
 z1=54, m1=131.30, z2= 6, m2= 12.01, sbe=7.42 eV, rho=2.26 g/cm\*\*3  
 ef=0.50, esb=0.00, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx  
 ne=38, na=11

E <sub>0</sub> (eV)	0°	15°	30°	45°	60°	65°	70°	75°	77.5°	80°	85°
53				1.90e-5				9.13e-1			
55								9.11e-1		9.97e-1	
56				1.90e-5				9.09e-1		9.97e-1	
59										9.97e-1	
60				1.90e-5						9.97e-1	
61										9.97e-1	
63										9.97e-1	
65				1.91e-5				9.05e-1		9.97e-1	
70			1.07e-5	1.89e-5				9.02e-1		9.96e-1	
75			1.01e-5	1.83e-5				8.98e-1		9.96e-1	
77								8.97e-1			
80			9.40e-6	1.95e-5				8.94e-1		9.96e-1	
85			8.18e-6								
90		8.91e-6	7.17e-6	1.80e-5				8.87e-1		9.96e-1	
95			7.55e-6								
100		8.43e-6	7.63e-6	1.75e-5				8.79e-1		9.95e-1	
105		8.95e-6									
110	8.72e-6	8.22e-6	1.00e-5							9.95e-1	
120	7.67e-6	8.33e-6	8.67e-6	2.00e-5	2.36e-2	1.43e-1	4.79e-1	8.64e-1		9.94e-1	
130	7.95e-6	7.20e-6	7.33e-6							9.94e-1	
135			7.00e-6								
140	6.91e-6	7.80e-6	8.00e-6	1.50e-5							
150	1.04e-5	9.40e-6	1.69e-5	2.00e-5	1.90e-2	1.21e-1	4.33e-1	8.41e-1		9.93e-1	
160		1.00e-5									
170	9.50e-6							8.24e-1		9.91e-1	
180	8.88e-6	8.00e-6									
190		4.00e-6									
200	7.50e-6	7.00e-6		3.00e-5	1.31e-2	9.55e-2	3.70e-1	7.98e-1	9.34e-1	9.90e-1	
220	6.67e-6										
230	6.00e-6									9.86e-1	
250	7.00e-6							7.58e-1		9.80e-1	
300	6.00e-6				3.00e-5			7.23e-1		9.54e-1	
500						5.90e-3		1.86e-1		8.62e-1	
1000						4.60e-3		9.86e-2		5.52e-1	
3000						2.90e-3		4.56e-2		2.79e-1	
10000						8.00e-4				1.84e-1	
30000										4.12e-2	
100000											1.32e-1

Energy reflection coefficient of Xe backscattered from C  
 ne=38, na=11

E <sub>0</sub> (eV)	0°	15°	30°	45°	60°	65°	70°	75°	77.5°	80°	85°
53				3.65e-6				2.90e-1		5.72e-1	
55					7.12e-6			2.91e-1		5.75e-1	
56						4.02e-6		2.91e-1		5.77e-1	
59					1.12e-5	2.89e-6			2.92e-1	5.78e-1	
60					2.91e-6	2.02e-6			2.92e-1	5.80e-1	
61									2.92e-1	5.83e-1	
63									2.92e-1	5.85e-1	
65									2.91e-1	5.88e-1	
70									2.88e-1	5.95e-1	
75										5.97e-1	
77										5.99e-1	
80										6.00e-1	
85											
90	1.89e-6	1.87e-6	1.81e-6					2.90e-1		5.92e-1	
95		1.48e-6									
100	1.68e-6	1.17e-6	8.03e-7							5.95e-1	
105	1.57e-6										
110	3.97e-5	1.43e-6	9.10e-7								
120	1.56e-6	1.62e-6	1.50e-6	6.82e-7	9.38e-4	1.13e-2	7.71e-2	2.85e-1			
130	4.76e-6	1.07e-6	8.06e-6	6.46e-7							
135											
140	1.17e-6	9.65e-7	6.08e-7	5.91e-7							
150	6.42e-6	6.33e-6	3.29e-6	4.26e-6	6.77e-4	9.15e-3	6.91e-2	2.75e-1			
160		2.24e-6									
170	2.54e-6							2.70e-1		6.03e-1	
180	4.36e-6	1.54e-6									
190		9.00e-7									
200	1.40e-6	9.07e-7		5.42e-6	4.15e-4	6.93e-3	5.79e-2	2.60e-1	4.25e-1	6.02e-1	
220	1.24e-6										
230	2.84e-6										
250	7.98e-7							2.43e-1		5.98e-1	
300	1.99e-6				2.14e-7			2.41e-2		5.93e-1	
500						9.16e-5		1.73e-1		5.59e-1	
1000						6.43e-5		8.45e-3		4.67e-1	
3000						2.77e-5		2.00e-3		2.32e-1	
10000						1.50e-6				7.71e-3	
30000										4.67e-3	
100000										3.32e-3	

# Xe → C

Average depth (mean range) of Xe implanted in C  
 z1=54, m1=131.30, z2= 6, m2= 12.01, sb=7.42 eV, rho=2.26 g/cm\*\*3  
 ef=0.50, esb=0.00, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx  
 ne=43, na=11

$E_0$ (eV)	0°	15°	30°	45°	60°	65°	70°	75°	77.5°	80°	85°
50	1.20e+1							2.48e+0			
53				8.24e+0				2.55e+0		2.12e+0	
55					8.57e+0			2.65e+0		2.21e+0	
56										2.25e+0	
59										2.29e+0	
60										2.35e+0	
61										2.44e+0	
63										2.52e+0	
65											
70			1.18e+1	8.89e+0							
75			1.21e+1	9.19e+0							
77			1.25e+1	9.47e+0							
80			1.28e+1	9.75e+0							
85			1.49e+1	1.03e+1							
90			1.31e+1	1.34e+1							
95			1.37e+1	1.07e+1							
100	1.62e+1	1.55e+1									
105								3.45e+0		3.01e+0	
110	1.68e+1	1.62e+1								3.10e+0	
120	1.74e+1	1.68e+1	1.48e+1	1.16e+1	7.21e+0	5.70e+0	4.54e+0	3.76e+0		3.30e+0	
130	1.80e+1	1.73e+1	1.53e+1							3.29e+0	
135			1.56e+1								
140	1.86e+1	1.79e+1	1.58e+1	1.24e+1							
150	1.91e+1	1.84e+1		1.28e+1	8.03e+0	6.36e+0	5.05e+0	4.16e+0		3.53e+0	
160		1.89e+1									
170	2.01e+1		1.71e+1	1.35e+1						3.86e+0	
180	2.06e+1	1.98e+1									
190		2.03e+1									
200	2.15e+1	2.07e+1	1.84e+1	1.45e+1	9.20e+0	7.27e+0	5.80e+0	4.80e+0	4.42e+0	4.20e+0	
220		2.15e+1									
230	2.28e+1										
250	2.36e+1	2.27e+1	2.01e+1	1.59e+1						4.54e+0	
300	2.54e+1	2.45e+1	2.17e+1	1.73e+1						4.98e+0	
500	3.14e+1	3.02e+1	2.69e+1	2.14e+1	1.41e+1					6.29e+0	
700	3.61e+1										
1000	4.20e+1	4.05e+1	3.61e+1	2.91e+1	1.95e+1						
2000	5.69e+1										
3000	6.84e+1	6.62e+1	5.90e+1	4.79e+1	3.30e+1						
4000	7.85e+1										
7000	1.03e+2										
10000	1.24e+2	1.20e+2	1.08e+2	8.80e+1	6.12e+1						
30000	2.33e+2	2.24e+2	2.01e+2	1.64e+2							
100000	5.17e+2	5.05e+2	4.51e+2	3.68e+2							
										2.56e+1	2.09e+1
										4.77e+1	
										1.06e+2	

# D → Al

Sputtering yield of Al by D  
 $z1 = 1$ ,  $m1 = 2.01$ ,  $z2 = 13$ ,  $m2 = 26.98$ ,  $sbe = 3.36$  eV,  $\rho = 2.70$  g/cm<sup>3</sup>  
 $ef = 0.98$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: testvmcx  
ne = 5, na = 1

E <sub>0</sub> (eV)	0°
40	7.55e-3
300	4.15e-2
1000	3.91e-2
3000	2.87e-2
10000	1.33e-2

Sputtered energy of Al by D  
ne = 5, na = 1

E <sub>0</sub> (eV)	0°
40	3.33e-4
300	1.07e-3
1000	4.64e-4
3000	1.63e-4
10000	2.46e-5

Particle reflection coefficient of D backscattered from Al  
 $z1 = 1$ ,  $m1 = 2.01$ ,  $z2 = 13$ ,  $m2 = 26.98$ ,  $sbe = 3.36$  eV,  $\rho = 2.70$  g/cm<sup>3</sup>  
 $ef = 0.98$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: testvmcx  
ne = 5, na = 1

E <sub>0</sub> (eV)	0°
40	4.24e-1
300	2.96e-1
1000	2.04e-1
3000	1.08e-1
10000	3.06e-2

Energy reflection coefficient of D backscattered from Al  
ne = 5, na = 1

E <sub>0</sub> (eV)	0°
40	2.14e-1
300	1.32e-1
1000	8.23e-2
3000	3.67e-2
10000	8.39e-3

Average depth (mean range) in Å of D implanted in Al  
ne = 5, na = 1

E <sub>0</sub> (eV)	0°
40	2.17e+1
300	9.32e+1
1000	2.52e+2
3000	6.66e+2
10000	1.95e+3

## He → Al

Sputtering yield of Al by He  
 $z1 = 2$ ,  $m1 = 4.00$ ,  $z2 = 13$ ,  $m2 = 26.98$ ,  $sbe = 3.36$  eV,  $\rho = 2.70$  g/cm<sup>3</sup>  
 $ef = 0.50$  eV,  $esb = 0.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: trspvmcx, IPP 9/82  
 $ne = 13$ ,  $na = 1$

$E_0$ (eV)	0°
15	1.83e-4
20	2.83e-3
30	1.46e-2
40	2.97e-2
50	4.20e-2
70	6.24e-2
100	8.64e-2
300	1.49e-1
500	1.62e-1
1000	1.63e-1
5000	1.10e-1
10000	7.62e-2
30000	3.47e-2

Sputtered energy of Al by He  
program: trspvmcx  
 $ne = 13$ ,  $na = 1$

$E_0$ (eV)	0°
15	7.37e-6
20	1.50e-4
30	9.58e-4
40	1.98e-3
50	2.74e-3
70	3.77e-3
100	4.38e-3
300	4.42e-3
500	3.48e-3
1000	2.45e-3
5000	5.37e-4
10000	1.95e-4
30000	3.63e-5

## He → Al

Particle reflection coefficient He backscattered from Al  
 $z1=2$ ,  $m1=4.00$ ,  $z2=13$ ,  $m2=26.98$ ,  $sbe=3.36$  eV,  $\rho=2.70$  g/cm\*\*3  
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: trspvmcx  
 $ne=13$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
15	4.86e-1
20	4.51e-1
30	4.04e-1
40	3.73e-1
50	3.59e-1
70	3.33e-1
100	3.12e-1
300	2.44e-1
500	2.17e-1
1000	1.79e-1
5000	8.30e-2
10000	4.94e-2
30000	1.38e-2

Energy reflection coefficient of He backscattered from Al  
 $ne=13$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
15	2.15e-1
20	1.95e-1
30	1.69e-1
40	1.53e-1
50	1.45e-1
70	1.31e-1
100	1.21e-1
300	9.05e-2
500	7.82e-2
1000	6.10e-2
5000	2.46e-2
10000	1.36e-2
30000	3.16e-3

Average depth (mean range) in Å of He implanted in Al  
 $ne=13$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
15	6.59e+0
20	7.83e+0
30	1.01e+1
40	1.21e+1
50	1.39e+1
70	1.73e+1
100	2.20e+1
300	4.85e+1
500	7.18e+1
1000	1.26e+2
5000	5.35e+2
10000	1.01e+3
30000	2.72e+3

## Ne → Al

Sputtering yield of Al by Ne  
 $z1=10$ ,  $m1=20.18$ ,  $z2=13$ ,  $m2=26.98$ ,  $sbe=3.36$  eV,  $\rho=2.70$  g/cm\*\*3  
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: IP P 9/82  
 $ne=14$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
20	2.40e-4
30	4.46e-3
50	3.90e-2
100	1.74e-1
200	3.85e-1
500	6.92e-1
1000	9.17e-1
2000	1.06e-0
5000	1.13e-0
10000	1.09e-0
20000	9.71e-1
50000	7.64e-1
100000	5.53e-1
200000	4.12e-1

# Al → Al

Sputtering yield of Al by Al

$z1=13$ ,  $m1= 26.98$ ,  $z2=13$ ,  $m2= 26.98$ ,  $sbe=3.36$  eV,  $\rho=2.70$  g/cm $^{**3}$   
 $ef=3.30$  eV,  $esb=3.36$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: trspvmcx  
nem = 6, na=1

$E_0$ (eV)	$0^\circ$
40	1.16e-2
80	8.75e-2
200	3.46e-1
500	7.22e-1
50000	1.04e-0
100000	7.92e-1

Sputtered energy of Al by Al  
nem = 6, na=1

$E_0$ (eV)	$0^\circ$
40	6.10e-4
80	3.31e-3
200	9.10e-3
500	1.15e-2
50000	1.43e-3
100000	6.57e-4

Particle reflection coefficient of Al backscattered from Al  
 $z1=13$ ,  $m1= 26.98$ ,  $z2=13$ ,  $m2= 26.98$ ,  $sbe=3.36$  eV,  $\rho=2.70$  g/cm $^{**3}$   
 $ef=3.30$  eV,  $esb=3.36$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: trspvmcx  
nem = 6, na=1

$E_0$ (eV)	$0^\circ$
40	1.28e-3
80	5.60e-3
200	9.40e-3
500	1.54e-2
50000	1.50e-3
100000	5.00e-4

Energy reflection coefficient of Al backscattered from Al  
nem = 6, na=1

$E_0$ (eV)	$0^\circ$
40	9.42e-5
80	3.39e-4
200	4.41e-4
500	6.12e-4
50000	8.67e-5

Average depth (mean range) in Å of Al implanted in Al  
nem = 6, na=1

$E_0$ (eV)	$0^\circ$
40	4.04e+0
80	6.34e+0
200	1.12e+1
500	1.98e+1
50000	7.33e+2
100000	1.46e+3

# Al → Al

Sputtering yield of Al by Al  
 $z_1=13$ ,  $m_1=26.98$ ,  $z_2=13$ ,  $m_2=26.98$ ,  $sbe=3.36$  eV,  $\rho=2.70$  g/cm $^{**3}$   
 $ef=3.30$  eV,  $esb=3.36$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=2$  (Moliere)  
program: trspvmcx  
 $ne=11$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
40	1.61e-2
60	6.88e-2
80	1.43e-1
200	5.88e-1
500	1.16e-0
1000	1.56e-0
5000	1.91e-0
10000	1.76e-0
20000	1.55e-0
50000	1.14e-0
100000	9.67e-1

Sputtered energy of Al by Al  
 $ne=11$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
40	9.29e-4
60	3.42e-3
80	6.39e-3
200	1.55e-2
500	1.81e-2
1000	1.56e-2
5000	7.29e-3
10000	4.75e-3
20000	2.81e-3
50000	1.27e-3
100000	6.13e-4

Particle reflection coefficient of Al backscattered from Al  
 $z_1=13$ ,  $m_1=26.98$ ,  $z_2=13$ ,  $m_2=26.98$ ,  $sbe=3.36$  eV,  $\rho=2.70$  g/cm $^{**3}$   
 $ef=3.30$  eV,  $esb=3.36$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=2$  (Moliere)  
program: trspvmcx  
 $ne=11$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
40	1.03e-3
60	3.35e-3
80	6.70e-3
200	1.45e-2
500	1.44e-2
1000	1.20e-2
5000	7.00e-3
10000	3.33e-3
20000	2.00e-3
50000	8.00e-4

Energy reflection coefficient of Al backscattered from Al  
 $ne=11$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
40	7.51e-5
60	2.47e-4
80	4.33e-4
200	7.47e-4
500	5.34e-4
1000	5.39e-4
5000	3.29e-4
10000	1.88e-4
20000	1.50e-4
50000	3.51e-5

Average depth (mean range) in Å of Al implanted in Al  
 $ne=11$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
40	2.33e+0
60	3.21e+0
80	4.03e+0
200	7.52e+0
500	1.43e+1
1000	2.28e+1
5000	8.26e+1
10000	1.51e+2
20000	2.89e+2
50000	7.09e+2
100000	1.43e+3

## Ar → Al

Sputtering yield of Al by Ar

$z1=18$ ,  $m1=39.95$ ,  $z2=13$ ,  $m2=26.98$ ,  $sbe=3.36$  eV,  $\rho=2.70$  g/cm $^{**3}$   
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: IP P 9/82, trslc, trvmc95c  
 $nem=18$ ,  $na=4$

$E_0$ (eV)	0°	30°	60°	85°
30	5.10e-4			
50	1.09e-2			
100	9.72e-2			
100	1.17e-1	3.78e-1	6.67e-1	1.93e-3
200	3.10e-1			
500	7.38e-1			
500	9.10e-1	1.58e-0	2.99e-0	3.71e-2
1000	1.08e-0			
1000	1.37e-0	2.21e-0	4.57e-0	1.43e-1
1000	1.10e-0			
2000	1.40e-0			
5000	1.73e-0			
10000	1.87e-0			
10000	2.39e-0	3.54e-0	9.08e-0	6.53e-0
20000	1.87e-0			
50000	1.69e-0			
100000	1.45e-0			
200000	1.18e-0			

Sputtered energy of Al by Ar  
program: trslc, trvmc95c  
 $nem=5$ ,  $na=4$

$E_0$ (eV)	0°	30°	60°	85°
100	3.67e-3	2.48e-2	9.43e-2	1.45e-4
500	1.33e-2	3.97e-2	1.61e-1	1.10e-3
1000	1.38e-2	3.67e-2	1.54e-1	3.74e-3
1000	1.16e-2			
10000	7.29e-3	1.86e-2	9.11e-2	1.07e-1

Particle reflection coefficient of Ar backscattered from Al

$z1=18$ ,  $m1=39.95$ ,  $z2=13$ ,  $m2=26.98$ ,  $sbe=3.36$  eV,  $\rho=2.70$  g/cm $^{**3}$   
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: trslc, trvmc95c  
 $nem=5$ ,  $na=4$

$E_0$ (eV)	0°	30°	60°	85°
100	3.14e-3	5.72e-2	5.67e-1	1.00e-0
500	2.32e-3	2.52e-2	3.01e-1	1.00e-0
1000	2.18e-3	1.84e-2	2.24e-1	9.99e-1
1000	2.80e-3			
10000	9.20e-4	7.47e-3	1.07e-1	8.01e-1

Energy reflection coefficient of Ar backscattered from Al  
 $nem=5$ ,  $na=4$

$E_0$ (eV)	0°	30°	60°	85°
100	6.99e-5	4.38e-3	1.88e-1	9.42e-1
500	3.83e-5	1.38e-3	8.07e-2	9.53e-1
1000	3.62e-5	9.37e-4	5.17e-2	9.43e-1
1000	1.33e-5			
10000	2.10e-5	4.47e-4	2.06e-2	6.39e-1

Average depth (mean range) in Å of Ar implanted in Al  
 $nem=5$ ,  $na=4$

$E_0$ (eV)	0°	30°	60°	85°
100	5.32e+0	4.55e+0	3.07e+0	1.20e+0
500	1.42e+1	1.23e+1	8.36e+0	4.42e+0
1000	2.16e+1	1.88e+1	1.26e+1	6.84e+0
1000	2.90e+1			
10000	1.05e+2	9.11e+1	5.89e+1	3.71e+1

## H → Si

Sputtering yield of Si by H  
 $z1 = 1, m1 = 1.01, z2 = 14, m2 = 28.09, sbe = 4.70, rho = 2.33 \text{ g/cm}^{**3}$   
 $ef = 0.95 \text{ eV}, esb = 1.00 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1$  (KrC)  
 program : trvmc95, IPP 9/82  
 $nem = 11, na = 1$

$E_0(\text{eV})$	$0^\circ$
50	5.23e-5
60	3.60e-4
70	8.90e-4
100	2.40e-3
200	7.60e-3
300	9.57e-3
500	1.10e-2
1000	1.05e-2
2000	9.00e-3
5000	5.50e-3
10000	3.60e-3

Sputtered energy of Si by H  
 program : trvmc95  
 $nem = 2, na = 1$

$E_0(\text{eV})$	$0^\circ$
50	5.16e-7
300	2.01e-4

Particle reflection coefficient of H backscattered from Si  
 $z1 = 1, m1 = 1.01, z2 = 14, m2 = 28.09, sbe = 4.70, rho = 2.32 \text{ g/cm}^{**3}$   
 $ef = 0.95 \text{ eV}, esb = 1.00 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1$  (KrC)  
 program : trvmc95  
 $nem = 2, na = 1$

$E_0(\text{eV})$	$0^\circ$
50	4.65e-1
300	3.35e-1

Energy reflection coefficient of H backscattered from Si  
 $nem = 2, na = 1$

$E_0(\text{eV})$	$0^\circ$
50	2.53e-1
300	1.58e-1

Average depth (mean range) in Å of H implanted in Si  
 $nem = 2, na = 1$

$E_0(\text{eV})$	$0^\circ$
50	3.33e+1
300	1.12e+2

# D → Si

Sputtering yield of Si by D

```

z1= 1, m1= 2.01, z2=14, m2= 28.09, sbe=4.70, rho=2.32 g/cm***3
ef=0.95 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : trvmc95, trspvmcx, IPP 9/82
ne=10, na= 9

```

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
25	1.90e-6	8.25e-3	1.11e-2	1.57e-2	1.87e-2	1.85e-2	1.08e-2	5.51e-3	2.51e-3
27	2.82e-5								
30	1.52e-4	1.22e-2	1.69e-2	2.54e-2	3.25e-2	3.46e-2	2.07e-2	1.02e-2	3.82e-3
50	3.09e-3	2.40e-2	3.45e-2	5.78e-2	8.53e-2	1.07e-1	7.40e-2	3.23e-2	7.37e-3
100	1.15e-2	3.59e-2	5.42e-2	9.78e-2	1.49e-1	2.13e-1	2.00e-1	1.01e-1	1.27e-2
200	2.03e-2	4.03e-2	6.32e-2	1.14e-1	1.77e-1	2.68e-1	3.42e-1	2.43e-1	2.93e-2
500	2.48e-2	3.85e-2	5.82e-2	1.04e-1	1.59e-1	2.57e-1	4.08e-1	4.39e-1	1.38e-1
1000	2.36e-2	2.96e-2	4.37e-2	7.80e-2	1.25e-1	2.06e-1	3.65e-1	4.59e-1	3.34e-1
2000	1.96e-2								
5000	1.22e-2								

Sputtered energy of Si by D

```

program : trvmc95
ne= 2, na= 1

```

E <sub>0</sub> (eV)	0°
25	1.67e-8
27	3.28e-7

Particle reflection coefficient of D backscattered from Si

```

z1= 1, m1= 2.01, z2=14, m2= 28.09, sbe=4.70, rho=2.32 g/cm***3
ef=0.95 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : trvmc95
ne= 3, na= 1

```

E <sub>0</sub> (eV)	0°
20	4.64e-1
25	4.51e-1
27	4.47e-1

Energy reflection coefficient of D backscattered from Si

```

ne= 3, na= 1

```

E <sub>0</sub> (eV)	0°
20	2.44e-1
25	2.34e-1
27	2.31e-1

Average depth (mean range) in Å of D implanted in Si

```

ne= 3, na= 1

```

E <sub>0</sub> (eV)	0°
20	1.67e+1
25	1.93e+1
27	2.02e+1

D on Si, Maxwellian velocity distribution, sheath potential 3 kT

```

z1= 1, m1= 2.01, z2=14, m2= 28.09, sbe=4.70 eV, rho= 2.32 g/cm***3
ef=0.95 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1(KrC)
program: trvmc95
ne=11

```

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
5	2.47e-4	1.56e-5	1.58e+0	4.99e-1	2.77e-1	1.39e+1	1.89e+1
7	1.19e-3	7.04e-5	2.07e+0	4.74e-1	2.57e-1	1.90e+1	2.33e+1
10	4.05e-3	2.26e-4	2.79e+0	4.52e-1	2.41e-1	2.66e+1	2.94e+1
20	1.47e-2	7.06e-4	4.79e+0	4.12e-1	2.11e-1	5.12e+1	4.72e+1
30	2.20e-2	9.09e-4	6.19e+0	3.89e-1	1.95e-1	7.51e+1	6.29e+1
50	2.97e-2	9.85e-4	8.30e+0	3.55e-1	1.73e-1	1.22e+2	9.20e+1
100	3.54e-2	7.88e-4	1.11e+1	3.06e-1	1.41e-1	2.31e+2	1.58e+2
200	3.62e-2	5.55e-4	1.53e+1	2.52e-1	1.08e-1	4.31e+2	2.81e+2
300	3.39e-2	3.82e-4	1.69e+1	2.14e-1	8.66e-2	6.08e+2	3.96e+2
500	2.76e-2	2.33e-4	2.12e+1	1.71e-1	6.30e-2	9.23e+2	6.17e+2
1000	2.03e-2	9.66e-5	2.38e+1	1.08e-1	3.47e-2	1.61e+3	1.13e+3

## He → Si

Sputtering yield of Si by He

```

z1= 2, m1= 4.00, z2=14, m2= 28.09, sbe=4.70, rho=2.32 g/cm***3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : trspvmcx, IPP 9/82
ne= 6, na= 1

```

E <sub>0</sub> (eV)	0°
50	1.64e-2
100	4.43e-2
300	8.77e-2
500	1.01e-1
1000	1.04e-1
4000	8.08e-2

Sputtered energy of Si by He

```
program : trspvmcx
```

```
ne= 6, na= 1
```

E <sub>0</sub> (eV)	0°
50	1.08e-3
100	2.61e-3
300	3.37e-3
500	2.88e-3
1000	1.99e-3
4000	6.47e-4

Particle reflection coefficient of He backscattered from Si

```

z1= 2, m1= 4.00, z2=14, m2= 28.09, sbe=4.70, rho=2.32 g/cm***3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : trspvmcx
ne= 6, na= 1

```

E <sub>0</sub> (eV)	0°
50	3.60e-1
100	3.16e-1
300	2.57e-1
500	2.27e-1
1000	1.88e-1
4000	1.06e-1

Energy reflection coefficient of He backscattered from Si

```
ne= 6, na= 1
```

E <sub>0</sub> (eV)	0°
50	1.47e-1
100	1.24e-1
300	9.54e-2
500	8.37e-2
1000	6.68e-2
4000	3.32e-2

Average depth (mean range) in Å of He implanted in Si

```
ne= 6, na= 1
```

E <sub>0</sub> (eV)	0°
50	1.69e+1
100	2.66e+1
300	5.75e+1
500	8.46e+1
1000	1.48e+2
4000	5.04e+2

## C → Si

C on Si, Maxwellian velocity distribution, sheath potential 9 kT  
 $z_1 = 6$ ,  $m_1 = 12.01$ ,  $z_2 = 14$ ,  $m_2 = 28.09$ ,  $sbe = 4.70$  eV,  $\rho = 2.32$  g/cm<sup>3</sup>  
 $ef = 4.65$  eV,  $esb = 4.70$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: trvmc  
ne = 5

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
5	5.27e-2	4.74e-3	4.94e+0	1.42e-1	2.72e-2	1.05e+1	7.91e+0
10	1.46e-1	9.82e-3	7.41e+0	1.50e-1	2.95e-2	2.15e+1	1.24e+1
20	2.75e-1	1.30e-2	1.04e+1	1.40e-1	2.72e-2	4.26e+1	1.92e+1
40	4.10e-1	1.35e-2	1.45e+1	1.24e-1	2.35e-2	8.37e+1	3.04e+1
50	5.57e-1	1.31e-2	1.58e+1	1.17e-1	2.14e-2	1.01e+2	3.54e+1

C on Si, Maxwellian velocity distribution, sheath potential 9 kT  
 $z_1 = 6$ ,  $m_1 = 12.01$ ,  $z_2 = 14$ ,  $m_2 = 28.09$ ,  $sbe = 4.70$  eV,  $\rho = 2.32$  g/cm<sup>3</sup>  
 $ef = 0.98$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: trvmc  
ne = 4

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
5	4.79e-2	4.27e-3	4.90e+0	2.27e-1	4.62e-2	1.12e+1	8.29e+0
10	1.42e-1	9.32e-3	7.24e+0	1.90e-1	3.69e-2	2.14e+1	1.26e+1
20	2.71e-1	1.30e-2	1.05e+1	1.57e-1	2.94e-2	4.13e+1	1.94e+1
40	4.10e-1	1.34e-2	1.43e+1	1.34e-1	2.48e-2	8.15e+1	3.05e+1

## Ne → Si

Sputtering yield of Si by Ne  
 $z1=10$ ,  $m1 = 20.18$ ,  $z2=14$ ,  $m2 = 28.09$ ,  $sbe = 4.70$ ,  $\rho = 2.32$  g/cm<sup>3</sup>  
 $ef = 0.50$  eV,  $esb = 0.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program : IPP 9/82  
ne=12, na= 1

E <sub>0</sub> (eV)	0°
30	7.60e-4
40	4.50e-3
50	1.15e-2
70	3.60e-2
100	8.00e-2
300	3.00e-1
1000	6.20e-1
3000	7.70e-1
10000	7.90e-1
30000	6.80e-1
100000	4.10e-1
300000	2.70e-1

## Mg → Si

Particle reflection coefficient of Mg backscattered from Si  
 $z1=12$ ,  $m1= 24.00$ ,  $z2=14$ ,  $m2= 28.09$ ,  $\rho = 2.33 \text{ g/cm}^{**3}$   
 $ef=1.00 \text{ eV}$ ,  $esb=1.00 \text{ eV}$ ,  $ca=1.00$ ,  $kk0=2$ ,  $kdee1=3$ ,  $ipot=1$  (KrC)  
program: trrange3  
*only low fluence!*  
 $nem = 2$ ,  $na = 1$

$E_0(\text{eV})$	$0^\circ$
100000	1.55e-3
200000	6.10e-4

Energy reflection coefficient of Mg backscattered from Si  
*only low fluence!*  
 $nem = 2$ ,  $na = 1$

$E_0(\text{eV})$	$0^\circ$
100000	1.03e-4
200000	3.36e-5

Average depth (mean range) in Å of Mg implanted in Si  
*only low fluence!*  
 $nem = 2$ ,  $na = 1$

$E_0(\text{eV})$	$0^\circ$
100000	1.78e+3
200000	3.47e+3

## Al → Si

Particle reflection coefficient of Al backscattered from Si  
 $z1=13$ ,  $m1= 27.00$ ,  $z2=14$ ,  $m2= 28.09$ ,  $\rho = 2.33 \text{ g/cm}^{**3}$   
 $ef=1.00 \text{ eV}$ ,  $esb=1.00 \text{ eV}$ ,  $ca=1.00$ ,  $kk0=2$ ,  $kdee1=3$ ,  $ipot=1$  (KrC)  
program: trrange3  
*only low fluence!*  
 $nem = 2$ ,  $na = 1$

$E_0(\text{eV})$	$0^\circ$
100000	9.17e-4
200000	3.65e-4

Energy reflection coefficient of Al backscattered from Si  
*only low fluence!*  
 $nem = 2$ ,  $na = 1$

$E_0(\text{eV})$	$0^\circ$
100000	4.86e-5
200000	1.73e-5

Average depth (mean range) in Å of Al implanted in Si  
*only low fluence!*  
 $nem = 2$ ,  $na = 1$

$E_0(\text{eV})$	$0^\circ$
100000	1.65e+3
200000	3.22e+3

## Si → Si

Sputtering yield of Si by Si  
 $z1=14$ ,  $m1=28.09$ ,  $z2=14$ ,  $m2=28.09$ ,  $sbe=4.70$  eV,  $\rho=2.32$  g/cm<sup>3</sup>  
 $ef=4.65$  eV,  $esb=4.70$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program : trvnc, trvnc95, IPP 9/82  
 $nem=18$ ,  $na=9$

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
30	4.70e-4								
40	2.00e-3								
50	1.40e-2								
70	3.80e-2								
100	6.20e-2								
300	3.00e-1								
500	4.40e-1	5.38e-1	8.43e-1	1.35e-0	1.76e-0	2.03e-0	1.69e-0	1.07e-0	3.50e-1
1000	7.00e-1								
1000	4.60e-1								
2000	8.96e-1	1.02e-0	1.47e-0	2.32e-0	3.12e-0	3.97e-0	4.24e-0	3.52e-0	1.26e-0
3000	9.60e-1								
10000	1.20e-0								
25000	1.13e-0								
30000	1.02e-0								
50000	1.09e-0								
75000	9.13e-1								
100000	7.36e-1								
100000	7.90e-1								

Sputtered energy of Si by Si  
program : trvnc95  
 $nem=2$ ,  $na=9$

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
500	9.04e-3	1.33e-2	2.87e-2	6.38e-2	1.01e-1	1.44e-1	1.54e-1	1.12e-1	6.76e-2
2000	9.22e-3	1.23e-2	2.46e-2	5.24e-2	8.53e-2	1.29e-1	1.69e-1	1.60e-1	6.76e-2

Particle reflection coefficient of Si backscattered from Si  
 $z1=14$ ,  $m1=28.09$ ,  $z2=14$ ,  $m2=28.09$ ,  $sbe=4.70$  eV,  $\rho=2.32$  g/cm<sup>3</sup>  
 $ef=4.65$  eV,  $esb=4.70$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program : trvnc95  
 $nem=2$ ,  $na=9$

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
500	1.20e-2	1.87e-2	4.32e-2	1.06e-1	1.91e-1	3.38e-1	6.05e-1	8.01e-1	
2000	1.08e-2	1.52e-2	3.13e-2	8.07e-2	1.42e-1	2.51e-1	4.44e-1	6.14e-1	9.00e-1

Energy reflection coefficient of Si backscattered from Si  
 $nem=2$ ,  $na=9$

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
500	5.55e-4	1.16e-3	4.46e-3	1.86e-2	4.77e-2	1.24e-1	3.39e-1	5.58e-1	
2000	4.51e-4	8.81e-4	3.00e-3	1.24e-2	3.06e-2	7.76e-2	2.09e-1	3.80e-1	7.57e-1

Average depth (mean range) in Å of Si implanted in Si  
 $nem=2$ ,  $na=9$

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
500	2.28e+1	2.21e+1	2.02e+1	1.75e+1	1.55e+1	1.35e+1	1.16e+1	1.06e+1	
2000	5.55e+1	5.39e+1	4.91e+1	4.23e+1	3.71e+1	3.21e+1	2.77e+1	2.57e+1	2.37e+1

## Si → Si

Sputtering yield of Si by Si  
 $z1=14$ ,  $m1 = 28.09$ ,  $m2 = 28.09$ ,  $sbe = 4.70$  eV,  $\rho = 2.32$  g/cm<sup>3</sup>  
 $ef = 4.60$  eV,  $esb = 4.70$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ , KrC potential  
 program : testsi, Gauss-Mehler integration (nnn = 16)  
 $ne = 12$ ,  $na = 15$

$E_0$ (eV)	0°	10°	20°	30°	40°	50°	55°	60°	65°	70°	75°	80°
25	1.64e-4											
30	5.42e-4											
40	2.79e-3											
50	7.93e-3											
70	2.72e-2											
100	6.81e-2											
200	2.13e-1	2.46e-1	3.40e-1	5.07e-1	7.06e-1	9.34e-1	1.03e-0	1.08e-0	1.06e-0	9.66e-1	7.47e-1	4.63e-1
500	5.08e-1											
1000	7.52e-1											
2000	9.72e-1											
5000	1.19e-0											
10000	1.24e-0											

$E_0$ (eV)	85°	87°	88°	89°
200	2.44e-1	1.89e-1	1.70e-1	1.64e-1

Sputtered energy of Si by Si  
 $ne = 12$ ,  $na = 15$

$E_0$ (eV)	0°	10°	20°	30°	40°	50°	55°	60°	65°	70°	75°	80°
25	9.07e-6											
30	3.17e-5											
40	1.60e-4											
50	4.21e-4											
70	1.28e-3											
100	2.78e-3											
200	6.40e-3	8.36e-3	1.46e-2	2.82e-2	4.99e-2	8.33e-2	1.04e-1	1.21e-1	1.33e-1	1.36e-1	1.18e-1	7.73e-2
500	1.00e-2											
1000	1.05e-2											
2000	9.64e-3											
5000	7.41e-3											
10000	5.48e-3											

$E_0$ (eV)	85°	87°	88°	89°
200	3.97e-2	2.91e-2	2.64e-2	2.54e-2

## Si → Si

Particle reflection coefficient of Si backscattered from Si  
 $z1=14$ ,  $m1= 28.09$ ,  $z2=14$ ,  $m2= 28.09$ ,  $sbe=4.70$  eV,  $\rho=2.32$  g/cm\*\*\*  
 $ef=4.60$  eV,  $esb=4.70$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ , KrC potential  
program : testsi, Gauss-Mehler integration (nnn=16)  
ne=12, na=15

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$55^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$
25	5.38e-6											
30	2.91e-5											
40	1.83e-4											
50	4.77e-4											
70	1.57e-3											
100	3.11e-3											
200	7.34e-3	1.02e-2	2.09e-2	4.50e-2	8.87e-2	1.77e-1	2.41e-1	3.27e-1	4.40e-1	5.71e-1	7.23e-1	8.67e-1
500	1.15e-2											
1000	1.11e-2											
2000	9.77e-3											
5000	6.89e-3											
10000	5.02e-3											

$E_0$ (eV)	$85^\circ$	$87^\circ$	$88^\circ$	$89^\circ$
200	9.48e-1	9.68e-1	9.71e-1	9.74e-1

Energy reflection coefficient of Si backscattered from Si  
ne=12, na=15

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$55^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$
25	3.04e-7											
30	1.98e-6											
40	1.27e-5											
50	3.20e-5											
70	8.79e-5											
100	1.69e-4											
200	3.41e-4	6.05e-4	1.75e-3	5.17e-3	1.49e-2	4.14e-2	6.80e-2	1.10e-1	1.78e-1	2.74e-1	4.11e-1	5.78e-1
500	5.06e-4											
1000	4.59e-4											
2000	4.39e-4											
5000	3.29e-4											
10000	2.40e-4											

$E_0$ (eV)	$85^\circ$	$87^\circ$	$88^\circ$	$89^\circ$
200	7.15e-1	7.52e-1	7.62e-1	7.68e-1

Average depth (mean range) in Å of Si implanted in Si  
ne=12, na=15

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$55^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$
25	2.81e+0											
30	3.21e+0											
40	3.93e+0											
50	4.56e+0											
70	5.71e+0											
100	7.16e+0											
200	1.11e+1	1.09e+1	1.05e+1	9.79e+0	8.96e+0	7.86e+0	7.43e+0	6.91e+0	6.26e+0	5.76e+0	5.25e+0	4.29e+0
500	1.97e+1											
1000	3.08e+1											
2000	4.93e+1											
5000	9.70e+1											
10000	1.70e+2											

$E_0$ (eV)	$85^\circ$	$87^\circ$	$88^\circ$	$89^\circ$
200	3.55e+0	3.19e+0	3.28e+0	2.88e+0

## Si → Si

Sputtering yield of Si by Si  
 z1=14, m1= 28.09, m2= 28.09, sbe=4.70 eV, rho=2.32 g/cm\*\*\*  
 ef=4.60 eV, esb=4.70 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=2 (Moliere potential)  
 program : testsi, Gauss-Mehler integration (nnn=16)  
 ne=12, na=16

$E_0$ (eV)	0°	10°	20°	30°	40°	50°	55°	60°	65°	70°	75°	80°
25	1.86e-4											
30	5.83e-4											
40	3.16e-3											
50	9.53e-3											
70	3.48e-2											
100	8.76e-2											
200	2.86e-1	3.19e-1	4.37e-1	6.16e-1	8.25e-1	1.03e-0	1.11e-0	1.12e-0	1.05e-0	9.12e-1	6.87e-1	4.18e-1
500	6.75e-1											
1000	9.64e-1											
2000	1.18e-0											
5000	1.27e-0											
10000	1.25e-0											

$E_0$ (eV)	85°	87°	88°	89°
200	2.08e-1	1.64e-1	1.53e-1	1.40e-1

Sputtered energy of Si by Si  
 ne=12, na=16

$E_0$ (eV)	0°	10°	20°	30°	40°	50°	55°	60°	65°	70°	75°	80°
25	1.01e-5											
30	3.36e-5											
40	1.86e-4											
50	5.28e-4											
70	1.74e-3											
100	3.69e-3											
200	8.63e-3	1.08e-2	1.89e-2	3.43e-2	5.85e-2	9.36e-2	1.14e-1	1.27e-1	1.35e-1	1.30e-1	1.06e-1	6.67e-2
500	1.29e-2											
1000	1.26e-2											
2000	1.05e-2											
5000	7.01e-3											
10000	4.67e-3											

$E_0$ (eV)	85°	87°	88°	89°
200	3.09e-2	2.26e-2	2.11e-2	1.87e-2

## Si → Si

Particle reflection coefficient of Si backscattered from Si  
 $z1=14$ ,  $m1= 28.09$ ,  $z2=14$ ,  $m2= 28.09$ ,  $sbe=4.70$  eV,  $\rho=2.32$  g/cm\*\*\*  
 $ef=4.60$  eV,  $esb=4.70$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=2$  (Moliere potential)  
program : testsi, Gauss-Mehler integration (nnn=16)  
ne=12, na=16

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$55^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$
25	2.13e-6											
30	2.78e-5											
40	1.93e-4											
50	6.27e-4											
70	1.67e-3											
100	4.03e-3											
200	9.50e-3	1.27e-2	2.56e-2	5.34e-2	1.13e-1	2.13e-1	2.86e-1	3.77e-1	4.96e-1	6.36e-1	7.71e-1	8.97e-1
500	1.23e-2											
1000	1.11e-2											
2000	8.58e-3											
5000	6.04e-3											
10000	4.03e-3											

$E_0$ (eV)	$85^\circ$	$87^\circ$	$88^\circ$	$89^\circ$
200	9.67e-1	9.78e-1	9.80e-1	9.83e-1

Energy reflection coefficient of Si backscattered from Si  
ne=12, na=16

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$55^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$
25	1.91e-7											
30	1.95e-6											
40	1.40e-5											
50	4.14e-5											
70	1.06e-4											
100	2.27e-4											
200	4.65e-4	7.71e-4	2.14e-3	6.34e-3	1.99e-2	5.16e-2	8.39e-2	1.32e-1	2.05e-1	3.16e-1	4.52e-1	6.07e-1
500	5.43e-4											
1000	4.69e-4											
2000	3.86e-4											
5000	2.91e-4											
10000	2.10e-4											

$E_0$ (eV)	$85^\circ$	$87^\circ$	$88^\circ$	$89^\circ$
200	7.38e-1	7.69e-1	7.75e-1	7.84e-1

Average depth (mean range) in Å of Si implanted in Si  
ne=12, na=16

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$55^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$
25	2.26e+0											
30	2.59e+0											
40	3.19e+0											
50	3.72e+0											
70	4.67e+0											
100	5.88e+0											
200	9.17e+0	9.04e+0	8.65e+0	8.06e+0	7.38e+0	6.56e+0	6.06e+0	5.71e+0	5.24e+0	4.69e+0	4.24e+0	3.54e+0
500	1.65e+1											
1000	2.65e+1											
2000	4.38e+1											
5000	9.16e+1											
10000	1.67e+2											

$E_0$ (eV)	$85^\circ$	$87^\circ$	$88^\circ$	$89^\circ$
200	2.66e+0	2.36e+0	2.25e+0	2.35e+0

## Si → Si

Sputtering yield of Si by Si  
 $z1=14$ ,  $m1= 28.09$ ,  $z2=14$ ,  $m2= 28.09$ ,  $sbe=4.70$  eV,  $\rho=2.33$  g/cm $^{**3}$   
 $ef=4.60$  eV,  $esb=4.70$  eV,  $ca=0.65$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=2$  (Moliere potential)  
program : testsi, Gauss-Mehler integration (nnn=16)  
ne= 4, na= 1

E <sub>0</sub> (eV)	0°
50	4.06e-3
70	1.38e-2
100	3.77e-2
200	1.37e-1

Sputtered energy of Si by Si  
ne= 4, na= 1

E <sub>0</sub> (eV)	0°
50	1.99e-4
70	6.24e-4
100	1.62e-3
200	4.60e-3

Particle reflection coefficient of Si backscattered from Si  
 $z1=14$ ,  $m1= 28.09$ ,  $z2=14$ ,  $m2= 28.09$ ,  $sbe=4.70$  eV,  $\rho=2.33$  g/cm $^{**3}$   
 $ef=4.60$  eV,  $esb=4.70$  eV,  $ca=0.65$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=2$  (Moliere potential)  
program : testsi, Gauss-Mehler integration (nnn=16)  
ne= 4, na= 1

E <sub>0</sub> (eV)	0°
50	3.35e-4
70	1.16e-3
100	2.97e-3
200	7.31e-3

Energy reflection coefficient of Si backscattered from Si  
ne= 4, na= 1

E <sub>0</sub> (eV)	0°
50	1.82e-5
70	6.87e-5
100	1.69e-4
200	3.86e-4

Average depth (mean range) in Å of Si implanted in Si  
ne= 4, na= 1

E <sub>0</sub> (eV)	0°
50	9.47e+0
70	1.13e+1
100	1.35e+1
200	1.94e+1

## Si → Si

Sputtering yield of Si by Si  
 $z1=14$ ,  $m1 = 28.09$ ,  $m2 = 28.09$ ,  $sbe=4.70$  eV,  $\rho = 2.32$  g/cm\*\*3  
 $ef=4.60$  eV,  $esb=4.70$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=4$  (Si-Si potential (with attractive part))  
program : testsi, Gauss-Mehler integration (nnn=16)  
ne=12, na=16

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$55^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$
25	1.29e-4											
30	3.84e-4											
40	1.77e-3											
50	5.16e-3											
70	1.83e-2											
100	4.74e-2											
200	1.70e-1	1.86e-1	2.54e-1	3.74e-1	5.30e-1	7.13e-1	8.00e-1	8.71e-1	9.09e-1	8.99e-1	8.24e-1	7.25e-1
500	4.11e-1											
1000	6.61e-1											
2000	9.50e-1											
5000	1.24e-0											
10000	1.29e-0											

$E_0$ (eV)	$85^\circ$	$87^\circ$	$88^\circ$	$89^\circ$
200	5.87e-1	5.44e-1	5.40e-1	5.37e-1

Sputtered energy of Si by Si  
ne=12, na=16

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$55^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$
25	7.26e-6											
30	2.17e-5											
40	9.58e-5											
50	2.73e-4											
70	8.55e-4											
100	1.92e-3											
200	5.39e-3	6.49e-3	1.08e-2	2.01e-2	3.61e-2	6.05e-2	7.56e-2	9.22e-2	1.08e-1	1.19e-1	1.18e-1	1.13e-1
500	8.61e-3											
1000	1.00e-2											
2000	1.03e-2											
5000	8.36e-3											
10000	6.03e-3											

$E_0$ (eV)	$85^\circ$	$87^\circ$	$88^\circ$	$89^\circ$
200	9.71e-2	9.11e-2	9.01e-2	9.05e-2

## $\text{Si} \rightarrow \text{Si}$

Particle reflection coefficient of Si backscattered from Si  
 $z1=14$ ,  $m1 = 28.09$ ,  $z2=14$ ,  $m2 = 28.09$ ,  $sbe=4.70$  eV,  $\rho=2.32$  g/cm\*\*3  
 $ef=4.60$  eV,  $esb=4.70$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=4$  (*Si-Si potential (with attractive part)*)  
program : testsi, Gauss-Mehler integration (nnn=16)  
ne=12, na=16

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$55^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$
25	1.38e-6											
30	9.13e-6											
40	7.08e-5											
50	1.99e-4											
70	6.20e-4											
100	1.83e-3											
200	5.10e-3	7.25e-3	1.28e-2	2.78e-2	5.67e-2	1.16e-1	1.63e-1	2.19e-1	2.95e-1	3.83e-1	4.96e-1	5.98e-1
500	9.35e-3											
1000	1.12e-2											
2000	1.03e-2											
5000	7.89e-3											
10000	5.32e-3											

$E_0$ (eV)	$85^\circ$	$87^\circ$	$88^\circ$	$89^\circ$
200	6.97e-1	7.22e-1	7.28e-1	7.32e-1

Energy reflection coefficient of Si backscattered from Si  
ne=12, na=16

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$55^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$
25	9.83e-8											
30	7.67e-7											
40	4.46e-6											
50	1.12e-5											
70	3.07e-5											
100	9.83e-5											
200	2.37e-4	4.21e-4	1.01e-3	2.75e-3	8.18e-3	2.34e-2	3.84e-2	6.08e-2	9.63e-2	1.47e-1	2.17e-1	3.02e-1
500	4.18e-4											
1000	4.93e-4											
2000	4.73e-4											
5000	3.80e-4											
10000	2.64e-4											

$E_0$ (eV)	$85^\circ$	$87^\circ$	$88^\circ$	$89^\circ$
200	3.87e-1	4.13e-1	4.15e-1	4.19e-1

Average depth (mean range) in Å of Si implanted in Si  
ne=12, na=16

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$55^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$
25	3.20e+0											
30	3.65e+0											
40	4.43e+0											
50	5.12e+0											
70	6.35e+0											
100	7.96e+0											
200	1.22e+1	1.21e+1	1.16e+1	1.07e+1	9.87e+0	8.73e+0	8.18e+0	7.67e+0	7.13e+0	6.56e+0	6.04e+0	5.44e+0
500	2.13e+1											
1000	3.22e+1											
2000	4.98e+1											
5000	9.66e+1											
10000	1.70e+2											

$E_0$ (eV)	$85^\circ$	$87^\circ$	$88^\circ$	$89^\circ$
200	5.00e+0	4.85e+0	4.85e+0	4.85e+0

## Si → Si

Sputtering yield of Si by Si  
 $z1=14$ ,  $m1 = 28.09$ ,  $m2 = 28.09$ ,  $sbe=4.70$  eV,  $\rho = 2.32$  g/cm\*\*\*  
 $ef=4.60$  eV,  $esb=4.70$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=3$  (ZBL potential)  
program : testsi, Gauss-Mehler integration (nnn=16)  
ne=12, na=16

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$55^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$
25	1.27e-4											
30	4.29e-4											
40	2.21e-3											
50	6.15e-3											
70	2.12e-2											
100	5.28e-2											
200	1.73e-1	1.99e-1	2.82e-1	4.33e-1	6.28e-1	8.43e-1	9.52e-1	1.03e-0	1.03e-0	9.81e-1	8.02e-1	5.18e-1
500	4.18e-1											
1000	6.26e-1											
2000	8.37e-1											
5000	1.06e-0											
10000	1.12e-0											

$E_0$ (eV)	$85^\circ$	$87^\circ$	$88^\circ$	$89^\circ$
200	2.77e-1	2.14e-1	1.97e-1	1.87e-1

Sputtered energy of Si by Si  
ne=12, na=16

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$55^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$
25	7.06e-6											
30	2.44e-5											
40	1.20e-4											
50	3.14e-4											
70	9.70e-4											
100	2.06e-3											
200	5.30e-3	6.84e-3	1.23e-2	2.40e-2	4.48e-2	7.46e-2	9.47e-2	1.15e-1	1.28e-1	1.38e-1	1.26e-1	8.94e-2
500	8.58e-3											
1000	9.25e-3											
2000	8.83e-3											
5000	7.10e-3											
10000	5.34e-3											

$E_0$ (eV)	$85^\circ$	$87^\circ$	$88^\circ$	$89^\circ$
200	4.77e-2	3.72e-2	3.26e-2	3.04e-2

## Si → Si

Particle reflection coefficient of Si backscattered from Si  
 $z1=14$ ,  $m1 = 28.09$ ,  $z2=14$ ,  $m2 = 28.09$ ,  $sbe=4.70$  eV,  $\rho=2.32$  g/cm\*\*3  
 $ef=4.60$  eV,  $esb=4.70$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=3$  (ZBL potential)  
program : testsi, Gauss-Mehler integration (nnn=16)  
ne=12, na=16

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$55^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$
25	3.50e-6											
30	2.38e-5											
40	1.45e-4											
50	3.83e-4											
70	1.14e-3											
100	2.45e-3											
200	7.06e-3	9.40e-3	1.94e-2	3.89e-2	8.17e-2	1.61e-1	2.22e-1	2.97e-1	4.03e-1	5.19e-1	6.71e-1	8.30e-1
500	1.05e-2											
1000	1.08e-2											
2000	9.57e-3											
5000	7.58e-3											
10000	5.53e-3											

$E_0$ (eV)	$85^\circ$	$87^\circ$	$88^\circ$	$89^\circ$
200	9.36e-1	9.54e-1	9.61e-1	9.63e-1

Energy reflection coefficient of Si backscattered from Si  
ne=12, na=16

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$55^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$
25	2.33e-7											
30	1.47e-6											
40	8.95e-6											
50	2.21e-5											
70	6.02e-5											
100	1.33e-4											
200	3.46e-4	5.44e-4	1.61e-3	4.36e-3	1.29e-2	3.63e-2	5.98e-2	9.47e-2	1.56e-1	2.40e-1	3.67e-1	5.38e-1
500	4.80e-4											
1000	4.60e-4											
2000	4.31e-4											
5000	3.54e-4											
10000	2.87e-4											

$E_0$ (eV)	$85^\circ$	$87^\circ$	$88^\circ$	$89^\circ$
200	6.84e-1	7.21e-1	7.32e-1	7.41e-1

Average depth (mean range) in Å of Si implanted in Si  
ne=12, na=16

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$55^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$
25	3.33e+0											
30	3.79e+0											
40	4.60e+0											
50	5.32e+0											
70	6.59e+0											
100	8.22e+0											
200	1.26e+1	1.24e+1	1.19e+1	1.11e+1	1.01e+1	8.92e+0	8.30e+0	7.76e+0	7.20e+0	6.49e+0	5.84e+0	5.05e+0
500	2.22e+1											
1000	3.45e+1											
2000	5.48e+1											
5000	1.06e+2											
10000	1.84e+2											

$E_0$ (eV)	$85^\circ$	$87^\circ$	$88^\circ$	$89^\circ$
200	4.16e+0	3.82e+0	3.76e+0	3.90e+0

## Si → Si

Sputtering yield of Si by Si  
 $z1=14$ ,  $m1 = 28.09$ ,  $z2=14$ ,  $m2 = 28.09$ ,  $sbe=4.70$  eV,  $\rho=2.32$  g/cm $^{**3}$   
 $ef=4.60$  eV,  $esb=4.70$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC potential)  
 program : testsi, Gauss-Mehler integration (nnn=number of pivots)  
 $ne=1$ ,  $n(nnn)=4$

E <sub>0</sub> (eV)	2	4	8	16
100	6.20e-2	6.61e-2	6.82e-2	6.79e-2

Sputtered energy of Si by Si  
 $ne=1$ ,  $np(nnn)=4$

E <sub>0</sub> (eV)	2	4	8	16
100	2.48e-3	2.65e-3	2.73e-3	2.77e-3

Particle reflection coefficient of Si backscattered from Si  
 $z1=14$ ,  $m1 = 28.09$ ,  $z2=14$ ,  $m2 = 28.09$ ,  $sbe=4.70$  eV,  $\rho=2.32$  g/cm $^{**3}$   
 $ef=4.60$  eV,  $esb=4.70$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC potential)  
 program : testsi, Gauss-Mehler integration (nnn=number of pivots)  
 $ne=1$ ,  $n(nnn)=4$

E <sub>0</sub> (eV)	2	4	8	16
100	3.07e-3	3.38e-3	3.17e-3	3.03e-3

Energy reflection coefficient of Si backscattered from Si  
 $ne=1$ ,  $n(nnn)=4$

E <sub>0</sub> (eV)	2	4	8	16
100	1.61e-4	1.90e-4	1.73e-4	1.64e-4

Average depth (mean range) in Å of Si implanted in Si  
 $ne=1$ ,  $n(nnn)=4$

E <sub>0</sub> (eV)	2	4	8	16
100	8.15e+0	7.39e+0	7.19e+0	7.15e+0

## Si → Si

Sputtering yield of Si by Si  
 $z_1=14$ ,  $m_1=28.09$ ,  $z_2=14$ ,  $m_2=28.09$ ,  $sbe=4.70$  eV,  $\rho=2.33$  g/cm $^{**3}$   
 $ef=4.65$  eV,  $esb=4.70$  eV,  $ca=1.00$ ,  $kk0=kk0r$ ,  $kdee1=kdee2=3$ , KrC potential  
 $e0=100$  eV,  $alpha=0.0$   
program : testsi, Gauss-Mehler integration (nnn=16)  
ne=1, n(kk0)=4

Potential	kk0=0	1	2	3
KrC	7.53e-2	6.35e-2	6.81e-2	7.13e-2
Mol	1.01e-1	8.20e-2	8.76e-2	9.39e-2
ZBL	5.82e-2	5.01e-2	5.28e-2	5.76e-2
Si-Si	7.45e-2	7.12e-2	4.74e-2	3.36e-2

Sputtered energy of Si by Si  
ne=1, n(kk0)=4

Potential	kk0=0	1	2	3
KrC	2.99e-3	2.62e-3	2.78e-3	2.87e-3
Mol	4.10e-3	3.41e-3	3.69e-3	3.89e-3
ZBL	2.29e-3	2.00e-3	2.06e-3	2.22e-3
Si-Si	3.17e-3	3.04e-3	1.92e-3	1.39e-3

Particle reflection coefficient of Si backscattered from Si  
 $z_1=14$ ,  $m_1=28.09$ ,  $z_2=14$ ,  $m_2=28.09$ ,  $sbe=4.70$  eV,  $\rho=2.33$  g/cm $^{**3}$   
 $ef=4.65$  eV,  $esb=4.70$  eV,  $ca=1.00$ ,  $kk0=kk0r$ ,  $kdee1=kdee2=3$ , KrC potential  
 $e0=100$  eV,  $alpha=0.0$   
program : testsi, Gauss-Mehler integration (nnn=16)  
ne=1, n(kk0)=4

Potential	kk0=0	1	2	3
KrC	2.59e-3	2.69e-3	3.11e-3	3.33e-3
Mol	3.06e-3	3.44e-3	4.03e-3	3.96e-3
ZBL	2.45e-3	2.29e-3	2.45e-3	2.78e-3
Si-Si	3.05e-3	3.05e-3	1.83e-3	1.15e-3

Energy reflection coefficient of Si backscattered from Si  
ne=1, n(kk0)=4

Potential	kk0=0	1	2	3
KrC	1.25e-4	1.48e-4	1.69e-4	1.97e-4
Mol	1.43e-4	1.92e-4	2.27e-4	2.21e-4
ZBL	1.21e-4	1.23e-4	1.33e-4	1.39e-4
Si-Si	1.63e-4	1.47e-4	9.83e-5	6.52e-5

Average depth (mean range) in Å of Si implanted in Si  
ne=1, n(kk0)=4

Potential	kk0=0	1	2	3
KrC	7.83e+0	7.21e+0	7.16e+0	7.14e+0
Mol	6.53e+0	5.93e+0	5.88e+0	5.89e+0
ZBL	8.84e+0	8.32e+0	8.22e+0	8.24e+0
Si-Si	8.36e+0	8.13e+0	7.96e+0	7.75e+0

## Si → Si

Sputtering yield of Si by Si  
 $z1=14$ ,  $m1= 28.09$ ,  $z2=14$ ,  $m2= 28.09$ ,  $sbe=4.70$  eV,  $\rho=2.32$  g/cm\*\*\*  
 $ef=4.65$  eV,  $esb=4.70$  eV,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$   
program : trspvmcx  
 $ne=1$ ;  $alpha=0$ .

$E_0$ (eV)	Pot.=KrC ca=1.00	Mol 1.00	ZBL 1.00	Mol 0.62
200	1.73e-1	2.84e-1	1.78e-1	1.26e-1

Sputtered energy of Si by Si  
 $ne=1$ ;  $alpha=0$ .

$E_0$ (eV)	Pot.=KrC ca=1.00	Mol 1.00	ZBL 1.00	Mol 0.62
200	5.34e-3	8.63e-3	5.55e-3	4.39e-3

Particle reflection coefficient of Si backscattered from Si  
 $z1=14$ ,  $m1= 28.09$ ,  $z2=14$ ,  $m2= 28.09$ ,  $sbe=4.70$  eV,  $\rho=2.32$  g/cm\*\*\*  
 $ef=4.65$  eV,  $esb=4.70$  eV,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$   
program : trspvmcx  
 $ne=1$ ;  $alpha=0$ .

$E_0$ (eV)	Pot.=KrC ca=1.00	Mol 1.00	ZBL 1.00	Mol 0.62
200	8.46e-3	1.11e-2	7.28e-3	6.54e-3

Energy reflection coefficient of Si backscattered from Si  
 $ne=1$ ;  $alpha=0$ .

$E_0$ (eV)	Pot.=KrC ca=1.00	Mol 1.00	ZBL 1.00	Mol 0.62
200	4.54e-4	5.77e-4	3.59e-4	3.49e-4

Average depth (mean range) in Å of Si implanted in Si  
 $ne=1$ ;  $alpha=0$ .

$E_0$ (eV)	Pot.=KrC ca=1.00	Mol 1.00	ZBL 1.00	Mol 0.62
200	1.31e+1	9.03e+0	1.24e+1	2.07e+1

## P → Si

Particle reflection coefficient of P backscattered from Si  
z1=15, m1= 31.00, z2=14, m2= 28.09, rho= 2.33 g/cm\*\*3  
ef=1.00 eV, esb=1.00 eV, ca=1.00, kk0=2, kdeel=3, ipot=1 (KrC)  
program: trrange3  
*only low fluence!*  
nem= 2, na= 1

E <sub>0</sub> (eV)	0°
100000	5.50e-4
200000	2.25e-4

Energy reflection coefficient of P backscattered from Si  
*only low fluence!*  
nem= 2, na= 1

E <sub>0</sub> (eV)	0°
100000	2.56e-5
200000	9.26e-6

Average depth (mean range) in Å of P implanted in Si  
*only low fluence!*  
nem= 2, na= 1

E <sub>0</sub> (eV)	0°
100000	1.43e+3
200000	2.81e+3

## Ar → Si

Sputtering yield of Si by Ar

```

z1=18, m1= 39.95, z2=14, m2= 28.09, sbe=4.70, rho=2.32 g/cm**3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : trspvmcx, IPP 9/82
ne=15, na= 1

```

E <sub>0</sub> (eV)	0°
50	1.79e-3
50	1.60e-3
100	3.08e-2
100	3.20e-2
300	2.33e-1
300	2.30e-1
500	3.96e-1
500	3.50e-1
1000	6.64e-1
1000	6.20e-1
3000	9.50e-1
4000	1.19e-0
10000	1.20e-0
30000	1.25e-0
100000	1.20e-0

Sputtered energy of Si by Ar

```

program : trspvmcx
ne= 6, na= 1

```

E <sub>0</sub> (eV)	0°
50	1.79e-3
50	1.60e-3
100	3.08e-2
100	3.20e-2
300	2.33e-1
300	2.30e-1
500	3.96e-1
500	3.50e-1
1000	6.64e-1
1000	6.20e-1
3000	9.50e-1
4000	1.19e-0
10000	1.20e-0
30000	1.25e-0
100000	1.20e-0

Particle reflection coefficient of Ar backscattered from Si

```

z1=18, m1= 39.95, z2=14, m2= 28.09, sbe=4.70, rho=2.32 g/cm**3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : trspvmcx
ne= 6, na= 1

```

E <sub>0</sub> (eV)	0°
50	7.83e-3
100	4.01e-3
300	3.93e-3
500	3.55e-3
1000	3.40e-3
4000	1.29e-3

Energy reflection coefficient of Ar backscattered from Si  
ne= 6, na= 1

E <sub>0</sub> (eV)	0°
50	1.04e-4
100	7.12e-5
300	8.09e-5
500	6.04e-5
1000	7.64e-5
4000	1.68e-5

Average depth (mean range) in Å of Ar implanted in Si  
ne= 6, na= 1

E <sub>0</sub> (eV)	0°
50	6.27e+0
100	9.36e+0
300	1.73e+1
500	2.30e+1
1000	3.44e+1
4000	8.24e+1

## Xe → Si

Sputtering yield of Si by Xe

```

z1=54, m1=131.30, z2=14, m2= 28.09, sbe=4.70, rho=2.32 g/cm**3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : trspvmcx, IPP 9/82
ne=18, na= 1

```

E <sub>0</sub> (eV)	0°
50	3.54e-5
50	4.00e-5
100	3.84e-3
100	3.65e-3
200	4.83e-2
300	1.14e-1
500	2.56e-1
500	2.74e-1
1000	5.53e-1
1000	5.84e-1
2000	9.76e-1
4000	1.48e-0
5000	1.54e-0
10000	2.09e-0
20000	2.51e-0
50000	2.99e-0
100000	3.13e-0
200000	3.10e-0

Sputtered energy of Si by Xe

```

program : trspvmcx
ne= 6, na= 1

```

E <sub>0</sub> (eV)	0°
50	8.90e-7
100	9.24e-5
300	2.09e-3
500	3.87e-3
1000	5.98e-3
4000	7.87e-3

Particle reflection coefficient of Xe backscattered from Si

```

z1=54, m1=131.30, z2=14, m2= 28.09, sbe=4.70, rho=2.32 g/cm**3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : trspvmcx
ne= 1, na= 1

```

E <sub>0</sub> (eV)	0°
50	6.13e-6

Energy reflection coefficient of Xe backscattered from Si

```

ne= 1, na= 1

```

E <sub>0</sub> (eV)	0°
50	1.44e-6

Average depth (mean range) in Å of Xe implanted in Si

```

ne= 6, na= 1

```

E <sub>0</sub> (eV)	0°
50	1.24e+1
100	1.72e+1
300	2.79e+1
500	3.48e+1
1000	4.72e+1
4000	8.91e+1

## Bi → Si

Average depth (mean range) in Å of Bi implanted in Si  
z1=83, m1=209.00, z2=14, m2= 28.09, rho= 2.33 g/cm\*\*3  
ef=1.00 eV, esb=1.00 eV, ca=1.00, kk0=2, kdeel=3, ipot=1 (KrC)  
program: trrange3  
*only low fluence!*  
ne= 2, na= 1

E <sub>0</sub> (eV)	0°
200000	8.94e+2
400000	1.48e+3

# D → Ti

Sputtering yield of Ti by D  
 $z1 = 1$ ,  $m1 = 2.01$ ,  $z2 = 22$ ,  $m2 = 47.90$ ,  $sbe = 4.89$  eV,  $\rho = 4.52$  g/cm<sup>3</sup>  
 $ef = 0.98$ ,  $esb = 1.00$ ,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = 4$ ,  $kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: testvmcx, IPP 9/82  
 $n_e = 8$ ,  $na = 1$

$E_0$ (eV)	0°
50	3.64e-4
70	2.49e-3
100	6.53e-3
300	2.14e-2
1000	2.72e-2
3000	2.17e-2
10000	1.13e-2
30000	5.00e-3

Sputtered energy of Ti by D  
program: testvmcx  
 $n_e = 8$ ,  $na = 1$

$E_0$ (eV)	0°
50	5.69e-6
70	6.59e-5
100	1.92e-4
300	5.04e-4
1000	3.56e-4
3000	1.36e-4
10000	3.13e-5
30000	3.70e-6

Particle reflection coefficient of D backscattered from Ti  
 $z1 = 1$ ,  $m1 = 2.01$ ,  $z2 = 22$ ,  $m2 = 47.90$ ,  $sbe = 4.89$  eV,  $\rho = 4.52$  g/cm<sup>3</sup>  
 $ef = 0.98$ ,  $esb = 1.00$ ,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = 4$ ,  $kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: testvmcx  
 $n_e = 8$ ,  $na = 1$

$E_0$ (eV)	0°
50	5.13e-1
70	4.95e-1
100	4.73e-1
300	4.01e-1
1000	3.09e-1
3000	1.89e-1
10000	7.85e-2
30000	1.95e-2

Energy reflection coefficient of D backscattered from Ti  
 $n_e = 8$ ,  $na = 1$

$E_0$ (eV)	0°
50	2.94e-1
70	2.78e-1
100	2.61e-1
300	2.08e-1
1000	1.46e-1
3000	7.62e-2
10000	2.55e-2
30000	5.22e-3

Average depth (mean range) in Å of D implanted in Ti  
 $n_e = 8$ ,  $na = 1$

$E_0$ (eV)	0°
50	2.78e+1
70	3.42e+1
100	4.29e+1
300	9.04e+1
1000	2.23e+2
3000	5.48e+2
10000	1.53e+3
30000	3.93e+3

## He → Ti

Sputtering yield of Ti by He  
 $z1 = 2$ ,  $m1 = 4.00$ ,  $z2 = 22$ ,  $m2 = 47.90$ ,  $sbe = 4.89$  eV,  $\rho = 4.52$  g/cm\*\*3  
 $ef = 0.50$ ,  $esb = 0.00$ ,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: testvmcx, IPP 9/82  
ne = 8, na = 1

$E_0$ (eV)	0°
40	3.31e-3
60	1.50e-2
100	3.58e-2
300	8.09e-2
1000	1.13e-1
3000	1.07e-1
10000	6.63e-2
30000	3.40e-2

Sputtered energy of Ti by He  
program: testvmcx  
ne = 8, na = 1

$E_0$ (eV)	0°
40	1.30e-4
60	7.34e-4
100	1.72e-3
300	2.62e-3
1000	1.82e-3
3000	8.56e-4
10000	2.07e-4
30000	4.89e-5

Particle reflection coefficient of He backscattered from Ti  
 $z1 = 2$ ,  $m1 = 4.00$ ,  $z2 = 22$ ,  $m2 = 47.90$ ,  $sbe = 4.89$  eV,  $\rho = 4.52$  g/cm\*\*3  
 $ef = 0.50$ ,  $esb = 0.00$ ,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: testvmcx  
ne = 8, na = 1

$E_0$ (eV)	0°
40	4.93e-1
60	4.58e-1
100	4.27e-1
300	3.62e-1
1000	2.87e-1
3000	2.06e-1
10000	1.09e-1
30000	3.95e-2

Energy reflection coefficient of He backscattered from Ti  
ne = 8, na = 1

$E_0$ (eV)	0°
40	2.53e-1
60	2.28e-1
100	2.06e-1
300	1.66e-1
1000	1.23e-1
3000	8.11e-2
10000	3.59e-2
30000	1.10e-2

Average depth (mean range) in Å of He implanted in Ti  
ne = 8, na = 1

$E_0$ (eV)	0°
40	1.38e+1
60	1.76e+1
100	2.39e+1
300	4.89e+1
1000	1.17e+2
3000	2.83e+2
10000	7.96e+2
30000	2.12e+3

## Ne → Ti

Sputtering yield of Ti by Ne  
 z1=10, m1= 20.18, z2=22, m2= 47.90, sbe=4.89 eV, rho=4.51 g/cm\*\*\*3  
 ef=0.50, esb=0.00, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx, IPP 9/82  
 ne=15, na=12

$E_0$ (eV)	0°	10°	20°	30°	40°	45°	50°	60°	70°	75°	80°	85°
38	1.02e-2	1.12e-2	1.43e-2	1.98e-2	2.75e-2	3.24e-2	3.71e-2	3.79e-2	2.34e-2	1.04e-2	2.10e-3	2.00e-5
50	3.00e-2											
100	1.45e-1											
200	3.23e-1											
380	5.33e-1	5.62e-1	6.58e-1	8.17e-1	1.03e-0	1.13e-0	1.24e-0	1.37e-0	1.18e-0	8.51e-1	3.46e-1	1.25e-2
500	6.14e-1											
1000	8.20e-1											
2000	9.98e-1											
3800	1.08e-0	1.15e-0	1.27e-0	1.61e-0	2.00e-0	2.32e-0	2.65e-0	3.47e-0	4.22e-0	4.30e-0	3.81e-0	1.38e-0
5000	1.09e-0											
10000	1.08e-0											
20000	9.40e-1											
50000	7.32e-1											
100000	5.51e-1											
200000	4.14e-1											

Sputtered energy of Ti by Ne  
 program: testvmcx, IPP 9/82  
 ne=15, na=12

$E_0$ (eV)	0°	10°	20°	30°	40°	45°	50°	60°	70°	75°	80°	85°
38	8.60e-4	1.04e-3	1.44e-3	2.39e-3	3.72e-3	4.67e-3	5.83e-3	6.97e-3	4.73e-3	2.26e-3	4.66e-4	7.46e-6
50	2.30e-3											
100	9.00e-3											
200	1.34e-2											
380	1.57e-2	1.70e-2	2.24e-2	3.12e-2	4.74e-2	5.60e-2	6.85e-2	9.23e-2	9.99e-2	8.31e-2	3.77e-2	8.54e-4
500	1.55e-2											
1000	1.41e-2											
2000	1.17e-2											
3798	8.92e-3	9.86e-3	1.24e-2	1.78e-2	2.62e-2	3.27e-2	4.01e-2	6.08e-2	8.71e-2	9.82e-2	9.83e-2	4.30e-2
5000	7.83e-3											
10000	5.21e-3											
20000	3.13e-3											
50000	1.43e-3											
100000	6.29e-4											
200000	3.03e-4											

## Ne → Ti

Particle reflection coefficient of Ne backscattered from Ti  
 z1=10, m1= 20.18, z2=22, m2= 47.90, sbe=4.89 eV, rho=4.51 g/cm\*\*3  
 ef=0.50, esb=0.00, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx  
 ne=15, na=12

$E_0$ (eV)	0°	10°	20°	30°	40°	45°	50°	60°	70°	75°	80°	85°
38	3.27e-1	3.49e-1	3.95e-1	4.60e-1	5.60e-1	6.14e-1	6.79e-1	8.17e-1	9.43e-1	9.83e-1	9.98e-1	1.00e-0
50	3.07e-1											
100	2.34e-1											
200	1.81e-1											
380	1.50e-1	1.58e-1	1.79e-1	2.11e-1	2.67e-1	3.00e-1	3.49e-1	4.67e-1	6.71e-1	8.07e-1	9.47e-1	1.00e-0
500	1.40e-1											
1000	1.15e-1											
2000	9.90e-2											
3798	8.05e-2	8.54e-2	9.52e-2	1.23e-1	1.60e-1	1.82e-1	2.14e-1	2.96e-1	4.24e-1	5.10e-1	6.40e-1	9.02e-1
5000	7.45e-2											
10000	5.89e-2											
20000	4.35e-2											
50000	2.39e-2											
100000	1.42e-2											
200000	7.56e-3											

Energy reflection coefficient of Ne backscattered from Ti  
 ne=15, na=12

$E_0$ (eV)	0°	10°	20°	30°	40°	45°	50°	60°	70°	75°	80°	85°
38	5.58e-2	6.46e-2	8.59e-2	1.23e-1	1.88e-1	2.34e-1	2.90e-1	4.43e-1	6.56e-1	7.81e-1	8.92e-1	9.68e-1
50	5.21e-2											
100	3.98e-2											
200	2.97e-2											
380	2.48e-2	2.74e-2	3.41e-2	4.70e-2	7.24e-2	9.00e-2	1.18e-1	2.04e-1	3.97e-1	5.64e-1	7.93e-1	9.68e-1
500	2.32e-2											
1000	1.85e-2											
2000	1.60e-2											
3798	1.32e-2	1.46e-2	1.76e-2	2.63e-2	4.04e-2	4.95e-2	6.41e-2	1.09e-1	2.01e-1	2.80e-1	4.27e-1	7.95e-1
5000	1.24e-2											
10000	9.68e-3											
20000	7.12e-3											
50000	3.89e-3											
100000	2.07e-3											
200000	1.10e-3											

Average depth (mean range) in Å of Ne implanted in Ti  
 ne=15, na=12

$E_0$ (eV)	0°	10°	20°	30°	40°	45°	50°	60°	70°	75°	80°	85°
38	6.91e+0	6.86e+0	6.76e+0	6.65e+0	6.49e+0	6.42e+0	6.35e+0	6.07e+0	5.70e+0	5.50e+0	5.19e+0	
50	7.58e+0											
100	9.90e+0											
200	1.35e+1											
380	1.87e+1	1.86e+1	1.82e+1	1.76e+1	1.67e+1	1.63e+1	1.58e+1	1.49e+1	1.40e+1	1.35e+1	1.27e+1	1.26e+1
500	2.17e+1											
1000	3.27e+1											
2000	5.51e+1											
3798	7.99e+1	7.91e+1	7.67e+1	7.31e+1	6.85e+1	6.58e+1	6.32e+1	5.75e+1	5.26e+1	5.13e+1	4.88e+1	4.65e+1
5000	9.84e+1											
10000	1.70e+2											
20000	3.09e+2											
50000	7.12e+2											
100000	1.37e+3											
200000	2.60e+3											

# Ar → Ti

Sputtering yield of Ti by Ar  
 $z1=18$ ,  $m1=39.95$ ,  $z2=22$ ,  $m2=47.90$ ,  $sbe=4.89$  eV,  $\rho=4.52$  g/cm\*\*\*  
 $ef=0.20$ ,  $0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program : trvmc95  
ne= 5, na= 5

$E_0$ (eV)	0°	20°	45°	50°	60°
640					2.29e-0
1000	1.04e-0				
1040		1.15e-0		2.14e-0	
1440					3.15e-0
5000				4.62e-0	3.84e-0

Sputtered energy of Ti by Ar  
ne= 5, na= 5

$E_0$ (eV)	0°	20°	45°	50°	60°
640					1.34e-1
1000	1.52e-2		2.22e-2	7.00e-2	
1040					1.33e-1
1440					1.34e-1
5000				6.66e-2	

Particle reflection coefficient of Ar backscattered from Ti  
 $z1=18$ ,  $m1=39.95$ ,  $z2=22$ ,  $m2=47.90$ ,  $sbe=4.89$  eV,  $\rho=4.52$  g/cm\*\*\*  
 $ef=0.20$ ,  $0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program : trvmc95  
ne= 5, na= 5

$E_0$ (eV)	0°	20°	45°	50°	60°
640					3.28e-1
1000	3.76e-2		6.04e-2	1.49e-1	
1040					3.08e-1
1440					2.88e-1
5000				1.33e-1	

Energy reflection coefficient of Ar backscattered from Ti  
ne= 5, na= 5

$E_0$ (eV)	0°	20°	45°	50°	60°
640					9.65e-2
1000	2.06e-3		4.33e-3	2.47e-2	
1040					9.13e-2
1440					8.45e-2
5000				2.59e-2	

Average depth (mean range) in Å of Ar implanted in Ti  
ne= 5, na= 5

$E_0$ (eV)	0°	20°	45°	50°	60°
640					1.33e+1
1000	2.40e+1		2.54e+1	2.10e+1	
1040					1.65e+1
1440					2.04e+1
5000				4.85e+1	

## Ti → Ti

Sputtering yield of Ti by Ti  
 $z1=22$ ,  $m1 = 47.90$ ,  $z2=22$ ,  $m2 = 47.90$ ,  $sbe=4.89$  eV,  $\rho=4.52$  g/cm $^{**3}$   
 $ef=4.85$ ,  $esb=4.89$ ,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: testvmcx, IPP 9/82  
 $ne=13$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
60	7.14e-3
80	1.96e-2
100	6.62e-2
100	3.62e-2
200	2.39e-1
300	2.41e-1
1000	1.04e-0
1000	7.16e-1
10000	2.14e-0
10000	1.73e-0
50000	1.62e-0
100000	1.71e-0
100000	1.39e-0

Sputtered energy of Ti by Ti  
program: testvmcx  
 $ne = 5$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
100	2.73e-3
200	7.43e-3
1000	1.45e-2
10000	8.88e-3
100000	2.10e-3

Particle reflection coefficient of Ti backscattered from Ti  
 $z1=22$ ,  $m1 = 47.90$ ,  $z2=22$ ,  $m2 = 47.90$ ,  $sbe=4.89$  eV,  $\rho=4.52$  g/cm $^{**3}$   
 $ef=4.85$ ,  $esb=4.89$ ,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: testvmcx  
 $ne = 5$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
100	4.19e-3
200	1.08e-2
1000	1.65e-2
10000	7.70e-3
100000	2.00e-3

Energy reflection coefficient of Ti backscattered from Ti  
 $ne = 5$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
100	2.36e-4
200	5.31e-4
1000	6.48e-4
10000	4.30e-4
100000	1.55e-4

Average depth (mean range) in Å of Ti implanted in Ti  
 $ne = 5$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
100	6.04e+0
200	9.03e+0
1000	2.23e+1
10000	9.72e+1
100000	6.60e+2

## Ti → Ti

Sputtering yield of Ti by Ti  
 $z1=22, m1=47.90, z2=22, m2=47.90, sbe=4.89 \text{ eV}, rho=4.52 \text{ g/cm}^{**3}$   
 $ef=4.85, esb=4.89, ca=0.75, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1$  (KrC)  
 program: testvmcx  
 $n_{\text{e}} = 8, n_{\text{a}} = 1$

$E_0(\text{eV})$	$0^\circ$
60	7.14e-3
80	1.96e-2
100	3.62e-2
300	2.41e-1
1000	7.16e-1
10000	1.73e-0
50000	1.62e-0
100000	1.39e-0

Sputtered energy of Ti by Ti  
 program: testvmcx  
 $n_{\text{e}} = 8, n_{\text{a}} = 1$

$E_0(\text{eV})$	$0^\circ$
60	3.29e-4
80	8.63e-4
100	1.49e-3
300	6.66e-3
1000	1.12e-2
10000	8.54e-3
50000	3.22e-3
100000	1.87e-3

Particle reflection coefficient of Ti backscattered from Ti  
 $z1=22, m1=47.90, z2=22, m2=47.90, sbe=4.89 \text{ eV}, rho=4.52 \text{ g/cm}^{**3}$   
 $ef=4.85, esb=4.89, ca=0.75, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1$  (KrC)  
 program: testvmcx  
 $n_{\text{e}} = 8, n_{\text{a}} = 1$

$E_0(\text{eV})$	$0^\circ$
60	7.96e-4
80	1.75e-3
100	2.91e-3
300	1.08e-2
1000	1.46e-2
10000	9.50e-3
50000	4.50e-3
100000	2.43e-3

Energy reflection coefficient of Ti backscattered from Ti  
 $n_{\text{e}} = 8, n_{\text{a}} = 1$

$E_0(\text{eV})$	$0^\circ$
60	4.19e-5
80	9.48e-5
100	1.61e-4
300	5.39e-4
1000	6.40e-4
10000	3.43e-4
50000	2.08e-4
100000	1.14e-4

Average depth (mean range) in Å of Ti implanted in Ti  
 $n_{\text{e}} = 8, n_{\text{a}} = 1$

$E_0(\text{eV})$	$0^\circ$
60	8.23e+0
80	9.56e+0
100	1.07e+1
300	1.86e+1
1000	3.49e+1
10000	1.36e+2
50000	4.59e+2
100000	8.27e+2

# D → V

Sputtering yield of V by D  
 $z1 = 1, m1 = 2.01, z2 = 23, m2 = 50.94, sbe = 5.33 \text{ eV}, rho = 6.10 \text{ g/cm}^{**3}$   
 $ef = 0.95 \text{ eV}, esb = 1.00 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdeel = 4, kdee2 = 3, ipot = ipotr = 1$  (KrC)  
 program: testvmcx  
 $ne = 11, na = 1$

E <sub>0</sub> (eV)	0°
50	7.42e-5
60	5.72e-4
70	1.49e-3
80	2.72e-3
100	5.27e-3
200	1.56e-2
500	2.60e-2
1000	2.68e-2
2000	2.49e-2
5000	1.84e-2
10000	1.30e-2

Sputtered energy of V by D  
 $ne = 11, na = 1$

E <sub>0</sub> (eV)	0°
50	6.86e-7
60	9.59e-6
70	3.12e-5
80	6.52e-5
100	1.36e-4
200	4.08e-4
500	5.15e-4
1000	3.53e-4
2000	2.09e-4
5000	7.78e-5
10000	3.00e-5

Particle reflection coefficient of D backscattered from V  
 $z1 = 1, m1 = 2.01, z2 = 23, m2 = 50.94, sbe = 5.33 \text{ eV}, rho = 6.10 \text{ g/cm}^{**3}$   
 $ef = 0.95 \text{ eV}, esb = 1.00 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdeel = 4, kdee2 = 3, ipot = ipotr = 1$  (KrC)  
 program: testvmcx  
 $ne = 11, na = 1$

E <sub>0</sub> (eV)	0°
50	5.32e-1
60	5.20e-1
70	5.10e-1
80	5.00e-1
100	4.86e-1
200	4.42e-1
500	3.75e-1
1000	3.17e-1
2000	2.50e-1
5000	1.52e-1
10000	8.55e-2

Energy reflection coefficient of D backscattered from V  
 $ne = 11, na = 1$

E <sub>0</sub> (eV)	0°
50	3.12e-1
60	3.02e-1
70	2.93e-1
80	2.86e-1
100	2.74e-1
200	2.39e-1
500	1.90e-1
1000	1.51e-1
2000	1.09e-1
5000	5.61e-2
10000	2.74e-2

Average depth (mean range) in Å of D implanted in V  
 $ne = 11, na = 1$

E <sub>0</sub> (eV)	0°
50	2.18e+1
60	2.44e+1
70	2.70e+1
80	2.93e+1
100	3.38e+1
200	5.35e+1
500	1.03e+2
1000	1.73e+2
2000	3.03e+2
5000	6.53e+2
10000	1.19e+3

# $V \rightarrow V$

Sputtering yield of V by V  
 $z1=23$ ,  $m1 = 50.94$ ,  $z2=23$ ,  $m2 = 50.94$ ,  $sbe=5.33$  eV,  $\rho=6.10$  g/cm $^{**3}$   
 $ef=5.28$  eV,  $esb=5.33$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: testvmcx  
 $ne=13$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
30	2.15e-4
40	1.18e-3
50	4.07e-3
60	9.75e-3
70	1.85e-2
80	3.04e-2
100	6.05e-2
200	2.48e-1
500	7.13e-1
1000	1.17e-0
2000	1.66e-0
5000	2.23e-0
10000	2.56e-0

Sputtered energy of V by V  
 $ne=13$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
30	1.16e-5
40	6.67e-5
50	2.32e-4
60	5.35e-4
70	9.56e-4
80	1.48e-3
100	2.70e-3
200	8.11e-3
500	1.51e-2
1000	1.71e-2
2000	1.67e-2
5000	1.36e-2
10000	1.08e-2

## $V \rightarrow V$

Particle reflection coefficient of V backscattered from V  
 $z1=23$ ,  $m1= 50.94$ ,  $z2=23$ ,  $m2= 50.94$ ,  $sbe=5.33$  eV,  $\rho=6.10$  g/cm $^{**3}$   
 $ef=5.28$  eV,  $esb=5.33$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: testvmcx  
ne=13, na=1

$E_0$ (eV)	$0^\circ$
30	4.37e-6
40	1.06e-4
50	4.65e-4
60	1.05e-3
70	1.75e-3
80	2.61e-3
100	4.23e-3
200	1.07e-2
500	1.57e-2
1000	1.69e-2
2000	1.65e-2
5000	1.27e-2
10000	1.01e-2

Energy reflection coefficient of V backscattered from V  
ne=13, na=1

$E_0$ (eV)	$0^\circ$
30	2.91e-7
40	7.69e-6
50	3.36e-5
60	7.39e-5
70	1.18e-4
80	1.79e-4
100	2.67e-4
200	5.59e-4
500	7.29e-4
1000	7.20e-4
2000	6.45e-4
5000	5.35e-4
10000	4.48e-4

Average depth (mean range) in Å of V implanted in V  
ne=13, na=1

$E_0$ (eV)	$0^\circ$
30	1.90e+0
40	2.36e+0
50	2.77e+0
60	3.14e+0
70	3.47e+0
80	3.79e+0
100	4.36e+0
200	6.65e+0
500	1.13e+1
1000	1.70e+1
2000	2.55e+1
5000	4.55e+1
10000	7.32e+1

## H → Fe

Particle reflection coefficient of H backscattered from Fe  
 $z1 = 1$ ,  $m1 = 1.01$ ,  $z2 = 26$ ,  $m2 = 55.85$ ,  $sbe = 4.34$  eV,  $\rho = 7.87$  g/cm<sup>3</sup>  
 $ef = 100.00$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = 0$ ,  $kk0r = 2$ ,  $kdee1 = 4$ ,  $kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
 $dx = 50000.00 \text{ \AA}$   
program: trvmc95  
 $ne = 1$ ,  $na = 4$

$E_0$ (eV)	83°	86°	88°	89°
3000000	5.19e-2	1.81e-1	3.83e-1	5.52e-1

Energy reflection coefficient of H backscattered from Fe  
 $ne = 1$ ,  $na = 4$

$E_0$ (eV)	83°	86°	88°	89°
3000000	1.91e-2	8.16e-2	2.32e-1	4.05e-1

Average depth (mean range) in Å of H implanted in Fe  
 $ne = 1$ ,  $na = 4$

$E_0$ (eV)	83°	86°	88°	89°
3000000	3.06e+4	2.54e+4	2.23e+4	2.13e+4

Particle transmission coefficient of H transmitted through Fe  
 $ne = 1$ ,  $na = 4$

$E_0$ (eV)	83°	86°	88°	89°
3000000	3.99e-1	1.53e-1	6.71e-2	4.08e-2

Energy transmission coefficient of H transmitted through Fe  
 $ne = 1$ ,  $na = 4$

$E_0$ (eV)	83°	86°	88°	89°
3000000	1.18e-1	3.60e-2	1.48e-2	9.05e-3

## D → Fe

D on Fe, Maxwellian velocity distribution, sheath potential 3 kT  
 $z1 = 1$ ,  $m1 = 2.01$ ,  $z2 = 26$ ,  $m2 = 55.85$ ,  $sbe = 4.34$  eV,  $\rho = 7.87$  g/cm<sup>3</sup>  
 $ef = 0.95$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: trvmc95  
 $ne = 11$

kT (eV)	Y	$Y_E$	$E_{sp}$	$R_N$	$R_E$	$E_b$	range
7	1.57e-4	5.87e-6	1.31e+0	6.20e-1	4.02e-1	2.27e+1	1.44e+1
8	3.56e-4	1.27e-5	1.43e+0	6.09e-1	3.91e-1	2.57e+1	1.56e+1
9	7.04e-4	2.44e-5	1.56e+0	5.99e-1	3.81e-1	2.86e+1	1.67e+1
10	1.20e-3	4.06e-5	1.70e+0	5.91e-1	3.73e-1	3.16e+1	1.78e+1
14	4.42e-3	1.39e-4	2.20e+0	5.67e-1	3.50e-1	4.32e+1	2.20e+1
20	1.10e-2	3.25e-4	2.95e+0	5.42e-1	3.27e-1	6.04e+1	2.75e+1
50	3.41e-2	7.66e-4	5.63e+0	4.84e-1	2.75e-1	1.42e+2	5.03e+1
100	4.50e-2	7.22e-4	8.02e+0	4.29e-1	2.33e-1	2.71e+2	8.21e+1
200	4.99e-2	5.44e-4	1.09e+1	3.75e-1	1.91e-1	5.11e+2	1.37e+2
500	4.55e-2	2.66e-4	1.46e+1	2.88e-1	1.31e-1	1.14e+3	2.82e+2
1000	3.63e-2	1.29e-4	1.77e+1	2.13e-1	8.51e-2	2.00e+3	4.96e+2

## T → Fe

Particle reflection coefficient of T backscattered from Fe  
 $z1 = 1$ ,  $m1 = 3.02$ ,  $z2 = 26$ ,  $m2 = 55.85$ ,  $sbe = 4.34$  eV,  $\rho = 7.87$  g/cm<sup>3</sup>  
 $ef = 100.00$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0\theta = 0$ ,  $kk0r = 2$ ,  $kdee1 = 4$ ,  $kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
 $dx = 15000.00$  Å  
program: trvrmc95  
ne = 1, na = 4

E <sub>0</sub> (eV)	79°	83°	86°	88°	89°
1000000	4.06e-2	1.35e-1	3.03e-1	4.94e-1	6.37e-1

Energy reflection coefficient of T backscattered from Fe  
ne = 1, na = 4

E <sub>0</sub> (eV)	79°	83°	86°	88°	89°
1000000	5.60e-3	2.01e-2	7.24e-2	2.02e-1	3.68e-1

Average depth (mean range) in Å of T implanted in Fe  
ne = 1, na = 4

E <sub>0</sub> (eV)	79°	83°	86°	88°	89°
1000000	8.63e+3	6.77e+3	5.57e+3	5.04e+3	4.90e+3

Particle transmission coefficient of T transmitted through Fe  
ne = 1, na = 4

E <sub>0</sub> (eV)	79°	83°	86°	88°	89°
1000000	1.33e-1	3.73e-2	1.41e-2	7.72e-3	5.24e-3

Energy transmission coefficient of T transmitted through Fe  
ne = 1, na = 4

E <sub>0</sub> (eV)	79°	83°	86°	88°	89°
1000000	6.63e-3	1.91e-3	8.99e-4	5.86e-4	4.35e-4

## He → Fe

Sputtering yield of Fe by He  
 $z1 = 2$ ,  $m1 = 4.00$ ,  $z2 = 26$ ,  $m2 = 55.85$ ,  $sbe = 4.34$  eV,  $\rho = 7.87$  g/cm $^{**3}$   
 $ef = 0.50$  eV,  $esb = 0.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: trspvmcx, IPP 9/82  
 $ne = 10$ ,  $na = 1$

$E_0$ (eV)	0°
40	5.02e-3
50	1.26e-2
70	3.04e-2
100	5.52e-2
300	1.24e-1
1000	1.66e-1
1000	1.72e-1
5000	1.42e-1
10000	1.06e-1
30000	5.15e-2

Sputtered energy of Fe by He  
program: testvmcx, trspvmcx  
 $ne = 11$ ,  $na = 1$

$E_0$ (eV)	0°
40	1.79e-4
50	5.15e-4
70	1.31e-3
100	2.30e-3
300	3.48e-3
1000	2.38e-3
1000	2.36e-3
3000	1.03e-3
5000	6.37e-4
10000	2.77e-4
30000	5.50e-5

## He → Fe

Particle reflection coefficient of He backscattered from Fe  
 z1= 2, m1= 4.00, z2=26, m2= 55.85, sbe=4.34 eV, rho= 7.87 g/cm\*\*3  
 ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 5.5 MeV : kk0=0, kdee1=5, ef=100 eV, esb=1.00 eV, dx=7000 nm  
 program: testvmcx, trvmc95  
 ne=11, na=5

E <sub>0</sub> (eV)	0°	83°	86°	88°	89°
40	5.62e-1				
50	5.38e-1				
70	5.05e-1				
100	4.75e-1				
300	3.99e-1				
1000	3.19e-1				
3000	2.40e-1				
5000	1.93e-1				
10000	1.33e-1				
30000	5.34e-2				
5500000		1.38e-2	8.17e-2	2.76e-1	4.72e-1

Energy reflection coefficient of He backscattered from Fe  
 ne=11, na=5

E <sub>0</sub> (eV)	0°	83°	86°	88°	89°
40	3.11e-1				
50	2.92e-1				
70	2.67e-1				
100	2.45e-1				
300	1.94e-1				
1000	1.43e-1				
3000	1.01e-1				
5000	7.59e-2				
10000	4.52e-2				
30000	1.51e-2				
5500000		3.67e-3	1.86e-2	9.78e-2	2.51e-1

Average depth (mean range) in Å of He implanted in Fe  
 program: testvmcx, trspvmcx  
 ne=10, na=1

E <sub>0</sub> (eV)	0°
40	9.20e+0
50	1.05e+1
70	1.28e+1
100	1.59e+1
300	3.21e+1
1000	7.55e+1
3000	1.79e+2
5000	2.72e+2
10000	4.92e+2
30000	1.30e+3

## Fe → Fe

Sputtering yield of Fe by Fe

```

z1=26, m1= 55.85, z2=26, m2= 55.85, sbe=4.34 eV, rho= 7.87 g/cm***3
ef=4.29 eV, esb=4.34 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program: testvmcx, IPP 9/82
ne=11, na= 1

```

E <sub>0</sub> (eV)	0°
50	9.84e-3
70	4.00e-2
100	1.18e-1
200	4.10e-1
500	1.12e-0
1000	1.80e-0
2000	2.47e-0
5000	3.19e-0
10000	3.91e-0
30000	3.88e-0
100000	3.38e-0

Sputtered energy of Fe by Fe

```

program: testvmcx
ne=11, na= 1

```

E <sub>0</sub> (eV)	0°
50	5.35e-4
70	2.05e-3
100	4.90e-3
200	1.29e-2
500	2.12e-2
1000	2.24e-2
2000	2.03e-2
5000	1.58e-2
10000	1.32e-2
30000	7.94e-3
100000	3.10e-3

Particle reflection coefficient of Fe backscattered from Fe

```

z1=26, m1= 55.85, z2=26, m2= 55.85, sbe=4.34 eV, rho= 7.87 g/cm***3
ef=4.29 eV, esb=4.34 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program: testvmcx
ne=11, na= 1

```

E <sub>0</sub> (eV)	0°
50	9.25e-4
70	3.06e-3
100	5.95e-3
200	1.38e-2
500	1.98e-2
1000	2.34e-2
2000	1.88e-2
5000	1.24e-2
10000	1.30e-2
30000	6.67e-3
100000	4.00e-3

Energy reflection coefficient of Fe backscattered from Fe  
ne=11, na= 1

E <sub>0</sub> (eV)	0°
50	6.52e-5
70	2.10e-4
100	3.79e-4
200	6.23e-4
500	8.52e-4
1000	9.52e-4
2000	7.11e-4
5000	4.40e-4
10000	4.76e-4
30000	3.61e-4
100000	2.29e-4

Average depth (mean range) in Å of Fe implanted in Fe  
ne=11, na= 1

E <sub>0</sub> (eV)	0°
50	2.06e+0
70	2.63e+0
100	3.36e+0
200	5.21e+0
500	8.82e+0
1000	1.31e+1
2000	1.98e+1
5000	3.57e+1
10000	5.52e+1
30000	1.26e+2
100000	3.39e+2

# $\mu \rightarrow \text{Ni}$

Particle reflection coefficient of  $\mu$  backscattered from Ni  
 z1 = 1, m1 = 0.11, z2 = 28, m2 = 58.71, sbe = 4.46 eV, rho = 8.90 g/cm\*\*3  
 ef = 0.50 eV, esb = 0.00 eV, ca = 1.00, kk0 = kk0r = 2, kddee2 = 3, ipot = ipotr = 1 (KrC)  
 10 - 1000 eV : kddee1 = 3, 1000 - 20000 eV : kddee1 = 4  
 program: trvrmc  
 ne = 8, na = 1

$E_0$ (eV)	0°
10	7.08e-1
100	4.25e-1
500	2.64e-1
1000	2.01e-1
1000	1.78e-1
5000	5.99e-2
10000	3.05e-2
20000	1.29e-2

Energy reflection coefficient of  $\mu$  backscattered from Ni  
 ne = 8, na = 1

$E_0$ (eV)	0°
10	4.39e-1
100	2.04e-1
500	1.04e-1
1000	7.05e-2
1000	6.25e-2
5000	1.81e-2
10000	8.96e-3
20000	4.63e-3

Average depth (mean range) in Å of  $\mu$  implanted in Ni  
 ne = 8, na = 1

$E_0$ (eV)	0°
10	5.53e+0
100	1.80e+1
500	4.61e+1
1000	7.19e+1
1000	6.60e+1
5000	2.13e+2
10000	3.76e+2
20000	7.21e+2

# H → Ni

Sputtering yield of Ni by H  
 z1= 1, m1= 1.01, z2=28, m2= 58.71, sbe=4.46 eV, rho= 8.90 g/cm\*\*3  
 ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: TESTVMCX, IPP 9/82  
 ne=13, na=16

E <sub>0</sub> (eV)	0°	10°	20°	30°	40°	50°	55°	60°	65°	70°	75°	80°
150	2.00e-3	2.10e-3	2.05e-3	2.20e-3	2.35e-3	2.35e-3	2.25e-3	2.05e-3	1.80e-3	1.20e-3	6.40e-4	
200	4.50e-3	4.50e-3	4.80e-3	5.40e-3	5.50e-3	6.20e-3	5.90e-3	6.10e-3	5.80e-3	4.70e-3	3.03e-3	1.05e-3
400	1.16e-2	1.25e-2	1.35e-2	1.45e-2	1.60e-2	1.90e-2		2.40e-2	2.65e-2	2.80e-2	3.05e-2	2.50e-2
500	1.44e-2											
700	1.52e-2											
1000	1.52e-2	1.40e-2	1.70e-2	1.95e-2	2.40e-2	3.30e-2		4.80e-2		7.10e-2	9.30e-2	9.80e-1
2000	1.42e-2											
3000	1.20e-2											
5000	1.10e-2											
10000	8.20e-3											
20000	4.50e-3											
50000	2.70e-3		2.55e-3		4.09e-3			9.68e-3				4.42e-2
100000	1.20e-3											

E <sub>0</sub> (eV)	85°	87°	88°	89°
1000	3.80e-2	3.60e-4		
50000	8.97e-2	1.54e-1	1.72e-1	7.68e-2

Sputtered energy of Ni by H  
 program: TESTVMCX  
 ne= 1, na= 3

E <sub>0</sub> (eV)	87°	88°	89°
50000	1.12e-4	1.39e-4	7.97e-5

Particle reflection coefficient of H backscattered from Ni  
 z1= 1, m1= 1.01, z2=28, m2= 58.71, sbe=4.46 eV, rho= 8.90 g/cm\*\*3  
 ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: TESTVMCX  
 ne= 1, na= 3

E <sub>0</sub> (eV)	87°	88°	89°
50000	6.69e-1	7.46e-1	9.26e-1

Energy reflection coefficient of H backscattered from Ni  
 ne= 1, na= 3

E <sub>0</sub> (eV)	87°	88°	89°
50000	4.20e-1	5.34e-1	8.55e-1

Average depth (mean range) in Å of H implanted in Ni  
 ne= 1, na= 3

E <sub>0</sub> (eV)	87°	88°	89°
50000	9.38e+2	9.41e+2	9.35e+2

## D → Ni

Sputtering yield of Ni by D  
 $z1 = 1, m1 = 2.01, z2 = 28, m2 = 58.71, sbe = 4.46 \text{ eV}, rho = 8.90 \text{ g/cm}^{**3}$   
 $ef = 0.98 \text{ eV}, esb = 1.00 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1$  (KrC)  
 program: IPP 9/82  
 $ne = 14, na = 1$

$E_0(\text{eV})$	0°
75	3.10e-3
100	7.90e-3
150	1.84e-2
200	2.52e-2
300	3.27e-2
500	4.13e-2
700	3.86e-2
1000	4.03e-2
2000	3.72e-2
3000	3.26e-2
5000	2.64e-2
10000	1.85e-2
50000	6.00e-3
100000	4.00e-3

## $^3\text{He} \rightarrow \text{Ni}$

Sputtering yield of Ni by  $^3\text{He}$   
 $z1 = 2, m1 = 3.02, z2 = 28, m2 = 58.71, sbe = 4.46 \text{ eV}, rho = 8.90 \text{ g/cm}^{**3}$   
 $ef = 0.50 \text{ eV}, esb = 0.00 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1$  (KrC)  
 program: IPP 9/82  
 $ne = 13, na = 1$

$E_0(\text{eV})$	0°
40	7.60e-4
50	3.70e-3
70	1.35e-2
100	3.50e-2
200	8.00e-2
300	1.00e-1
750	1.30e-1
1500	1.40e-1
2000	1.40e-1
5000	1.20e-1
20000	5.50e-2
30000	6.47e-2
50000	3.18e-2

# He → Ni

Sputtering yield of Ni by He  
 z1= 2, m1= 4.00, z2=28, m2= 58.71, sbe=4.46 eV, rho=8.90 g/cm\*\*3  
 ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: TESTVMCX, TRSPV1CS, TRSPV1C, IPP 9/82  
 ne=30, na= 9

E <sub>0</sub> (eV)	0°	30°	60°	75°	80°	85°	87°	88°	89°
26	4.28e-6								
28	5.49e-5								
30	2.06e-4								
35	1.27e-3								
40	3.27e-3								
50	1.00e-2								
70	2.83e-2								
100	5.38e-2								
150	8.20e-2								
150	7.14e-2								
200	1.02e-1								
200	9.64e-2								
300	1.29e-1								
300	1.20e-1								
500	1.54e-1								
500	1.40e-1								
700	1.54e-1								
1000	1.75e-1								
1000	1.63e-1								
1500	1.68e-1								
2000	1.58e-1								
3000	1.77e-1								
3000	1.48e-1								
5000	1.35e-1								
10000	1.19e-1								
10000	1.03e-1								
20000	6.97e-2								
30000	6.47e-2								
50000	3.64e-2								
100000	2.23e-2	3.28e-2	8.44e-2	2.34e-1	3.27e-1	7.50e-1	9.37e-1	9.98e-1	4.12e-1

Sputtered energy of Ni by He  
 program: TESTVMCX, TRSPV1CS, TRSPV1C  
 ne=17, na= 6

E <sub>0</sub> (eV)	0°	75°	85°	87°	88°	89°
26	6.35e-8					
28	1.42e-6					
30	3.60e-6					
35	3.37e-5					
40	1.04e-4					
50	3.95e-4					
70	1.18e-3					
100	2.20e-3					
150	3.06e-3					
200	3.41e-3					
300	3.56e-3					
500	3.19e-3					
1000	2.38e-3					
3000	1.15e-3					
10000	3.38e-4					
30000	6.86e-5	1.99e-4	8.59e-4	9.78e-4	1.08e-3	5.17e-4
100000						

## He → Ni

Particle reflection coefficient of He backscattered from Ni  
 z1= 2, m1= 4.00, z2=28, m2= 58.71, sbe=4.46 eV, rho=8.90 g/cm\*\*3  
 ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: TESTVMCX, TRSPV1CS, TRSPV1C  
 ne=17, na= 6

$E_0$ (eV)	0°	75°	85°	87°	88°	89°
26	6.37e-1					
28	6.27e-1					
30	6.18e-1					
35	5.98e-1					
40	5.81e-1					
50	5.58e-1					
70	5.23e-1					
100	4.91e-1					
150	4.61e-1					
200	4.37e-1					
300	4.13e-1					
500	3.81e-1					
1000	3.30e-1					
3000	2.50e-1					
10000	1.46e-1					
30000	6.06e-2	3.04e-1	5.76e-1	6.76e-1	7.37e-1	9.26e-1
100000						

Energy reflection coefficient of He backscattered from Ni  
 ne=17, na= 6

$E_0$ (eV)	0°	75°	85°	87°	88°	89°
26	3.72e-1					
28	3.64e-1					
30	3.57e-1					
35	3.41e-1					
40	3.28e-1					
50	3.09e-1					
70	2.83e-1					
100	2.58e-1					
150	2.37e-1					
200	2.22e-1					
300	2.05e-1					
500	1.83e-1					
1000	1.54e-1					
3000	1.05e-1					
10000	5.32e-2	9.81e-2	3.15e-1	4.43e-1	5.37e-1	8.55e-1
30000	1.82e-2					
100000						

Average depth (mean range) in Å of He implanted in Ni  
 ne=17, na= 6

$E_0$ (eV)	0°	75°	85°	87°	88°	89°
26	6.79e+0					
28	7.06e+0					
30	7.33e+0					
35	7.98e+0					
40	8.60e+0					
50	9.77e+0					
70	1.19e+1					
100	1.47e+1					
150	1.90e+1					
200	2.27e+1					
300	2.95e+1					
500	4.18e+1					
1000	6.78e+1					
3000	1.60e+2					
10000	4.43e+2	1.24e+3	1.08e+3	1.07e+3	1.08e+3	1.03e+3
30000	1.15e+3					
100000						

# Ne → Ni

Sputtering yield of Ni by Ne  
 z1=10, m1= 20.18, z2=28, m2= 58.71, sbe=4.46 eV, rho=8.90 g/cm\*\*\*3  
 ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: TESTVMCX, IPP 9/82  
 ne=49, na= 18

$E_0$ (eV)	$0^\circ$	$5^\circ$	$10^\circ$	$15^\circ$	$20^\circ$	$25^\circ$	$30^\circ$	$40^\circ$	$45^\circ$	$50^\circ$	$55^\circ$	$60^\circ$
18	2.61e-6											
19	1.05e-5											
20	3.01e-5											
22	1.22e-4											
23	2.18e-4											
25	5.44e-4											
25	5.40e-4											
27	1.12e-3											
27	1.11e-3											
28	1.52e-3											
30	2.50e-3											
30	2.00e-3											
35	7.38e-3											
40	1.51e-2											
40	1.30e-2											
50	3.91e-2											
50	3.90e-2											
70	1.08e-1											
70	1.11e-1											
100	2.23e-1											
100	2.38e-1											
150	3.90e-1											
150	4.17e-1											
200	5.32e-1											
200	5.66e-1											
300	7.53e-1											
300	8.05e-1											
500	1.03e-0											
500	1.09e-0											
700	1.29e-0											
1000	1.41e-0											
1000	1.47e-0	1.45e-0	1.52e-0	1.57e-0	1.68e-0	1.80e-0	1.95e-0	2.29e-0	2.50e-0	2.63e-0	2.76e-0	2.82e-0
1500	1.62e-0											
2000	1.75e-0											
3000	1.85e-0											
3000	1.78e-0											
5000	1.90e-0											
7000	1.79e-0											
10000	1.86e-0											
10000	1.81e-0											
15000	1.67e-0											
20000	1.56e-0											
30000	1.48e-0											
30000	1.39e-0											
50000	1.18e-0											
100000	9.33e-1											
100000	8.89e-1											
200000	6.94e-1											
300000	5.00e-1											

$E_0$ (eV)	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$	$82.5^\circ$	$89^\circ$
1000	2.77e-0	2.44e-0	1.81e-0	7.62e-1	2.93e-1	3.23e-2

## Ne → Ni

Sputtered energy of Ni by Ne  
 program: TESTVMCX  
 ne=26, na= 18

$E_0$ (eV)	0°	5°	10°	15°	20°	25°	30°	40°	45°	50°	55°	60°
18	1.15e-6											
19	2.88e-6											
20	2.29e-6											
22	9.66e-6											
23	2.10e-5											
25	4.22e-5											
25	4.14e-5											
27	9.91e-5											
27	8.54e-5											
28	1.20e-4											
30	2.00e-4											
35	6.21e-4											
40	1.28e-3											
50	3.24e-3											
70	8.17e-3											
100	1.45e-2											
150	2.03e-2											
200	2.34e-2											
300	2.57e-2											
500	2.56e-2											
1000	2.26e-2											
1000	2.27e-2	2.17e-2	2.38e-2	2.59e-2	2.88e-2	3.25e-2	3.81e-2	5.12e-2	6.15e-2	7.29e-2	8.13e-2	9.37e-2
3000	1.52e-2											
10000	7.18e-3											
30000	3.12e-3											
100000	7.92e-4											

$E_0$ (eV)	65°	70°	75°	80°	82.5°	89°
1000	1.02e-1	1.03e-1	8.78e-2	4.19e-2	1.50e-2	9.96e-4

## Ne → Ni

Particle reflection coefficient of Ne backscattered from Ni  
 z1=10, m1= 20.18, z2=28, m2= 58.71, sbe=4.46 eV, rho=8.90 g/cm\*\*\*  
 ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: TESTVMCX  
 ne=25, na= 18

$E_0$ (eV)	0°	5°	10°	15°	20°	25°	30°	40°	45°	50°	55°	60°
18	5.48e-1											
19	5.47e-1											
20	5.45e-1											
22	5.41e-1											
25	5.33e-1											
25	5.51e-1											
27	5.28e-1											
27	5.54e-1											
28	5.40e-1											
30	5.16e-1											
35	5.01e-1											
40	4.86e-1											
50	4.56e-1											
70	4.08e-1											
100	3.57e-1											
150	3.12e-1											
200	2.83e-1											
300	2.48e-1											
500	2.13e-1											
1000	1.79e-1											
1000	1.59e-1	1.68e-1	1.70e-1	1.79e-1	1.90e-1	2.01e-1	2.15e-1	2.66e-1	3.08e-1	3.37e-1	3.97e-1	4.55e-1
3000	1.31e-1											
10000	8.58e-2											
30000	5.52e-2											
100000	2.60e-2											

$E_0$ (eV)	65°	70°	75°	80°	82.5°	89°
1000	5.37e-1	6.46e-1	7.79e-1	9.35e-1	9.83e-1	1.00e-0

Energy reflection coefficient of Ne backscattered from Ni  
 ne=25, na= 18

$E_0$ (eV)	0°	5°	10°	15°	20°	25°	30°	40°	45°	50°	55°	60°
18	1.08e-1											
19	1.09e-1											
20	1.09e-1											
22	1.10e-1											
25	1.10e-1											
25	1.10e-1											
27	1.10e-1											
27	1.10e-1											
28	1.09e-1											
30	1.08e-1											
35	1.07e-1											
40	1.05e-1											
50	9.94e-2											
70	9.03e-2											
100	7.97e-2											
150	6.87e-2											
200	6.15e-2											
300	5.35e-2											
500	4.48e-2											
1000	3.66e-2											
1000	3.35e-2	3.52e-2	3.61e-2	3.93e-2	4.26e-2	4.91e-2	5.58e-2	8.05e-2	1.02e-1	1.23e-1	1.62e-1	2.08e-1
3000	2.65e-2											
10000	1.71e-2											
30000	1.06e-2											
100000	4.54e-3											

$E_0$ (eV)	65°	70°	75°	80°	82.5°	89°
1000	2.78e-1	3.89e-1	5.57e-1	7.93e-1	9.02e-1	9.70e-1

## Ne → Ni

Average depth (mean range) in Å of Ne implanted in Ni  
 z1=10, m1= 20.18, z2=28, m2= 58.71, sbe=4.46 eV, rho=8.90 g/cm\*\*\*  
 ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: TESTVMCX  
 ne=25, na= 18

E <sub>0</sub> (eV)	0°	5°	10°	15°	20°	25°	30°	40°	45°	50°	55°	60°
18	1.73e+0											
19	1.80e+0											
20	1.87e+0											
22	1.99e+0											
25	2.16e+0											
25	2.21e+0											
27	2.26e+0											
27	2.31e+0											
28	2.36e+0											
30	2.41e+0											
35	2.64e+0											
40	2.84e+0											
50	3.22e+0											
70	3.87e+0											
100	4.69e+0											
150	5.90e+0											
200	6.93e+0											
300	8.76e+0											
500	1.19e+1											
1000	1.83e+1											
1000	1.94e+1	1.94e+1	1.91e+1	1.91e+1	1.88e+1	1.85e+1	1.81e+1	1.72e+1	1.70e+1	1.64e+1	1.59e+1	1.55e+1
3000	3.81e+1											
10000	9.50e+1											
30000	2.47e+2											
100000	7.48e+2											

E <sub>0</sub> (eV)	65°	70°	75°	80°	82.5°	89°
1000	1.50e+1	1.48e+1	1.41e+1	1.35e+1	1.40e+1	8.58e+0

# Ar → Ni

Sputtering yield of Ni by Ar  
 z1=18, m1= 39.95, z2=28, m2= 58.71, sbe=4.46 eV, rho=8.90 g/cm\*\*3  
 ef=0.20 (0.5) eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdeel=kdeel2=3, ipot=ipotr=1 (KrC)  
 program: TRS1C, TESTVMCX, TRVMC, TRSPV1C, IPP 9/82, newtrspd, trsp1cn  
 ne=42, na= 8

$E_0$ (eV)	0°	30°	45°	50°	55°	60°	75°	80°
18	3.92e-6							
19	1.45e-5							
20	2.02e-5		9.43e-4				6.41e-4	
22	7.61e-5							
25	1.51e-4		4.47e-3				2.17e-3	
27	3.44e-4							
30	5.39e-4		1.27e-2				4.37e-3	
32	9.48e-4							
35	1.54e-3							
40	3.43e-3		4.35e-2				1.13e-2	
50	1.30e-2		8.87e-2				2.05e-2	
50	1.16e-2							
60	2.92e-2							
70	5.21e-2		2.03e-1				4.34e-2	
70	5.35e-2							
100	1.49e-1		3.87e-1				8.27e-2	
100	1.60e-1							
150	3.52e-1							
200	4.93e-1		9.25e-1				2.53e-1	
200	5.32e-1							
290	7.65e-1	1.09e-0	1.32e-0	1.33e-0	1.29e-0	1.19e-0	4.30e-1	
300	7.78e-1	1.12e-0	1.35e-0	1.38e-0	1.35e-0	1.25e-0	4.49e-1	1.32e-1
300	8.51e-1							
500	1.19e-0		2.02e-0				8.71e-1	
500	1.29e-0							
700	1.61e-0							
1000	1.80e-0		3.15e-0				1.95e-0	
1000	1.90e-0							
1000	1.97e-0	2.70e-0	3.32e-0			3.62e-0	2.05e-0	
2000	2.49e-0							
3000	2.69e-0							
3000	2.70e-0							
10000	3.25e-0							
10000	3.13e-0							
20000	2.88e-0							
30000	3.06e-0							
30000	2.92e-0							
50000	2.81e-0							
100000	2.48e-0							
100000	2.24e-0							
200000	1.82e-0							
300000	1.64e-0							

# Ar → Ni

Sputtered energy of Ni by Ar  
 z1=18, m1= 39.95, z2=28, m2= 58.71, sbe=4.46 eV, rho=8.90 g/cm\*\*3  
 ef=0.20 (0.5) eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: TRS1C, TESTVMCX, TRVMC, TRSPV1C, newtrspd, trsplcn  
 ne=24, na= 8

$E_0$ (eV)	0°	30°	45°	50°	55°	60°	75°	80°
18	3.92e-6							
19	1.45e-5							
20	2.02e-5		9.43e-4				6.41e-4	
22	7.61e-5							
25	1.51e-4		4.47e-3				2.17e-3	
27	3.44e-4							
30	5.39e-4		1.27e-2				4.37e-3	
32	9.48e-4							
35	1.54e-3							
40	3.43e-3		4.35e-2				1.13e-2	
50	1.30e-2		8.87e-2				2.05e-2	
50	1.16e-2							
60	2.92e-2							
70	5.21e-2		2.03e-1				4.34e-2	
70	5.35e-2							
100	1.49e-1		3.87e-1				8.27e-2	
100	1.60e-1							
150	3.52e-1							
200	4.93e-1		9.25e-1				2.53e-1	
200	5.32e-1							
290	7.65e-1	1.09e-0	1.32e-0	1.33e-0	1.29e-0	1.19e-0	4.30e-1	
300	7.78e-1	1.12e-0	1.35e-0	1.38e-0	1.35e-0	1.25e-0	4.49e-1	1.32e-1
300	8.51e-1							
500	1.19e-0		2.02e-0				8.71e-1	
500	1.29e-0							
700	1.61e-0							
1000	1.80e-0		3.15e-0				1.95e-0	
1000	1.90e-0							
1000	1.97e-0	2.70e-0	3.32e-0			3.62e-0	2.05e-0	
2000	2.49e-0							
3000	2.69e-0							
3000	2.70e-0							
10000	3.25e-0							
10000	3.13e-0							
20000	2.88e-0							
30000	3.06e-0							
30000	2.92e-0							
50000	2.81e-0							
100000	2.48e-0							
100000	2.24e-0							
200000	1.82e-0							
300000	1.64e-0							

# Ar → Ni

Particle reflection coefficient of Ar backscattered from Ni  
 z1=18, m1= 39.95, z2=28, m2= 58.71, sbe=4.46 eV, rho=8.90 g/cm\*\*3  
 ef=0.20 (0.5) eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdeel=kdee2=3, ipot=ipotr=1 (KrC)  
 program: TRS1C, TESTVMCX, TRVMC, TRSPV1C, newtrspd, trsplcn  
 ne=24, na= 8

E <sub>0</sub> (eV)	0°	30°	45°	50°	55°	60°	75°	80°
18	2.61e-1							
19	2.55e-1							
20	2.51e-1		6.15e-1				9.85e-1	
22	2.43e-1							
25	2.34e-1		6.07e-1				9.85e-1	
27	2.29e-1							
30	2.24e-1		5.97e-1				9.85e-1	
32	2.21e-1							
35	2.18e-1							
40	2.12e-1		5.82e-1				9.84e-1	
50	2.05e-1		5.68e-1				9.83e-1	
60	2.00e-1							
70	1.97e-1		5.41e-1				9.81e-1	
100	1.83e-1		5.02e-1				9.77e-1	
200	1.52e-1		4.20e-1				9.59e-1	
290	1.35e-1	2.23e-1	3.64e-1	4.35e-1	5.27e-1	6.17e-1	9.42e-1	
300	1.37e-1	2.23e-1	3.62e-1	4.31e-1	5.16e-1	6.09e-1	9.38e-1	9.92e-1
500	1.13e-1		3.02e-1				8.95e-1	
1000	8.44e-2		2.41e-1				7.97e-1	
1000	7.71e-2	1.31e-1	2.21e-1			4.11e-1	8.00e-1	
3000	5.77e-2							
10000	3.65e-2							
30000	2.43e-2							
100000	1.01e-2							

Energy reflection coefficient of Ar backscattered from Ni  
 ne=24, na= 8

E <sub>0</sub> (eV)	0°	30°	45°	50°	55°	60°	75°	80°
18	1.09e-2							
19	1.12e-2							
20	1.14e-2		1.49e-1				6.78e-1	
22	1.19e-2						6.91e-1	
25	1.25e-2		1.53e-1					
27	1.27e-2							
30	1.31e-2		1.56e-1				6.98e-1	
32	1.34e-2							
35	1.37e-2							
40	1.40e-2		1.59e-1				7.09e-1	
50	1.43e-2		1.59e-1				7.15e-1	
60	1.44e-2							
70	1.42e-2		1.53e-1				7.20e-1	
100	1.34e-2		1.42e-1				7.20e-1	
200	1.13e-2		1.14e-1				6.99e-1	
290	9.74e-3	3.38e-2	9.44e-2	1.34e-1	1.95e-1	2.69e-1	6.73e-1	
300	9.82e-3	3.34e-2	9.31e-2	1.31e-1	1.87e-1	2.62e-1	6.74e-1	8.49e-1
500	8.48e-3		7.14e-2				6.26e-1	
1000	6.22e-3		5.29e-2				5.26e-1	
1000	5.79e-3	1.84e-2	4.94e-2			1.52e-1	5.28e-1	
3000	4.27e-3							
10000	3.04e-3							
30000	2.11e-3							
100000	8.23e-4							

Average depth (mean range) in Å of Ar implanted in Ni  
 ne=24, na= 8

E <sub>0</sub> (eV)	0°	30°	45°	50°	55°	60°	75°	80°
18	1.11e+0							
19	1.15e+0							
20	1.19e+0		1.02e+0				5.29e-1	
22	1.27e+0						6.05e-1	
25	1.39e+0		1.20e+0					
27	1.47e+0							
30	1.58e+0		1.36e+0				6.93e-1	
32	1.65e+0							
35	1.76e+0							
40	1.93e+0		1.66e+0				8.80e-1	
50	2.24e+0		1.93e+0				1.03e+0	
60	2.54e+0							
70	2.80e+0		2.40e+0				1.36e+0	
100	3.51e+0		3.00e+0				1.81e+0	
200	5.30e+0		4.50e+0				3.01e+0	
290	6.57e+0	6.04e+0	5.47e+0	5.30e+0	5.07e+0	4.83e+0	3.86e+0	
300	6.69e+0	6.18e+0	5.57e+0	5.39e+0	5.16e+0	4.91e+0	3.96e+0	5.38e+0
500	8.93e+0		7.38e+0				8.12e+0	
1000	1.33e+1		1.08e+1				9.39e+0	
1000	1.20e+1		1.09e+1					
3000	2.63e+1		1.21e+1					
10000	6.03e+1							
30000	1.42e+2							
100000	4.23e+2							

# Ar → Ni

Sputtering yield of Ni by Ar  
 $z1=18$ ,  $m1=39.95$ ,  $z2=28$ ,  $m2=58.71$ ,  $sbe=4.46$  eV,  $\rho=8.90$  g/cm $^{**3}$   
 $ef=0.20$ ,  $esb=0.00$ ,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=3$  (ZBL)  
program: TRVMC  
nem = 7, na = 7

$E_0$ (eV)	0°	30°	45°	50°	55°	60°	75°
50	1.10e-2		6.83e-2				
70	4.61e-2		1.62e-1				
100	1.38e-1		3.31e-1				
200	5.06e-1		8.55e-1				
290	7.80e-1	1.06e-0	1.26e-0	1.25e-0	1.22e-0	1.10e-0	3.88e-1
500	1.32e-0		1.99e-0				
1000	2.04e-0		3.21e-0				

Sputtered energy of Ni by Ar  
nem = 7, na = 7

$E_0$ (eV)	0°	30°	45°	50°	55°	60°	75°
50	7.04e-4		9.70e-3				
70	2.95e-3		2.20e-2				
100	7.95e-3		4.07e-2				
200	2.13e-2		7.90e-2				
290	2.57e-2	5.47e-2	9.43e-2	1.06e-1	1.13e-1	1.16e-1	4.94e-2
500	3.02e-2		1.03e-1				
1000	2.97e-2		1.00e-1				

Particle reflection coefficient of Ar backscattered from Ni  
 $z1=18$ ,  $m1=39.95$ ,  $z2=28$ ,  $m2=58.71$ ,  $sbe=4.46$  eV,  $\rho=8.90$  g/cm $^{**3}$   
 $ef=0.20$ ,  $esb=0.00$ ,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=3$  (ZBL)  
program: TRVMC  
nem = 7, na = 7

$E_0$ (eV)	0°	30°	45°	50°	55°	60°	75°
50	2.44e-1		5.82e-1				
70	2.19e-1		5.61e-1				
100	2.04e-1		5.20e-1				
200	1.72e-1		4.33e-1				
290	1.39e-1	2.32e-1	3.69e-1	4.48e-1	5.33e-1	6.35e-1	9.44e-1
500	1.09e-1		3.04e-1				
1000	8.17e-2		2.27e-1				

Energy reflection coefficient of Ar backscattered from Ni  
nem = 7, na = 7

$E_0$ (eV)	0°	30°	45°	50°	55°	60°	75°
50	1.29e-2		1.47e-1				
70	1.32e-2		1.48e-1				
100	1.35e-2		1.39e-1				
200	1.22e-2		1.15e-1				
290	9.96e-3	3.52e-2	9.26e-2	1.35e-1	1.90e-1	2.69e-1	6.68e-1
500	8.53e-3		7.27e-2				
1000	6.56e-3		5.15e-2				

Average depth (mean range) in Å of Ar implanted in Ni  
nem = 7, na = 7

$E_0$ (eV)	0°	30°	45°	50°	55°	60°	75°
50	1.58e+0		1.33e+0				
70	2.08e+0		1.73e+0				
100	2.71e+0		2.27e+0				
200	4.36e+0		3.64e+0				
290	5.55e+0	5.12e+0	4.49e+0	4.42e+0	4.13e+0	3.92e+0	3.09e+0
500	7.76e+0		6.30e+0				
1000	1.19e+1		9.62e+0				

## Ni → Ni

Sputtering yield of Ni by Ni  
 $z1=28$ ,  $m1=58.71$ ,  $z2=28$ ,  $m2=58.71$ ,  $sbe=4.46$  eV,  $\rho=8.90$  g/cm $^{**3}$   
 $ef=4.41$  eV,  $esb=4.46$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: TESTVMCX, TRSPV1C, TRSPV1CS, IPP 9/82  
 $ne=26$ ,  $na=13$

$E_0$ (eV)	$0^\circ$	$15^\circ$	$30^\circ$	$45^\circ$	$50^\circ$	$55^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$	$80^\circ$	$85^\circ$	$87^\circ$
14											1.20e-3		
15	2.49e-6										2.93e-3		
16											8.86e-3		
18	1.51e-5										2.00e-2		
20	3.72e-5										3.28e-2		
25	1.79e-4										6.01e-2		
30	5.33e-4											1.13e-1	
40	2.63e-3										1.56e-1		
50	8.72e-3										1.98e-1		
60											2.90e-1		
70	3.63e-2										4.04e-1		
80											1.07e-0		
100	1.08e-1										2.18e-0		
100	1.24e-1		3.30e-1	4.80e-1	5.00e-1	4.90e-1	4.80e-1	4.20e-1	3.80e-1		2.30e-0		
200	4.08e-1										4.24e-0		
500	1.16e-0										5.19e-0		
1000	1.89e-0										8.72e-0		
1000	2.03e-0		2.90e-0	3.70e-0	3.90e-0	4.00e-0	3.90e-0	3.80e-0	3.10e-0		1.29e+1		
2000	2.81e-0										2.02e+1		
2500	2.90e-0	3.22e-0	4.10e-0	5.47e-0		6.38e-0	6.66e-0	6.70e-0			2.41e+1		
3000	3.06e-0												
5000	3.63e-0												
10000	4.11e-0												
30000	4.40e-0												
100000	4.20e-0												
300000	3.05e-0												

Sputtered energy of Ni by Ni  
program: TESTVMCX, TRSPV1C, TRSPV1CS  
 $ne=23$ ,  $na=9$

$E_0$ (eV)	$0^\circ$	$15^\circ$	$30^\circ$	$45^\circ$	$55^\circ$	$60^\circ$	$65^\circ$	$75^\circ$	$85^\circ$
14								4.09e-4	
15	9.94e-6							6.05e-4	
16									
18	4.18e-6							1.92e-3	
20	4.61e-6							4.36e-3	
25	1.17e-5							7.41e-3	
30	2.92e-5							1.33e-2	
40	1.53e-4								
50	4.80e-4							2.35e-2	
60									
70	1.86e-3							3.07e-2	
80								3.65e-2	
100	4.81e-3							5.72e-2	
200	1.31e-2							9.95e-2	
500	2.26e-2							1.38e-1	
1000	2.42e-2							1.75e-1	
2000								1.81e-1	
2500	2.14e-2	2.73e-2	4.80e-2	9.03e-2	1.34e-1	1.58e-1	1.80e-1	1.31e-2	
3000	2.10e-2								
5000									
10000	1.43e-2							1.93e-1	
30000	8.56e-3							1.87e-1	
100000	4.24e-3							1.53e-1	

## Ni → Ni

Particle reflection coefficient of Ni backscattered from Ni  
 z1=28, m1= 58.71, z2=28, m2= 58.71, sbe=4.46 eV, rho=8.90 g/cm\*\*3  
 ef=4.41 eV, esb=4.46 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: TESTVMCX, TRSPV1C, TRSPV1CS  
 ne=23, na= 9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	60°	65°	75°	85°
14								1.42e-2	
15	1.45e-7							3.16e-2	
16									
18	7.47e-7							8.73e-2	
20	5.50e-7							1.87e-1	
25								2.99e-1	
30	2.75e-6							5.02e-1	
40	1.24e-4								
50	5.72e-4								
60								7.39e-1	
70	2.69e-3								
80								8.31e-1	
100	6.13e-3							8.65e-1	
200	1.39e-2							8.98e-1	
500	2.16e-2							8.59e-1	
1000	2.15e-2							7.81e-1	
2000								6.75e-1	
2500	1.90e-2	2.62e-2	5.30e-2	1.20e-1	2.09e-1	2.71e-1	3.62e-1	6.32e-1	9.93e-1
3000	1.76e-2								
5000								5.24e-1	
10000	1.23e-2							4.37e-1	
30000	8.27e-3							3.82e-1	
100000	4.00e-3							3.16e-1	

Energy reflection coefficient of Ni backscattered from Ni  
 ne=23, na= 9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	60°	65°	75°	85°
14								3.87e-3	
15	6.08e-6							9.38e-3	
16									
18	1.63e-6							2.85e-2	
20	1.62e-6							6.63e-2	
25								1.13e-1	
30	1.50e-7							2.08e-1	
40	7.34e-6								
50	4.27e-5								
60								3.50e-1	
70	1.89e-4								
80								4.34e-1	
100	3.98e-4							4.79e-1	
200	7.14e-4							5.56e-1	
500	8.74e-4							5.48e-1	
1000	8.32e-4							4.84e-1	
2000								3.88e-1	
2500	7.22e-4	1.39e-3	4.85e-3	1.88e-2	4.85e-2	7.60e-2	1.26e-1	3.55e-1	9.12e-1
3000	6.28e-4								
5000								2.64e-1	
10000	4.57e-4							2.09e-1	
30000	4.46e-4							1.66e-1	
100000	1.86e-4							1.33e-1	

Average depth (mean range) in Å of Ni implanted in Ni  
 ne=23, na= 9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	60°	65°	75°	85°
15	4.63e-1								
18	6.47e-1								
20	7.44e-1								
25	9.41e-1								
30	1.12e+0								
40	1.47e+0							2.40e-2	
50	1.76e+0							2.77e-1	
60									
70	2.27e+0								
80								5.74e-1	
100	2.91e+0							8.09e-1	
200	4.52e+0							1.79e+0	
500	7.84e+0							3.83e+0	
1000	1.16e+1							6.00e+0	
2000								9.11e+0	
2500	1.99e+1	1.94e+1	1.77e+1	1.54e+1	1.37e+1	1.29e+1	1.21e+1	1.04e+1	8.13e+0
3000	2.24e+1								
5000								1.59e+1	
10000	4.79e+1							2.41e+1	
30000	1.05e+2							5.00e+1	
100000	2.85e+2							1.26e+2	

## Kr → Ni

Sputtering yield of Ni by Kr  
 $z1=36$ ,  $m1 = 83.80$ ,  $z2=28$ ,  $m2 = 58.71$ ,  $sbe=4.46$  eV,  $\rho=8.90$  g/cm $^{**3}$   
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: TESTVMCX, IPP 9/82  
 $ne=20$ ,  $na= 2$

$E_0$ (eV)	$0^\circ$	$75^\circ$
20		8.09e-4
22	5.93e-6	
25	2.19e-5	
30	1.08e-4	6.12e-3
40	8.67e-4	1.54e-2
50	3.02e-3	2.77e-2
70	1.65e-2	5.96e-2
100	6.46e-2	1.14e-1
100	6.36e-2	
150	1.80e-1	
200	3.07e-1	3.32e-1
300	6.34e-1	
500	1.01e-0	1.07e-0
1000	1.93e-0	2.23e-0
2000		4.49e-0
3000	3.26e-0	
5000		9.48e-0
10000	4.43e-0	1.50e+1
30000	5.06e-0	2.36e+1
100000	4.99e-0	

Sputtered energy of Ni by Kr  
program: TESTVMCX  
 $ne=16$ ,  $na= 2$

$E_0$ (eV)	$0^\circ$	$75^\circ$
20		1.53e-4
22	3.32e-6	
25	1.48e-6	
30	4.16e-6	1.24e-3
40	3.88e-5	3.05e-3
50	1.28e-4	5.44e-3
70	6.78e-4	1.08e-2
100	2.41e-3	1.87e-2
150	5.81e-3	
200	8.96e-3	4.36e-2
500	1.81e-2	9.66e-2
1000		1.42e-1
2000		1.89e-1
5000		2.16e-1
10000		2.16e-1
30000		1.83e-1

## Kr → Ni

Particle reflection coefficient of Kr backscattered from Ni  
 z1=36, m1= 83.80, z2=28, m2= 58.71, sbe=4.46 eV, rho=8.90 g/cm\*\*\*3  
 ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: TESTVMCX  
 ne=16, na= 2

E <sub>0</sub> (eV)	0°	75°
20		9.77e-1
22	1.86e-1	
25	1.60e-1	
30	1.28e-1	9.78e-1
40	8.98e-2	9.77e-1
50	6.78e-2	9.76e-1
70	4.42e-2	9.73e-1
100	2.79e-2	9.69e-1
150	1.56e-2	
200	1.05e-2	9.50e-1
500	5.00e-3	8.91e-1
1000		8.07e-1
2000		6.83e-1
5000		5.29e-1
10000		4.31e-1
30000		3.57e-1

Energy reflection coefficient of Kr backscattered from Ni  
 ne=16, na= 2

E <sub>0</sub> (eV)	0°	75°
20		5.58e-1
22	6.62e-5	
25	7.65e-5	
30	1.04e-4	5.82e-1
40	1.33e-4	5.94e-1
50	1.45e-4	6.02e-1
70	1.58e-4	6.11e-1
100	1.50e-4	6.14e-1
150	1.28e-4	
200	1.09e-4	6.02e-1
500	7.86e-5	5.46e-1
1000		4.70e-1
2000		3.66e-1
5000		2.50e-1
10000		1.75e-1
30000		1.34e-1

Average depth (mean range) in Å of Kr implanted in Ni  
 ne=16, na= 2

E <sub>0</sub> (eV)	0°	75°
20		4.33e-1
22	1.17e+0	
25	1.27e+0	
30	1.45e+0	5.39e-1
40	1.79e+0	6.37e-1
50	2.08e+0	7.38e-1
70	2.60e+0	9.34e-1
100	3.27e+0	1.23e+0
150	4.17e+0	
200	4.94e+0	2.03e+0
500	8.26e+0	3.80e+0
1000		5.75e+0
2000		8.54e+0
5000		1.39e+1
10000		2.11e+1
30000		4.14e+1

## Xe → Ni

Sputtering yield of Ni by Xe  
 $z1=54$ ,  $m1=131.30$ ,  $z2=28$ ,  $m2=58.71$ ,  $sbe=4.46$  eV,  $\rho=8.90$  g/cm<sup>3</sup>  
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: TESTVMCX, IPP 9/82  
ne=38, na= 2

E <sub>0</sub> (eV)	0°	60°
15	7.78e-6	
18	1.52e-4	
20	5.87e-4	
25	6.23e-6	4.38e-3
30	3.83e-5	1.34e-2
40	3.53e-4	4.56e-2
50	1.36e-3	9.03e-2
70	8.28e-3	2.00e-1
70	6.40e-3	
100	3.66e-2	3.90e-1
100	3.47e-2	
150	1.22e-1	
200	2.19e-1	9.61e-1
200	2.39e-1	
300	4.25e-1	
300	4.88e-1	
500	8.13e-1	2.34e-0
500	9.68e-1	
1000	1.60e-0	4.16e-0
1000	1.77e-0	
1500	2.40e-0	
2000	2.60e-0	6.81e-0
2000	2.82e-0	
3000	3.44e-0	
5000	3.98e-0	1.17e+1
5000	4.18e-0	
7000	4.78e-0	
10000	5.20e-0	1.55e+1
10000	4.95e-0	
15000	5.67e-0	
20000	5.98e-0	1.94e+1
20000	5.90e-0	
30000	6.53e-0	
50000	7.06e-0	2.38e+1
50000	6.63e-0	
100000	7.18e-0	2.41e+1
100000	6.76e-0	
200000	6.79e-0	

Sputtered energy of Ni by Xe  
program: TESTVMCX  
ne=19, na= 2

E <sub>0</sub> (eV)	0°	60°
15	7.19e-6	
18	1.83e-5	
20	7.12e-5	
25	1.92e-6	7.52e-4
30	3.64e-6	1.86e-3
40	1.38e-5	6.73e-3
50	4.75e-5	1.34e-2
70	2.95e-4	2.92e-2
100	1.24e-3	5.36e-2
200	5.76e-3	1.04e-1
300	8.98e-3	
500	1.38e-2	1.58e-1
1000	1.85e-2	1.79e-1
2000	1.96e-2	1.77e-1
5000	1.76e-2	1.59e-1
10000	1.57e-2	1.45e-1
20000	1.25e-2	1.24e-1
50000	9.31e-2	1.03e-1
100000	6.41e-2	8.22e-2

## Xe → Ni

Particle reflection coefficient of Xe backscattered from Ni  
 z1=54, m1=131.30, z2=28, m2= 58.71, sbe=4.46 eV, rho=8.90 g/cm\*\*3  
 ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: TESTVMCX  
 ne=18, na= 2

E <sub>0</sub> (eV)	0°	60°
15		6.67e-1
18		6.60e-1
20		6.56e-1
25	1.20e-1	6.48e-1
30	8.73e-2	6.38e-1
40	4.86e-2	6.31e-1
50	2.87e-2	6.18e-1
70	1.17e-2	5.99e-1
100	3.34e-3	5.70e-1
200	1.00e-4	4.98e-1
500		3.67e-1
1000		2.63e-1
2000		2.04e-1
5000		1.31e-1
10000		1.10e-1
20000		8.46e-2
50000		7.20e-2
100000		4.96e-3

Energy reflection coefficient of Xe backscattered from Ni  
 ne=18, na= 2

E <sub>0</sub> (eV)	0°	60°
15		1.18e-1
18		1.22e-1
20		1.25e-1
25	1.43e-6	1.29e-1
30	4.90e-7	1.33e-1
40	1.94e-6	1.39e-1
50	1.67e-6	1.39e-1
70	1.52e-6	1.39e-1
100	1.03e-6	1.36e-1
200	1.16e-6	1.19e-1
500		8.11e-2
1000		5.13e-2
2000		3.33e-2
5000		1.68e-2
10000		1.39e-2
20000		1.03e-2
50000		8.15e-3
100000		5.77e-3

Average depth (mean range) in Å of Xe implanted in Ni  
 ne=19, na= 2

E <sub>0</sub> (eV)	0°	60°
15		5.83e-1
18		6.44e-1
20		6.84e-1
25	1.47e+0	7.79e-1
30	1.69e+0	8.71e-1
40	2.10e+0	1.05e+0
50	2.46e+0	1.23e+0
70	3.10e+0	1.54e+0
100	3.91e+0	1.97e+0
200	5.93e+0	3.08e+0
300	7.37e+0	
500	9.64e+0	5.18e+0
1000	1.36e+1	7.44e+0
2000	1.92e+1	1.05e+1
5000	3.08e+1	1.67e+1
10000	4.50e+1	2.46e+1
20000	6.65e+1	3.65e+1
50000	1.19e+2	6.32e+1
100000	1.93e+2	1.02e+2

## H → Cu

Sputtering yield of Cu by H  
 $z1 = 1$ ,  $m1 = 1.01$ ,  $z2 = 29$ ,  $m2 = 63.54$ ,  $sbe = 3.52$  eV,  $\rho = 8.95$  g/cm<sup>3</sup>  
 $ef = 0.98$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = 3, 4$ ,  $kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: TESTVMCX, IPP 9/82  
 $n_e = 16$ ,  $na = 10$

$E_0$ (eV)	0°	30°	50°	70°	78°	80°	85°	87°	88°	89°
80	1.57e-4									
100	1.01e-3									
150	4.82e-3									
200	8.89e-3									
300	1.39e-2									
500	2.10e-2									
1000	1.95e-2									
2000	1.80e-2									
5000	1.40e-2									
10000	9.68e-3									
20000	3.20e-3									
26700	5.10e-3									
40000	2.80e-3									
50000	3.01e-3	3.87e-3	7.02e-3	2.27e-2	3.87e-2	6.02e-2	1.22e-1	1.75e-1	1.97e-1	9.74e-2
80000	2.30e-3									
100000	2.20e-3									

Sputtered energy of Cu by H  
program: TESTVMCX  
 $n_e = 9$ ,  $na = 6$

$E_0$ (eV)	0°	80°	85°	87°	88°	89°
80	9.12e-7					
100	8.93e-6					
150	5.37e-5					
200	1.03e-4					
300	1.55e-4					
1000	1.34e-4					
2000	7.86e-5					
10000	9.70e-6	3.58e-5	7.65e-5	1.13e-4	1.35e-4	8.36e-5
50000						

Particle reflection coefficient of H backscattered from Cu  
 $z1 = 1$ ,  $m1 = 1.01$ ,  $z2 = 29$ ,  $m2 = 63.54$ ,  $sbe = 3.52$  eV,  $\rho = 8.95$  g/cm<sup>3</sup>  
 $ef = 0.98$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = 3, 4$ ,  $kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: TESTVMCX  
 $n_e = 9$ ,  $na = 6$

$E_0$ (eV)	0°	80°	85°	87°	88°	89°
80	5.62e-1					
100	5.46e-1					
150	5.14e-1					
200	4.94e-1					
300	4.62e-1					
1000	3.48e-1					
2000	2.74e-1					
10000	9.79e-2	4.13e-1	5.78e-1	6.71e-1	7.45e-1	9.17e-1
50000						

Energy reflection coefficient of H backscattered from Cu  
 $n_e = 9$ ,  $na = 6$

$E_0$ (eV)	0°	80°	85°	87°	88°	89°
80	3.41e-1					
100	3.26e-1					
150	2.98e-1					
200	2.80e-1					
300	2.54e-1					
1000	1.69e-1					
2000	1.20e-1					
10000	3.14e-2	1.62e-1	3.08e-1	4.26e-1	5.37e-1	8.40e-1
50000						

Average depth (mean range) in Å of H implanted in Cu  
 $n_e = 9$ ,  $na = 6$

$E_0$ (eV)	0°	80°	85°	87°	88°	89°
80	2.58e+1					
100	2.94e+1					
150	3.75e+1					
200	4.47e+1					
300	5.76e+1					
1000	1.29e+2					
2000	2.15e+2					
10000	7.61e+2	1.06e+3	9.98e+2	9.85e+2	9.79e+2	1.01e+3
50000						

# D → Cu

Sputtering yield of Cu by D  
 z1= 1, m1= 2.01, z2=29, m2= 63.54, sb e=3.52 eV, rho=8.95 g/cm\*\*3  
 ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx, IPP 9/82, newtrim  
 ne=28, na=11

$E_0$ (eV)	0°	30°	45°	60°	65°	70°	75°	77.5°	80°	85°	87°
37	2.80e-5										
40	1.43e-4		1.10e-4								
42	2.89e-4										
45	5.69e-4		4.68e-4								
47	8.71e-4		7.56e-4								
50	1.47e-3		1.26e-3	7.31e-4	5.60e-4	3.10e-4	1.31e-4		3.85e-5		
53					8.95e-4						
55			2.27e-3								
60	3.56e-3										
70	6.24e-3						1.34e-3				
75	8.80e-3								6.39e-4		
80	9.39e-3										
100	1.64e-2	1.81e-2	1.84e-2	1.71e-2	1.49e-2			8.95e-3		3.60e-3	
120	2.17e-2										
150	2.59e-2										
200	3.50e-2							6.57e-2			
250	4.06e-2										
300	4.34e-2	5.52e-2	6.39e-2	9.37e-2	1.05e-1			1.24e-1	1.09e-1	8.55e-2	
500	4.62e-2										
1000	5.39e-2	6.93e-2	9.19e-2	1.44e-1	1.75e-1			2.50e-1		2.58e-1	1.00e-1
2000	5.16e-2				1.85e-1						
2000	4.83e-2										
3000	3.93e-2		8.51e-2	1.39e-1	1.62e-1			2.70e-1		3.34e-1	
10000	2.47e-2		5.45e-2		1.13e-1			1.92e-1		2.85e-1	4.16e-1
30000	9.31e-3										
53000	6.10e-3										
80000	6.20e-3										
160000	2.90e-3										

Sputtered energy of Cu by D  
 program: testvmcx, newtrim  
 ne=15, na= 8

$E_0$ (eV)	0°	30°	45°	60°	65°	75°	77.5°	80°
40			9.90e-7					
45			6.20e-6					
47			1.09e-5					
50								
53								
55			4.17e-5					
70								
75								
100		4.19e-4						
200	7.16e-4			4.13e-4				
300	7.60e-4	9.23e-4		1.74e-3				
500	6.15e-4							
1000	4.75e-4		8.33e-4	1.45e-3				
2000	2.63e-4				1.24e-3			
3000	1.69e-4		3.78e-4	7.05e-4	1.47e-3			

# D → Cu

Particle reflection coefficient of D backscattered from Cu  
 $z1 = 1$ ,  $m1 = 2.01$ ,  $z2 = 29$ ,  $m2 = 63.54$ ,  $sbe = 3.52$  eV,  $\rho = 8.95$  g/cm\*\*3  
 $ef = 0.98$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: testvmcx, newtrim  
ne=15, na= 8

$E_0$ (eV)	0°	30°	45°	60°	65°	75°	77.5°	80°
40			7.09e-1					
45			6.99e-1					
47			6.95e-1					
50				7.98e-1				
53					8.40e-1			
55			6.81e-1					
70						9.48e-1		
75						9.32e-1		
100							9.83e-1	
200	4.87e-1	5.74e-1		7.35e-1				
300	4.53e-1	5.00e-1		6.49e-1				
500	4.21e-1							
1000	3.59e-1		4.75e-1	5.65e-1				
2000	2.91e-1				5.49e-1	7.01e-1		
3000	2.45e-1		3.67e-1	4.71e-1		6.19e-1		

Energy reflection coefficient of D backscattered from Cu  
ne=15, na= 8

$E_0$ (eV)	0°	30°	45°	60°	65°	75°	77.5°	80°
40			5.09e-1					
45			4.97e-1					
47			3.92e-1					
50				6.32e-1				
53					6.22e-1			
55			4.70e-1					
70						8.67e-1		
75						8.43e-1		
100				5.50e-1				
200	2.76e-1	3.55e-1						
300	2.50e-1	2.90e-1		4.48e-1				
500	2.25e-1							
1000	1.81e-1		2.72e-1	3.60e-1				
2000	1.34e-1				3.45e-1	5.24e-1		
3000	1.08e-1		1.85e-1	2.67e-1		4.21e-1		

Average depth (mean range) in Å of D implanted in Cu  
ne=15, na= 8

$E_0$ (eV)	0°	30°	45°	60°	65°	75°	77.5°	80°
40			1.60e+1					
45			1.71e+1					
47			1.61e+1					
50				1.79e+1				
53					1.80e+1			
55			1.89e+1					
70						1.75e+1		
75						2.14e+1		
100				2.71e+1				
200	4.47e+1	2.79e+1						
300	5.84e+1	5.69e+1		5.45e+1				
500	8.33e+1							
1000	1.39e+2		1.31e+2	1.24e+2				
2000	2.37e+2				2.03e+2	1.20e+2		
3000	3.28e+2		2.99e+2	2.78e+2		2.70e+2		

D on Cu, Maxwellian velocity distribution, sheath potential 3 kT  
 $z1 = 1$ ,  $m1 = 2.01$ ,  $z2 = 29$ ,  $m2 = 63.54$ ,  $sbe = 3.52$  eV,  $\rho = 8.95$  g/cm\*\*3  
 $ef = 0.98$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: testvmcx  
ne= 4

$kT$ (eV)	$Y$	$Y_E$	$E_{sp}$	$R_N$	$R_E$	$E_b$	range
15	8.64e-3	2.37e-4	2.06e+0	5.85e-1	3.67e-1	4.71e+1	2.35e+1
20	1.64e-2	4.25e-4	2.59e+0	5.65e-1	3.49e-1	6.17e+1	2.82e+1
25	2.35e-2	5.78e-4	3.08e+0	5.50e-1	3.35e-1	7.60e+1	3.23e+1
1000	4.55e-2	1.39e-4	1.52e+1	2.33e-1	9.75e-2	2.10e+3	4.79e+2

## He → Cu

Sputtering yield of Cu by He

```

z1= 2, m1= 4.00, z2=29, m2= 63.54, sb e=3.52 eV, rho= 8.95 g/cm**3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program: trspvrmcx, IPP 9/82
ne=15, na= 1

```

E <sub>0</sub> (eV)	0°
50	2.04e-2
50	1.93e-2
70	4.58e-2
100	7.86e-2
100	7.77e-2
200	1.33e-1
300	1.60e-1
500	1.90e-1
500	1.91e-1
1000	2.17e-1
1000	2.13e-1
2000	2.16e-1
4000	1.92e-1
5000	1.74e-1
10000	1.31e-1

Sputtered energy of Cu by He

```
program: trspvrmcx
```

```
ne=14, na= 1
```

E <sub>0</sub> (eV)	0°
50	8.02e-4
50	7.59e-4
70	1.84e-3
100	2.87e-3
100	2.92e-3
200	3.84e-3
300	3.88e-3
500	3.49e-3
500	3.53e-3
1000	2.48e-3
2000	1.65e-3
4000	8.52e-4
5000	5.99e-4
10000	2.96e-4

## He → Cu

Particle reflection coefficient of He backscattered from Cu  
 z1= 2, m1= 4.00, z2=29, m2= 63.54, sbe=3.52 eV, rho= 8.95 g/cm\*\*3  
 ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trspvmcx  
 ne=14, na= 1

$E_0$ (eV)	0°
50	5.62e-1
50	5.63e-1
70	5.29e-1
100	5.00e-1
200	4.54e-1
300	4.20e-1
500	3.91e-1
500	3.93e-1
1000	3.49e-1
1000	3.50e-1
2000	2.92e-1
4000	2.33e-1
5000	2.20e-1
10000	1.50e-1

Energy reflection coefficient of He backscattered from Cu  
 ne=13, na= 1

$E_0$ (eV)	0°
50	3.17e-1
70	2.89e-1
100	2.68e-1
200	2.33e-1
300	2.11e-1
500	1.90e-1
500	1.91e-1
1000	1.64e-1
1000	1.66e-1
2000	1.32e-1
4000	9.66e-2
5000	8.78e-2
10000	5.45e-2

Average depth (mean range) in Å of He implanted in Cu  
 ne=14, na= 1

$E_0$ (eV)	0°
50	1.08e+1
70	1.31e+1
100	1.61e+1
100	1.60e+1
200	2.47e+1
300	3.21e+1
500	4.55e+1
500	4.58e+1
1000	7.33e+1
1000	7.34e+1
2000	1.25e+2
4000	2.15e+2
5000	2.63e+2
10000	4.70e+2

## Ne → Cu

Sputtering yield of Cu by Ne

$z1=10, m1= 20.18, z2=29, m2= 63.54, sbe=3.52 \text{ eV}, rho= 8.95 \text{ g/cm}^{**3}$   
 $ef=0.50 \text{ eV}, esb=0.00 \text{ eV}, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1$  (KrC)  
 program: testvmcx  
 $n_{\text{e}} = 7, n_{\text{a}} = 1$

$E_0(\text{eV})$	$0^\circ$
50	8.36e-2
100	3.33e-1
200	7.10e-1
500	1.30e-0
1000	1.72e-0
2000	2.08e-0
4000	2.26e-0

Sputtered energy of Cu by Ne

$n_{\text{e}} = 7, n_{\text{a}} = 1$

$E_0(\text{eV})$	$0^\circ$
50	6.64e-3
100	1.98e-2
200	2.80e-2
500	2.85e-2
1000	2.44e-2
2000	1.93e-2
4000	1.36e-2

Particle reflection coefficient of Ne backscattered from Cu

$z1=10, m1= 20.18, z2=29, m2= 63.54, sbe=3.52 \text{ eV}, rho= 8.95 \text{ g/cm}^{**3}$   
 $ef=0.50 \text{ eV}, esb=0.00 \text{ eV}, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1$  (KrC)  
 program: testvmcx  
 $n_{\text{e}} = 7, n_{\text{a}} = 1$

$E_0(\text{eV})$	$0^\circ$
50	4.65e-1
100	3.67e-1
200	2.91e-1
500	2.28e-1
1000	1.86e-1
2000	1.60e-1
4000	1.32e-1

Energy reflection coefficient of Ne backscattered from Cu

$n_{\text{e}} = 7, n_{\text{a}} = 1$

$E_0(\text{eV})$	$0^\circ$
50	1.13e-1
100	8.89e-2
200	6.90e-2
500	5.13e-2
1000	4.13e-2
2000	3.40e-2
4000	2.89e-2

Average depth (mean range) in Å of Ne implanted in Cu

$n_{\text{e}} = 7, n_{\text{a}} = 1$

$E_0(\text{eV})$	$0^\circ$
50	3.58e+0
100	5.17e+0
200	7.57e+0
500	1.30e+1
1000	1.98e+1
2000	3.14e+1
4000	5.07e+1

# Ar → Cu

Sputtering yield of Cu by Ar  
 z1=18, m1= 39.95, z2=29, m2= 63.54, sbe=3.52 eV, rho= 8.95 g/cm\*\*\*  
 ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx, trspvmcx, trspv1cs  
 ne=20, na=12

E <sub>0</sub> (eV)	0°	15°	30°	45°	50°	55°	60°	65°	70°	75°	80°	85°
10								4.63e-6			1.14e-6	
11					3.65e-6			1.06e-4			1.45e-5	
12			3.16e-6	2.10e-5								
13		2.49e-6										
14	1.84e-6	9.58e-6	5.61e-5	2.17e-4		4.71e-4	5.66e-4	6.10e-4	4.65e-4	2.56e-4	5.73e-5	
15						9.79e-4	1.20e-3	1.10e-3	8.64e-4			
16	2.12e-5	6.31e-5	2.41e-4	9.23e-4		1.60e-3	1.86e-3	1.78e-3	1.29e-3	6.58e-4	1.43e-4	
18	7.78e-5	1.86e-4	6.09e-4	2.34e-3		3.96e-3		3.99e-3				
20	1.80e-4	4.00e-4	1.44e-3	4.77e-3		7.79e-3	7.98e-3	6.80e-3	4.82e-3	2.03e-3	4.80e-4	
25	8.40e-4	1.72e-3	5.36e-3	1.57e-2		2.25e-2		1.78e-2			1.16e-3	
30	3.12e-3	5.52e-3	1.46e-2	3.34e-2	4.05e-2	4.33e-2	4.08e-2		3.33e-2	2.08e-2	9.09e-3	2.06e-3
40	1.54e-2	2.38e-2	4.85e-2	8.92e-2		9.89e-2		6.94e-2			4.46e-3	
50	3.96e-2	5.54e-2	9.91e-2	1.55e-1	1.65e-1	1.61e-1		1.13e-1	7.14e-2	3.21e-2	7.62e-3	
100	2.65e-1											
300	1.05e-0	1.15e-0	1.41e-0	1.66e-0	1.65e-0	1.64e-0	1.52e-0	1.28e-0	9.67e-1	5.76e-1	1.83e-1	7.76e-3
500	1.55e-0											
1000	2.27e-0											
2000	3.10e-0											
3000	3.48e-0											
4000	3.50e-0											

Sputtered energy of Cu by Ar  
 ne=21, na=12

E <sub>0</sub> (eV)	0°	15°	30°	45°	50°	55°	60°	65°	70°	75°	80°	85°
10								1.03e-6			3.44e-7	
11												
12								1.63e-5			2.70e-6	
13		2.60e-6		1.54e-6	3.61e-6							
14	1.89e-6	1.99e-6	6.55e-6	2.83e-5		6.90e-5	8.63e-5	9.70e-5	7.92e-5	4.66e-5	1.08e-5	
15						1.46e-4	1.85e-4	1.91e-4	1.61e-4			
16	3.65e-6	5.32e-6	2.31e-5	1.23e-4		2.49e-4	3.02e-4	3.03e-4	2.32e-4	1.28e-4	2.77e-5	
18	6.24e-6	1.36e-5	6.12e-5	3.10e-4		6.00e-4		7.09e-4				
20	1.21e-5											
20	1.09e-5	2.93e-5	1.58e-4	7.01e-4		1.23e-3	1.36e-3	1.23e-3	9.29e-4	4.03e-4	9.47e-5	
25	5.57e-5	1.39e-4	5.73e-4	2.21e-3		3.66e-3		3.35e-3			2.58e-4	
30	2.16e-4	4.65e-4	1.60e-3	4.70e-3	6.17e-3	7.21e-3	7.31e-3	6.35e-3	4.26e-3	1.84e-3	3.99e-4	
40	1.10e-3	2.04e-3	5.23e-3	1.23e-2		1.65e-2		1.34e-2			8.27e-4	
50	2.72e-3	4.43e-3	1.03e-2	2.08e-2	2.40e-2	2.60e-2		2.10e-2	1.38e-2	6.12e-3	1.31e-3	
100	1.34e-2											
300	2.87e-2	3.55e-2	5.98e-2	9.99e-2	1.12e-1	1.23e-1	1.28e-1	1.20e-1	9.62e-2	5.95e-2	1.57e-2	3.19e-4
500	3.03e-2											
1000	2.85e-2											
2000	2.68e-2											
3000	2.32e-2											
4000	1.85e-2											

# Ar → Cu

Particle reflection coefficient of Ar backscattered from Cu  
 $z_1=18$ ,  $m_1=39.95$ ,  $z_2=29$ ,  $m_2=63.54$ ,  $sbe=3.52$  eV,  $\rho=8.95$  g/cm $^3$   
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: testvmcx, trspvmcx, trspv1cs  
ne=22, na=12

$E_0$ (eV)	0°	15°	30°	45°	50°	55°	60°	65°	70°	75°	80°	85°
5	4.86e-1							9.08e-1			9.97e-1	
10	3.42e-1							9.08e-1			9.98e-1	
11												
12				4.57e-1	6.40e-1							
13		3.39e-1										
14	2.93e-1	3.33e-1	4.45e-1	6.34e-1		7.75e-1	8.46e-1	9.07e-1	9.54e-1	9.85e-1	9.98e-1	
15						7.74e-1	8.45e-1	9.07e-1	9.55e-1			
16	2.81e-1	3.23e-1	4.37e-1	6.28e-1		7.73e-1	8.43e-1	9.06e-1	9.55e-1	9.85e-1	9.98e-1	
18	2.73e-1	3.16e-1	4.31e-1	6.24e-1		7.70e-1						
20	2.67e-1	3.11e-1	4.15e-1	6.20e-1		7.67e-1	8.40e-1	9.05e-1	9.54e-1	9.86e-1	9.98e-1	
25	2.57e-1	3.01e-1	4.17e-1	6.12e-1		7.59e-1						
30	2.52e-1	2.95e-1	4.08e-1	6.04e-1	6.76e-1	7.53e-1	8.29e-1	8.98e-1	9.52e-1	9.85e-1	9.98e-1	
40	2.44e-1	2.85e-1	3.98e-1	5.88e-1		7.38e-1						
50	2.38e-1	2.77e-1	3.85e-1	5.74e-1	6.47e-1	7.27e-1						
100	2.14e-1											
300	1.51e-1	1.75e-1	2.36e-1	3.63e-1	4.36e-1	5.08e-1	6.05e-1	7.21e-1	8.31e-1	9.32e-1	9.91e-1	1.00e-0
500	1.25e-1											
1000	9.64e-2											
1000	1.01e-1											
2000	8.42e-2											
3000	7.03e-2											
4000	6.26e-2											

Energy reflection coefficient of Ar backscattered from Cu  
ne=22, na=12

$E_0$ (eV)	0°	15°	30°	45°	50°	55°	60°	65°	70°	75°	80°	85°
5	3.27e-3							4.34e-1			7.67e-1	
10	1.18e-2							4.43e-1			7.81e-1	
11												
12				6.29e-2	1.51e-1							
13		2.74e-2										
14	1.46e-2	2.82e-2	6.63e-2	1.56e-1		2.72e-1	3.53e-1	4.50e-1	5.60e-1	6.77e-1	7.91e-1	
15						2.74e-1	3.55e-1	4.52e-1	5.64e-1			
16	1.55e-2	2.95e-2	6.89e-2	1.60e-1		2.77e-1	3.57e-1	4.55e-1	5.67e-1	6.85e-1	7.99e-1	
18	1.63e-2	3.04e-2	7.08e-2	1.63e-1		2.79e-1						
20	1.71e-2	3.11e-2	7.22e-2	1.66e-1		2.82e-1	3.64e-1	4.62e-1	5.77e-1	6.96e-1	8.12e-1	
25	1.82e-2	3.21e-2	7.45e-2	1.69e-1		2.86e-1						
30	1.90e-2	3.25e-2	7.53e-2	1.72e-1	2.23e-1	2.90e-1	3.71e-1	4.72e-1	5.89e-1	7.13e-1	8.31e-1	
40	1.99e-2	3.23e-2	7.47e-2	1.73e-1		2.91e-1						
50	1.99e-2	3.18e-2	7.27e-2	1.71e-1	2.23e-1	2.90e-1						
100	1.85e-2											
300	1.31e-2	1.79e-2	3.87e-2	9.61e-2	1.37e-1	1.87e-1	2.64e-1	3.69e-1	5.07e-1	6.70e-1	8.49e-1	9.68e-1
500	1.11e-2											
1000	8.26e-3											
1000	8.72e-3											
2000	7.59e-3											
3000	6.63e-3											
4000	5.01e-3											

Average depth (mean range) in Å of Ar implanted in Cu  
ne=21, na=11

$E_0$ (eV)	0°	15°	30°	45°	50°	55°	60°	65°	70°	75°	80°
5	5.43e-1							5.60e-1			3.30e-1
10	8.65e-1							6.21e-1			3.53e-1
11											
12											
13		9.54e-1	8.51e-1	8.16e-1							
14	1.06e+0	1.00e+0	9.49e-1	9.04e-1		8.14e-1	7.54e-1	6.83e-1	5.96e-1	4.95e-1	3.79e-1
15						8.53e-1	7.88e-1	7.10e-1	6.23e-1		
16	1.16e+0	1.11e+0	1.05e+0	9.90e-1		8.87e-1	8.20e-1	7.41e-1	6.48e-1	5.33e-1	4.01e-1
18	1.26e+0	1.21e+0	1.14e+0	1.08e+0		9.66e-1					
20	1.35e+0	1.30e+0	1.23e+0	1.16e+0		1.04e+0	9.60e-1				
25	1.58e+0	1.53e+0	1.45e+0	1.35e+0		1.22e+0					
30	1.79e+0	1.74e+0	1.66e+0	1.54e+0	1.47e+0	1.39e+0	1.27e+0				
40	2.17e+0	2.12e+0	2.02e+0	1.87e+0		1.69e+0	1.27e+0				
50	2.53e+0	2.47e+0	2.36e+0	2.17e+0	2.08e+0	1.97e+0	1.76e+0				
100	3.90e+0										
300	7.25e+0	7.10e+0	6.64e+0	6.05e+0	5.86e+0	5.68e+0	5.34e+0	5.14e+0	4.82e+0	4.53e+0	4.00e+0
500	9.61e+0										
1000	1.45e+1										
2000	2.22e+1										
3000	2.89e+1										
4000	3.39e+1										

## Ar → Cu

Sputtering yield of Cu by Ar  
 $z_1=18$ ,  $m_1=39.95$ ,  $z_2=29$ ,  $m_2=63.54$ ,  $sbe=3.52$  eV,  $\rho=8.95$  g/cm $^{**3}$   
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr$   
 $\alpha=0$ .  
program: trspvmcx  
ne= 1, na= 1

$E_0$ (eV)	Y	$Y_E$	$R_N$	$R_E$	range	potential
100	2.65e-1	1.34e-2	2.14e-1	1.85e-2	3.90e+0	KrC
100	2.52e-1	1.53e-2	2.88e-1	2.34e-2	2.43e+0	Moliere
100	2.41e-1	1.36e-2	2.35e-1	1.92e-2	3.01e+0	ZBL

## Cu → Cu

Sputtering yield of Cu by Cu  
 $z_1=29$ ,  $m_1=63.54$ ,  $z_2=29$ ,  $m_2=63.54$ ,  $sbe=3.52$  eV,  $\rho=8.95$  g/cm $^{**3}$   
 $ef=3.45$  eV,  $esb=3.52$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: IPP 9/82  
ne=24, na=10

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	70°	75°	80°	85°
14	1.00e-5									
16	4.00e-5									
18	1.00e-4									
20	1.90e-4	6.10e-4	2.54e-3	9.63e-3	1.71e-2	2.13e-2				
23	4.60e-4									
25	7.50e-4									
28	1.39e-3									
30	1.98e-3									
32	2.70e-3									
50	2.45e-2	4.28e-2	1.02e-1	1.83e-1	2.06e-1	1.83e-1				
60	4.84e-2									
70	7.93e-2									
80	1.16e-1									
100	1.87e-1	2.55e-1	4.19e-1	5.60e-1	5.69e-1	4.60e-1				
200	5.85e-1									
300	9.47e-1	1.07e-0	1.40e-0	1.71e-0	1.71e-0	1.43e-0				
500	1.50e-0									
1000	2.40e-0	2.59e-0	3.30e-0	4.06e-0	4.42e-0	4.14e-0	3.56e-0			
2000	3.35e-0									
3000	3.80e-0	4.21e-0	5.33e-0	6.96e-0		8.86e-0	8.46e-0			
5000	4.51e-0									
10000	5.14e-0	5.84e-0	7.24e-0	1.02e+1	1.26e+1	1.53e+1	1.57e+1	1.56e+1	1.26e+1	4.25e-0
30000	5.57e-0									
100000	4.66e-0	5.35e-0	6.71e-0	9.45e-0		1.95e+1		3.03e+1	1.85e+1	

# Cu → Cu

Sputtered energy of Cu by Cu  
 z1=29, m1= 63.54, z2=29, m2= 63.54, sbe=3.52 eV, rho=8.95 g/cm\*\*\*  
 ef=3.47 eV, esb=3.52 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx  
 ne=43, na=14

$E_0$ (eV)	$0^\circ$	$15^\circ$	$25^\circ$	$30^\circ$	$35^\circ$	$40^\circ$	$45^\circ$	$55^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$
7										$7.19e-6$		
7.5					$2.51e-6$					$2.12e-6$		
8					$2.36e-6$					$4.48e-6$		
9					$5.25e-6$					$1.83e-5$		
10			$3.00e-6$		$9.23e-6$					$5.59e-5$		
11			$2.55e-6$									
11.8											$2.34e-4$	
12	$4.09e-6$	$2.56e-6$	$2.06e-5$	$1.51e-5$	$2.39e-5$	$3.66e-5$	$5.89e-5$	$1.42e-4$		$2.71e-4$		$3.80e-4$
13				$2.56e-5$						$5.07e-4$		
14	$3.91e-6$	$6.11e-6$		$3.86e-5$			$1.82e-4$			$7.74e-4$		
15				$5.98e-5$								
16	$3.26e-6$	$1.35e-5$		$8.14e-5$			$4.24e-4$	$9.62e-4$		$1.55e-3$		$1.88e-3$
17				$1.17e-4$						$2.25e-3$		
18	$1.28e-5$	$2.66e-5$		$1.56e-4$			$8.26e-4$					
20	$9.71e-6$	$4.10e-5$		$2.69e-4$			$1.44e-3$	$3.02e-3$		$4.22e-3$		
22		$6.71e-5$										
23	$2.31e-5$	$8.70e-5$		$5.73e-4$			$2.68e-3$					
25	$6.85e-5$			$8.35e-4$								
27		$2.24e-4$										
28	$7.23e-5$											
30	$1.06e-4$	$3.64e-4$		$1.92e-3$			$6.82e-3$	$1.18e-2$		$1.39e-2$	$1.31e-2$	
32	$1.46e-4$											
35		$7.24e-4$		$3.43e-3$								
40	$4.96e-4$	$1.38e-3$		$5.47e-3$			$1.55e-2$			$2.46e-2$		$2.34e-2$
50	$1.30e-3$	$2.97e-3$		$1.01e-2$			$2.50e-2$	$3.44e-2$				
60	$2.43e-3$											
70	$3.77e-3$	$7.27e-3$		$1.98e-2$			$4.26e-2$			$5.25e-2$		
95							$6.00e-2$					
100	$8.00e-3$	$1.35e-2$		$3.20e-2$			$6.32e-2$	$7.76e-2$		$7.16e-2$		$3.99e-2$
120							$7.30e-2$					
200	$1.74e-2$	$2.55e-2$		$5.22e-2$			$9.52e-2$			$1.15e-1$		
300	$2.27e-2$	$3.09e-2$		$5.91e-2$			$1.10e-1$	$1.38e-1$		$1.41e-1$		$8.03e-2$
500	$2.58e-2$						$1.15e-1$			$1.70e-1$		
1000	$2.78e-2$	$3.39e-2$		$6.10e-2$			$1.11e-1$	$1.55e-1$		$1.88e-1$	$1.84e-1$	
2000										$1.90e-1$		
3000	$2.17e-2$	$2.75e-2$		$4.69e-2$			$8.81e-2$		$1.61e-1$	$1.82e-1$	$1.98e-1$	
5000	$1.96e-2$									$1.68e-1$		
10000	$1.46e-2$	$1.92e-2$		$3.33e-2$			$6.51e-2$	$9.96e-2$		$1.50e-1$	$1.68e-1$	$1.87e-1$
30000	$9.30e-3$	$1.11e-2$		$2.08e-2$			$4.48e-2$			$1.10e-1$		
100000	$3.32e-3$	$5.67e-3$		$9.98e-3$			$2.02e-2$			$6.34e-2$		

$E_0$ (eV)	$80^\circ$	$85^\circ$
6.5	$1.61e-6$	
7	$2.98e-6$	
7.4	$4.40e-6$	
8	$1.14e-5$	$4.15e-5$
9	$3.83e-5$	
10	$1.04e-4$	$1.11e-4$
11	$2.27e-4$	
12	$4.16e-4$	$4.19e-4$
14	$1.02e-3$	$1.02e-3$
15		$1.42e-3$
16	$1.85e-3$	$1.86e-3$
18	$2.89e-3$	
20	$4.04e-3$	$3.66e-3$
30	$9.53e-3$	$8.10e-3$
40	$1.36e-2$	$1.03e-2$
50	$1.64e-2$	$1.17e-2$
70	$1.96e-2$	
100	$2.21e-2$	$1.16e-2$
200	$2.83e-2$	
300	$3.39e-2$	$7.35e-3$
500	$4.76e-2$	
1000	$7.27e-2$	$7.63e-3$
3000	$1.32e-1$	$1.80e-2$
10000	$1.76e-1$	$6.68e-2$
30000	$1.75e-1$	$1.15e-1$
100000	$1.30e-1$	$1.18e-1$
300000		$9.87e-2$

# Cu → Cu

Particle reflection coefficient of Cu backscattered from Cu  
 z1=29, m1= 63.54, z2=29, m2= 63.54, sbe=3.52 eV, rho=8.95 g/cm\*\*3  
 ef=3.47 eV, esb=3.52 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx  
 ne=43, na=14

$E_0$ (eV)	$0^\circ$	$15^\circ$	$25^\circ$	$30^\circ$	$35^\circ$	$40^\circ$	$45^\circ$	$55^\circ$	$60^\circ$	$65^\circ$	$70^\circ$	$75^\circ$
7										$8.29e-6$		
7.5										$4.60e-5$		
8					$5.05e-8$					$1.38e-4$		
9					$5.00e-8$					$7.32e-4$		
10				$2.02e-8$			$6.70e-6$				$2.38e-3$	
11					$1.50e-7$							
11.8					$3.33e-7$							
12	$2.22e-8$	$2.00e-7$	$4.29e-7$	$2.00e-6$	$1.03e-5$	$8.04e-5$	$3.09e-4$	$2.50e-3$		$9.07e-3$		
13					$7.00e-6$					$1.02e-2$		
14	$1.75e-7$						$1.18e-3$			$1.64e-2$		
15							$6.10e-5$			$2.46e-2$		
16		$1.33e-6$					$3.21e-3$	$1.54e-2$		$4.61e-2$		
17							$2.61e-4$			$5.89e-2$		
18	$1.00e-6$	$9.00e-6$					$6.95e-3$					
20	$7.50e-7$	$3.70e-5$			$4.41e-4$		$1.26e-2$	$4.29e-2$		$1.06e-1$		
22		$9.40e-5$					$2.47e-2$					
23	$1.14e-6$	$1.49e-4$			$3.04e-3$							
25	$4.00e-6$				$5.13e-3$							
27		$4.48e-4$										
28	$2.60e-5$											
30	$4.87e-5$	$8.78e-4$			$1.16e-2$			$6.47e-2$	$1.49e-1$	$2.92e-1$	$3.78e-1$	
32	$9.71e-5$											
35		$2.25e-3$			$2.03e-2$							
40	$5.15e-4$	$3.71e-3$			$2.96e-2$			$1.26e-1$		$4.42e-1$		
50	$1.92e-3$	$7.71e-3$			$4.77e-2$			$1.74e-1$	$3.30e-1$			$7.62e-1$
60	$3.18e-3$											
70	$4.53e-3$	$1.63e-2$			$7.30e-2$			$2.35e-1$		$6.40e-1$		
95												
100	$9.78e-3$	$2.47e-2$			$9.45e-2$			$2.64e-1$	$4.55e-1$	$6.84e-1$		$8.89e-1$
120								$2.70e-1$				
200	$1.83e-2$	$3.67e-2$			$1.03e-1$			$2.62e-1$		$6.67e-1$		
300	$2.08e-2$	$3.83e-2$			$1.01e-1$			$2.35e-1$	$4.08e-1$	$6.25e-1$		$8.88e-1$
500	$2.28e-2$							$2.07e-1$		$5.55e-1$		
1000	$2.18e-2$	$3.13e-2$			$7.03e-2$			$1.67e-1$	$2.79e-1$	$4.64e-1$	$6.01e-1$	
2000										$3.72e-1$		
3000	$2.44e-2$	$2.76e-2$			$5.46e-2$			$1.14e-1$		$2.70e-1$	$3.35e-1$	$4.44e-1$
5000	$1.62e-2$									$2.96e-1$		
10000	$1.44e-2$	$1.30e-2$			$4.33e-2$			$7.97e-2$	$1.50e-1$	$2.53e-1$	$3.36e-1$	$4.54e-1$
30000	$9.67e-3$	$1.00e-2$			$2.70e-2$			$5.40e-2$		$2.13e-1$		
100000	$3.00e-3$	$4.67e-3$			$1.36e-2$			$4.10e-2$		$1.80e-1$		

$E_0$ (eV)	$80^\circ$	$85^\circ$
6.5	$1.84e-5$	
7	$8.86e-5$	
7.4	$2.26e-4$	
8	$7.76e-4$	
9	$3.48e-3$	$4.24e-3$
10	$8.85e-3$	$1.04e-2$
11	$1.74e-2$	
12	$2.96e-2$	$3.35e-2$
14	$6.42e-2$	$7.35e-2$
15		$9.68e-2$
16	$1.11e-1$	$1.25e-1$
18	$1.68e-1$	
20	$2.29e-1$	$2.54e-1$
30	$5.26e-1$	$5.70e-1$
40	$7.29e-1$	$7.76e-1$
50	$8.36e-1$	$8.78e-1$
70	$9.19e-1$	
100	$9.51e-1$	$9.79e-1$
200	$9.70e-1$	
300	$9.70e-1$	$9.97e-1$
500	$9.61e-1$	
1000	$9.30e-1$	$9.98e-1$
3000	$8.05e-1$	$9.88e-1$
10000	$6.14e-1$	$9.13e-1$
30000	$5.09e-1$	$7.58e-1$
100000	$4.70e-1$	$6.17e-1$

# Cu → Cu

Energy reflection coefficient of Cu backscattered from Cu  
 z1=29, m1= 63.54, z2=29, m2= 63.54, sbe=3.52 eV, rho=8.95 g/cm\*\*3  
 ef=3.47 eV, esb=3.52 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx  
 ne=43, na=14

$E_0$ (eV)	0°	15°	25°	30°	35°	40°	45°	55°	60°	65°	70°	75°
7										2.24e-6		
7.5										6.90e-6		
8					5.06e-7					2.18e-5		
9					7.35e-6					1.35e-4		
10			6.78e-7		3.77e-7					5.01e-4		
11					5.51e-7							
11.8										2.24e-3		
12	2.64e-8	9.95e-8	8.71e-8	8.68e-7	1.68e-6	1.15e-5	5.21e-5	5.19e-4		2.55e-3		
13					6.42e-7					4.35e-3		
14	4.76e-7				2.04e-6			2.07e-4		6.73e-3		
15					6.53e-6							
16		2.53e-7			1.57e-5			5.77e-4	3.61e-3	1.32e-2		
17					3.00e-5					1.70e-2		
18	2.44e-6	3.29e-6			5.45e-5		1.27e-3					
20	2.93e-7	1.11e-5			1.44e-4		2.37e-3	1.04e-2		3.22e-2		
22		9.40e-6										
23	7.58e-7	1.51e-5			4.26e-4		4.78e-3					
25	2.80e-7				7.45e-4							
27		4.71e-5										
28	1.49e-6											
30	2.91e-6	9.15e-5			1.73e-3		1.34e-2	3.92e-2		9.81e-2	1.40e-1	
32	6.25e-6											
35		2.28e-4			3.11e-3							
40	3.30e-5	3.67e-4			4.52e-3		2.76e-2			1.59e-1		
50	1.37e-4	8.10e-4			7.45e-3		3.95e-2	9.69e-2				
60	2.02e-4											
70	3.10e-4	1.61e-3			1.11e-2		5.53e-2			2.62e-1		
95							6.27e-2					
100	6.02e-4	2.23e-3			1.39e-2		6.28e-2	1.47e-1		2.98e-1		5.17e-1
120							6.40e-2					
200	9.33e-4	2.84e-3			1.34e-2		6.04e-2			3.02e-1		
300	1.15e-3	2.62e-3			1.22e-2		5.01e-2	1.28e-1		2.82e-1		5.68e-1
500	9.76e-4						4.10e-2			2.41e-1		
1000	8.42e-4	1.61e-3			7.18e-3		2.96e-2	7.48e-2		1.84e-1	2.99e-1	
2000										1.31e-1		
3000	9.87e-4	1.28e-3			4.57e-3		1.58e-2		7.24e-2	1.11e-1	1.83e-1	
5000	5.77e-4									9.18e-2		
10000	5.02e-4	8.13e-4			3.44e-3		1.14e-2	3.20e-2		7.66e-2	1.25e-1	2.04e-1
30000	4.25e-4	5.81e-4			2.87e-3		7.83e-3			6.66e-2		
100000	7.11e-5	3.04e-4			1.09e-3		5.56e-3			5.46e-2		

$E_0$ (eV)	80°	85°
6.5	3.16e-6	
7	1.42e-5	
7.4	3.98e-5	
8	1.48e-4	
9	7.91e-4	9.91e-4
10	2.27e-3	2.75e-3
11	4.87e-3	
12	8.83e-3	1.02e-2
14	2.08e-2	2.45e-2
15		3.33e-2
16	3.82e-2	4.41e-2
18	6.02e-2	
20	8.54e-2	9.81e-2
30	2.27e-1	2.56e-1
40	3.50e-1	3.93e-1
50	4.39e-1	4.89e-1
70	5.48e-1	
100	6.28e-1	7.07e-1
200	7.18e-1	
300	7.38e-1	8.69e-1
500	7.39e-1	
1000	7.05e-1	9.18e-1
3000	5.70e-1	9.01e-1
10000	3.74e-1	7.82e-1
30000	2.69e-1	5.88e-1
100000	2.44e-1	4.25e-1
300000		4.28e-1

# Cu → Cu

Average depth (mean range) in Å of Cu implanted in Cu  
 $z1=29$ ,  $m1=63.54$ ,  $z2=29$ ,  $m2=63.54$ ,  $sbe=3.52$  eV,  $\rho=8.95$  g/cm\*\*3  
 $ef=3.47$  eV,  $esb=3.52$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: testvmcx  
 $n_{\text{e}}=38$ ,  $n_{\text{a}}=14$

$E_0$ (eV)	0°	15°	25°	30°	35°	40°	45°	55°	60°	65°	70°	75°
8				5.15e-3								
9				6.78e-2			1.59e-2					
10		1.83e-1		1.35e-1			5.78e-2					
11		2.69e-1		2.02e-1			9.87e-2					
12	3.84e-1	3.52e-1	3.01e-1	2.67e-1	2.28e-1	1.85e-1	1.38e-1	3.00e-2				
13				3.27e-1								
14	5.45e-1	5.00e-1		3.82e-1			2.08e-1					
15				4.33e-1								
16	6.75e-1	6.18e-1		4.79e-1			2.69e-1	1.13e-1				
17				5.20e-1								
18	7.81e-1	7.19e-1		5.60e-1			3.24e-1					
20	8.73e-1	8.07e-1		6.35e-1			3.75e-1	1.87e-1		9.19e-3		
22		8.89e-1										
23	1.00e-0	9.32e-1		7.38e-1			4.49e-1					
25	1.09e-0			8.06e-1								
27		1.09e-0										
28	1.21e-0											
30	1.30e-0	1.20e-0		9.69e-1			6.36e-1	3.94e-1		1.57e-1	5.39e-2	
32	1.37e-0											
35		1.38e-0		1.13e-0								
40	1.66e-0	1.56e-0		1.28e-0			9.00e-1			3.49e-1		2.74e-1
50	1.97e-0	1.85e-0		1.57e-0			1.17e-0	8.87e-1				
60	2.26e-0											
70	2.51e-0	2.39e-0		2.09e-0			1.67e-0			1.02e-0		
95							2.21e-0					
100	3.21e-0	3.06e-0		2.75e-0			2.30e-0	1.99e-0		1.56e-0		9.91e-1
120							2.66e-0					
200	4.94e-0	4.79e-0		4.39e-0			3.83e-0			2.90e-0		
300	6.25e-0	6.06e-0		5.65e-0			4.92e-0	4.38e-0		3.72e-0		2.88e-0
500	8.36e-0						6.57e-0			5.10e-0		
1000	1.24e+1	1.21e+1		1.11e+1			9.87e-0	8.73e-0		7.72e-0	7.25e-0	
2000										1.12e+1		
3000	2.34e+1	2.30e+1		2.09e+1			1.85e+1		1.52e+1	1.42e+1	1.31e+1	
5000	3.16e+1									1.91e+1		
10000	5.02e+1	4.74e+1		4.46e+1			3.86e+1	3.37e+1		2.86e+1	2.78e+1	2.54e+1
30000	1.07e+2	1.06e+2		9.73e+1			8.50e+1			5.96e+1		
100000	3.00e+2	2.81e+2		2.54e+2			2.19e+2			1.59e+2		

$E_0$ (eV)	80°	85°
50	1.32e-1	3.05e-2
70	3.87e-1	
100	7.71e-1	4.52e-1
200	1.54e-0	
300	2.36e-0	1.46e-0
500	3.67e-0	
1000	5.55e-0	4.57e-0
3000	1.12e+1	9.26e-0
10000	2.44e+1	2.28e+1
30000	4.83e+1	4.52e+1
100000	1.30e+2	1.06e+2
300000		1.78e+2

Cu on Cu, Maxwellian velocity distribution, sheath potential 3 kT  
 $z1=29$ ,  $m1=63.54$ ,  $z2=29$ ,  $m2=63.54$ ,  $sbe=3.52$ ,  $\rho=8.95$  g/cm\*\*3  
 $ef=3.50$  eV,  $esb=3.52$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: testvmcx  
 $n_{\text{e}} = 3$

kT (eV)	Y	$Y_E$	$E_{sp}$	$R_N$	$R_E$	$E_b$	range
15	5.67e-1	2.60e-2	7.57e+0	4.39e-2	4.37e-3	1.64e+1	4.20e+0
20	8.15e-1	3.19e-2	8.64e+0	4.13e-2	4.00e-3	2.13e+1	5.05e+0
25	1.01e-0	3.41e-2	9.32e+0	4.05e-2	3.40e-3	2.31e+1	5.71e+0

## Xe → Cu

Sputtering yield of Cu by Xe

```

z1=54, m1=131.30, z2=29, m2= 63.54, sbe=3.52 eV, rho= 8.95 g/cm***3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program: trspvmcx, trspv1cs
nem= 8, na= 1

```

E <sub>0</sub> (eV)	0°
50	6.48e-3
100	8.69e-2
300	6.50e-1
500	1.17e-0
1000	2.13e-0
2000	3.30e-0
3000	4.09e-0
4000	4.51e-0

Sputtering yield of Cu by Xe  
nem= 8, na= 1

E <sub>0</sub> (eV)	0°
50	2.35e-4
100	2.79e-3
300	1.32e-2
500	1.80e-2
1000	2.19e-2
2000	2.32e-2
3000	2.23e-2
4000	1.97e-2

Particle reflection coefficient of Xe backscattered from Cu

```

z1=54, m1=131.30, z2=29, m2= 63.54, sbe=3.52 eV, rho= 8.95 g/cm***3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program: trspvmcx, trspv1cs
nem= 7, na= 1

```

E <sub>0</sub> (eV)	0°
50	2.77e-2
100	4.26e-3
300	2.20e-4
500	1.00e-4
2000	2.80e-4
3000	3.07e-4
4000	6.00e-4

Energy reflection coefficient of Xe backscattered from Cu  
nem= 7, na= 1

E <sub>0</sub> (eV)	0°
50	2.40e-6
100	2.86e-6
300	1.54e-6
500	1.21e-6
2000	1.91e-6
3000	2.45e-6
4000	8.91e-7

Average depth (mean range) in Å of Xe implanted in Cu  
nem= 8, na= 1

E <sub>0</sub> (eV)	0°
50	2.66e+0
100	4.17e+0
300	7.73e+0
500	1.01e+1
1000	1.42e+1
2000	2.03e+1
3000	2.49e+1
4000	2.86e+1

## D → Ga

Sputtering yield of Ga by D

```

z1= 1, m1= 2.01, z2=31, m2= 69.72, sbe=2.82 eV, rho=5.91 g/cm**3
ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program: testvmcx, IPP 9/82
ne=10, na= 2

```

E <sub>0</sub> (eV)	0°	65°
30	1.58e-6	8.75e-7
50	2.54e-3	1.63e-3
70	7.80e-3	7.06e-3
100	1.55e-2	2.08e-2
200	3.13e-2	6.90e-2
500	4.45e-2	1.37e-1
1000	4.92e-2	1.65e-1
2000	4.52e-2	1.64e-1
5000	3.48e-2	1.38e-1
10000	2.38e-2	1.05e-1

Sputtered energy of Ga by D

```

program: testvmcx
ne=10, na= 2

```

E <sub>0</sub> (eV)	0°	65°
30	2.28e-9	3.45e-9
50	4.39e-5	2.95e-5
70	1.64e-4	1.63e-4
100	3.48e-4	4.75e-4
200	5.99e-4	1.40e-3
500	5.60e-4	1.84e-3
1000	4.08e-4	1.52e-3
2000	2.37e-4	9.67e-4
5000	8.52e-5	4.60e-4
10000	3.41e-5	2.22e-4

Particle reflection coefficient of D backscattered from Ga

```

z1= 1, m1= 2.01, z2=31, m2= 69.72, sbe=2.82 eV, rho=5.91 g/cm**3
ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program: testvmcx
ne=10, na= 2

```

E <sub>0</sub> (eV)	0°	65°
30	5.93e-1	8.32e-1
50	5.68e-1	7.95e-1
70	5.48e-1	7.69e-1
100	5.29e-1	7.47e-1
200	4.91e-1	7.04e-1
500	4.27e-1	6.48e-1
1000	3.71e-1	6.03e-1
2000	3.04e-1	5.57e-1
5000	2.03e-1	4.76e-1
10000	1.27e-1	4.03e-1

Energy reflection coefficient of D backscattered from Ga  
ne=10, na= 2

E <sub>0</sub> (eV)	0°	65°
30	3.72e-1	6.80e-1
50	3.47e-1	6.30e-1
70	3.29e-1	5.96e-1
100	3.11e-1	5.63e-1
200	2.79e-1	5.10e-1
500	2.29e-1	4.46e-1
1000	1.88e-1	3.98e-1
2000	1.43e-1	3.49e-1
5000	8.20e-2	2.68e-1
10000	4.44e-2	2.00e-1

Average depth (mean range) in Å of D implanted in Ga  
ne=10, na= 2

E <sub>0</sub> (eV)	0°	65°
30	2.42e+1	2.31e+1
50	3.25e+1	3.09e+1
70	3.96e+1	3.74e+1
100	4.89e+1	4.64e+1
200	7.54e+1	7.04e+1
500	1.38e+2	1.26e+2
1000	2.27e+2	2.03e+2
2000	3.85e+2	3.33e+2
5000	7.98e+2	6.50e+2
10000	1.43e+3	1.08e+3

# D → Ga

D on Ga, Maxwellian velocity distribution, sheath potential 0 kT  
 z1= 1, m1= 2.01, z2=31, m2= 69.72, sb=2.82 eV, rho= 5.91 g/cm\*\*3  
 ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx  
 ne=10

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
10	2.71e-4	1.76e-5	1.30e+0	7.53e-1	5.49e-1	1.46e+1	1.86e+1
20	3.00e-3	1.53e-4	2.04e+0	7.21e-1	5.03e-1	2.79e+1	2.79e+1
30	7.39e-3	3.13e-4	2.55e+0	6.99e-1	4.77e-1	4.10e+1	3.54e+1
50	1.83e-2	6.09e-4	3.32e+0	6.69e-1	4.42e-1	6.60e+1	4.76e+1
100	4.07e-2	9.38e-4	4.60e+0	6.34e-1	4.03e-1	1.27e+2	7.25e+1
200	6.73e-2	1.04e-3	6.16e+0	5.87e-1	3.57e-1	2.43e+2	1.15e+2
500	9.35e-2	8.54e-4	9.15e+0	5.24e-1	2.94e-1	5.62e+2	2.19e+2
1000	1.03e-1	5.86e-4	1.14e+1	4.67e-1	2.42e-1	1.04e+3	3.67e+2
2000	9.78e-2	3.32e-4	1.35e+1	3.98e-1	1.86e-1	1.87e+3	6.21e+2
5000	8.22e-2	1.43e-4	1.74e+1	3.06e-1	1.19e-1	3.88e+3	1.27e+3

D on Ga, Maxwellian velocity distribution, sheath potential 3 kT  
 ne=11

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
5	6.50e-5	2.23e-6	8.56e-1	6.39e-1	4.43e-1	1.66e+1	2.15e+1
7	6.93e-4	1.94e-5	9.81e-1	6.20e-1	4.02e-1	2.27e+1	2.60e+1
10	3.35e-3	9.02e-5	1.35e+0	6.00e-1	3.82e-1	3.19e+1	3.18e+1
20	1.63e-2	3.95e-4	2.43e+0	5.64e-1	3.45e-1	6.12e+1	4.81e+1
50	4.01e-2	7.06e-4	4.40e+0	5.10e-1	2.97e-1	1.46e+2	8.48e+1
100	5.30e-2	6.79e-4	6.41e+0	4.64e-1	2.58e-1	2.78e+2	1.35e+2
200	5.90e-2	4.94e-4	8.39e+0	4.07e-1	2.16e-1	5.30e+2	2.21e+2
500	5.36e-2	2.28e-4	1.07e+1	3.20e-1	1.50e-1	1.18e+3	4.41e+2
1000	4.28e-2	1.14e-4	1.34e+1	2.47e-1	1.04e-1	2.11e+3	7.65e+2
2000	3.40e-2	5.40e-5	1.59e+1	1.65e-1	5.98e-2	3.62e+3	1.34e+3
5000	1.72e-2	1.08e-5	1.57e+1	7.35e-2	2.07e-2	7.07e+3	2.87e+3

## T → Ga

Sputtering yield of Ga by T  
 $z1 = 1$ ,  $m1 = 3.01$ ,  $z2 = 31$ ,  $m2 = 69.72$ ,  $sbe = 2.97$  eV,  $\rho = 5.91$  g/cm<sup>3</sup>  
 $ef = 0.90$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: newtrim (Laszlo), IPP 9/82  
ne = 8, na = 2

$E_0$ (eV)	0°	65°
50	8.73e-3	7.60e-3
100	2.85e-2	4.97e-2
200	5.00e-2	1.24e-1
500	6.84e-2	2.11e-1
1000	7.15e-2	2.46e-1
2000	6.81e-2	2.54e-1
5000	5.24e-2	2.00e-1
10000	3.56e-2	

Sputtered energy of Ga by T  
program: newtrim (Laszlo)  
ne = 8, na = 2

$E_0$ (eV)	0°	65°
50	2.62e-4	2.48e-4
100	8.73e-4	1.60e-3
200	1.23e-3	3.29e-3
500	1.05e-3	3.64e-3
1000	7.22e-4	2.84e-3
2000	4.07e-4	1.84e-3
5000	1.76e-4	8.14e-4
10000	6.22e-5	

Particle reflection coefficient of T backscattered from Ga  
 $z1 = 1$ ,  $m1 = 3.01$ ,  $z2 = 31$ ,  $m2 = 69.72$ ,  $sbe = 2.97$  eV,  $\rho = 5.91$  g/cm<sup>3</sup>  
 $ef = 0.90$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: newtrim (Laszlo)  
ne = 8, na = 2

$E_0$ (eV)	0°	65°
50	5.36e-1	7.81e-1
100	5.02e-1	7.30e-1
200	4.65e-1	6.88e-1
500	4.11e-1	6.31e-1
1000	3.61e-1	5.98e-1
2000	3.00e-1	5.44e-1
5000	2.08e-1	4.74e-1
10000	1.37e-1	

Energy reflection coefficient of T backscattered from Ga  
ne = 8, na = 2

$E_0$ (eV)	0°	65°
50	3.14e-1	6.08e-1
100	2.85e-1	5.43e-1
200	2.56e-1	4.90e-1
500	2.17e-1	4.32e-1
1000	1.82e-1	3.95e-1
2000	1.42e-1	3.43e-1
5000	8.66e-2	2.79e-1
10000	4.90e-2	

Average depth (mean range) in Å of T implanted in Ga  
ne = 8, na = 2

$E_0$ (eV)	0°	65°
50	3.02e+1	2.84e+1
100	4.60e+1	4.29e+1
200	7.17e+1	6.61e+1
500	1.35e+2	1.23e+2
1000	2.26e+2	2.01e+2
2000	3.92e+2	3.39e+2
5000	8.45e+2	6.97e+2
10000	1.55e+3	

# $T \rightarrow Ga$

T on Ga, Maxwellian velocity distribution, sheath potential 0 kT  
 $z1 = 1$ ,  $m1 = 3.01$ ,  $z2 = 31$ ,  $m2 = 69.72$ ,  $sbe = 2.97$  eV,  $\rho = 5.91$  g/cm $^{**3}$   
 $ef = 0.90$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: newtrim(Laszlo)  
ne = 9

kT (eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
10	1.11e-3	9.34e-5	1.69e+0	7.29e-1	5.17e-1	1.42e+1	1.69e+1
20	7.80e-3	5.20e-4	2.67e+0	6.98e-1	4.76e-1	2.73e+1	2.57e+1
50	3.46e-2	1.54e-3	4.34e+0	6.48e-1	4.22e-1	6.50e+1	4.47e+1
100	7.13e-2	2.03e-3	5.72e+0	6.07e-1	3.81e-1	1.26e+2	6.97e+1
200	1.08e-1	2.13e-3	7.88e+0	5.73e-1	3.45e-1	2.41e+2	1.11e+2
500	1.42e-1	1.53e-3	1.08e+1	5.11e-1	2.88e-1	5.66e+2	2.20e+2
1000	1.58e-1	1.15e-3	1.46e+1	4.66e-1	2.44e-1	1.05e+3	3.75e+2
2000	1.39e-1	6.18e-4	1.77e+1	4.04e-1	1.96e-1	1.92e+3	6.54e+2
5000	1.18e-1	2.56e-4	2.16e+1	3.14e-1	1.29e-1	4.07e+3	1.38e+3

T on Ga, Maxwellian velocity distribution, sheath potential 3 kT  
ne = 9

kT (eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
10	9.56e-3	3.68e-4	1.93e+0	5.70e-1	3.49e-1	3.06e+1	2.97e+1
20	3.07e-2	9.94e-4	3.23e+0	5.39e-1	3.21e-1	5.94e+1	4.49e+1
50	6.50e-2	1.46e-3	5.60e+0	4.84e-1	2.76e-1	1.43e+2	8.05e+1
100	8.10e-2	1.24e-3	7.63e+0	4.46e-1	2.45e-1	2.76e+2	1.33e+2
200	8.47e-2	8.85e-4	1.04e+1	3.99e-1	2.12e-1	5.30e+2	2.22e+2
500	7.77e-2	3.98e-4	1.28e+1	3.18e-1	1.56e-1	1.23e+3	4.55e+2
1000	6.48e-2	2.17e-4	1.67e+1	2.49e-1	1.07e-1	2.16e+3	8.12e+2
2000	4.91e-2	9.75e-5	1.99e+1	1.76e-1	6.65e-2	3.79e+3	1.46e+3
5000	3.06e-2	2.81e-5	2.30e+1	8.45e-2	2.56e-2	7.58e+3	3.19e+3

T on Ga, Maxwellian velocity distribution, sheath potential 9 kT  
ne = 5

kT (eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
10	3.18e-2	9.61e-4	3.33e+0	5.15e-1	2.97e-1	6.35e+1	4.85e+1
20	5.52e-2	1.34e-3	5.32e+0	4.75e-1	2.66e-1	1.23e+2	7.54e+1
50	7.79e-2	1.17e-3	8.28e+0	4.19e-1	2.25e-1	2.95e+2	1.43e+2
100	8.25e-2	7.50e-4	1.00e+1	3.69e-1	1.87e-1	5.58e+2	2.40e+2
200	7.11e-2	4.15e-4	1.29e+1	3.16e-1	1.52e-1	1.06e+3	4.18e+2

## Ga → Ga

Sputtering yield of Ga by Ga  
 z1=31, m1= 69.72, z2=31, m2= 69.72, sbe=2.97 eV, rho=5.91 g/cm\*\*\*3  
 ef=2.47 eV, esb=2.97 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: newtrim (Laszlo), IPP 9/82  
 ne=12, na= 8

E <sub>0</sub> (eV)	0°	30°	45°	55°	60°	65°	70°	80°
20	5.56e-4				4.94e-2			
50	4.60e-2				3.48e-1			
100	2.37e-1	5.25e-1	7.57e-1	8.28e-1	8.03e-1			
150	4.43e-1	8.22e-1	1.12e-0	1.22e-0	1.19e-0			
200	6.33e-1	1.07e-0	1.45e-0	1.56e-0	1.55e-0			
300	9.46e-1	1.49e-0	1.98e-0	2.17e-0	2.16e-0			
500	1.43e-0				3.19e-0			
900	2.08e-0	3.02e-0	3.94e-0	4.57e-0	4.71e-0			
1000	2.22e-0	3.14e-0	4.20e-0	4.84e-0	5.02e-0	4.97e-0	4.63e-0	2.37e-0
2000	3.10e-0				7.32e-0			
5000	4.07e-0				1.08e+1			
10000	4.96e-0				1.41e+1			

Sputtered energy of Ga by Ga  
 program: newtrim (Laszlo)  
 ne=12, na= 8

E <sub>0</sub> (eV)	0°	30°	45°	55°	60°	65°	70°	80°
20	3.05e-5				9.85e-3			
50	2.13e-3				6.15e-2			
100	8.31e-3	3.53e-2	7.45e-2	1.01e-1	1.09e-1			
150	1.30e-2	4.43e-2	8.92e-2	1.21e-1	1.32e-1			
200	1.59e-2	4.85e-2	9.64e-2	1.31e-1	1.45e-1			
300	1.94e-2	5.23e-2	1.02e-1	1.40e-1	1.58e-1			
500	2.21e-2				1.67e-1			
900	2.33e-2	5.43e-2	9.95e-2	1.44e-1	1.66e-1			
1000	2.36e-2	5.30e-2	9.81e-2	1.41e-1	1.67e-1	1.86e-1	1.98e-1	1.24e-1
2000	2.23e-2				1.57e-1			
5000	1.73e-2				1.34e-1			
10000	1.49e-2				1.20e-1			

## Ga → Ga

Particle reflection coefficient of backscattered Ga from Ga  
 z1=31, m1 = 69.72, z2=31, m2 = 69.72, sbe=2.97 eV, rho=5.91 g/cm\*\*3  
 ef=2.47 eV, esb=2.97 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: newtrim (Laszlo)  
 ne=12, na = 8

$E_0$ (eV)	0°	30°	45°	55°	60°	65°	70°	80°
20	2.43e-5				1.14e-1			
50	3.46e-3				4.10e-1			
100	1.13e-2	7.66e-2	2.08e-1	3.68e-1	4.73e-1		7.08e-1	9.19e-1
150	1.63e-2	8.10e-2	2.06e-1	3.54e-1	4.53e-1		6.96e-1	
200	1.92e-2	8.08e-2	1.96e-1	3.38e-1	4.32e-1		6.80e-1	9.28e-1
300	2.34e-2	7.91e-2	1.82e-1	3.11e-1	3.97e-1		6.39e-1	
500	2.43e-2				3.54e-1			
900	2.15e-2	6.48e-2	1.37e-1	2.39e-1	3.02e-1		5.09e-1	
1000	2.66e-2	6.42e-2	1.35e-1	2.33e-1	2.93e-1	3.81e-1	4.93e-1	8.37e-1
2000	2.05e-2				2.49e-1			
5000	1.71e-2				2.11e-1			
10000	1.16e-2				1.87e-1			

Energy reflection coefficient of Ga backscattered from Ga  
 ne=12, na = 8

$E_0$ (eV)	0°	30°	45°	55°	60°	65°	70°	80°
20	3.37e-6				3.22e-2			
50	2.16e-4				1.41e-1			
100	6.01e-4	1.02e-2	4.67e-2	1.14e-1	1.72e-1		3.49e-1	6.00e-1
150	7.95e-4	9.89e-3	4.37e-2	1.07e-1	1.64e-1		3.52e-1	
200	8.77e-4	9.50e-3	4.03e-2	9.96e-2	1.53e-1		3.43e-1	6.55e-1
300	1.05e-3	8.61e-3	3.53e-2	8.79e-2	1.35e-1		3.16e-1	
500	9.41e-4				1.12e-1			
900	7.65e-4	5.72e-3	2.18e-2	5.54e-2	8.73e-2		2.24e-1	
1000	9.73e-4	6.00e-3	2.10e-2	5.36e-2	8.31e-2	1.34e-1	2.15e-1	5.84e-1
2000	6.36e-4				6.39e-2			
5000	6.81e-4				5.05e-2			
10000	2.77e-4				4.46e-2			

Average depth (mean range) in Å of Ga implanted in Ga  
 ne=12, na = 8

$E_0$ (eV)	0°	30°	45°	55°	60°	65°	70°	80°
20	2.39e+0				7.67e-1			
50	4.24e+0				2.16e+0			
100	6.26e+0	5.52e+0	4.78e+0	4.21e+0	3.89e+0		3.15e+0	2.09e+0
150	7.80e+0	6.95e+0	6.08e+0	5.44e+0	5.09e+0		4.23e+0	
200	9.07e+0	8.12e+0	7.13e+0	6.42e+0	6.01e+0		5.10e+0	3.74e+0
300	1.12e+1	1.00e+1	8.84e+0	7.99e+0	7.55e+0		6.51e+0	
500	1.46e+1				9.81e+0			
900	1.99e+1	1.78e+1	1.57e+1	1.41e+1	1.32e+1		1.17e+1	
1000	2.09e+1	1.88e+1	1.64e+1	1.49e+1	1.38e+1	1.31e+1	1.22e+1	1.05e+1
2000	3.02e+1				2.02e+1			
5000	5.18e+1				3.34e+1			
10000	7.99e+1				5.02e+1			

## Ga → Ga

Ga on Ga, Maxwellian velocity distribution, sheath potential 0 kT  
 $z_1=31$ ,  $m_1 = 69.72$ ,  $z_2=31$ ,  $m_2 = 69.72$ ,  $sbe=2.97$  eV,  $\rho_{\text{ho}} = 5.91$  g/cm\*\*3  
 $ef=2.92$  (2.47) eV,  $esb=2.97$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: testvmcx, newtrim(Laszlo)  
ne=12

kT(eV)	Y	$Y_E$	$E_{sp}$	$R_N$	$R_E$	$E_b$	range
2	2.99e-4	1.90e-4	2.54e+0	6.95e-4	7.41e-4	4.27e+0	1.53e-1
3	1.47e-3	8.26e-4	3.38e+0	3.79e-3	3.38e-3	5.35e+0	3.29e-1
5	8.53e-3	3.81e-3	4.46e+0	1.91e-2	1.47e-2	7.67e+0	6.74e-1
10	4.91e-2	1.55e-2	6.29e+0	7.73e-2	4.91e-2	1.27e+1	1.26e+0
20	1.77e-1	3.76e-2	8.48e+0	1.66e-1	8.96e-2	2.16e+1	2.24e+0
50	5.77e-1	7.00e-2	1.22e+1	2.54e-1	1.16e-1	4.58e+1	4.42e+0
100	1.10e-0	8.75e-2	1.59e+1	2.75e-1	1.16e-1	8.40e+1	6.83e+0
200	1.90e-0	9.78e-2	2.05e+1	2.65e-1	1.01e-1	1.52e+2	1.00e+1
500	3.47e-0	9.96e-2	2.88e+1	2.31e-1	8.28e-2	3.61e+2	1.63e+1
1000	4.98e-0	9.47e-2	3.82e+1	2.05e-1	7.15e-2	6.99e+2	2.36e+1
2000	6.67e-0	8.60e-2	5.10e+1	1.88e-1	6.12e-2	1.29e+3	3.50e+1
5000	9.45e-0	7.25e-2	7.56e+1	1.58e-1	5.07e-2	3.16e+3	5.89e+1

Ga on Ga, Maxwellian velocity distribution, sheath potential 3 kT  
ne=12

kT(eV)	Y	$Y_E$	$E_{sp}$	$R_N$	$R_E$	$E_b$	range
2	1.02e-3	2.54e-4	2.49e+0	8.79e-4	3.38e-4	3.85e+0	1.07e+0
3	5.42e-3	1.15e-3	3.20e+0	4.59e-3	1.55e-3	5.06e+0	1.52e+0
5	2.92e-2	4.85e-3	4.15e+0	1.65e-2	4.73e-3	7.17e+0	2.32e+0
10	1.55e-1	1.73e-2	5.58e+0	4.20e-2	9.64e-3	1.15e+1	3.71e+0
20	4.47e-1	3.28e-2	7.33e+0	5.95e-2	1.07e-2	1.81e+1	5.66e+0
50	1.16e-0	4.56e-2	9.83e+0	6.31e-2	8.67e-3	3.43e+1	9.32e+0
100	1.93e-0	4.85e-2	1.266e+1	5.89e-2	7.14e-3	6.05e+1	1.33e+1
200	2.90e-0	4.77e-2	1.64e+1	5.09e-2	5.54e-3	1.09e+2	1.90e+1
500	4.27e-0	4.08e-2	2.39e+1	4.20e-2	4.18e-3	2.49e+2	3.18e+1
1000	5.30e-0	3.63e-2	3.39e+1	3.73e-2	4.22e-3	5.62e+2	4.59e+1
2000	6.07e-0	2.94e-2	4.78e+1	2.49e-2	1.99e-3	7.88e+2	7.28e+1
5000	7.78e-0	2.10e-2	6.77e+1	2.88e-2	2.78e-3	2.42e+3	1.36e+2

Ga on Ga, Maxwellian velocity distribution, sheath potential 9 kT  
ne=11

kT(eV)	Y	$Y_E$	$E_{sp}$	$R_N$	$R_E$	$E_b$	range
1.4	1.25e-3	1.54e-4	1.90e+0	4.93e-4	1.01e-4	3.15e+0	1.75e+0
2	6.21e-3	7.25e-4	2.57e+0	2.50e-3	4.47e-4	3.92e+0	2.36e+0
5	1.17e-1	8.51e-3	4.00e+0	1.78e-2	2.36e-3	7.27e+0	4.25e+0
10	3.90e-1	1.91e-2	5.38e+0	3.15e-2	3.26e-3	1.14e+1	6.33e+0
20	8.66e-1	2.82e-2	7.15e+0	3.73e-2	3.13e-3	1.85e+1	9.15e+0
50	1.79e-0	3.34e-2	1.03e+1	3.83e-2	2.58e-3	3.71e+1	1.48e+1
100	2.62e-0	3.17e-2	1.33e+1	3.36e-2	2.01e-3	6.57e+1	2.13e+1
200	3.58e-0	2.97e-2	1.83e+1	2.90e-2	1.52e-3	1.15e+2	3.06e+1
500	4.80e-0	2.36e-2	2.71e+1	2.40e-2	1.50e-3	3.43e+2	5.31e+1
1000	5.53e-0	1.89e-2	3.75e+1	2.05e-2	1.23e-3	6.62e+2	7.81e+1
2000	6.41e-0	1.48e-2	5.07e+1	1.75e-2	1.37e-3	1.72e+3	1.27e+2

## Hg → Ga

Sputtering yield of Ga by Hg  
 $z1=80$ ,  $m1=200.59$ ,  $z2=31$ ,  $m2=69.72$ ,  $sbe=2.97$  eV,  $\rho=5.91$  g/cm<sup>3</sup>  
 $ef=2.10$ ,  $esb=2.60$ ,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: newtrim (Laszlo), IPP 9/82  
only low fluence!  $ne=4$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
100	7.97e-2
200	3.20e-1
300	5.62e-1
400	7.90e-1

Sputtered energy of Ga by Hg  
 $z1=80$ ,  $m1=200.59$ ,  $z2=31$ ,  $m2=69.72$ ,  $sbe=2.97$  eV,  $\rho=5.91$  g/cm<sup>3</sup>  
 $ef=2.10$ ,  $esb=2.60$ ,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: newtrim (Laszlo)  
only low fluence!  $ne=4$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
100	2.17e-3
200	6.60e-3
300	9.58e-3
400	1.17e-2

Average depth (mean range) in Å of Hg implanted in Ga  
only low fluence!  $ne=4$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
100	1.02e+1
200	1.42e+1
300	1.70e+1
400	1.94e+1

## Mg → Ge

Particle reflection coefficient of Mg backscattered from Ge  
 $z1=12$ ,  $m1= 24.00$ ,  $z2=32$ ,  $m2= 72.59$ ,  $\rho = 5.32 \text{ g/cm}^{**3}$   
 $ef=1.00 \text{ eV}$ ,  $esb=1.00 \text{ eV}$ ,  $ca=1.00$ ,  $kk0=2$ ,  $kdee1=3$ ,  $ipot=1$  (KrC )  
program: trange3  
only low fluence!  
nem= 2, na= 1

$E_0(\text{eV})$	$0^\circ$
100000	3.55e-2
200000	1.94e-2

Energy reflection coefficient of Mg backscattered from Ge  
only low fluence!  
nem= 2, na= 1

$E_0(\text{eV})$	$0^\circ$
100000	6.72e-3
200000	3.44e-3

Average depth (mean range) in Å of Mg implanted in Ge  
only low fluence!  
nem= 2, na= 1

$E_0(\text{eV})$	$0^\circ$
100000	1.21e+3
200000	2.30e+3

## Al → Ge

Particle reflection coefficient of Al backscattered from Ge  
 $z1=13$ ,  $m1= 27.00$ ,  $z2=32$ ,  $m2= 72.59$ ,  $\rho = 5.32 \text{ g/cm}^{**3}$   
 $ef=1.00 \text{ eV}$ ,  $esb=1.00 \text{ eV}$ ,  $ca=1.00$ ,  $kk0=2$ ,  $kdee1=3$ ,  $ipot=1$  (KrC )  
program: trange3  
only low fluence!  
nem= 2, na= 1

$E_0(\text{eV})$	$0^\circ$
100000	3.24e-2
200000	1.85e-2

Energy reflection coefficient of Al backscattered from Ge  
*only low fluence!*  
nem= 2, na= 1

$E_0(\text{eV})$	$0^\circ$
100000	5.60e-3
200000	3.02e-3

Average depth (mean range) in Å of Al implanted in Ge  
*only low fluence!*  
nem= 2, na= 1

$E_0(\text{eV})$	$0^\circ$
100000	1.12e+3
200000	2.14e+3

## Si → Ge

Particle reflection coefficient of Si backscattered from Ge  
 $z1=14$ ,  $m1= 29.00$ ,  $z2=32$ ,  $m2= 72.59$ ,  $\rho = 5.32 \text{ g/cm}^{**3}$   
 $ef=1.00 \text{ eV}$ ,  $esb=1.00 \text{ eV}$ ,  $ca=1.00$ ,  $kk0=2$ ,  $kdee1=3$ ,  $ipot=1$  (KrC )  
program: trrange3  
*only low fluence!*  
 $nem = 2$ ,  $na = 1$

$E_0(\text{eV})$	$0^\circ$
100000	$3.02\text{e-}2$
200000	$1.74\text{e-}2$

Energy reflection coefficient of Si backscattered from Ge  
*only low fluence!*  
 $nem = 2$ ,  $na = 1$

$E_0(\text{eV})$	$0^\circ$
100000	$5.02\text{e-}3$
200000	$2.70\text{e-}3$

Average depth (mean range) in Å of Si implanted in Ge  
*only low fluence!*  
 $nem = 2$ ,  $na = 1$

$E_0(\text{eV})$	$0^\circ$
100000	$1.04\text{e+}3$
200000	$1.99\text{e+}3$

## P → Ge

Particle reflection coefficient of P backscattered from Ge  
 $z1=15$ ,  $m1= 31.00$ ,  $z2=32$ ,  $m2= 72.59$ ,  $\rho = 5.32 \text{ g/cm}^{**3}$   
 $ef=1.00 \text{ eV}$ ,  $esb=1.00 \text{ eV}$ ,  $ca=1.00$ ,  $kk0=2$ ,  $kdee1=3$ ,  $ipot=1$  (KrC )  
program: trrange3  
*only low fluence!*  
 $nem = 2$ ,  $na = 1$

$E_0(\text{eV})$	$0^\circ$
100000	$2.81\text{e-}2$
200000	$1.67\text{e-}2$

Energy reflection coefficient of P backscattered from Ge  
*only low fluence!*  
 $nem = 2$ ,  $na = 1$

$E_0(\text{eV})$	$0^\circ$
100000	$4.32\text{e-}3$
200000	$2.46\text{e-}3$

Average depth (mean range) in Å of P implanted in Ge  
*only low fluence!*  
 $nem = 2$ ,  $na = 1$

$E_0(\text{eV})$	$0^\circ$
100000	$9.73\text{e+}2$
200000	$1.86\text{e+}3$

## Ar → Ge

Sputtering yield of Ge by Ar  
 z1=18, m1= 39.95, z2=29, m2= 63.54, sbe=3.88 eV, rho= 5.32 g/cm\*\*3  
 ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: IPP 9/82  
 ne=12, na= 1

E <sub>0</sub> (eV)	0°
50	4.42e-2
100	2.06e-1
200	4.88e-1
500	1.01e-0
1000	1.43e-0
2000	1.83e-0
5000	2.29e-0
10000	2.49e-0
20000	2.54e-0
50000	2.32e-0
100000	1.97e-0
200000	1.59e-0

Sputtered energy of Ge by Ar  
 ne=12, na= 1

E <sub>0</sub> (eV)	0°
50	3.10e-3
100	1.04e-2
200	1.71e-2
500	2.17e-2
1000	2.08e-2
2000	1.81e-2
5000	1.37e-2
10000	1.04e-2
20000	7.61e-3
50000	4.16e-3
100000	2.36e-3
200000	1.23e-3

## Ar → Ge

Particle reflection coefficient of Ar backscattered from Ge  
 $z1=18$ ,  $m1=39.95$ ,  $z2=29$ ,  $m2=63.54$ ,  $sbe=3.88$  eV,  $\rho=5.32$  g/cm $^{**3}$   
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program:  
 $ne=12$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
50	2.44e-1
100	1.93e-1
200	1.58e-1
500	1.23e-1
1000	1.02e-1
2000	8.56e-2
5000	7.11e-2
10000	5.83e-2
20000	4.29e-2
50000	2.92e-2
100000	1.91e-2
200000	1.17e-2

Energy reflection coefficient of Ar backscattered from Ge  
 $ne=12$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
50	2.72e-2
100	2.22e-2
200	1.80e-2
500	1.38e-2
1000	1.10e-2
2000	9.52e-3
5000	7.99e-3
10000	6.38e-3
20000	4.86e-3
50000	3.42e-3
100000	2.09e-3
200000	1.29e-3

Average depth (mean range) in Å of Ar implanted in Ge  
 $ne=12$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
50	8.14e+0
100	1.05e+1
200	1.37e+1
500	2.06e+1
1000	2.93e+1
2000	4.32e+1
5000	7.56e+1
10000	1.21e+2
20000	2.03e+2
50000	4.29e+2
100000	8.00e+2
200000	1.53e+3

## Bi → Ge

Average depth (mean range) in Å of Bi implanted in Ge  
 $z1=83$ ,  $m1=209.00$ ,  $z2=32$ ,  $m2=72.59$ ,  $\rho=5.32$  g/cm $^{**3}$   
 $ef=1.00$  eV,  $esb=1.00$  eV,  $ca=1.00$ ,  $kk0=2$ ,  $kdee1=3$ ,  $ipot=1$  (KrC)  
program: trrange3  
only low fluence!  
 $ne=2$ ,  $na=1$

$E_0$ (eV)	$0^\circ$
200000	5.24e+2
400000	8.74e+2

## Xe → Zr

Sputtering yield of Zr by Xe

$z1=54$ ,  $m1=131.30$ ,  $z2=40$ ,  $m2=91.22$ ,  $sbe=6.33$  eV,  $\rho=6.49$  g/cm<sup>3</sup>  
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program : IPP 9/82  
ne = 8, na = 1

$E_0$ (eV)	0°
50	9.70e-5
50	1.47e-4
50	1.27e-4
50	1.27e-4
100	1.13e-2
200	1.01e-1
500	4.33e-1
1000	8.46e-1

Sputtered energy of Zr by Xe  
ne = 8, na = 1

$E_0$ (eV)	0°
50	4.10e-6
50	6.54e-6
50	5.75e-6
50	5.71e-6
100	4.32e-4
200	3.11e-3
500	9.16e-3
1000	1.29e-2

Particle reflection coefficient of Xe backscattered from Zr  
 $z1=54$ ,  $m1=131.30$ ,  $z2=40$ ,  $m2=91.22$ ,  $sbe=6.33$  eV,  $\rho=6.49$  g/cm<sup>3</sup>  
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program :  
ne = 8, na = 1

$E_0$ (eV)	0°
50	7.60e-3
50	7.58e-3
50	6.70e-3
50	5.91e-3
100	5.25e-3
200	5.14e-3
500	4.49e-3
1000	4.27e-3

Energy reflection coefficient of Xe backscattered from Zr  
ne = 8, na = 1

$E_0$ (eV)	0°
50	1.33e-4
50	1.32e-4
50	1.28e-4
50	1.30e-4
100	9.67e-5
200	7.31e-5
500	6.90e-5
1000	6.18e-5

Average depth (mean range) in Å of Xe implanted in Zr  
ne = 7, na = 1

$E_0$ (eV)	0°
50	5.43e+0
50	8.65e+0
50	8.66e+0
50	8.68e+0
100	1.06e+1
200	1.34e+1
1000	2.50e+1

## D → Nb

Sputtering yield of Nb by D

`z1= 1, m1= 2.01, z2=41, m2= 92.91, sbe=7.59 eV, rho= 8.60 g/cm**3  
ef=0.95 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
program: testvmcx, IPP 9/82  
nem= 7, na= 1`

E <sub>0</sub> (eV)	0°
140	2.77e-4
200	1.69e-3
300	4.53e-3
500	8.70e-3
1000	1.34e-2
2000	1.44e-2
5000	1.23e-2

Sputtered energy of Zr by Xe

`program: testvmcx  
nem= 7, na= 1`

E <sub>0</sub> (eV)	0°
140	2.65e-6
200	2.60e-5
300	7.56e-5
500	1.40e-4
1000	1.69e-4
2000	1.26e-4
5000	5.82e-5

Particle reflection coefficient of D backscattered from Nb

`z1= 1, m1= 2.01, z2=41, m2= 92.91, sbe=7.59 eV, rho= 8.60 g/cm**3  
ef=0.95 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
program: testvmcx  
nem= 7, na= 1`

E <sub>0</sub> (eV)	0°
140	5.54e-1
200	5.34e-1
300	5.09e-1
500	4.75e-1
1000	4.20e-1
2000	3.56e-1
5000	2.54e-1

Energy reflection coefficient of D backscattered from Nb  
nem= 7, na= 1

E <sub>0</sub> (eV)	0°
140	3.36e-1
200	3.18e-1
300	2.96e-1
500	2.68e-1
1000	2.25e-1
2000	1.78e-1
5000	1.11e-1

Average depth (mean range) in Å of D implanted in Nb  
nem= 7, na= 1

E <sub>0</sub> (eV)	0°
140	5.55e+1
200	6.87e+1
300	8.82e+1
500	1.23e+2
1000	1.95e+2
2000	3.23e+2
5000	6.55e+2

## H → Mo

Sputtering yield of Mo by H  
 $z1 = 1$ ,  $m1 = 1.01$ ,  $z2 = 42$ ,  $m2 = 95.94$ ,  $sbe = 6.83$  eV,  $\rho = 10.21$  g/cm<sup>3</sup>  
 $ef = 0.95, 0.98$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = 3, 4$ ,  $kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: TESTVMCX, IPP 9/82  
 $n_{\text{e}} = 2$ ,  $n_{\text{a}} = 14$

$E_0$ (eV)	0°	15°	25°	30°	45°	50°	60°	70°	75°	80°	85°	87°
2000	5.99e-3	5.89e-3		7.06e-3	1.05e-2		1.75e-2	2.84e-2	3.87e-2	5.30e-2	5.16e-2	1.90e-2
50000	1.36e-3		1.94e-3			4.95e-3			1.91e-2	3.01e-2	6.63e-2	9.43e-2

$E_0$ (eV)	88°	89°
50000	1.09e-1	6.30e-2

Sputtered energy of Mo by H  
program: TESTVMCX  
 $n_{\text{e}} = 2$ ,  $n_{\text{a}} = 12$

$E_0$ (eV)	0°	15°	30°	45°	60°	70°	75°	80°	85°	87°	88°	89°
2000	3.25e-5	3.23e-5	3.74e-5	6.02e-5	9.92e-5	1.67e-4	2.46e-4	3.54e-4	4.16e-4	1.77e-4	1.08e-4	7.12e-5
50000								2.99e-5	6.27e-5	8.93e-5		

Particle reflection coefficient of H backscattered from Mo  
 $z1 = 1$ ,  $m1 = 1.01$ ,  $z2 = 42$ ,  $m2 = 95.94$ ,  $sbe = 6.83$  eV,  $\rho = 10.21$  g/cm<sup>3</sup>  
 $ef = 0.95, 0.98$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = 3, 4$ ,  $kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: TESTVMCX  
 $n_{\text{e}} = 2$ ,  $n_{\text{a}} = 12$

$E_0$ (eV)	0°	15°	30°	45°	60°	70°	75°	80°	85°	87°	88°	89°
2000	3.37e-1	3.49e-1	3.84e-1	4.45e-1	5.37e-1	6.19e-1	6.69e-1	7.35e-1	8.63e-1	9.66e-1	7.29e-1	8.91e-1
50000								4.15e-1	5.65e-1	6.59e-1	4.02e-1	5.06e-1

Energy reflection coefficient of H backscattered from Mo  
 $n_{\text{e}} = 2$ ,  $n_{\text{a}} = 12$

$E_0$ (eV)	0°	15°	30°	45°	60°	70°	75°	80°	85°	87°	88°	89°
2000	1.59e-1	1.66e-1	1.92e-1	2.38e-1	3.21e-1	4.06e-1	4.68e-1	5.58e-1	7.53e-1	9.21e-1		
50000								1.54e-1	2.88e-1	4.02e-1	5.06e-1	7.84e-1

Average depth (mean range) in Å of H implanted in Mo  
 $n_{\text{e}} = 2$ ,  $n_{\text{a}} = 12$

$E_0$ (eV)	0°	15°	30°	45°	60°	70°	75°	80°	85°	87°	88°	89°
2000	2.51e+2	2.49e+2	2.42e+2	2.34e+2	2.24e+2	2.19e+2	2.17e+2	2.14e+2	2.14e+2	2.14e+2	2.14e+2	2.14e+2
50000								8.18e+2	7.73e+2	7.66e+2	7.62e+2	7.73e+2

## D → Mo

Sputtering yield of Mo by D  
 z1= 1, m1= 2.01, z2=42, m2= 95.94, sbe=6.83 eV, rho=10.21 g/cm\*\*\*  
 ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=3, 4, kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx, trspv1cs, newtrim (Laszlo), IPP 9/82  
 ne=12, na=10

E <sub>0</sub> (eV)	0°	25°	50°	65°	75°	80°	85°	87°	88°	89°
120	1.50e-4			1.34e-4						
130	3.35e-4				3.00e-4					
140	5.81e-4				5.63e-4					
150	8.72e-4				8.62e-4					
170	1.52e-3				1.62e-3					
200	2.86e-3				3.26e-3					
500	1.14e-2				2.42e-2					
1000	1.67e-2				4.59e-2					
2000	1.69e-2				6.51e-2					
5000	1.46e-2				6.30e-2					
50000	3.50e-3	4.70e-3	1.01e-2		4.38e-2	6.84e-2	1.34e-1	1.82e-1	1.98e-1	1.16e-1
100000	2.50e-3	2.62e-3	4.80e-3		2.60e-2	4.59e-2	9.15e-2	1.41e-1	1.58e-1	1.60e-1

Sputtered energy of Mo by D  
 program: testvmcx, trspv1cs, newtrim (Laszlo)  
 ne=12, na= 7

E <sub>0</sub> (eV)	0°	65°	80°	85°	87°	88°	89°
120	1.14e-6	1.21e-6					
130	3.16e-6	2.93e-6					
140	6.01e-6	6.39e-6					
150	1.00e-5	1.06e-5					
170	2.05e-5	2.38e-5					
200	4.35e-5	5.18e-5					
500	1.75e-4	3.80e-4					
1000	2.02e-4	5.58e-4					
2000	1.37e-4	5.87e-4					
5000	6.46e-5	3.15e-4	7.17e-5	1.61e-4	2.43e-4	2.53e-4	1.74e-4
50000			3.26e-5	7.83e-5	1.19e-4	1.24e-4	1.28e-4
100000							

# D → Mo

Particle reflection coefficient of D backscattered from Mo  
 z1= 1, m1= 2.01, z2=42, m2= 95.94, sbe=6.83 eV, rho=10.21 g/cm\*\*3  
 ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=3, 4, kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx, trspv1cs, newtrim (Laszlo)  
 ne=13, na= 7

E <sub>0</sub> (eV)	0°	65°	80°	85°	87°	88°	89°
20	6.71e-1						
120	5.68e-1	7.76e-1					
130	5.65e-1	7.70e-1					
140	5.59e-1	7.65e-1					
150	5.56e-1	7.61e-1					
170	5.48e-1	7.52e-1					
200	5.41e-1	7.43e-1					
500	4.84e-1	6.83e-1					
1000	4.26e-1	6.39e-1					
2000	3.63e-1	5.89e-1					
5000	2.60e-1	5.19e-1					
50000			4.46e-1	5.96e-1	6.81e-1	7.44e-1	8.95e-1
100000			3.67e-1	5.34e-1	6.35e-1	6.92e-1	8.21e-1

Energy reflection coefficient of D backscattered from Mo  
 ne=13, na= 7

E <sub>0</sub> (eV)	0°	65°	80°	85°	87°	88°	89°
20	4.45e-1						
120	3.50e-1	6.05e-1					
130	3.46e-1	5.97e-1					
140	3.42e-1	5.90e-1					
150	3.38e-1	5.84e-1					
170	3.32e-1	5.73e-1					
200	3.24e-1	5.60e-1					
500	2.75e-1	4.90e-1					
1000	2.29e-1	4.38e-1					
2000	1.83e-1	3.85e-1					
5000	1.14e-1	3.10e-1					
50000			1.86e-1	3.26e-1	4.38e-1	5.38e-1	7.99e-1
100000			1.16e-1	2.46e-1	3.58e-1	4.49e-1	6.52e-1

Average depth (mean range) in of D implanted in Mo  
 ne=13, na= 7

E <sub>0</sub> (eV)	0°	65°	80°	85°	87°	88°	89°
20	1.59e+1						
120	4.40e+1	4.19e+1					
130	4.62e+1	4.39e+1					
140	4.82e+1	4.58e+1					
150	5.03e+1	4.76e+1					
170	5.41e+1	5.14e+1					
200	5.99e+1	5.66e+1					
500	1.06e+2	9.88e+1					
1000	1.70e+2	1.55e+2					
2000	2.80e+2	2.50e+2					
5000	5.67e+2	4.81e+2					
50000			1.10e+3	1.05e+3	1.04e+3	1.05e+3	1.06e+3
100000			1.55e+3	1.43e+3	1.42e+3	1.41e+3	1.41e+3

## D → Mo

D on Mo, Maxwellian velocity distribution, sheath potential 0 kT  
 z1= 1, m1= 2.01, z2=42, m2= 95.94, sbe=6.89 eV, rho=10.20 g/cm\*\*3  
 ef=0.90 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: newtrim (Laszlo)  
 ne= 8

kT(eV)	Y	$Y_E$	$E_{sp}$	$R_N$	$R_E$	$E_b$	range
40	3.27e-4	1.52e-5	3.71e+0	7.26e-1	5.09e-1	5.60e+1	3.45e+1
50	7.49e-4	3.12e-5	4.16e+0	7.14e-1	4.93e-1	6.92e+1	3.91e+1
100	4.57e-3	1.42e-4	6.23e+0	6.71e-1	4.46e-1	1.33e+2	5.86e+1
200	1.21e-2	2.83e-4	9.40e+0	6.31e-1	4.00e-1	2.54e+2	9.03e+1
500	2.77e-2	3.80e-4	1.37e+1	5.66e-1	3.36e-1	5.95e+2	1.66e+2
1000	3.57e-2	2.77e-4	1.56e+1	5.18e-1	2.87e-1	1.12e+3	2.73e+2
2000	3.81e-2	2.09e-4	2.19e+1	4.53e-1	2.27e-1	2.00e+3	4.49e+2
5000	3.73e-2	1.05e-4	2.82e+1	3.61e-1	1.55e-1	4.29e+3	9.09e+2

D on Mo, Maxwellian velocity distribution, sheath potential 3 kT  
 ne= 9

kT(eV)	Y	$Y_E$	$E_{sp}$	$R_N$	$R_E$	$E_b$	range
20	1.86e-4	4.06e-6	2.19e+0	6.09e-1	3.93e-1	6.45e+1	3.90e+1
30	9.74e-4	2.07e-5	3.19e+0	5.87e-1	3.70e-1	9.46e+1	4.95e+1
50	4.51e-3	8.39e-5	4.65e+0	5.57e-1	3.40e-1	1.53e+2	6.72e+1
100	1.23e-2	1.97e-4	8.00e+0	5.14e-1	3.02e-1	2.94e+2	1.04e+2
200	1.77e-2	2.15e-4	1.22e+1	4.59e-1	2.57e-1	5.61e+2	1.66e+2
500	2.15e-2	1.49e-4	1.72e+1	3.79e-1	1.92e-1	1.26e+3	3.21e+2
1000	1.99e-2	8.92e-5	2.24e+1	3.06e-1	1.40e-1	2.29e+3	5.44e+2
2000	1.54e-2	3.93e-5	2.55e+1	2.16e-1	8.58e-2	3.97e+3	9.46e+2
4000	1.05e-2	1.43e-5	2.73e+1	1.35e-1	4.52e-2	6.69e+3	1.66e+3

## T → Mo

Sputtering yield of Mo by T

```

z1= 1, m1= 3.02, z2=42, m2= 95.94, sbe=6.89 eV, rho=10.20 g/cm***3
ef=0.90 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program: newtrim, IPP 9/82
nem= 7, na= 2

```

E <sub>0</sub> (eV)	0°	65°
100	9.32e-4	7.36e-4
170	6.67e-3	8.00e-3
300	1.59e-2	2.93e-2
500	2.20e-2	5.84e-2
1000	2.73e-2	9.33e-2
2000	2.90e-2	1.01e-1
5000	2.58e-2	9.56e-2

Sputtered energy of Mo by T

```

program: newtrim
nem= 7, na= 2

```

E <sub>0</sub> (eV)	0°	65°
100	1.45e-5	1.28e-5
170	1.57e-4	2.00e-4
300	3.37e-4	7.16e-4
500	4.43e-4	1.18e-3
1000	4.31e-4	1.44e-3
2000	2.78e-4	1.09e-3
5000	1.32e-4	5.25e-4

Particle reflection coefficient of T backscattered from Mo

```

z1= 1, m1= 3.02, z2=42, m2= 95.94, sbe=6.89 eV, rho=10.20 g/cm***3
ef=0.90 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program: newtrim
nem= 7, na= 2

```

E <sub>0</sub> (eV)	0°	65°
100	5.58e-1	7.77e-1
170	5.33e-1	7.40e-1
300	4.98e-1	7.08e-1
500	4.68e-1	6.83e-1
1000	4.20e-1	6.37e-1
2000	3.61e-1	5.94e-1
5000	2.68e-1	5.21e-1

Energy reflection coefficient of T backscattered from Mo  
nem= 7, na= 2

E <sub>0</sub> (eV)	0°	65°
100	3.39e-1	6.07e-1
170	3.16e-1	5.58e-1
300	2.88e-1	5.20e-1
500	2.63e-1	4.89e-1
1000	2.27e-1	4.34e-1
2000	1.83e-1	3.99e-1
5000	1.21e-1	3.20e-1

Average depth (mean range) in of T implanted in Mo  
nem= 7, na= 2

E <sub>0</sub> (eV)	0°	65°
100	3.78e+1	3.58e+1
170	5.21e+1	4.89e+1
300	7.49e+1	6.96e+1
500	1.05e+2	9.68e+1
1000	1.70e+2	1.55e+2
2000	2.88e+2	2.56e+2
5000	5.95e+2	5.08e+2

# T → Mo

T on Mo, Maxwellian velocity distribution, sheath potential 0 kT  
 z1= 1, m1= 2.01, z2=42, m2= 95.94, sbe=6.89 eV, rho=10.20 g/cm\*\*3  
 ef=0.90 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: newtrim (Laszlo)  
 ne=10

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
30	5.42e-4	3.62e-5	4.02e+0	7.28e-1	5.12e-1	4.22e+1	2.76e+1
40	1.49e-3	8.85e-5	4.77e+0	7.11e-1	4.92e-1	5.53e+1	3.26e+1
70	6.27e-3	2.88e-4	6.46e+0	6.81e-1	4.56e-1	9.42e+1	4.57e+1
100	1.10e-2	4.18e-4	7.60e+0	6.58e-1	4.33e-1	1.32e+2	5.66e+1
170	2.23e-2	6.64e-4	1.01e+1	6.29e-1	4.01e-1	2.15e+2	7.87e+1
300	3.81e-2	8.09e-4	1.28e+1	5.92e-1	3.64e-1	3.70e+2	1.15e+2
500	4.99e-2	8.12e-4	1.64e+1	5.62e-1	3.38e-1	6.03e+2	1.67e+2
1000	5.75e-2	6.24e-4	2.17e+1	5.06e-1	2.83e-1	1.12e+3	2.82e+2
2000	6.42e-2	4.20e-4	2.60e+1	4.51e-1	2.31e-1	2.03e+3	4.73e+2
5000	5.52e-2	2.01e-4	3.63e+1	3.69e-1	1.68e-1	4.54e+3	9.86e+2

T on Mo, Maxwellian velocity distribution, sheath potential 3 kT  
 ne=10

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
20	7.85e-4	2.65e-5	3.37e+0	5.90e-1	3.73e-1	6.32e+1	3.71e+1
40	7.49e-3	2.18e-4	5.81e+0	5.55e-1	3.39e-1	1.22e+2	5.64e+1
70	1.79e-2	4.42e-4	8.61e+0	5.21e-1	3.09e-1	2.08e+2	8.06e+1
100	2.48e-2	5.30e-4	1.07e+1	5.00e-1	2.94e-1	2.95e+2	1.02e+2
170	3.13e-2	5.00e-4	1.35e+1	4.65e-1	2.62e-1	4.78e+2	1.48e+2
300	3.40e-2	4.07e-4	1.80e+1	4.22e-1	2.30e-1	8.18e+2	2.24e+2
500	3.44e-2	2.92e-4	2.12e+1	3.78e-1	1.96e-1	1.30e+3	3.31e+2
1000	3.23e-2	1.66e-4	2.57e+1	3.11e-1	1.47e-1	2.37e+3	5.75e+2
2000	2.51e-2	8.08e-5	3.21e+1	2.27e-1	9.50e-2	4.18e+3	1.02e+3
5000	1.36e-2	2.01e-5	3.71e+1	1.25e-1	4.19e-1	8.39e+3	2.22e+3

## He → Mo

Sputtering yield of Mo by He  
 $z1 = 2$ ,  $m1 = 4.00$ ,  $z2 = 42$ ,  $m2 = 95.94$ ,  $sbe = 6.83$  eV,  $\rho = 10.21$  g/cm<sup>3</sup>  
 $ef = 0.50$  eV,  $esb = 0.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = 5$ ,  $kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: testvmcx, IPP 9/82  
 $nem = 2$ ,  $nam = 9$

$E_0$ (eV)	0°	25°	50°	75°	80°	85°	87°	88°	89°
50000	2.64e-2	3.50e-2	6.95e-2	2.45e-1	3.75e-1	6.17e-1	6.56e-1	5.91e-1	9.49e-2
100000	1.67e-2	2.27e-2	3.97e-2	1.64e-1	2.40e-1	4.47e-1	6.04e-1	6.10e-1	3.65e-1

Sputtered energy of Mo by He  
program: testvmcx  
 $nem = 2$ ,  $nam = 5$

$E_0$ (eV)	80°	85°	87°	88°	89°
50000	5.93e-4	1.12e-3	1.31e-3	1.27e-3	2.04e-4
100000	2.70e-4	5.08e-4	6.78e-4	7.90e-4	5.06e-4

Particle reflection coefficient of He backscattered from Mo  
 $z1 = 2$ ,  $m1 = 4.00$ ,  $z2 = 42$ ,  $m2 = 95.94$ ,  $sbe = 6.83$  eV,  $\rho = 10.21$  g/cm<sup>3</sup>  
 $ef = 0.50$  eV,  $esb = 0.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = 5$ ,  $kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: testvmcx  
 $nem = 2$ ,  $nam = 5$

$E_0$ (eV)	80°	85°	87°	88°	89°
50000	4.85e-1	6.14e-1	6.98e-1	7.93e-1	9.73e-1
100000	4.15e-1	5.77e-1	6.61e-1	7.42e-1	8.88e-1

Energy reflection coefficient of He backscattered from Mo  
 $nem = 2$ ,  $nam = 5$

$E_0$ (eV)	80°	85°	87°	88°	89°
50000	2.41e-1	3.77e-1	4.94e-1	6.30e-1	9.47e-1
100000	1.70e-1	3.15e-1	4.23e-1	5.29e-1	7.88e-1

Average depth (mean range) in of He implanted in Mo  
 $nem = 2$ ,  $nam = 5$

$E_0$ (eV)	80°	85°	87°	88°	89°
50000	6.57e+2	6.23e+2	6.43e+2	6.50e+2	6.73e+2
100000	9.82e+2	9.31e+2	9.08e+2	9.18e+2	9.29e+2

# He → Mo

Sputtering yield of Mo (7 isotopes) by He  
 z1 = 2, m1 = 4.00, z2=42, sbe=6.83 eV, rho=10.21 g/cm\*\*\*3  
 ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 m2 = 91.91, 93.91, 94.91, 95.90, 96.91, 97.91, 99.91  
 c2=0.1483, 0.0925, 0.1592, 0.1668, 0.0956, 0.2413, 0.0963  
 alpha=0.00  
 program: trvmc95  
 ne=12, na= 1, n(m2)= 7

E <sub>0</sub> (eV)	m2=91.91	93.91	94.91	95.90	96.91	97.91	99.91	nh
70	1.466e-4	7.796e-5	1.226e-4	1.176e-4	6.176e-5	1.432e-4	4.763e-5	850000000
70	1.470e-4	7.734e-5	1.224e-4	1.180e-4	6.169e-5	1.422e-4	4.737e-5	850000000
70	1.465e-4	7.712e-5	1.228e-4	1.176e-4	6.205e-5	1.419e-4	4.791e-5	600000000
100	9.730e-4	5.651e-4	9.390e-4	9.465e-4	5.251e-4	1.274e-3	4.730e-4	600000000
100	9.730e-4	5.660e-4	9.387e-4	9.466e-4	5.239e-4	1.274e-3	4.736e-4	190000000
100	9.699e-4	5.665e-4	9.394e-4	9.493e-4	5.219e-4	1.276e-3	4.721e-4	160000000
200	4.490e-3	2.711e-3	4.586e-3	4.722e-3	2.664e-3	6.620e-3	2.560e-3	350000000
500	1.018e-2	6.231e-3	1.064e-2	1.106e-2	6.279e-3	1.571e-2	6.168e-3	250000000
1000	1.347e-2	8.282e-3	1.415e-2	1.472e-2	8.379e-3	2.101e-2	8.275e-3	150000000
2000	1.535e-2	9.469e-3	1.619e-2	1.687e-2	9.610e-3	2.413e-2	9.514e-3	90000000
5000	1.519e-2	9.366e-3	1.604e-2	1.670e-2	9.542e-3	2.393e-2	9.451e-3	50000000
5000	1.518e-2	9.369e-3	1.603e-2	1.676e-2	9.546e-3	2.403e-2	9.493e-3	15000064

Sputtered energy of Mo (7 isotopes) by He  
 ne=12, na= 1, n(m2)= 7

E <sub>0</sub> (eV)	m2=91.91	93.91	94.91	95.90	96.91	97.91	99.91	nh
70	2.713e-6	1.348e-6	2.050e-6	1.897e-6	9.614e-7	2.156e-6	6.657e-7	850000000
70	2.714e-6	1.337e-6	2.046e-6	1.910e-6	9.611e-7	2.144e-6	6.634e-7	850000000
70	2.709e-6	1.333e-6	2.049e-6	1.902e-6	9.649e-7	2.133e-6	6.744e-7	600000000
100	2.767e-5	1.555e-5	2.538e-5	2.518e-5	1.375e-5	3.283e-5	1.181e-5	600000000
100	2.766e-5	1.559e-5	2.550e-5	2.515e-5	1.373e-5	3.285e-5	1.178e-5	190000000
100	2.746e-5	1.553e-5	2.541e-5	2.527e-5	1.369e-5	3.289e-5	1.177e-5	160000000
200	1.431e-4	8.493e-5	1.422e-4	1.449e-4	8.128e-5	2.000e-4	7.604e-5	350000000
500	2.500e-4	1.511e-4	2.560e-4	2.641e-4	1.491e-4	3.707e-4	1.436e-4	250000000
1000	2.389e-4	1.447e-4	2.459e-4	2.548e-4	1.439e-4	3.591e-4	1.399e-4	150000000
2000	1.825e-4	1.112e-4	1.887e-4	1.955e-4	1.107e-4	2.769e-4	1.083e-4	90000000
5000	9.999e-5	6.063e-5	1.035e-4	1.072e-4	6.139e-5	1.520e-4	5.911e-5	50000000
5000	9.963e-5	6.116e-5	1.035e-4	1.075e-4	6.100e-5	1.523e-4	5.950e-5	15000064

## He → Mo

Particle reflection coefficient of He backscattered from Mo (7 isotopes)  
 z1= 2, m1= 4.00, z2=42, sbe=6.83 eV, rho=10.21 g/cm\*\*3  
 ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kddee1=kddee2=3, ipot=ipotr=1 (KrC)  
 m2= 91.91, 93.91, 94.91, 95.90, 96.91, 97.91, 99.91  
 c2=0.1483, 0.0925, 0.1592, 0.1668, 0.0956, 0.2413, 0.0963  
 alpha=0.00  
 program: trvmc95  
 ne=12, na= 1

$E_0$ (eV)	$0^\circ$	nh
70	5.9232e-1	850000000
70	5.9231e-1	850000000
70	5.9231e-1	600000000
100	5.7147e-1	600000000
100	5.7148e-1	190000000
100	5.7146e-1	160000000
200	5.3703e-1	350000000
500	4.9565e-1	250000000
1000	4.6152e-1	150000000
2000	4.2144e-1	90000000
5000	3.5541e-1	50000000
5000	3.5512e-1	15000064

Energy reflection coefficient of He backscattered from Mo (7 isotopes)  
 ne=12, na= 1

$E_0$ (eV)	$0^\circ$	nh
70	3.6532e-1	850000000
70	3.6532e-1	850000000
70	3.6533e-1	600000000
100	3.4733e-1	600000000
100	3.4735e-1	190000000
100	3.4733e-1	160000000
200	3.1877e-1	350000000
500	2.8680e-1	250000000
1000	2.6180e-1	150000000
2000	2.3298e-1	90000000
5000	1.8597e-1	50000000
5000	1.8583e-1	15000064

Average depth (mean range) in Å of He implanted in Mo (7 isotopes)  
 ne=12, na= 1

$E_0$ (eV)	$0^\circ$	nh
70	2.0181e+1	850000000
70	2.0180e+1	850000000
70	2.0179e+1	600000000
100	2.4804e+1	600000000
100	2.4804e+1	190000000
100	2.4805e+1	160000000
200	3.7600e+1	350000000
500	6.7532e+1	250000000
1000	1.0880e+2	150000000
2000	1.8160e+2	90000000
5000	3.7809e+2	50000000
5000	3.7819e+2	15000064

## C → Mo

```

C on Mo, Maxwellian velocity distribution, sheath potential 9 kT
z1= 6, m1= 12.01, z2=42, m2= 95.94, sbe=6.83 eV, rho=10.21 g/cm**3
ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1(KrC)
program: trvmc
only low fluence!
ne= 4

```

kT(eV)	Y	Y_E	E_sp	R_N	R_E	E_b	range
5	1.19e-2	8.05e-4	3.71e+0	5.53e-1	2.65e-1	2.64e+1	7.44e+0
10	7.12e-2	4.66e-3	7.21e+0	4.85e-1	2.22e-1	5.03e+1	1.07e+1
20	1.80e-1	9.44e-3	1.15e+1	4.29e-1	1.88e-1	9.65e+1	1.55e+1
40	3.22e-1	1.18e-2	1.61e+1	3.90e-1	1.64e-1	1.85e+2	2.31e+1

## O → Mo

```

Sputtering yield of Mo by O)
z1= 8, m1= 16.00, z2=42, m2= 95.94, sbe=6.83 eV, rho=10.20 g/cm**3
ef=0.95 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program: IPP 9/82
only low fluence!
ne= 9, na= 1

```

E_0(eV)	0°
20	2.80e-4
30	3.60e-3
40	1.22e-2
50	2.15e-2
70	5.48e-2
100	1.07e-1
200	2.28e-1
500	4.51e-1
1000	6.42e-1

## Ne → Mo

Sputtering yield of Mo (7 isotopes) by Ne  
 z1=10, m1= 20.18, z2=42, sbe=6.83 eV, rho=10.21 g/cm\*\*3  
 ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 m2= 91.91, 93.91, 94.91, 95.90, 96.91, 97.91, 99.91  
 c2=0.1483, 0.0925, 0.1592, 0.1668, 0.0956, 0.2413, 0.0963  
 alpha=0.00  
 program: trvmc95  
 ne= 2, na= 1, n(m2)= 7

E <sub>0</sub> (eV)	m2=91.91	93.91	94.91	95.90	96.91	97.91	99.91	nh
100	1.499e-2	9.102e-3	1.546e-2	1.597e-2	9.033e-2	2.252e-2	8.754e-3	350000000
100	1.494e-2	9.083e-3	1.541e-2	1.592e-2	9.004e-3	2.245e-2	8.730e-3	350000000

Sputtered energy of Mo (7 isotopes) by Ne  
 ne= 2, na= 1, n(m2)= 7

E <sub>0</sub> (eV)	m2=91.91	93.91	94.91	95.90	96.91	97.91	99.91	nh
100	1.162e-3	6.982e-4	1.178e-3	1.210e-3	6.809e-4	1.688e-3	6.487e-4	350000000
100	1.157e-3	6.951e-4	1.173e-3	1.205e-3	6.770e-4	1.680e-3	6.455e-4	350000000

Particle reflection coefficient of Ne backscattered from Mo (7 isotopes)

z1=10, m1= 20.18, z2=42, sbe=6.83 eV, rho=10.21 g/cm\*\*3  
 ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 m2= 91.91, 93.91, 94.91, 95.90, 96.91, 97.91, 99.91  
 c2=0.1483, 0.0925, 0.1592, 0.1668, 0.0956, 0.2413, 0.0963  
 alpha=0.00  
 program: trvmc95  
 ne= 2, na= 1

E <sub>0</sub> (eV)	0°	nh
100	4.3782e-1	350000000
100	4.3782e-1	350000000

Energy reflection coefficient of Ne backscattered from Mo (7 isotopes)

ne= 2, na= 1

E <sub>0</sub> (eV)	0°	nh
100	1.5043e-1	350000000
100	1.5043e-1	350000000

Average depth (mean range) in Å of Ne implanted in Mo (7 isotopes)

ne= 2, na= 1

E <sub>0</sub> (eV)	0°	nh
100	7.6080e+0	350000000
100	7.6258e+0	350000000

# Ar → Mo

Sputtering yield of Mo (2 isotopes) by Ar  
 z1=18, m1= 39.95, z2=42, m2= 92.00, 100.00, sbe=6.83 eV, rho=10.21 g/cm\*\*3  
 ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 alpha=0.00  
 program: testvmcx, trvmc  
 ne= 8, na= 1, n(m2)= 2

E <sub>0</sub> (eV)	m2=92.00	100.00	92	100	nh
5000	1.096e-0	1.065e-0	0.5000	0.5000	2000000
5000	1.096e-0	1.066e-0	0.5000	0.5000	2000000
5000	1.094e-0	1.065e-0	0.5000	0.5000	1500000
5000	1.078e-0	1.079e-0	0.4930	0.5070	2000000
5000	1.079e-0	1.082e-0	0.4920	0.5080	2000000
5000	1.072e-0	1.086e-0	0.4900	0.5100	2000000
10000	1.243e-0	1.211e-0	0.5000	0.5000	1600000
10000	1.225e-0	1.225e-0	0.4935	0.5065	1700000

Sputtered energy of Mo (2 isotopes) by Ar  
 ne= 8, na= 1, n(m2)= 2

E <sub>0</sub> (eV)	m2=92.00	100.00	92	100	nh
5000	9.773e-3	9.226e-3	0.5000	0.5000	2000000
5000	9.786e-3	9.239e-3	0.5000	0.5000	2000000
5000	9.753e-3	9.253e-3	0.5000	0.5000	1500000
5000	9.638e-3	9.362e-3	0.4930	0.5070	2000000
5000	9.643e-3	9.395e-3	0.4920	0.5080	2000000
5000	9.576e-3	9.431e-3	0.4900	0.5100	2000000
10000	7.501e-3	7.061e-3	0.5000	0.5000	1600000
10000	7.366e-3	7.134e-3	0.4935	0.5065	1700000

Particle reflection coefficient of Ar backscattered from Mo (2 isotopes)  
 z1=18, m1= 39.95, z2=42, m2= 92.00, 100.00, sbe=6.83 eV, rho=10.21 g/cm\*\*3  
 ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 alpha=0.00  
 program: testvmcx, trvmc  
 ne= 8, na= 1

E <sub>0</sub> (eV)	0°	92	100	nh
5000	1.2234e-1	0.5000	0.5000	2000000
5000	1.2257e-1	0.5000	0.5000	2000000
5000	1.2208e-1	0.5000	0.5000	1500000
5000	1.2281e-1	0.4930	0.5070	2000000
5000	1.2308e-1	0.4920	0.5080	2000000
5000	1.2240e-1	0.4900	0.5100	2000000
10000	1.0202e-1	0.5000	0.5000	1600000
10000	1.0170e-1	0.4935	0.5065	1700000

Energy reflection coefficient of Ar backscattered from Mo (2 isotopes)  
 ne= 8, na= 1

E <sub>0</sub> (eV)	0°	92	100	nh
5000	1.9446e-2	0.5000	0.5000	2000000
5000	1.9386e-2	0.5000	0.5000	2000000
5000	1.9323e-2	0.5000	0.5000	1500000
5000	1.9436e-2	0.4930	0.5070	2000000
5000	1.9469e-2	0.4920	0.5080	2000000
5000	1.9393e-2	0.4900	0.5100	2000000
10000	1.6201e-2	0.5000	0.5000	1600000
10000	1.6227e-2	0.4935	0.5065	1700000

Average depth (mean range) in of Ar implanted in Mo (2 isotopes)  
 ne= 8, na= 1

E <sub>0</sub> (eV)	0°	92	100	nh
5000	4.7541e+1	0.5000	0.5000	2000000
5000	4.7528e+1	0.5000	0.5000	2000000
5000	4.7615e+1	0.5000	0.5000	1500000
5000	4.7580e+1	0.4930	0.5070	2000000
5000	4.7609e+1	0.4920	0.5080	2000000
5000	4.7609e+1	0.4900	0.5100	2000000
10000	7.5684e+1	0.5000	0.5000	1600000
10000	7.5765e+1	0.4935	0.5065	1700000

# Ar → Mo

Sputtering yield of Mo (7 isotopes) by Ar  
 z1=18, m1= 39.95, z2=42, sbe=6.83 eV, rho=10.21 g/cm\*\*3  
 ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 m2= 91.91, 93.91, 94.91, 95.90, 96.91, 97.91, 99.91  
 c2=0.1483, 0.0925, 0.1592, 0.1668, 0.0956, 0.2413, 0.0963  
 alpha=0.00, rd=50.00  
 program: trvrmc95  
 ne=20, na= 4, n(m2)= 7

E <sub>0</sub> (eV)	m2=91.91	93.91	94.91	95.90	96.91	97.91	99.91	nh	comment
50	1.113e-3	6.586e-4	1.105e-3	1.130e-3	6.305e-4	1.551e-3	5.871e-4	500000000	
70	4.954e-3	2.987e-3	5.056e-3	5.205e-3	2.934e-3	7.276e-3	2.803e-3	300000000	
70	4.961e-3	2.988e-3	5.055e-3	5.211e-3	2.936e-3	7.278e-3	2.802e-3	500000000	
100	1.363e-2	8.311e-3	1.415e-2	1.465e-2	8.297e-3	2.068e-2	8.064e-3	200000000	
100	1.363e-2	8.308e-3	1.413e-2	1.463e-2	8.296e-3	2.068e-2	8.065e-3	350000000	
200	4.522e-2	2.780e-2	4.748e-2	4.938e-2	2.808e-2	7.047e-2	2.770e-2	100000000	
200	4.522e-2	2.781e-2	4.751e-2	4.942e-2	2.811e-2	7.042e-2	2.771e-2	210000000	
500	1.127e-1	6.958e-2	1.191e-1	1.241e-1	7.074e-2	1.776e-1	7.013e-2	80000000	
1000	1.772e-1	1.096e-1	1.877e-1	1.958e-1	1.117e-1	2.806e-1	1.110e-1	50000000	
2000	2.479e-1	1.534e-1	2.630e-1	2.744e-1	1.568e-1	3.942e-1	1.560e-1	25000064	
5000	3.358e-1	2.083e-1	3.570e-1	3.725e-1	2.129e-1	5.358e-1	2.122e-1	10000000	
5000	3.362e-1	2.083e-1	3.572e-1	3.729e-1	2.131e-1	5.360e-1	2.126e-1	15000064	
10000	3.836e-1	2.377e-1	4.070e-1	4.259e-1	2.431e-1	6.119e-1	2.427e-1	8000000	
20000	3.985e-1	2.470e-1	4.241e-1	4.427e-1	2.528e-1	6.368e-1	2.525e-1	9000064	
20000	4.005e-1	2.483e-1	4.262e-1	4.454e-1	2.544e-1	6.401e-1	2.536e-1	9000064	rd=60.00 Å
100	1.571e-2	9.564e-3	1.625e-2	1.684e-2	9.542e-3	2.378e-2	9.264e-3	350000000	alpha=15°
100	2.173e-2	1.321e-2	2.246e-2	2.322e-2	1.315e-2	3.276e-2	1.275e-2	350000000	alpha=30°
100	3.005e-2	1.832e-2	3.114e-2	3.224e-2	1.826e-2	4.556e-2	1.775e-2	400000000	alpha=60°
100	1.477e-2	9.007e-3	1.535e-2	1.588e-2	9.011e-3	2.248e-2	8.774e-3	240000000	zbl
5000	3.743e-1	2.321e-1	3.980e-1	4.155e-1	2.378e-1	5.979e-1	2.370e-1	10000000	zbl

Sputtered energy of Mo (7 isotopes) by Ar  
 ne=20, na= 4, n(m2)= 7

E <sub>0</sub> (eV)	m2=91.91	93.91	94.91	95.90	96.91	97.91	99.91	nh	comment
50	9.598e-5	5.629e-5	9.446e-5	9.605e-5	5.344e-5	1.310e-4	4.917e-5	500000000	
70	4.123e-4	2.469e-4	4.163e-4	4.272e-4	2.400e-4	5.940e-4	2.273e-4	300000000	
70	4.125e-4	2.470e-4	4.165e-4	4.279e-4	2.403e-4	5.936e-4	2.273e-4	500000000	
100	1.027e-3	6.234e-4	1.058e-3	1.091e-3	6.166e-4	1.531e-3	5.940e-4	200000000	
100	1.028e-3	6.226e-4	1.056e-3	1.091e-3	6.161e-4	1.531e-3	5.938e-4	350000000	
200	2.500e-3	1.529e-3	2.606e-3	2.702e-3	1.533e-3	3.834e-3	1.500e-3	100000000	
200	2.500e-3	1.529e-3	2.605e-3	2.704e-3	1.533e-3	3.835e-3	1.500e-3	210000000	
500	3.737e-3	2.294e-3	3.912e-3	4.068e-3	2.314e-3	5.794e-3	2.278e-3	80000000	
1000	3.956e-3	2.434e-3	4.152e-3	4.320e-3	2.456e-3	6.157e-3	2.423e-3	50000000	
2000	3.710e-3	2.283e-3	3.896e-3	4.049e-3	2.310e-3	5.781e-3	2.275e-3	25000064	
5000	2.985e-3	1.835e-3	3.131e-3	3.260e-3	1.853e-3	4.649e-3	1.831e-3	10000000	
5000	2.986e-3	1.834e-3	3.135e-3	3.265e-3	1.857e-3	4.644e-3	1.830e-3	15000064	
10000	2.322e-3	1.421e-3	2.427e-3	2.530e-3	1.435e-3	3.604e-3	1.417e-3	8000000	
20000	1.651e-3	1.013e-3	1.734e-3	1.800e-3	1.019e-3	2.562e-3	9.997e-4	9000064	
20000	1.660e-3	1.018e-3	1.739e-3	1.808e-3	1.031e-3	2.569e-3	1.009e-3	9000064	rd=60.00 Å
100	1.294e-3	7.833e-4	1.327e-3	1.373e-3	7.754e-4	1.927e-3	7.467e-4	350000000	alpha=15°
100	2.166e-3	1.310e-3	2.223e-3	2.292e-3	1.295e-3	3.219e-3	1.248e-3	350000000	alpha=30°
100	4.992e-3	3.028e-3	5.132e-3	5.298e-3	2.993e-3	7.447e-3	2.887e-3	400000000	alpha=60°
100	1.148e-3	6.959e-4	1.183e-3	1.219e-3	6.905e-4	1.718e-3	6.666e-4	240000000	zbl
5000	3.501e-3	1.876e-3	3.189e-3	3.319e-3	1.891e-3	4.746e-3	1.868e-3	10000000	zbl

# Ar → Mo

Particle reflection coefficient of Ar backscattered from Mo (7 isotopes)  
 z1=18, m1= 39.95, z2=42, sbe=6.83 eV, rho=10.21 g/cm\*\*3  
 ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 m2= 91.91, 93.91, 94.91, 95.90, 96.91, 97.91, 99.91  
 c2=0.1483, 0.0925, 0.1592, 0.1668, 0.0956, 0.2413, 0.0963  
 alpha=0.00, rd=50.00  
 program: trvrmc95  
 ne=20, na= 4, n(m2)= 7

E <sub>0</sub> (eV)	0°	nh	comment
50	4.082e-1	500000000	
70	3.711e-1	300000000	
70	3.711e-1	500000000	
100	3.337e-1	200000000	
100	3.338e-1	350000000	
200	2.725e-1	100000000	
200	2.727e-1	210000000	
500	2.140e-1	80000000	
1000	1.819e-1	50000000	
2000	1.565e-1	25000064	
5000	1.284e-1	10000000	
5000	1.283e-1	15000064	
10000	1.088e-1	8000000	
20000	8.981e-2	9000064	rd=60.00 Å
20000	8.988e-2	9000064	
100	3.584e-1	350000000	alpha=15°
100	4.326e-1	350000000	alpha=30°
100	7.666e-1	400000000	alpha=60°
100	3.834e-1	240000000	zbl
5000	1.232e-1	10000000	zbl

Energy reflection coefficient of Ar backscattered from Mo (7 isotopes)  
 ne=20, na= 4, n(m2)= 7

E <sub>0</sub> (eV)	0°	nh	comment
50	7.077e-2	500000000	
70	6.549e-2	300000000	
70	6.550e-2	500000000	
100	5.937e-2	200000000	
100	5.938e-2	350000000	
200	4.806e-2	100000000	
200	4.810e-2	210000000	
500	3.660e-2	80000000	
1000	3.055e-2	50000000	
2000	2.612e-2	25000064	
5000	2.163e-2	10000000	
5000	2.163e-2	15000064	
10000	1.871e-2	8000000	
20000	1.581e-2	9000064	rd=60.00 Å
20000	1.585e-2	9000064	
100	7.092e-2	350000000	alpha=15°
100	1.112e-1	350000000	alpha=30°
100	4.006e-1	400000000	alpha=60°
100	7.006e-2	240000000	zbl
5000	2.169e-2	10000000	zbl

Average depth (mean range) in Å of Ar implanted in Mo (7 isotopes)  
 ne=20, na= 4, n(m2)= 7

E <sub>0</sub> (eV)	0°	nh	comment
50	3.963e+0	500000000	
70	4.675e+0	300000000	
70	4.675e+0	500000000	
100	5.569e+0	200000000	
100	5.569e+0	350000000	
200	7.874e+0	100000000	
200	7.873e+0	210000000	
500	1.268e+1	80000000	
1000	1.853e+1	50000000	
2000	2.766e+1	25000064	
5000	4.901e+1	10000000	
5000	4.899e+1	15000064	
10000	7.877e+1	8000000	
20000	1.323e+2	9000064	rd=60.00 Å
20000	1.324e+2	9000064	
100	5.501e+0	350000000	alpha=15°
100	5.322e+0	350000000	alpha=30°
100	4.654e+0	400000000	alpha=60°
100	4.243e+0	240000000	zbl
5000	4.397e+1	10000000	zbl

## Kr → Mo

Sputtering yield of Mo by Kr

$z1=36$ ,  $m1= 83.80$ ,  $z2=42$ ,  $m2= 95.94$ ,  $sbe=6.89$  eV,  $\rho=10.20$  g/cm $^{**3}$   
 $ef=0.30$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: trspvnc, trvnc  
ne= 6, na= 2

$E_0$ (eV)	$0^\circ$	$45^\circ$
50	9.15e-4	
53		3.40e-2
100	3.20e-2	
500	6.36e-1	
1000	1.19e-0	
5000	2.69e-0	

Sputtered energy of Mo by Kr  
ne= 6, na= 2

$E_0$ (eV)	$0^\circ$	$45^\circ$
50	5.54e-5	
53		4.86e-3
100	1.67e-3	
500	1.63e-2	
1000	2.08e-2	
5000	1.95e-2	

Particle reflection coefficient of Kr backscattered from Mo

$z1=36$ ,  $m1= 83.80$ ,  $z2=42$ ,  $m2= 95.94$ ,  $sbe=6.89$  eV,  $\rho=10.20$  g/cm $^{**3}$   
 $ef=0.30$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: trspvnc, trvnc  
ne= 6, na= 2

$E_0$ (eV)	$0^\circ$	$45^\circ$
50	1.44e-1	
53		4.52e-1
100	1.23e-1	
500	8.89e-2	
1000	6.92e-2	
5000	4.19e-2	

Energy reflection coefficient of Kr backscattered from Mo  
ne= 6, na= 2

$E_0$ (eV)	$0^\circ$	$45^\circ$
50	6.90e-3	
53		1.05e-1
100	5.89e-3	
500	3.97e-3	
1000	3.26e-3	
5000	2.37e-3	

Average depth (mean range) in Å of Kr implanted in Mo  
ne= 6, na= 2

$E_0$ (eV)	$0^\circ$	$45^\circ$
50	3.33e+0	
53		2.65e+0
100	4.85e+0	
500	1.08e+1	
1000	1.52e+1	
5000	3.61e+1	

# Mo → Mo

Sputtering yield of Mo by Mo  
 $z1=42$ ,  $m1 = 95.94$ ,  $z2=42$ ,  $m2 = 95.94$ ,  $sbe=6.89$ ,  $6.83$  eV,  $\rho=10.21$  g/cm\*\*\*  
 $ef=6.39$ ,  $6.78$  eV,  $esb=6.89$ ,  $6.83$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: newtrim (Laszlo), testvmcx, IPP 9/82  
ne=28, na=14

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$45^\circ$	$50^\circ$	$55^\circ$	$57.5^\circ$	$60^\circ$	$62.5^\circ$	$65^\circ$
15												$2.04e-4$
17												$3.88e-4$
18												$5.49e-4$
20												$6.49e-4$
25	$6.90e-6$											$4.04e-3$
30	$2.61e-5$											$1.15e-2$
35	$7.30e-5$											
40	$7.56e-5$											
42	$1.27e-4$											
45	$2.45e-4$											
48	$4.44e-4$											
50	$6.36e-4$											
65	$3.87e-3$											
80	$1.04e-2$											
100	$2.59e-2$											
200	$1.51e-1$											
250	$2.46e-1$											
300	$3.15e-1$	$3.61e-1$	$4.84e-1$	$6.50e-1$	$8.68e-1$							$9.92e-1$
350	$3.90e-1$	$4.51e-1$	$5.71e-1$	$7.83e-1$	$9.94e-1$	$1.10e-0$	$1.04e-0$	$1.07e-0$	$1.07e-0$	$1.07e-0$	$1.04e-0$	$1.19e-0$
500	$6.14e-1$											$1.53e-0$
1000	$1.12e-0$	$1.20e-0$	$1.44e-0$	$1.77e-0$	$2.17e-0$	$2.41e-0$	$2.60e-0$	$2.73e-0$	$2.81e-0$	$2.82e-0$	$2.80e-0$	$2.71e-0$
2000	$1.76e-0$	$1.87e-0$	$2.21e-0$	$2.53e-0$	$3.28e-0$							$4.38e-0$
5000	$2.88e-0$											
10000	$3.42e-0$											
20000	$3.96e-0$											
45000	$4.87e-0$											
50000	$4.88e-0$											
100000	$4.11e-0$											

$E_0$ (eV)	$70^\circ$	$80^\circ$
300	$8.53e-1$	$3.99e-1$
350	$9.84e-1$	$4.55e-1$
1000		$1.18e-0$
2000	$4.11e-0$	$2.21e-0$

Sputtered energy of Mo by Mo  
program: newtrim (Laszlo), testvmcx  
ne=27, na=14

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$45^\circ$	$50^\circ$	$55^\circ$	$57.5^\circ$	$60^\circ$	$62.5^\circ$	$65^\circ$
15												$3.40e-5$
17												$6.70e-5$
18												$9.49e-5$
20												$1.26e-4$
25	$3.37e-7$											$8.11e-4$
30	$1.32e-6$											$2.45e-3$
35	$3.78e-6$											
40	$4.75e-6$											
42	$7.68e-6$											
45	$1.55e-5$											
48	$2.76e-5$											
50	$3.89e-5$											
65	$2.25e-4$											
80	$5.51e-4$											
100	$1.27e-3$											
200	$5.76e-3$											
250	$8.21e-3$											
300	$9.82e-3$	$1.23e-2$	$2.15e-2$	$3.66e-2$	$6.36e-2$							$1.29e-1$
350	$1.10e-2$	$1.45e-2$	$2.30e-2$	$4.03e-2$	$6.77e-2$	$8.51e-2$	$9.80e-2$	$1.12e-1$	$1.20e-1$	$1.25e-1$	$1.26e-1$	$1.38e-1$
500	$1.47e-2$											$1.51e-1$
1000	$1.89e-2$	$2.17e-2$	$3.18e-2$	$4.94e-2$	$7.78e-2$	$9.88e-2$	$1.17e-1$	$1.36e-1$	$1.52e-1$	$1.56e-1$	$1.67e-1$	$1.75e-1$
2000	$1.99e-2$	$2.41e-2$	$3.17e-2$	$4.56e-2$	$7.59e-2$							$1.79e-1$
5000	$2.04e-2$											
10000	$1.60e-2$											
20000	$1.39e-2$											
50000	$1.07e-2$											
100000	$5.69e-3$											

$E_0$ (eV)	$70^\circ$	$80^\circ$
300	$1.20e-1$	$6.03e-2$
350	$1.29e-1$	$6.45e-1$
1000		$9.86e-2$
2000	$1.94e-1$	$1.32e-1$

## Mo → Mo

Particle reflection coefficient of Mo backscattered from Mo  
 $z1=42$ ,  $m1=95.94$ ,  $z2=42$ ,  $m2=95.94$ ,  $sbe=6.89$ ,  $6.83$  eV,  $\rho=10.21$  g/cm\*\*\*  
 $ef=6.39$ ,  $6.78$  eV,  $esb=6.89$ ,  $6.83$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: newtrim (Laszlo), testvmcx  
ne=28, na=14

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$45^\circ$	$50^\circ$	$55^\circ$	$57.5^\circ$	$60^\circ$	$62.5^\circ$	$65^\circ$
15												6.12e-5
17												3.62e-4
18												7.06e-4
20												1.88e-3
25												1.14e-2
30												3.33e-2
35	3.04e-7											
40	8.33e-6											
42	1.15e-5											
45	2.28e-5											
48	4.46e-5											
50	6.97e-5											
50	2.87e-4											1.67e-1
65	3.12e-4											3.62e-1
80	9.97e-4											4.46e-1
100	2.12e-3											5.41e-1
200	1.07e-2											
265	1.04e-2											
300	1.24e-2	1.98e-2	3.37e-2	7.45e-2	1.40e-1	1.86e-1	2.47e-1	3.33e-1	3.77e-1	4.29e-1	4.67e-1	5.38e-1
350	1.36e-2	1.96e-2	3.70e-2	7.22e-2	1.40e-1	1.86e-1	2.51e-1	3.24e-1	3.67e-1	4.16e-1	4.70e-1	5.29e-1
500	2.02e-2											5.13e-1
1000	2.40e-2	2.60e-2	4.06e-2	6.85e-2	1.13e-1	1.51e-1	2.05e-1	2.68e-1	2.89e-1	3.41e-1	3.91e-1	4.34e-1
2000	2.85e-2	3.05e-2	3.63e-2	6.35e-2	1.07e-1			1.93e-1	2.15e-1	2.51e-1	2.95e-1	3.79e-1
5000	2.04e-2											3.12e-1
10000	2.20e-2											2.78e-1
20000	1.67e-2											2.38e-1
50000	8.80e-3											2.26e-1
100000												2.20e-1

$E_0$ (eV)	$70^\circ$	$80^\circ$
300	6.63e-1	9.07e-1
350	6.59e-1	9.07e-1
1000		8.72e-1
2000	4.88e-1	8.20e-1

Energy reflection coefficient of Mo backscattered from Mo  
ne=29, na=14

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$45^\circ$	$50^\circ$	$55^\circ$	$57.5^\circ$	$60^\circ$	$62.5^\circ$	$65^\circ$
15												1.35e-5
17												8.03e-5
18												1.57e-4
20												4.31e-4
25												2.78e-3
30	3.00e-9											8.83e-3
35	1.85e-8											
40	5.66e-7											
42	6.67e-7											
45	1.51e-6											
48	2.97e-6											
50	5.05e-6											
50	2.36e-5											5.40e-2
65	2.15e-5											
80	6.66e-5											1.29e-1
100	1.21e-4											1.68e-1
200	6.24e-4											2.25e-1
265	5.67e-4											
300	6.36e-4	1.22e-3	2.87e-3	9.32e-3	2.42e-2	3.79e-2	6.30e-2	1.01e-1	1.22e-1	1.52e-1	1.89e-1	2.26e-1
350	6.85e-4	1.16e-3	3.05e-3	8.25e-3	2.49e-2		6.15e-2	9.63e-2	1.20e-1	1.46e-1	1.81e-1	2.21e-1
500	9.14e-4											2.13e-1
500	1.11e-3											
1000	9.35e-4	1.64e-3	2.81e-3	7.20e-3	1.61e-2	2.65e-2	4.45e-2	6.70e-2	8.12e-2	1.04e-1	1.33e-1	1.67e-1
2000	1.07e-3	1.14e-3	2.05e-3	5.24e-3	1.41e-2		3.77e-2	4.81e-2	6.45e-2	7.94e-2	1.02e-1	1.33e-1
5000	8.24e-4											9.42e-2
10000	8.85e-4											8.24e-2
20000	5.31e-4											6.47e-2
50000	4.91e-4											6.17e-2
100000												6.09e-2

$E_0$ (eV)	$70^\circ$	$80^\circ$
300	3.31e-1	6.05e-1
350	3.27e-1	6.16e-1
1000		6.15e-1
2000	2.06e-1	5.64e-1

## Mo → Mo

Average depth (mean range) in Å of Mo implanted in Mo  
 z1=42, m1 = 95.94, z2=42, m2 = 95.94, sbe=6.89, 6.83 eV, rho=10.21 g/cm\*\*\*  
 ef=6.39, 6.78 eV, esb=6.89, 6.83 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: newtrim (Laszlo), testvmcx  
 ne=28, na=14

$E_0$ (eV)	0°	10°	20°	30°	40°	45°	50°	55°	57.5°	60°	62.5°	65°
15												3.09e-1
17												3.33e-1
18												3.45e-1
20												3.60e-1
25	1.67e+0											4.22e-1
30	1.92e+0											5.05e-1
35	2.13e+0											
40	1.92e+0											
42	2.00e+0											
45	2.11e+0											
48	2.22e+0											
50	2.33e+0											
50	2.88e+0											8.00e-1
65	3.16e+0											
80	3.67e+0											
100	4.19e+0											1.38e+0
200	6.14e+0											1.82e+0
265	6.92e+0											3.40e+0
300	7.60e+0	7.50e+0	7.22e+0	6.81e+0	6.26e+0		5.58e+0	5.32e+0	5.10e+0	4.89e+0	4.77e+0	4.48e+0
350	8.32e+0	8.20e+0	7.99e+0	7.37e+0	6.84e+0	6.45e+0	6.15e+0	5.75e+0	5.69e+0	5.36e+0	5.17e+0	5.01e+0
500	9.97e+0											6.08e+0
1000	1.45e+1	1.39e+1	1.36e+1	1.27e+1	1.17e+1	1.14e+1	1.06e+1	1.03e+1	9.71e+0	9.60e+0	9.34e+0	8.95e+0
2000	2.07e+1	1.99e+1	1.96e+1	1.85e+1	1.67e+1		1.53e+1	1.41e+1	1.41e+1	1.35e+1	1.30e+1	1.25e+1
5000	3.41e+1											2.05e+1
10000	4.99e+1											3.00e+1
20000	7.53e+1											4.58e+1
50000	1.40e+2											8.29e+1
100000	2.40e+2											1.35e+2

$E_0$ (eV)	70°	80°
300	4.09e+0	2.86e+0
350	4.62e+0	3.26e+0
1000		6.88e+0
2000	1.16e+1	9.99e+0

## Mo → Mo

Mo on Mo, Maxwellian velocity distribution, sheath potential 0 kT  
 z1=42, m1= 95.94, z2=42, m2= 95.94, sbe=6.89, 6.83 eV, rho=10.20 g/cm\*\*\*  
 ef=6.39, 6.78 eV, esb=6.89, 6.83 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: newtrim (Laszlo), testvmcx  
 ne=12

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
5	4.52e-4	2.70e-4	5.96e+0	9.49e-4	9.60e-4	1.01e+1	3.11e-1
7	1.68e-3	9.30e-4	7.78e+0	3.94e-3	3.48e-3	1.24e+1	4.75e-1
10	5.73e-3	2.77e-3	9.69e+0	1.31e-2	1.06e-2	1.63e+1	6.82e-1
20	3.89e-2	1.29e-2	1.33e+1	6.02e-2	3.94e-2	2.63e+1	1.26e+0
50	2.01e-1	4.17e-2	2.08e+1	1.64e-1	8.67e-2	5.27e+1	2.57e+0
100	4.90e-1	6.56e-2	2.67e+1	2.27e-1	1.04e-1	9.16e+1	4.24e+0
200	9.48e-1	7.58e-2	3.14e+1	2.62e-1	1.11e-1	1.66e+2	6.60e+0
500	1.87e-0	9.43e-2	5.13e+1	2.63e-1	8.87e-2	3.44e+2	1.16e+1
1000	3.00e-0	9.74e-2	6.47e+1	2.16e-1	8.32e-2	7.67e+2	1.55e+1
2000	4.23e-0	1.18e-1	1.13e+2	2.29e-1	7.18e-2	1.26e+3	2.40e+1
5000	6.15e-0	8.80e-2	1.35e+2	2.06e-1	8.81e-2	4.05e+3	3.76e+1
10000	8.54e-0	7.72e-2	1.76e+2	1.55e-1	4.41e-2	5.54e+3	5.63e+1

Mo on Mo, Maxwellian velocity distribution, sheath potential 3 kT  
 ne=13

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
4	5.91e-4	1.47e-4	4.96e+0	4.64e-4	1.87e-4	8.06e+0	1.11e+0
5	1.60e-3	3.75e-4	5.86e+0	1.34e-3	4.95e-4	9.27e+0	1.35e+0
7	5.67e-3	1.21e-3	7.49e+0	4.46e-3	1.49e-3	1.17e+1	1.76e+0
10	1.97e-2	3.50e-3	8.88e+0	1.16e-2	3.48e-3	1.50e+1	2.27e+0
20	1.14e-1	1.37e-2	1.21e+1	3.34e-2	7.91e-3	2.36e+1	3.61e+0
50	4.69e-1	3.17e-2	1.69e+1	5.56e-2	9.56e-3	4.30e+1	6.23e+0
100	9.48e-1	4.10e-2	2.16e+1	5.94e-2	8.20e-3	6.90e+1	9.05e+0
200	1.57e-0	4.61e-2	2.95e+1	5.54e-2	5.29e-3	9.58e+1	1.31e+1
500	2.60e-0	3.68e-2	3.52e+1	4.50e-2	3.80e-3	2.11e+2	2.04e+1
1000	3.69e-0	3.63e-2	4.93e+1	4.73e-2	4.84e-3	5.13e+2	3.08e+1
2000	4.40e-0	3.44e-2	7.81e+1	4.29e-2	3.83e-3	8.96e+2	4.72e+1
5000	5.65e-0	2.47e-2	1.08e+2	2.26e-2	1.28e-3	1.41e+3	7.97e+1
10000	6.23e-0	1.85e-2	1.47e+2	2.33e-2	2.98e-3	6.34e+3	1.26e+2

Mo on Mo, Maxwellian velocity distribution, sheath potential 9 kT  
 ne=15

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
2.4	3.27e-4	4.18e-5	3.38e+0	9.20e-5	1.95e-5	5.59e+0	1.57e+0
3	9.41e-4	1.16e-4	4.07e+0	3.37e-4	7.17e-5	7.03e+0	1.87e+0
4	3.47e-3	4.12e-4	5.22e+0	1.43e-3	2.61e-4	8.03e+0	2.30e+0
5	8.61e-3	9.54e-4	6.10e+0	3.02e-3	5.21e-4	9.50e+0	2.68e+0
7	3.01e-2	2.86e-3	7.32e+0	7.37e-3	1.11e-3	1.16e+1	3.32e+0
10	8.06e-2	6.23e-3	8.51e+0	1.44e-2	1.90e-3	1.45e+1	4.13e+0
20	2.93e-1	1.52e-2	1.14e+1	2.56e-2	2.77e-3	2.38e+1	6.16e+0
30	5.00e-1	2.06e-2	1.36e+1	3.19e-2	2.96e-3	3.06e+1	7.66e+0
50	8.46e-1	2.60e-2	1.69e+1	3.50e-2	2.77e-3	4.35e+1	9.97e+0
100	1.47e-0	2.98e-2	2.23e+1	3.70e-2	2.44e-3	7.27e+1	1.43e+1
200	2.21e-0	3.00e-2	2.99e+1	3.32e-2	2.25e-3	1.49e+2	2.05e+1
500	3.28e-0	2.66e-2	4.45e+1	2.85e-2	1.72e-3	3.32e+2	3.38e+1
1000	4.11e-0	2.31e-2	6.17e+1	2.50e-2	1.49e-3	6.56e+2	5.06e+1
2000	4.80e-0	1.80e-2	8.23e+1	1.63e-2	4.95e-4	6.66e+2	7.61e+1
5000	5.41e-0	1.37e-2	1.38e+2	9.06e-3	8.90e-4	5.36e+3	1.48e+2

## Xe → Mo

Sputtering yield of Mo (2 isotopes) by Xe  
 z1=54, m1=131.30, z2=42, m2= 92.00, 100.00, sbe=6.83 eV, rho=10.21 g/cm\*\*3  
 ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 alpha=0.00  
 program: trvmc  
 ne= 4, na= 1, n(m2)= 2

E <sub>0</sub> (eV)	m2=92.00	100.00	c2(92)	c2(100)
5000	1.457e-0	1.419e-0	0.5000	0.5000
5000	1.437e-0	1.438e-0	0.4935	0.5065
10000	1.917e-0	1.871e-0	0.5000	0.5000
10000	1.894e-0	1.896e-0	0.4940	0.5060

Sputtered energy of Mo (2 isotopes) by Xe  
 ne= 4, na= 1, n(m2)= 2

E <sub>0</sub> (eV)	m2=92.00	100.00	c2(92)	c2(100)
5000	9.875e-3	9.406e-3	0.5000	0.5000
5000	9.759e-3	9.563e-3	0.4935	0.5065
10000	8.936e-3	8.500e-3	0.5000	0.5000
10000	8.847e-3	8.628e-3	0.4940	0.5060

Particle reflection coefficient of Xe backscattered from Mo (2 isotopes)  
 z1=54, m1=131.30, z2=42, m2= 92.00, 100.00, sbe=6.83 eV, rho=10.21 g/cm\*\*3  
 ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 alpha=0.00  
 program: trvmc  
 ne= 4, na= 1

E <sub>0</sub> (eV)	0°	c2(92)	c2(100)
5000	6.6469e-3	0.5000	0.5000
5000	6.5269e-3	0.4935	0.5065
10000	5.4627e-3	0.5000	0.5000
10000	5.4736e-3	0.4940	0.5060

Energy reflection coefficient of Xe backscattered from Mo (2 isotopes)  
 ne= 4, na= 1

E <sub>0</sub> (eV)	0°	c2(92)	c2(100)
5000	1.0724e-4	0.5000	0.5000
5000	1.1108e-4	0.4935	0.5065
10000	9.6071e-5	0.5000	0.5000
10000	9.7227e-5	0.4940	0.5060

Average depth (mean range) in Å of Xe implanted in Mo (2 isotopes)  
 ne= 4, na= 1

E <sub>0</sub> (eV)	0°	c2(92)	c2(100)
5000	3.3742e+1	0.5000	0.5000
5000	3.3737e+1	0.4935	0.5065
10000	4.8992e+1	0.5000	0.5000
10000	4.8991e+1	0.4940	0.5060

## Xe → Mo

Sputtering yield of Mo (7 isotopes) by Xe  
 z1=54, m1=131.30, z2=42, sbe=6.83 eV, rho=10.21 g/cm\*\*3  
 ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 m2= 91.91, 93.91, 94.91, 95.90, 96.91, 97.91, 99.91  
 c2=0.1483, 0.0925, 0.1592, 0.1668, 0.0956, 0.2413, 0.0963  
 alpha=0.00  
 program: trvmc95  
 ne= 2, na= 1, n(m2)= 7

E <sub>0</sub> (eV)	m2=91.91	93.91	94.91	95.90	96.91	97.91	99.91	nh
100	1.838e-3	1.120e-3	1.901e-3	1.969e-3	1.114e-3	2.777e-3	1.082e-3	1500000000
100	1.837e-3	1.118e-3	1.894e-3	1.968e-3	1.113e-3	2.781e-3	1.083e-3	400000000

Sputtered energy of Mo (7 isotopes) by Xe  
 ne= 2, na= 1, n(m2)= 7

E <sub>0</sub> (eV)	m2=91.91	93.91	94.91	95.90	96.91	97.91	99.91	nh
100	7.508e-5	4.579e-5	7.770e-5	8.056e-5	4.556e-5	1.137e-5	4.432e-5	1500000000
100	7.511e-5	4.570e-5	7.748e-5	8.057e-5	4.562e-5	1.138e-5	4.443e-5	400000000

Particle reflection coefficient of Xe backscattered from Mo (7 isotopes)  
 z1=54, m1=131.30, z2=42, sbe=6.83 eV, rho=10.21 g/cm\*\*3  
 ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 m2= 91.91, 93.91, 94.91, 95.90, 96.91, 97.91, 99.91  
 c2=0.1483, 0.0925, 0.1592, 0.1668, 0.0956, 0.2413, 0.0963  
 alpha=0.00  
 program: trvmc95  
 ne= 2, na= 1

E <sub>0</sub> (eV)	0°	nh
100	9.5655e-3	1500000000
100	9.5666e-3	400000000

Energy reflection coefficient of Xe backscattered from Mo (7 isotopes)  
 ne= 2, na= 1

E <sub>0</sub> (eV)	0°	nh
100	1.6728e-4	1500000000
100	1.6738e-4	400000000

Average depth (mean range) in Å of Xe implanted in Mo (7 isotopes)  
 ne= 2, na= 1

E <sub>0</sub> (eV)	0°	nh
100	4.8206e+0	1500000000
100	4.8206e+0	400000000

## Hg → Mo

Sputtering yield of Mo by Hg  
 z1=80, m1=200.59, z2=42, m2= 95.94, sbe=6.83 eV, rho=10.20 g/cm\*\*3  
 ef=0.95 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: IPP 9/82  
 only low fluence!  
 ne=12, na= 1

E <sub>0</sub> (eV)	0°
50	3.70e-5
100	5.30e-3
200	7.52e-2
500	4.13e-1
1000	9.39e-1
2000	1.62e-0
5000	2.73e-0
10000	3.74e-0
20000	4.72e-0
50000	5.89e-0
100000	6.74e-0
200000	7.09e-0

# Rn → Mo

Sputtering yield of Mo (7 isotopes) by Rn  
 z1=86, m1=222.00, z2=42, sbe=6.83 eV, rho=10.21 g/cm\*\*3  
 ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 m2= 91.91, 93.91, 94.91, 95.90, 96.91, 97.91, 99.91  
 c2=0.1483, 0.0925, 0.1592, 0.1668, 0.0956, 0.2413, 0.0963  
 alpha=0.00  
 program: trvmc95  
 ne= 4, na= 1, n(m2)= 7

E <sub>0</sub> (eV)	m2=91.91	93.91	94.91	95.90	96.91	97.91	99.91	nh
100	6.991e-4	4.259e-4	7.237e-4	7.484e-4	4.244e-4	1.057e-4	4.118e-4	1500000000
100	7.002e-4	4.270e-4	7.238e-4	7.496e-4	4.242e-4	1.056e-4	4.107e-4	900000000
100	6.983e-4	4.256e-4	7.244e-4	7.509e-4	4.239e-4	1.054e-4	4.137e-4	350000000
5000	4.320e-1	2.679e-1	4.588e-1	4.795e-1	2.742e-1	6.890e-1	2.733e-1	10000000

Sputtered energy of Mo (7 isotopes) by Rn  
 ne= 4, na= 1, n(m2)= 7

E <sub>0</sub> (eV)	m2=91.91	93.91	94.91	95.90	96.91	97.91	99.91	nh
100	2.515e-5	1.533e-5	2.610e-5	2.698e-5	1.533e-5	3.817e-5	1.488e-5	1500000000
100	2.518e-5	1.540e-5	2.608e-5	2.704e-5	1.528e-5	3.814e-5	1.483e-5	900000000
100	2.510e-5	1.529e-5	2.603e-5	2.706e-5	1.532e-5	3.802e-5	1.494e-5	350000000
5000	2.692e-3	1.662e-3	2.843e-3	2.960e-3	1.684e-3	4.231e-3	1.672e-3	10000000

Particle reflection coefficient of Rn backscattered from Mo (7 isotopes)

z1=86, m1=222.00, z2=42, sbe=6.83 eV, rho=10.21 g/cm\*\*3  
 ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 m2= 91.91, 93.91, 94.91, 95.90, 96.91, 97.91, 99.91  
 c2=0.1483, 0.0925, 0.1592, 0.1668, 0.0956, 0.2413, 0.0963  
 alpha=0.00  
 program: trvmc95  
 ne= 4, na= 1

E <sub>0</sub> (eV)	0°	nh
100	2.9659e-5	1500000000
100	2.9227e-5	900000000
100	2.9600e-5	350000000
5000	2.1510e-4	10000000

Energy reflection coefficient of Rn backscattered from Mo (7 isotopes)  
 ne= 4, na= 1

E <sub>0</sub> (eV)	0°	nh
100	2.0536e-7	1500000000
100	2.0395e-7	900000000
100	2.0724e-7	350000000
5000	9.4885e-7	10000000

Average depth (mean range) in Å of Rn implanted in Mo (7 isotopes)  
 ne= 4, na= 1

E <sub>0</sub> (eV)	0°	nh
100	6.5227e+0	1500000000
100	6.5227e+0	900000000
100	6.5225e+0	350000000
5000	3.8657e+1	10000000

## He → Pd

Sputtering yield of Pd by He

```

z1= 2, m1= 4.00, z2=46, m2=106.40, sbe=3.91 eV, rho=11.96 g/cm***3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : trspvmcx
ne= 3, na= 1

```

E <sub>0</sub> (eV)	30°
500	1.42e-1
1000	1.81e-1
1500	2.00e-1

Sputtered energy of Pd by He  
ne= 3, na= 1

E <sub>0</sub> (eV)	30°
500	2.44e-3
1000	2.11e-3
1500	1.73e-3

Particle reflection coefficient He backscattered from Pd

```

z1= 2, m1= 4.00, z2=46, m2=106.40, sbe=3.91 eV, rho=11.96 g/cm***3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : trspvmcx
ne= 3, na= 1

```

E <sub>0</sub> (eV)	30°
500	5.22e-1
1000	4.83e-1
1500	4.52e-1

Energy reflection coefficient He backscattered from Pd  
ne= 3, na= 1

E <sub>0</sub> (eV)	30°
500	2.99e-1
1000	2.68e-1
1500	2.46e-1

Average depth (mean range) in Å of He implanted in Pd  
ne= 3, na= 1

E <sub>0</sub> (eV)	30°
500	5.63e+1
1000	8.68e+1
1500	1.13e+2

## Xe → Pd

Sputtering yield of Pd by Xe

```

z1=54, m1=131.30, z2=46, m2=106.40, sbe=3.91 eV, rho=11.96 g/cm**3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kddee1=kddee2=3, ipot=ipotr=1 (KrC)
program : trspvmcx
ne= 3, na= 1

```

E <sub>0</sub> (eV)	30°
500	1.95e-0
1000	3.24e-0
1500	4.08e-0

Sputtered energy of Pd by Xe  
ne= 3, na= 1

E <sub>0</sub> (eV)	30°
500	6.04e-2
1000	6.43e-2
1500	6.22e-2

Particle reflection coefficient Xe backscattered from Pd

```

z1=54, m1=131.30, z2=46, m2=106.40, sbe=3.91 eV, rho=11.96 g/cm**3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kddee1=kddee2=3, ipot=ipotr=1 (KrC)
program : trspvmcx
ne= 3, na= 1

```

E <sub>0</sub> (eV)	30°
500	7.42e-2
1000	6.84e-2
1500	5.34e-2

Energy reflection coefficient Xe backscattered from Pd  
ne= 3, na= 1

E <sub>0</sub> (eV)	30°
500	5.33e-3
1000	4.32e-3
1500	3.43e-3

Average depth (mean range) in Å of Xe implanted in Pd  
ne= 3, na= 1

E <sub>0</sub> (eV)	30°
500	8.74e+0
1000	1.20e+1
1500	1.48e+1

# D → Ag

Sputtering yield of Ag by D

```

z1= 1, m1= 2.01, z2=47, m2=107.87, rho=10.47 g/cm***3
ef=0.95 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program: testvmcx
ne= 6, na= 3, n(sbe)= 5

```

sbe	2.66 eV	2.76 eV	2.87 eV	2.91 eV	2.95 eV	2.76 eV	2.95 eV	2.76 eV	2.87 eV	2.95 eV
E <sub>0</sub> (eV)	0°	0°	0°	0°	0°	50°	50°	70°	70°	70°
50	2.51e-4	1.45e-4	1.02e-4	5.11e-5	3.81e-5					
55	6.54e-4	4.46e-4	2.99e-4	2.43e-4	2.06e-4					
60	1.25e-3	9.58e-4	6.69e-4	5.92e-4	5.24e-4	9.07e-4	4.78e-4	3.75e-4	2.59e-4	1.99e-4
70	2.91e-3	2.33e-3	1.89e-3	1.67e-3	1.54e-3					
80	4.92e-3	4.13e-3	3.45e-3	3.23e-3	2.99e-3					
100	9.39e-3	8.28e-3	7.25e-3	6.79e-3	6.59e-3					

Sputtered energy of Ag by D

```
ne= 6, na= 3, n(sbe)= 5
```

sbe	2.66 eV	2.76 eV	2.87 eV	2.91 eV	2.95 eV	2.76 eV	2.95 eV	2.76 eV	2.87 eV	2.95 eV
E <sub>0</sub> (eV)	0°	0°	0°	0°	0°	50°	50°	70°	70°	70°
50	1.60e-6	7.87e-7	4.59e-7	2.10e-7	1.45e-7					
55	5.46e-6	3.35e-6	2.02e-6	1.59e-6	1.25e-6					
60	1.26e-5	8.69e-6	5.66e-6	4.87e-6	4.20e-6	8.73e-6	4.04e-6	3.54e-6	2.24e-6	1.57e-6
70	3.42e-5	2.66e-5	2.07e-5	1.80e-5	1.72e-5					
80	6.47e-5	5.29e-5	4.26e-5	3.95e-5	3.67e-5					
100	1.35e-4	1.17e-4	1.03e-4	9.44e-5	9.09e-5					

Particle reflection coefficient of D backscattered from Ag

```

z1= 1, m1= 2.01, z2=47, m2=107.87, rho=10.47 g/cm***3
ef=0.95 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program: testvmcx
ne= 6, na= 3, n(sbe)= 5

```

sbe	2.66 eV	2.76 eV	2.87 eV	2.91 eV	2.95 eV	2.76 eV	2.95 eV	2.76 eV	2.87 eV	2.95 eV
E <sub>0</sub> (eV)	0°	0°	0°	0°	0°	50°	50°	70°	70°	70°
50	6.26e-1	6.26e-1	6.37e-1	6.26e-1	6.26e-1					
55	6.22e-1	6.21e-1	6.21e-1	6.21e-1	6.21e-1					
60	6.17e-1	6.17e-1	6.17e-1	6.17e-1	6.17e-1	7.29e-1	7.29e-1	8.68e-1	8.68e-1	8.68e-1
70	6.09e-1	6.09e-1	6.10e-1	6.09e-1	6.09e-1					
80	6.02e-1	6.02e-1	6.02e-1	6.03e-1	6.02e-1					
100	5.91e-1	5.91e-1	5.91e-1	5.90e-1	5.91e-1					

Energy reflection coefficient of D backscattered from Ag

```
ne= 6, na= 3, n(sbe)= 5
```

sbe	2.66 eV	2.76 eV	2.87 eV	2.91 eV	2.95 eV	2.76 eV	2.95 eV	2.76 eV	2.87 eV	2.95 eV
E <sub>0</sub> (eV)	0°	0°	0°	0°	0°	50°	50°	70°	70°	70°
50	4.08e-1	4.08e-1	4.14e-1	4.08e-1	4.08e-1					
55	4.03e-1	4.03e-1	4.03e-1	4.03e-1	4.03e-1					
60	3.99e-1	3.98e-1	3.99e-1	3.99e-1	3.99e-1	5.35e-1	5.35e-1	7.41e-1	7.41e-1	7.41e-1
70	3.90e-1	3.90e-1	3.91e-1	3.90e-1	3.90e-1					
80	3.83e-1	3.83e-1	3.83e-1	3.84e-1	3.83e-1					
100	3.72e-1	3.72e-1	3.72e-1	3.71e-1	3.72e-1					

Average depth (mean range) in Å of D implanted in Ag

```
ne= 6, na= 3, n(sbe)= 5
```

sbe	2.66 eV	2.76 eV	2.87 eV	2.91 eV	2.95 eV	2.76 eV	2.95 eV	2.76 eV	2.87 eV	2.95 eV
E <sub>0</sub> (eV)	0°	0°	0°	0°	0°	50°	50°	70°	70°	70°
50	3.00e+1	3.00e+1	2.23e+1	3.00e+1	3.00e+1					
55	3.16e+1	3.16e+1	3.16e+1	3.16e+1	3.16e+1					
60	3.32e+1	3.31e+1	3.31e+1	3.31e+1	3.31e+1	3.23e+1	3.23e+1	3.18e+1	3.17e+1	3.17e+1
70	3.62e+1	3.61e+1	3.61e+1	3.61e+1	3.61e+1					
80	3.89e+1	3.89e+1	3.89e+1	3.89e+1	3.89e+1					
100	4.41e+1	4.41e+1	4.41e+1	4.41e+1	4.41e+1					

## He → Ag

Sputtering yield of Ag by He

```

z1= 2, m1= 4.00, z2=47, m2=107.87, sbe=2.97 eV, rho=10.47 g/cm***3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=1, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program:
nem= 8, na= 2

```

E <sub>0</sub> (eV)	0°	75°
50	8.62e-3	
100	4.43e-2	
300	1.20e-1	
500	1.51e-1	
1000	1.82e-1	
2000	1.70e-1	4.64e-1
4000	2.00e-1	
10000	1.52e-1	

Sputtered energy of Ag by He

```
nem= 6, na= 1
```

E <sub>0</sub> (eV)	0°
50	2.05e-4
100	1.17e-3
300	2.27e-3
500	2.21e-3
1000	1.71e-3
4000	7.58e-4

Particle reflection coefficient of He backscattered from Ag

```

z1= 2, m1= 4.00, z2=47, m2=107.87, sbe=2.97 eV, rho=10.47 g/cm***3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=1, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program:
nem= 6, na= 1

```

E <sub>0</sub> (eV)	0°
50	6.10e-1
100	5.68e-1
300	5.07e-1
500	4.79e-1
1000	4.33e-1
4000	3.32e-1

Energy reflection coefficient of He backscattered from Ag

```
nem= 6, na= 1
```

E <sub>0</sub> (eV)	0°
50	3.75e-1
100	3.36e-1
300	2.82e-1
500	2.62e-1
1000	2.28e-1
4000	1.57e-1

Average depth (mean range) in Å of He implanted in Ag

```
nem= 6, na= 1
```

E <sub>0</sub> (eV)	0°
50	1.80e+1
100	2.61e+1
300	4.88e+1
500	6.58e+1
1000	1.03e+2
4000	2.72e+2

## Na → Ag

Sputtering yield of Ag by Na  
 $z_1=11$ ,  $m_1=22.99$ ,  $z_2=47$ ,  $m_2=107.87$ ,  $sbe=2.97$  eV,  $\rho=10.47$  g/cm<sup>3</sup>  
 $ef=eV$ ,  $esb=eV$ ,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: IPP 9/82  
*only low fluence!*  
 $n_e = 1$ ,  $n_a = 7$

$E_0$ (eV)	0°	15°	30°	40°	50°	60°	70°
30000	2.34e-0	2.74e-0	3.33e-0	4.11e-0	5.22e-0	7.08e-0	9.42e-0

Sputtered energy of Ag by Na  
program:  
*only low fluence!*  
 $n_e = 1$ ,  $n_a = 7$

$E_0$ (eV)	0°	15°	30°	40°	50°	60°	70°
30000	4.15e-3	4.92e-3	6.85e-3	9.60e-3	1.41e-2	2.14e-2	3.24e-2

Particle reflection coefficient of Na backscattered from Ag  
 $z_1=11$ ,  $m_1=22.99$ ,  $z_2=47$ ,  $m_2=107.87$ ,  $sbe=2.97$  eV,  $\rho=10.47$  g/cm<sup>3</sup>  
 $ef=eV$ ,  $esb=eV$ ,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program:  
*only low fluence!*  
 $n_e = 1$ ,  $n_a = 7$

$E_0$ (eV)	0°	15°	30°	40°	50°	60°	70°
30000	1.21e-1	1.35e-1	1.64e-1	2.05e-1	2.57e-1	3.40e-1	4.41e-1

Energy reflection coefficient of Na backscattered from Ag  
 $n_e = 1$ ,  $n_a = 7$

$E_0$ (eV)	0°	15°	30°	40°	50°	60°	70°
30000	3.25e-2	3.69e-2	4.91e-2	6.97e-2	9.70e-2	1.49e-1	2.26e-1

Average depth (mean range) in Å of Na implanted in Ag  
 $n_e = 1$ ,  $n_a = 7$

$E_0$ (eV)	0°	15°	30°	40°	50°	60°	70°
30000	2.80e+2	2.72e+2	2.56e+2	2.40e+2	2.28e+2	2.10e+2	1.93e+2

## $\text{Ar} \rightarrow \text{Ag}$

Sputtering yield of Ag by Ar

```

z1=18, m1= 39.95, z2=47, m2=107.87, sbe=2.97 eV, rho=10.47 g/cm**3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=1, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program: trspvmcx, trspv1cs
ne= 7, na= 1

```

$E_0(\text{eV})$	$0^\circ$
50	1.27e-1
100	4.37e-1
300	1.28e-0
500	1.83e-0
1000	2.64e-0
2500	4.03e-0
4000	4.22e-0

Sputtered energy of Ag by Ar

```

ne= 7, na= 1

```

$E_0(\text{eV})$	$0^\circ$
50	9.64e-3
100	2.39e-2
300	3.68e-2
500	3.82e-2
1000	3.49e-2
2500	3.19e-2
4000	2.38e-2

Particle reflection coefficient of Ar backscattered from Ag

```

z1=18, m1= 39.95, z2=47, m2=107.87, sbe=2.97 eV, rho=10.47 g/cm**3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=1, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program: trspvmcx, trspv1cs
ne= 7, na= 1

```

$E_0(\text{eV})$	$0^\circ$
50	4.19e-1
100	3.48e-1
300	2.61e-1
500	2.35e-1
1000	2.00e-1
2500	1.83e-1
4000	1.44e-1

Energy reflection coefficient of Ar backscattered from Ag

```

ne= 7, na= 1

```

$E_0(\text{eV})$	$0^\circ$
50	8.62e-2
100	7.08e-2
300	5.07e-2
500	4.41e-2
1000	3.68e-2
2500	3.53e-2
4000	2.48e-2

Average depth (mean range) in Å of Ar implanted in Ag

```

ne= 7, na= 1

```

$E_0(\text{eV})$	$0^\circ$
50	4.46e+0
100	6.23e+0
300	1.07e+1
500	1.38e+1
1000	2.00e+1
2500	3.42e+1
4000	4.41e+1

# $K \rightarrow Ag$

Sputtering yield of Ag by K  
 $z1=19$ ,  $m1=39.10$ ,  $z2=47$ ,  $m2=107.87$ ,  $sbe=2.97$  eV,  $\rho=10.47$  g/cm\*\*3  
 $ef=eV$ ,  $esb=eV$ ,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: IPP 9/82  
*only low fluence!*  
 $n_{\text{e}} = 1$ ,  $n_{\text{a}} = 8$

$E_0$ (eV)	$0^\circ$	$15^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$60^\circ$	$70^\circ$	$80^\circ$
30000	4.76e-0	4.99e-0	6.52e-0	8.05e-0	1.03e+1	1.34e+1	1.68e+1	1.79e+1

Sputtered energy of Ag by K  
program:  
*only low fluence!*  
 $n_{\text{e}} = 1$ ,  $n_{\text{a}} = 8$

$E_0$ (eV)	$0^\circ$	$15^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$60^\circ$	$70^\circ$	$80^\circ$
30000	8.42e-3	9.33e-3	1.55e-2	2.27e-2	3.44e-2	5.00e-2	7.27e-2	9.49e-2

Particle reflection coefficient of K backscattered from Ag  
 $z1=19$ ,  $m1=39.10$ ,  $z2=47$ ,  $m2=107.87$ ,  $sbe=2.97$  eV,  $\rho=10.47$  g/cm\*\*3  
 $ef=eV$ ,  $esb=eV$ ,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program:  
*only low fluence!*  
 $n_{\text{e}} = 1$ ,  $n_{\text{a}} = 8$

$E_0$ (eV)	$0^\circ$	$15^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$60^\circ$	$70^\circ$	$80^\circ$
30000	8.21e-2	8.83e-2	1.20e-1	1.52e-1	2.12e-1	2.90e-1	3.95e-1	5.66e-1

Energy reflection coefficient of K backscattered from Ag  
 $n_{\text{e}} = 1$ ,  $n_{\text{a}} = 7$

$E_0$ (eV)	$0^\circ$	$15^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$60^\circ$	$70^\circ$	$80^\circ$
30000	1.43e-2	1.63e-2	2.74e-2	3.83e-2	6.59e-2	1.06e-1	1.80e-1	3.41e-1

Average depth (mean range) in Å of K implanted in Ag  
 $n_{\text{e}} = 1$ ,  $n_{\text{a}} = 8$

$E_0$ (eV)	$0^\circ$	$15^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$60^\circ$	$70^\circ$	$80^\circ$
30000	1.72e+2	1.69e+2	1.58e+2	1.49e+2	1.35e+2	1.25e+2	1.13e+2	1.05e+2

## Xe → Ag

Sputtering yield of Ag by Xe

```

z1=54, m1=131.30, z2=47, m2=107.87, sbe=2.97 eV, rho=10.47 g/cm**3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=1, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program: trspvmcx, trspv1cs
ne= 6, na= 1

```

E <sub>0</sub> (eV)	0°
50	2.75e-2
100	2.06e-1
300	1.05e-0
500	1.71e-0
1000	2.85e-0
4000	5.79e-0

Sputtered energy of Ag by Xe  
ne= 6, na= 1

E <sub>0</sub> (eV)	0°
50	1.15e-3
100	6.95e-3
300	2.11e-2
500	2.63e-2
1000	2.91e-2
4000	2.59e-2

Particle reflection coefficient of Xe backscattered from Ag  
z1=54, m1=131.30, z2=47, m2=107.87, sbe=2.97 eV, rho=10.47 g/cm\*\*3  
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=1, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
program: trspvmcx, trspv1cs  
ne= 6, na= 1

E <sub>0</sub> (eV)	0°
50	4.29e-2
100	2.83e-2
300	1.97e-2
500	1.95e-2
1000	1.60e-2
4000	1.30e-2

Energy reflection coefficient of Xe backscattered from Ag  
ne= 6, na= 1

E <sub>0</sub> (eV)	0°
50	5.51e-4
100	5.07e-4
300	3.45e-4
500	3.88e-4
1000	2.89e-4
4000	2.37e-4

Average depth (mean range) in Å of Xe implanted in Ag  
ne= 6, na= 1

E <sub>0</sub> (eV)	0°
50	3.63e+0
100	5.26e+0
300	8.99e+0
500	1.14e+1
1000	1.57e+1
4000	3.08e+1

## H → In

Sputtering yield of In by H

```

z1= 1, m1= 1.01, z2=49, m2=114.82, sbe=2.49 eV, rho=7.31 g/cm**3
ef=0.95 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program: TESTVMCX, IPP 9/82
ne= 1, na=10

```

E <sub>0</sub> (eV)	0°	15°	30°	45°	60°	70°	75°	80°	85°	87°
2000	1.65e-2	1.79e-2	2.24e-2	2.94e-2	5.41e-2	7.68e-2	1.04e-1	1.33e-1	1.42e-1	9.06e-2

Sputtered energy of In by H

```

program: testvmcx
ne= 1, na=10

```

E <sub>0</sub> (eV)	0°	15°	30°	45°	60°	70°	75°	80°	85°	87°
2000	5.16e-5	5.90e-5	6.64e-5	9.36e-5	1.82e-4	2.67e-4	3.59e-4	5.18e-4	6.52e-4	4.71e-4

Particle reflection coefficient of H backscattered from In

```

z1= 1, m1= 1.01, z2=49, m2=114.82, sbe=2.49 eV, rho=7.31 g/cm**3
ef=0.95 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program: testvmcx
ne= 1, na=10

```

E <sub>0</sub> (eV)	0°	15°	30°	45°	60°	70°	75°	80°	85°	87°
2000	3.60e-1	3.71e-1	4.07e-1	4.69e-1	5.55e-1	6.28e-1	6.74e-1	7.35e-1	8.28e-1	9.16e-1

Energy reflection coefficient of H backscattered from In

```

ne= 1, na=10

```

E <sub>0</sub> (eV)	0°	15°	30°	45°	60°	70°	75°	80°	85°	87°
2000	1.74e-1	1.83e-1	2.08e-1	2.56e-1	3.33e-1	4.15e-1	4.74e-1	5.58e-1	6.99e-1	8.42e-1

Average depth (mean range) in Å of H implanted in In

```

ne= 1, na=10

```

E <sub>0</sub> (eV)	0°	15°	30°	45°	60°	70°	75°	80°	85°	87°
2000	4.02e+2	3.97e+2	3.89e+2	3.75e+2	3.67e+2	3.56e+2	3.47e+2	3.49e+2	3.47e+2	3.49e+2

## D → In

Sputtering yield of In by D  
 $z1 = 1$ ,  $m1 = 2.01$ ,  $z2 = 49$ ,  $m2 = 114.82$ ,  $sbe = 2.52$  eV,  $\rho = 7.31$  g/cm<sup>3</sup>  
 $ef = 0.90$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: newtrim (Laszlo), IPP 9/82  
 $n_{\text{e}} = 7$ ,  $n_{\text{a}} = 2$

$E_0$ (eV)	0°	65°
100	6.98e-3	7.79e-3
200	2.10e-2	3.60e-2
500	3.71e-2	9.42e-2
1000	4.29e-2	1.27e-1
2000	4.20e-2	1.38e-1
5000	3.67e-2	1.36e-1
10000	2.81e-2	1.10e-1

Sputtered energy of In by D  
program: newtrim (Laszlo)  
 $n_{\text{e}} = 7$ ,  $n_{\text{a}} = 2$

$E_0$ (eV)	0°	65°
100	9.77e-5	1.17e-4
200	2.89e-4	5.01e-4
500	3.89e-4	9.72e-4
1000	2.93e-4	9.44e-4
2000	1.93e-4	7.11e-4
5000	8.29e-5	3.64e-4
10000	3.45e-5	1.92e-4

Particle reflection coefficient of D backscattered from In  
 $z1 = 1$ ,  $m1 = 2.01$ ,  $z2 = 49$ ,  $m2 = 114.82$ ,  $sbe = 2.52$  eV,  $\rho = 7.31$  g/cm<sup>3</sup>  
 $ef = 0.90$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: newtrim (Laszlo)  
 $n_{\text{e}} = 7$ ,  $n_{\text{a}} = 2$

$E_0$ (eV)	0°	65°
100	5.90e-1	7.68e-1
200	5.57e-1	7.40e-1
500	5.01e-1	6.96e-1
1000	4.53e-1	6.55e-1
2000	3.89e-1	6.09e-1
5000	2.89e-1	5.31e-1
10000	2.05e-1	4.67e-1

Energy reflection coefficient of D backscattered from In  
 $n_{\text{e}} = 7$ ,  $n_{\text{a}} = 2$

$E_0$ (eV)	0°	65°
100	3.69e-1	5.91e-1
200	3.38e-1	5.52e-1
500	2.89e-1	4.98e-1
1000	2.49e-1	4.53e-1
2000	2.01e-1	4.04e-1
5000	1.33e-1	3.24e-1
10000	8.25e-2	2.61e-1

Average depth (mean range) in Å of D implanted in In  
 $n_{\text{e}} = 7$ ,  $n_{\text{a}} = 2$

$E_0$ (eV)	0°	65°
100	6.90e+1	6.56e+1
200	1.02e+2	9.65e+1
500	1.76e+2	1.65e+2
1000	2.78e+2	2.57e+2
2000	4.51e+2	4.06e+2
5000	8.92e+2	7.64e+2
10000	1.55e+3	1.27e+3

# D → In

D on In, Maxwellian velocity distribution, sheath potential 0 kT  
 z1= 1, m1= 2.01, z2=49, m2=114.82, sbe=2.52 eV, rho= 7.31 g/cm\*\*3  
 ef=0.90 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx, newtrim (Laszlo)  
 ne=8

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
20	9.93e-4	3.60e-5	1.45e+0	7.41e-1	5.34e-1	2.88e+1	4.05e+1
50	9.15e-3	2.37e-4	2.59e+0	7.04e-1	4.85e-1	6.90e+1	6.68e+1
100	2.44e-2	4.52e-4	3.70e+0	6.77e-1	4.48e-1	1.32e+2	1.00e+2
200	4.62e-2	6.19e-4	5.37e+0	6.37e-1	4.04e-1	2.55e+2	1.51e+2
500	7.50e-2	5.35e-4	7.11e+0	5.82e-1	3.48e-1	5.96e+2	2.69e+2
1000	8.71e-2	4.04e-4	9.21e+0	5.31e-1	3.00e-1	1.12e+3	4.34e+2
2000	9.03e-2	2.69e-4	1.19e+1	4.74e-1	2.44e-1	2.06e+3	7.22e+2
5000	8.23e-2	1.25e-4	1.52e+1	3.83e-1	1.70e-1	4.45e+3	1.43e+3

D on In, Maxwellian velocity distribution, sheath potential 3 kT  
 ne=9

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
10	6.86e-4	1.25e-5	9.14e-1	6.48e-1	4.32e-1	3.34e+1	4.65e+1
20	7.38e-3	1.25e-4	1.70e+0	6.18e-1	4.00e-1	6.46e+1	6.78e+1
50	2.63e-2	3.59e-4	3.42e+0	5.76e-1	3.57e-1	1.55e+2	1.14e+2
100	3.91e-2	4.02e-4	5.15e+0	5.35e-1	3.20e-1	2.99e+2	1.75e+2
200	5.15e-2	3.65e-4	7.06e+0	4.88e-1	2.79e-1	5.69e+2	2.75e+2
500	5.31e-2	2.01e-4	9.44e+0	4.04e-1	2.11e-1	1.31e+3	5.17e+2
1000	4.91e-2	1.13e-4	1.15e+1	3.28e-1	1.55e-1	2.36e+3	8.63e+2
2000	3.48e-2	5.12e-5	1.48e+1	2.45e-1	1.03e-1	4.20e+3	1.47e+3
5000	2.40e-2	1.44e-5	1.50e+1	1.33e-1	4.39e-2	8.24e+3	3.09e+3

## T → In

Sputtering yield of In by T  
 $z1 = 1$ ,  $m1 = 3.01$ ,  $z2 = 49$ ,  $m2 = 114.82$ ,  $sbe = 2.52$  eV,  $\rho = 7.31$  g/cm<sup>3</sup>  
 $ef = 0.90$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: newtrim (Laszlo), IPP 9/82  
ne = 8, na = 2

$E_0$ (eV)	0°	65°
50	3.48e-3	
100	1.74e-2	2.38e-2
200	3.91e-2	7.84e-2
500	6.03e-2	1.63e-1
1000	6.99e-2	2.06e-1
2000	7.12e-2	2.27e-1
5000	6.33e-2	2.12e-1
10000	4.95e-2	

Sputtered energy of In by T  
program: newtrim (Laszlo)  
ne = 8, na = 2

$E_0$ (eV)	0°	65°
50	6.17e-5	
100	3.70e-4	5.30e-4
200	7.14e-4	1.51e-3
500	7.48e-4	2.05e-3
1000	5.94e-4	1.83e-3
2000	3.80e-4	1.33e-3
5000	1.76e-4	6.87e-4
10000	7.57e-5	

Particle reflection coefficient of T backscattered from In  
 $z1 = 1$ ,  $m1 = 3.01$ ,  $z2 = 49$ ,  $m2 = 114.82$ ,  $sbe = 2.52$  eV,  $\rho = 7.31$  g/cm<sup>3</sup>  
 $ef = 0.90$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: newtrim (Laszlo)  
ne = 8, na = 2

$E_0$ (eV)	0°	65°
50	6.02e-1	
100	5.72e-1	7.61e-1
200	5.45e-1	7.29e-1
500	4.97e-1	6.88e-1
1000	4.49e-1	6.52e-1
2000	3.92e-1	6.08e-1
5000	2.99e-1	5.39e-1
10000	2.18e-1	

Energy reflection coefficient of T backscattered from In  
ne = 8, na = 2

$E_0$ (eV)	0°	65°
50	3.80e-1	
100	3.52e-1	5.80e-1
200	3.26e-1	5.40e-1
500	2.86e-1	4.94e-1
1000	2.49e-1	4.55e-1
2000	2.06e-1	4.09e-1
5000	1.41e-1	3.40e-1
10000	9.21e-2	

Average depth (mean range) in Å of T implanted in In  
ne = 8, na = 2

$E_0$ (eV)	0°	65°
50	4.51e+1	
100	6.62e+1	6.30e+1
200	9.93e+1	9.39e+1
500	1.76e+2	1.64e+2
1000	2.81e+2	2.59e+2
2000	4.60e+2	4.23e+2
5000	9.38e+2	8.18e+2
10000	1.67e+3	

# $T \rightarrow In$

T on In, Maxwellian velocity distribution, sheath potential 0 kT  
 z1= 1, m1= 3.01, z2=49, m2=114.82, sbe=2.52 eV, rho= 7.31 g/cm\*\*3  
 ef=0.90 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: newtrim (Laszlo)  
 ne=8

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
20	3.70e-3	1.73e-4	1.87e+0	7.27e-1	5.18e-1	2.85e+1	3.84e+1
50	2.18e-2	7.17e-4	3.30e+0	6.92e-1	4.73e-1	6.85e+1	6.42e+1
100	4.98e-2	1.09e-3	4.39e+0	6.65e-1	4.38e-1	1.32e+2	9.73e+1
200	8.17e-2	1.26e-3	6.19e+0	6.32e-1	4.04e-1	2.57e+2	1.48e+2
500	1.24e-1	1.05e-3	8.49e+0	5.81e-1	3.56e-1	6.13e+2	2.71e+2
1000	1.42e-1	7.89e-4	1.11e+1	5.33e-1	3.05e-1	1.14e+3	4.52e+2
2000	1.48e-1	5.22e-4	1.40e+1	4.78e-1	2.59e-1	2.14e+3	7.55e+2
5000	1.21e-1	2.20e-4	1.81e+1	3.95e-1	1.79e-1	4.53e+3	1.57e+3

T on In, Maxwellian velocity distribution, sheath potential 3 kT  
 ne=8

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
20	1.97e-2	4.62e-4	2.35e+0	6.03e-1	3.86e-1	6.40e+1	6.52e+1
50	5.10e-2	8.68e-4	4.26e+0	5.67e-1	3.49e-1	1.54e+2	1.11e+2
100	7.03e-2	8.96e-4	6.37e+0	5.30e-1	3.16e-1	2.98e+2	1.73e+2
200	8.40e-2	6.75e-4	8.04e+0	4.84e-1	2.81e-1	5.81e+2	2.74e+2
500	8.35e-2	3.70e-4	1.11e+1	4.10e-1	2.19e-1	1.33e+3	5.33e+2
1000	7.61e-2	2.06e-4	1.35e+1	3.42e-1	1.68e-1	2.15e+3	9.13e+2
2000	5.98e-2	1.07e-4	1.78e+1	2.58e-1	1.14e-1	4.40e+3	1.59e+3
5000	3.51e-2	3.09e-5	2.20e+1	1.46e-1	5.13e-2	8.79e+3	3.41e+3

T on In, Maxwellian velocity distribution, sheath potential 9 kT  
 ne=6

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
10	2.13e-2	4.69e-4	2.42e+0	5.84e-1	3.64e-1	6.84e+1	6.93e+1
20	4.30e-2	7.90e-4	4.04e+0	5.50e-1	3.34e-1	1.33e+2	1.04e+2
50	6.74e-2	7.99e-4	6.51e+0	5.05e-1	2.93e-1	3.19e+2	1.85e+2
100	7.55e-2	5.85e-4	8.51e+0	4.55e-1	2.59e-1	6.26e+2	2.97e+2
200	7.60e-2	3.75e-4	1.09e+1	3.95e-1	2.10e-1	1.17e+3	4.89e+2
500	7.10e-2	1.92e-4	1.48e+1	3.19e-1	1.53e-1	2.63e+3	9.99e+2

# In → In

Sputtering yield of In by In

$z1=49$ ,  $m1=114.82$ ,  $z2=49$ ,  $m2=114.82$ ,  $sbe=2.52$  eV,  $\rho=7.31$  g/cm<sup>3</sup>  
 $ef=2.02$  eV,  $esb=2.52$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: newtrim (Laszlo), IPP 9/82  
nem = 9, na = 8

$E_0$ (eV)	0°	30°	45°	55°	60°	65°	70°	80°
20	1.31e-3				7.76e-2			
50	6.65e-2				4.49e-1			
100	2.97e-1	6.00e-1	8.66e-1	9.76e-1	9.64e-1			
200	7.49e-1	1.22e-0	1.63e-0	1.79e-0	1.79e-0	1.70e-0	1.50e-0	7.54e-1
500	1.76e-0				3.57e-0			
1000	2.76e-0	3.78e-0	4.85e-0	5.48e-0	5.63e-0	5.61e-0	5.29e-0	3.04e-0
2000	4.00e-0				8.44e-0			
5000	5.89e-0				1.34e+1			
10000	7.18e-0				1.78e+1			

Sputtering yield of In by In

program: newtrim (Laszlo)  
nem = 9, na = 8

$E_0$ (eV)	0°	30°	45°	55°	60°	65°	70°	80°
20	7.21e-5				1.55e-2			
50	2.87e-3				7.44e-2			
100	9.76e-3	3.68e-2	7.77e-2	1.09e-1	1.20e-1			
200	1.79e-2	5.07e-2	9.82e-2	1.36e-1	1.52e-1	1.61e-1	1.57e-1	8.70e-2
500	2.58e-2				1.73e-1			
1000	2.76e-2	5.99e-2	1.07e-1	1.51e-1	1.75e-1	1.96e-1	2.08e-1	1.49e-1
2000	2.75e-2				1.69e-1			
5000	2.43e-2				1.57e-1			
10000	2.06e-2				1.41e-1			

Particle reflection coefficient of In backscattered from In

$z1=49$ ,  $m1=114.82$ ,  $z2=49$ ,  $m2=114.82$ ,  $sbe=2.52$  eV,  $\rho=7.31$  g/cm<sup>3</sup>  
 $ef=2.02$  eV,  $esb=2.52$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: newtrim (Laszlo)  
nem = 9, na = 8

$E_0$ (eV)	0°	30°	45°	55°	60°	65°	70°	80°
20	5.76e-5				1.24e-1			
50	3.90e-3				3.69e-1			
100	1.32e-2	7.25e-2	1.86e-1	3.25e-1	4.21e-1			
200	2.11e-2	8.03e-2	1.86e-2	3.09e-1	3.94e-1	4.96e-1	6.18e-1	8.88e-1
500	3.02e-2				3.39e-1			
1000	2.98e-2	7.39e-2	1.43e-1	2.39e-1	2.92e-1	3.83e-1	4.84e-1	7.99e-1
2000	2.75e-2				2.65e-1			
5000	2.57e-2				2.31e-1			
10000	1.87e-2				2.01e-1			

Energy reflection coefficient of In backscattered from In

nem = 9, na = 8

$E_0$ (eV)	0°	30°	45°	55°	60°	65°	70°	80°
20	4.85e-6				3.55e-2			
50	2.12e-4				1.22e-1			
100	6.56e-4	8.85e-3	3.81e-2	9.35e-2	1.43e-1			
200	9.20e-4	8.54e-3	3.53e-2	8.40e-2	1.28e-1	1.96e-1	2.91e-1	5.92e-1
500	1.11e-3				9.98e-2			
1000	1.13e-3	6.08e-3	2.05e-2	5.26e-2	8.01e-2	1.27e-1	1.99e-1	5.23e-1
2000	9.73e-4				6.74e-2			
5000	6.69e-4				5.16e-2			
10000	5.60e-4				4.94e-2			

Average depth (mean range) in Å of In implanted in In

nem = 9, na = 8

$E_0$ (eV)	0°	30°	45°	55°	60°	65°	70°	80°
20	3.58e+0				1.44e+0			
50	5.83e+0				3.27e+0			
100	8.19e+0	7.28e+0	6.37e+0	5.69e+0	5.31e+0			
200	1.14e+1	1.02e+1	9.04e+0	8.22e+0	7.72e+0	7.22e+0	4.46e+0	3.24e+0
500	1.73e+1				1.19e+1			
1000	2.39e+1	2.16e+1	1.89e+1	1.70e+1	1.63e+1	1.51e+1	1.45e+1	1.24e+1
2000	3.29e+1				2.27e+1			
5000	5.19e+1				3.51e+1			
10000	7.67e+1				5.11e+1			

## In → In

In on In, Maxwellian velocity distribution, sheath potential 0 kT  
 $z_1=49$ ,  $m_1=114.82$ ,  $z_2=49$ ,  $m_2=114.82$ ,  $sbe=2.52$  eV,  $\rho = 7.31$  g/cm\*\*3  
 $ef=2.02$  eV,  $esb=2.52$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: testvmcx, newtrim (Laszlo)  
ne=12

kT(eV)	Y	$Y_E$	$E_{sp}$	$R_N$	$R_E$	$E_b$	range
2	5.91e-4	3.45e-4	2.34e+0	9.82e-4	9.47e-4	3.86e+0	5.14e-1
3	2.68e-3	1.38e-3	3.08e+0	5.09e-3	4.26e-3	5.01e+0	7.73e-1
5	1.34e-2	5.75e-3	4.28e+0	2.13e-2	1.56e-2	7.30e+0	1.28e+0
10	6.98e-2	2.05e-2	5.87e+0	7.75e-2	4.67e-2	1.21e+1	2.06e+0
20	2.26e-1	4.44e-2	7.87e+0	1.58e-1	8.11e-2	2.05e+1	3.31e+0
50	6.75e-1	7.61e-2	1.13e+1	2.35e-1	1.02e-1	4.35e+1	5.87e+0
100	1.28e-1	9.52e-2	1.49e+1	2.52e-1	1.01e-1	7.98e+1	8.59e+0
200	2.22e-0	1.04e-1	1.89e+1	2.52e-1	9.11e-2	1.45e+2	1.22e+1
500	4.04e-0	1.10e-1	2.75e+1	2.29e-1	8.04e-2	3.55e+2	1.86e+1
1000	6.07e-0	1.06e-1	3.50e+1	2.19e-1	6.88e-2	6.35e+2	2.59e+1
2000	8.48e-0	1.02e-1	4.68e+1	1.89e-1	5.89e-2	1.21e+3	3.44e+1
5000	1.25e+1	9.19e-2	7.39e+1	1.59e-1	4.31e-2	2.73e+3	5.86e+1

In on In, Maxwellian velocity distribution, sheath potential 3 kT  
ne=12

kT(eV)	Y	$Y_E$	$E_{sp}$	$R_N$	$R_E$	$E_b$	range
1.4	4.41e-4	1.02e-4	1.62e+0	2.15e-4	8.75e-5	2.85e+0	1.39e+0
2	2.02e-3	4.47e-4	2.21e+0	1.16e-3	4.23e-4	3.64e+0	1.84e+0
3	9.22e-3	1.85e-3	3.01e+0	5.11e-3	1.58e-3	4.64e+0	2.45e+0
5	4.25e-2	6.48e-3	3.81e+0	1.64e-2	4.27e-3	6.50e+0	3.48e+0
10	1.91e-1	1.93e-2	5.05e+0	3.96e-2	8.25e-3	1.04e+1	5.19e+0
20	5.23e-1	3.43e-2	6.56e+0	5.71e-2	9.38e-3	1.64e+1	7.44e+0
50	1.33e-0	4.87e-2	9.20e+0	6.66e-2	8.18e-3	3.08e+1	1.15e+1
100	2.24e-0	5.36e-2	1.19e+1	6.63e-2	7.16e-3	5.39e+1	1.58e+1
200	3.42e-0	5.32e-2	1.55e+1	6.41e-2	5.97e-3	9.30e+1	2.18e+1
500	5.58e-0	5.04e-2	2.26e+1	5.12e-2	4.54e-3	2.22e+2	3.41e+1
1000	7.62e-0	4.55e-2	3.02e+1	4.89e-2	4.96e-3	5.14e+2	4.80e+1
2000	9.22e-0	3.76e-2	4.05e+1	4.07e-2	3.23e-3	7.88e+2	6.81e+1

In on In, Maxwellian velocity distribution, sheath potential 9 kT  
ne=12

kT(eV)	Y	$Y_E$	$E_{sp}$	$R_N$	$R_E$	$E_b$	range
1.1	8.29e-4	9.79e-5	1.45e+0	2.01e-4	4.00e-5	2.41e+0	2.34e+0
1.4	2.44e-3	2.94e-4	1.85e+0	7.26e-4	1.39e-4	2.94e+0	2.75e+0
2	1.12e-2	1.20e-3	2.36e+0	2.63e-3	4.15e-4	3.48e+0	3.53e+0
5	1.49e-1	9.77e-3	3.61e+0	1.77e-2	2.06e-3	6.40e+0	5.82e+0
10	4.60e-1	2.07e-2	4.94e+0	3.21e-2	2.90e-3	9.96e+0	8.24e+0
20	9.99e-1	3.00e-2	6.59e+0	4.05e-2	3.13e-3	1.70e+1	1.13e+1
50	2.11e-0	3.64e-2	9.48e+0	4.53e-2	2.88e-3	3.49e+1	1.74e+1
100	3.28e-0	3.88e-2	1.30e+1	4.09e-2	2.32e-3	6.25e+1	2.39e+1
200	4.73e-0	3.73e-2	1.74e+1	4.09e-2	2.44e-3	1.32e+2	3.32e+1
500	6.92e-0	3.28e-2	2.60e+1	3.69e-2	1.55e-3	2.31e+2	5.20e+1
1000	8.48e-0	2.50e-2	3.25e+1	2.39e-2	1.54e-3	7.08e+2	7.80e+1
2000	1.01e+1	2.07e-2	4.47e+1	4.38e-2	2.24e-3	1.12e+3	1.17e+2

## $\text{Cs} \rightarrow \text{Cs}$

Sputtering yield of Cs by Cs  
 $z1=55$ ,  $m1=132.91$ ,  $z2=55$ ,  $m2=132.91$ ,  $sbe=0.82$  eV,  $\rho=1.899$  g/cm $^{**3}$   
 $ef=0.77$  eV,  $esb=0.82$  eV,  $iwc=2$ ,  $inel=3$ ,  $ipot=1$  (KrC)  
program: tridyn (idrel=1)  
ne = 9, na = 6

$E_0$ (eV)	0°	10°	20°	30°	40°	50°
100	7.68e-1					
500	3.05e-0					
1000	4.74e-0					
2000	6.94e-0					
4000	2.14e+1	2.19e+1	2.30e+1	2.48e+1	2.67e+1	2.81e+1
8000	2.82e+1					
20000	1.62e+1					
40000	1.91e+1					
80000	1.99e+1					

Sputtered energy of Cs by Cs  
ne = 9, na = 6

$E_0$ (eV)	0°	10°	20°	30°	40°	50°
100	1.69e-2					
500	2.93e-2					
1000	3.10e-2					
2000	3.07e-2					
4000	4.69e-2	5.00e-2	6.13e-2	8.21e-2	1.14e-1	1.56e-1
8000	3.70e-2					
20000	1.88e-2					
40000	1.68e-2					
80000	1.13e-2					

Particle reflection coefficient of Cs backscattered from Cs  
 $z1=55$ ,  $m1=132.91$ ,  $z2=55$ ,  $m2=132.91$ ,  $sbe=0.82$  eV,  $\rho=1.899$  g/cm $^{**3}$   
 $ef=0.77$  eV,  $esb=0.82$  eV,  $iwc=2$ ,  $inel=3$ ,  $ipot=1$  (KrC)  
program: tridyn (idrel=1)  
ne = 9, na = 6

$E_0$ (eV)	0°	10°	20°	30°	40°	50°
100	2.17e-2					
500	3.24e-2					
1000	3.25e-2					
2000	3.10e-2					
4000	2.99e-2	3.39e-2	4.52e-2	7.21e-2	1.14e-1	1.85e-1
8000	2.56e-2					
20000	1.83e-2					
40000	1.60e-2					
80000	1.40e-2					

Energy reflection coefficient of Cs backscattered from Cs  
ne = 9, na = 6

$E_0$ (eV)	0°	10°	20°	30°	40°	50°
100	9.25e-4					
500	1.15e-3					
1000	1.13e-3					
2000	1.05e-3					
4000	9.28e-4	1.18e-3	2.44e-3	5.58e-3	1.36e-2	3.25e-2
8000	7.95e-4					
20000	6.67e-4					
40000	6.06e-4					
80000	4.60e-4					

Average depth (mean range) in Å of Cs implanted in Cs  
ne = 9, na = 6

$E_0$ (eV)	0°	10°	20°	30°	40°	50°
100	4.51e+1					
500	8.30e+1					
1000	1.10e+2					
2000	1.47e+2					
4000	1.88e+2	1.86e+2	1.79e+2	1.69e+2	1.56e+2	1.42e+2
8000	2.72e+2					
20000	4.83e+2					
40000	7.15e+2					
80000	1.13e+3					

## $\text{Cs} \rightarrow \text{Cs}$

Sputtering yield of Cs by Cs  
z1=55, m1=132.91, z2=55, m2=132.91, sbe=0.82 eV, rho=1.899 g/cm\*\*3  
ef=0.77 eV, esb=0.82 eV, iwc=2, inel=3, ipot=3 (ZBL)  
program: tridyn (idrel=1)  
ne= 5, na= 1

E <sub>0</sub> (eV)	0°
4000	8.25e+0
5000	8.76e+0
20000	1.37e+1
40000	1.52e+1
80000	1.61e+1

Sputtered energy of Cs by Cs  
ne= 5, na= 1

E <sub>0</sub> (eV)	0°
4000	2.46e-2
5000	2.30e-2
20000	1.79e-2
40000	1.37e-2
80000	1.00e-3

## Kr → Sm

Sputtering yield of Sm by Kr  
 z1=36, m1= 83.80, z2=62, m2=150.35, sbe=2.16 eV, rho=7.54 g/cm\*\*3  
 ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program : IPP 9/82  
 ne=16, na= 1

E <sub>0</sub> (eV)	0°	comment
50	1.62e-1	
100	4.82e-1	
200	1.01e-0	
200	9.97e-1	
200	1.01e-0	
200	1.35e-0	kdee1=kdee2=2 (OR)
200	7.73e-1	kdee1=kdee2=1 (LS)
500	1.98e-0	
1000	2.80e-0	
2000	4.15e-0	
5000	5.47e-0	
10000	7.08e-0	
20000	7.99e-0	
50000	8.65e-0	
100000	8.55e-0	
200000	7.92e-0	

Sputtered energy of Sm by Kr  
 program :  
 ne=16, na= 1

E <sub>0</sub> (eV)	0°	comment
50	9.24e-3	
100	1.98e-2	
200	2.85e-2	
200	2.81e-2	
200	2.85e-2	
200	3.85e-2	kdee1=kdee2=2 (OR)
200	2.19e-2	kdee1=kdee2=1 (LS)
500	3.13e-2	
1000	3.42e-2	
2000	3.18e-2	
5000	2.67e-2	
10000	2.23e-2	
20000	1.70e-2	
50000	1.16e-2	
100000	7.82e-3	
200000	4.97e-3	

# Kr → Sm

Particle reflection coefficient of Kr backscattered from Sm  
 z1=36, m1= 83.80, z2=62, m2=150.35, sbe=2.16 eV, rho=7.54 g/cm\*\*3  
 ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program : IPP 9/82  
 ne=16, na= 1

E <sub>0</sub> (eV)	0°	comment
50	2.38e-1	
100	2.01e-1	
200	1.81e-1	
200	1.74e-1	
200	1.74e-1	
200	1.97e-1	kdee1=kdee2=2 (OR)
200	1.62e-1	kdee1=kdee2=1 (LS)
500	1.46e-1	
1000	1.28e-1	
2000	1.19e-1	
5000	9.66e-2	
10000	8.41e-2	
20000	7.55e-2	
50000	5.72e-2	
100000	4.02e-2	
200000	3.09e-2	

Energy reflection coefficient of Kr backscattered from Sm  
 ne=16, na= 1

E <sub>0</sub> (eV)	0°	comment
50	2.53e-2	
100	2.13e-2	
200	1.92e-2	
200	1.80e-2	
200	1.76e-2	
200	2.14e-2	kdee1=kdee2=2 (OR)
200	1.64e-2	kdee1=kdee2=1 (LS)
500	1.46e-2	
1000	1.29e-2	
2000	1.16e-2	
5000	9.70e-3	
10000	8.62e-3	
20000	7.86e-3	
50000	6.06e-3	
100000	4.64e-3	
200000	3.30e-3	

Average depth (mean range) in Å of Kr implanted in Sm  
 ne=15, na= 1

E <sub>0</sub> (eV)	0°	comment
50	1.07e+1	
100	1.33e+1	
200	1.68e+1	
200	1.70e+1	
200	1.68e+1	
200	1.76e+1	kdee1=kdee2=2 (OR)
200	1.63e+1	kdee1=kdee2=1 (LS)
500	2.39e+1	
1000	2.83e+1	
2000	4.36e+1	
5000	6.55e+1	
10000	1.00e+2	
20000	1.53e+2	
50000	2.81e+2	
100000	4.70e+2	

## H → Ta

Sputtering yield of Ta by H  
 $z1 = 1, m1 = 1.01, z2 = 73, m2 = 180.95, sbe = 8.10 \text{ eV}, rho = 16.60 \text{ g/cm}^{**3}$   
 $ef = 0.98 \text{ eV}, esb = 1.00 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = 4, kdee2 = 3, ipot = ipotr = 1 \text{ (KrC)}$   
 program: testvmcx, IPP 9/82  
 $n_{\text{e}} = 1, n_{\text{a}} = 8$

$E_0 \text{ (eV)}$	$0^\circ$	$30^\circ$	$50^\circ$	$70^\circ$	$80^\circ$	$85^\circ$	$87^\circ$	$88^\circ$
25000	1.95e-3	3.63e-3	7.48e-3	1.93e-2	3.68e-2	6.69e-2	8.30e-2	7.81e-1

Sputtered energy of Ta by H  
 program: testvmcx  
 $n_{\text{e}} = 1, n_{\text{a}} = 4$

$E_0 \text{ (eV)}$	$80^\circ$	$85^\circ$	$87^\circ$	$88^\circ$
25000	4.55e-5	9.12e-5	1.30e-4	1.23e-4

Particle reflection coefficient of H backscattered from Ta  
 $z1 = 1, m1 = 1.01, z2 = 73, m2 = 180.95, sbe = 8.10 \text{ eV}, rho = 16.60 \text{ g/cm}^{**3}$   
 $ef = 0.98 \text{ eV}, esb = 1.00 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = 4, kdee2 = 3, ipot = ipotr = 1 \text{ (KrC)}$   
 program: testvmcx  
 $n_{\text{e}} = 1, n_{\text{a}} = 4$

$E_0 \text{ (eV)}$	$80^\circ$	$85^\circ$	$87^\circ$	$88^\circ$
25000	5.70e-1	6.86e-1	7.59e-1	8.21e-1

Energy reflection coefficient of H backscattered from Ta  
 $n_{\text{e}} = 1, n_{\text{a}} = 4$

$E_0 \text{ (eV)}$	$80^\circ$	$85^\circ$	$87^\circ$	$88^\circ$
25000	3.35e-1	4.80e-1	5.86e-1	6.86e-1

Average depth (mean range) in Å of H implanted in Ta  
 $n_{\text{e}} = 1, n_{\text{a}} = 4$

$E_0 \text{ (eV)}$	$80^\circ$	$85^\circ$	$87^\circ$	$88^\circ$
25000	8.61e+2	8.53e+2	8.50e+2	8.45e+2

# H → W

Sputtering yield of W by H  
 z1= 1, m1= 1.01, z2=74, m2=183.65, esb=8.68 eV, rho=19.29 g/cm\*\*3  
 ef=0.95 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx, trvmc  
 ne=11, na=12

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	60°	65°	70°	75°	80°	85°	87°
500	1.18e-5	1.43e-5	1.23e-5	1.65e-5	1.88e-5		2.03e-5		1.17e-5	6.44e-6	8.94e-7	
550	4.25e-5	4.28e-5	5.43e-5	5.53e-5	6.10e-5		5.80e-5		4.15e-5	2.39e-5	3.99e-6	
600	8.88e-5	9.04e-5	9.68e-5	1.21e-4	1.34e-4		1.31e-4		9.76e-5	5.70e-5	1.20e-5	
700	2.42e-4	2.55e-4	2.85e-4	3.04e-4	3.43e-4		3.39e-4		2.82e-4	1.87e-4	3.85e-5	
800	4.18e-4	4.62e-4	5.22e-4	5.70e-4	6.28e-4		6.86e-4		5.85e-4	3.86e-4	1.02e-4	
900	6.72e-4	6.70e-4	7.36e-4	8.36e-4	9.57e-4		1.02e-3		9.32e-4	6.94e-4	2.12e-4	
1000	8.64e-4	9.04e-4	9.91e-4	1.09e-3	1.24e-3		1.49e-3		1.44e-3	1.14e-3	3.91e-4	
2000	2.42e-3	2.41e-3	2.82e-3	3.70e-3		4.90e-3		7.16e-3	9.77e-3	1.23e-2	1.18e-2	4.48e-3
5000	3.32e-3											
10000	3.15e-3											
20000	2.50e-3											

Sputtered energy of W by H  
 ne=11, na=12

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	60°	65°	70°	75°	80°	85°	87°
500	1.85e-8	2.14e-8	2.08e-8	2.63e-8	2.96e-8		3.46e-8		1.92e-8	9.19e-9	1.35e-9	
550	8.45e-8	9.95e-8	1.20e-7	1.26e-7	1.37e-7		1.38e-7		9.42e-8	5.16e-8	8.59e-9	
600	2.37e-7	2.42e-7	2.47e-7	3.26e-7	3.64e-7		3.70e-7		2.77e-7	1.53e-7	3.07e-8	
700	7.82e-7	8.33e-7	9.38e-7	1.03e-6	1.17e-6		1.21e-6		1.00e-6	6.37e-7	1.25e-7	
800	1.53e-6	1.67e-6	1.94e-6	2.28e-6	2.37e-6		2.67e-6		2.35e-6	1.51e-6	4.02e-7	
900	2.66e-6	2.67e-6	2.95e-6	3.46e-6	3.96e-6		4.32e-6		3.90e-6	2.95e-6	9.06e-7	
1000	3.55e-6	3.68e-6	4.08e-6	4.67e-6	5.37e-6		6.44e-6		6.22e-6	5.10e-6	1.66e-6	
2000	1.01e-5	9.89e-6	1.17e-5	1.49e-5		2.12e-5		3.03e-5	4.31e-5	5.60e-5	6.16e-5	2.55e-5
5000	9.74e-6											
10000	5.94e-6											
20000	2.97e-6											

# H → W

Particle reflection coefficient of H backscattered from W  
 z1= 1, m1= 1.01, z2=74, m2=183.65, esb=8.68 eV, rho=19.29 g/cm\*\*3  
 ef=0.95 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx, trvmc  
 ne=17, na=12

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	60°	65°	70°	75°	80°	85°	87°
10	7.58e-1	7.67e-1	7.93e-1	8.40e-1	8.80e-1	9.22e-1	9.59e-1	9.72e-1	9.80e-1			
20	7.17e-1	7.29e-1	7.52e-1	8.05e-1	8.51e-1	9.04e-1	9.57e-1	9.77e-1	9.88e-1			
50	6.68e-1	6.77e-1	7.05e-1	7.51e-1	7.97e-1	8.59e-1	9.37e-1	9.73e-1	9.93e-1			
100	6.32e-1	6.41e-1	6.67e-1	7.15e-1	7.56e-1	8.17e-1	9.06e-1	9.58e-1	9.93e-1			
200	5.94e-1	6.05e-1	6.29e-1	6.75e-1	7.19e-1	7.75e-1	8.61e-1	9.29e-1	9.90e-1			
300	5.71e-1	5.80e-1	6.09e-1	6.55e-1	6.97e-1	7.54e-1	8.35e-1	9.04e-1	9.85e-1			
500	5.39e-1	5.49e-1	5.77e-1	6.25e-1	6.68e-1	7.24e-1	8.03e-1	8.69e-1	9.72e-1			
550	5.32e-1	5.42e-1	5.71e-1	6.19e-1	6.62e-1	7.18e-1	7.97e-1	8.63e-1	9.69e-1			
600	5.27e-1	5.36e-1	5.64e-1	6.14e-1	6.57e-1	7.13e-1	7.92e-1	8.57e-1	9.65e-1			
700	5.15e-1	5.25e-1	5.55e-1	6.04e-1	6.48e-1	7.04e-1	7.82e-1	8.46e-1	9.58e-1			
800	5.05e-1	5.15e-1	5.45e-1	5.95e-1	6.40e-1	6.96e-1	7.74e-1	8.37e-1	9.51e-1			
900	4.95e-1	5.06e-1	5.36e-1	5.86e-1	6.32e-1	6.89e-1	7.66e-1	8.28e-1	9.45e-1			
1000	4.87e-1	4.97e-1	5.27e-1	5.78e-1	6.25e-1	6.83e-1	7.60e-1	8.21e-1	9.38e-1			
2000	4.25e-1											
5000	3.23e-1											
10000	2.40e-1											
20000	1.55e-1											

Energy reflection coefficient of H backscattered from W  
 ne=17, na=12

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	60°	65°	70°	75°	80°	85°	87°
10	5.64E-1	5.77E-1	6.15E-1	6.83E-1	7.45E-1	8.13E-1	8.80E-1	9.05E-1	9.21E-1			
20	5.13E-1	5.27E-1	5.62E-1	6.34E-1	7.04E-1	7.90E-1	8.84E-1	9.23E-1	9.47E-1			
50	4.51E-1	4.63E-1	4.97E-1	5.59E-1	6.25E-1	7.21E-1	8.53E-1	9.20E-1	9.62E-1			
100	4.10E-1	4.19E-1	4.50E-1	5.09E-1	5.67E-1	6.56E-1	8.01E-1	8.95E-1	9.65E-1			
200	3.70E-1	3.81E-1	4.08E-1	4.62E-1	5.16E-1	5.96E-1	7.30E-1	8.45E-1	9.60E-1			
300	3.47E-1	3.55E-1	3.84E-1	4.37E-1	4.89E-1	5.64E-1	6.90E-1	8.05E-1	9.51E-1			
500	3.16E-1	3.25E-1	3.53E-1	4.04E-1	4.54E-1	5.25E-1	6.42E-1	7.50E-1	9.29E-1			
550	3.10E-1	3.19E-1	3.47E-1	3.98E-1	4.48E-1	5.19E-1	6.33E-1	7.39E-1	9.23E-1			
600	3.05E-1	3.14E-1	3.41E-1	3.92E-1	4.42E-1	5.12E-1	6.25E-1	7.30E-1	9.17E-1			
700	2.95E-1	3.04E-1	3.32E-1	3.82E-1	4.32E-1	5.01E-1	6.12E-1	7.13E-1	9.05E-1			
800	2.86E-1	2.95E-1	3.23E-1	3.73E-1	4.23E-1	4.92E-1	6.01E-1	6.99E-1	8.93E-1			
900	2.78E-1	2.87E-1	3.14E-1	3.64E-1	4.14E-1	4.83E-1	5.91E-1	6.87E-1	8.82E-1			
1000	2.71E-1	2.80E-1	3.07E-1	3.57E-1	4.07E-1	4.76E-1	5.82E-1	6.76E-1	8.71E-1			
2000	2.21E-1	2.30E-1	2.56E-1	3.06E-1								
5000	1.50E-1											
10000	9.88E-2											
20000	5.54E-2											

Average depth (mean range) in Å of H implanted in W  
 ne=17, na=12

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	60°	65°	70°	75°	80°	85°	87°
10	1.30E+1	1.29E+1	1.29E+1	1.28E+1	1.27E+1							
20	1.82E+1	1.82E+1	1.82E+1	1.80E+1	1.79E+1	1.77E+1	1.76E+1	1.77E+1	1.76E+1			
50	2.86E+1	2.86E+1	2.85E+1	2.83E+1	2.80E+1	2.80E+1	2.77E+1	2.76E+1	2.75E+1			
100	4.09E+1	4.06E+1	4.04E+1	4.01E+1	3.97E+1	3.93E+1	3.90E+1	3.90E+1	3.90E+1			
200	5.85E+1	5.81E+1	5.76E+1	5.70E+1	5.62E+1	5.61E+1	5.57E+1	5.52E+1	5.51E+1			
300	7.27E+1	7.27E+1	7.16E+1	7.08E+1	7.01E+1	6.94E+1	6.85E+1	6.86E+1	6.85E+1			
500	9.63E+1	9.59E+1	9.49E+1	9.33E+1	9.23E+1	9.12E+1	9.04E+1	9.00E+1	9.00E+1			
550	1.02E+2	1.01E+2	1.00E+2	9.84E+1	9.73E+1	9.61E+1	9.51E+1	9.49E+1	9.49E+1			
600	1.07E+2	1.06E+2	1.05E+2	1.03E+2	1.02E+2	1.01E+2	9.98E+1	9.94E+1	9.93E+1			
700	1.17E+2	1.16E+2	1.15E+2	1.13E+2	1.11E+2	1.10E+2	1.09E+2	1.08E+2	1.08E+2			
800	1.26E+2	1.26E+2	1.24E+2	1.22E+2	1.20E+2	1.18E+2	1.17E+2	1.17E+2	1.17E+2			
900	1.36E+2	1.35E+2	1.33E+2	1.30E+2	1.29E+2	1.27E+2	1.25E+2	1.25E+2	1.25E+2			
1000	1.44E+2	1.44E+2	1.42E+2	1.39E+2	1.37E+2	1.35E+2	1.33E+2	1.33E+2	1.32E+2			
2000	2.22E+2	2.21E+2	2.17E+2	2.11E+2								
5000	4.12E+2											
10000	6.81E+2											
20000	1.16E+3											

## H → W

H on W, Maxwellian velocity distribution, sheath potential 3 kT  
 z1= 1, m1= 1.01, z2=74, m2=183.85, sbe=8.68 eV, rho=19.30 g/cm\*\*3  
 ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1(KrC)  
 program: testvmcx  
 ne=7

kT(eV)	Y	Y_E	E_sp	R_N	R_E	E_b	range
50	1.00e-6		9.63e-1	6.04e-1		1.59e+2	6.17e+1
70	1.15e-5		1.78e+0	5.84e-1		2.19e+2	7.46e+1
100	7.50e-5		2.77e+0	5.63e-1		3.05e+2	9.16e+1
150	4.96e-4		3.77e+0	5.35e-1		4.44e+2	1.16e+2
200	1.07e-3		4.95e+0	5.15e-1		5.78e+2	1.38e+2
300	1.90e-3		6.99e+0	4.81e-1		8.35e+2	1.78e+2
500	2.99e-3		1.01e+1	4.34e-1		1.32e+3	2.48e+2

# D → W

Sputtering yield of W by D  
 z1= 1, m1= 2.01, z2=74, m2=183.85, esb=8.68 eV, rho=19.30 g/cm\*\*3  
 ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trspvmcx  
 ne=22, na=9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
250	2.34e-5	2.33e-5	2.50e-5	3.08e-5	3.00e-5	2.64e-5	1.43e-5	5.19e-6	2.86e-6
260	5.05e-5								
270	7.63e-5	8.21e-5	8.33e-5	1.00e-4	9.70e-5	9.17e-5	5.54e-5	2.16e-5	3.40e-6
290	1.62e-4								
300	2.08e-4	2.21e-4	2.37e-4	2.82e-4	2.73e-4				
300	2.33e-4								
310	2.87e-4								
320	3.55e-4								
350	5.98e-4	6.04e-4	6.83e-4	7.34e-4	7.85e-4	7.52e-4	4.75e-4	2.60e-4	4.13e-5
350									
400	1.11e-3	1.16e-3	1.18e-3	1.33e-3	1.53e-3	1.39e-3	9.83e-4	5.91e-4	9.55e-5
400	1.09e-3								
500	2.20e-3	2.32e-3	2.49e-3	2.74e-3	2.93e-3	3.08e-3	2.50e-3	1.72e-3	3.56e-4
500	2.37e-3								
600	3.39e-3	3.31e-3	3.42e-3	4.11e-3	4.55e-3	4.76e-3	4.73e-3	3.78e-3	1.12e-3
700	4.22e-3	4.14e-3	4.84e-3	5.23e-3	6.38e-3	7.10e-3	7.42e-3	6.92e-3	2.52e-3
700									
1000	6.55e-3	7.11e-3	7.78e-3	9.22e-3	1.07e-2	1.26e-2	1.82e-2	2.04e-2	1.15e-2
1000	6.22e-3								
2000	9.54e-3								
5000	1.05e-2								
10000									

Sputtered energy of W by D  
 ne=22, na=9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
250	6.43e-8	6.37e-8	6.80e-8	8.51e-8	8.95e-8	8.06e-8	3.89e-8	1.41e-8	4.10e-9
260	1.61e-7								
270	2.80e-7	3.12e-7	3.24e-7	4.06e-7	3.95e-7	3.79e-7	2.21e-7	7.90e-8	1.06e-8
290	7.66e-7								
300	1.04e-6	1.11e-6	1.20e-6	1.47e-6	1.44e-6	1.27e-6	8.06e-7	3.90e-7	4.63e-8
300	1.17e-6								
310	1.55e-6								
320	1.99e-6								
350	3.89e-6	3.98e-6	4.56e-6	5.02e-6	5.41e-6	5.12e-6	3.23e-6	1.75e-6	2.64e-7
350									
400	8.04e-6	8.70e-6	8.56e-6	1.02e-5	1.21e-5	1.10e-5	7.77e-6	4.66e-6	7.04e-7
400	7.99e-6								
500	1.87e-5	1.96e-5	2.18e-5	2.41e-5	2.66e-5	2.76e-5	2.25e-5	1.55e-5	3.04e-6
500	2.00e-5								
600	3.03e-5	2.88e-5	3.12e-5	3.75e-5	4.14e-5	4.39e-5	4.36e-5	3.54e-5	1.03e-5
700	3.77e-5	3.78e-5	4.23e-5	4.93e-5	5.80e-5	6.48e-5	7.03e-5	6.41e-5	2.45e-5
700									
1000	5.60e-5	6.18e-5	6.73e-5	8.18e-5	9.43e-1	1.14e-4	1.63e-4	1.86e-4	1.25e-4
1000	5.40e-5								
2000	6.78e-5								
5000	4.48e-5								
10000									

# D → W

Particle reflection coefficient of D backscattered from W  
 z1= 1, m1= 2.01, z2=74, m2=183.85, esb=8.68 eV, rho=19.30 g/cm\*\*3  
 ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trspvmcx  
 ne=28, na=9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	7.61E-1	7.70E-1	7.98E-1	8.42E-1	8.82E-1	9.23E-1	9.60E-1	9.73E-1	9.80E-1
20	7.24E-1	7.33E-1	7.60E-1	8.10E-1	8.53E-1	9.06E-1	9.58E-1	9.78E-1	9.88E-1
50	6.79E-1	6.87E-1	7.14E-1	7.58E-1	8.05E-1	8.64E-1	9.39E-1	9.74E-1	9.93E-1
100	6.49E-1	6.54E-1	6.81E-1	7.27E-1	7.63E-1	8.23E-1	9.09E-1	9.60E-1	9.93E-1
200	6.12E-1	6.24E-1	6.43E-1	6.90E-1	7.31E-1	7.86E-1	8.69E-1	9.32E-1	9.90E-1
200	6.14e-1								
250	6.02E-1	6.11E-1	6.37E-1	6.80E-1	7.21E-1	7.74E-1	8.55E-1	9.20E-1	9.88E-1
260	6.01e-1								
270	5.98E-1	6.07E-1	6.33E-1	6.77E-1	7.17E-1	7.70E-1	8.50E-1	9.15E-1	9.87E-1
290	5.95E-1								
300	5.92E-1	6.01E-1	6.28E-1	6.72E-1	7.12E-1	7.64E-1	8.44E-1	9.09E-1	9.86E-1
300	5.93e-1								
310	5.91E-1								
320	5.89E-1								
350	5.84E-1	5.93E-1	6.20E-1	6.64E-1	7.04E-1	7.57E-1	8.34E-1	9.00E-1	9.83E-1
350									
400	5.77E-1	5.85E-1	6.12E-1	6.57E-1	6.97E-1	7.50E-1	8.27E-1	8.91E-1	9.80E-1
400	5.78e-1								
500	5.64E-1	5.73E-1	6.00E-1	6.45E-1	6.86E-1	7.38E-1	8.14E-1	8.77E-1	9.74E-1
500	5.58e-1								
600	5.53E-1	5.61E-1	5.88E-1	6.36E-1	6.78E-1	7.29E-1	8.03E-1	8.65E-1	9.67E-1
700	5.43E-1	5.50E-1	5.79E-1	6.25E-1	6.68E-1	7.22E-1	7.94E-1	8.55E-1	9.61E-1
700									
1000	5.17E-1	5.28E-1	5.57E-1	6.05E-1	6.46E-1	7.03E-1	7.74E-1	8.33E-1	9.42E-1
1000	5.12e-1								
2000	4.57e-1								
5000	3.64e-1								
10000	2.71e-1								

Energy reflection coefficient of D backscattered from W  
 ne=28, na=9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	5.71E-1	5.85E-1	6.24E-1	6.90E-1	7.52E-1	8.20E-1	8.85E-1	9.11E-1	9.25E-1
20	5.25E-1	5.36E-1	5.74E-1	6.44E-1	7.12E-1	7.98E-1	8.90E-1	9.28E-1	9.51E-1
50	4.69E-1	4.79E-1	5.12E-1	5.73E-1	6.40E-1	7.33E-1	8.61E-1	9.26E-1	9.67E-1
100	4.33E-1	4.42E-1	4.71E-1	5.30E-1	5.83E-1	6.72E-1	8.12E-1	9.04E-1	9.70E-1
200	3.94E-1	4.06E-1	4.31E-1	4.85E-1	5.39E-1	6.16E-1	7.47E-1	8.56E-1	9.66E-1
200	3.95e-1								
250	3.84E-1	3.93E-1	4.21E-1	4.73E-1	5.25E-1	6.00E-1	7.26E-1	8.37E-1	9.62E-1
260	3.82e-1								
270	3.79E-1	3.89E-1	4.17E-1	4.69E-1	5.20E-1	5.94E-1	7.19E-1	8.29E-1	9.60E-1
290	3.76e-1								
300	3.74B-1	3.83E-1	4.12E-1	4.63E-1	5.14E-1	5.87E-1	7.09E-1	8.19E-1	9.57E-1
310	3.74e-1								
320	3.71E-1								
350	3.66E-1	3.75E-1	4.03E-1	4.54E-1	5.04E-1	5.76E-1	6.95E-1	8.04E-1	9.52E-1
350									
400	3.59E-1	3.67E-1	3.96E-1	4.47E-1	4.96E-1	5.67E-1	6.84E-1	7.90E-1	9.47E-1
400	3.59e-1								
500	3.46E-1	3.56E-1	3.83E-1	4.33E-1	4.84E-1	5.52E-1	6.65E-1	7.67E-1	9.37E-1
500	3.45e-1								
600	3.36E-1	3.44E-1	3.73E-1	4.23E-1	4.73E-1	5.41E-1	6.49E-1	7.49E-1	9.25E-1
700	3.27E-1	3.35E-1	3.64E-1	4.13E-1	4.62E-1	5.32E-1	6.37E-1	7.34E-1	9.14E-1
700									
1000	3.04E-1	3.14E-1	3.42E-1	3.92E-1	4.38E-1	5.08E-1	6.09E-1	7.00E-1	8.83E-1
1000	3.03e-1								
2000	2.55e-1								
5000	1.83e-1								
10000	1.21e-1								

# D → W

Average depth (mean range) in Å of D implanted in W  
ne=28, na=9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	1.33E+1	1.33E+1	1.33E+1	1.32E+1	1.32E+1	1.31E+1	1.30E+1	1.30E+1	1.29E+1
20	1.90E+1	1.89E+1	1.89E+1	1.87E+1	1.86E+1	1.86E+1	1.84E+1	1.84E+1	1.82E+1
50	3.04E+1	3.01E+1	3.00E+1	2.96E+1	2.94E+1	2.95E+1	2.94E+1	2.89E+1	2.91E+1
100	4.37E+1	4.32E+1	4.31E+1	4.23E+1	4.21E+1	4.20E+1	4.18E+1	4.15E+1	4.19E+1
200	6.30E+1	6.28E+1	6.25E+1	6.15E+1	6.12E+1	6.03E+1	6.04E+1	5.94E+1	5.98E+1
200	6.28e+1								
250	7.11E+1	7.09E+1	7.03E+1	6.95E+1	6.89E+1	6.83E+1	6.78E+1	6.77E+1	6.76E+1
260	7.27e+1								
270	7.42E+1	7.40E+1	7.35E+1	7.25E+1	7.19E+1	7.13E+1	7.07E+1	7.05E+1	7.03E+1
290	7.73e+1								
300	7.88E+1	7.85E+1	7.78E+1	7.69E+1	7.62E+1	7.55E+1	7.49E+1	7.48E+1	7.45E+1
300	7.87e+1								
310	8.01E+1								
320	8.16E+1								
350	8.58E+1	8.56E+1	8.49E+1	8.38E+1	8.31E+1	8.23E+1	8.17E+1	8.14E+1	8.12E+1
350									
400	9.28E+1	9.25E+1	9.16E+1	9.03E+1	8.94E+1	8.88E+1	8.79E+1	8.76E+1	8.75E+1
400	9.27e+1								
500	1.06E+2	1.05E+2	1.04E+2	1.03E+2	1.02E+2	1.01E+2	9.98E+1	9.96E+1	9.94E+1
500	1.02e+2								
600	1.18E+2	1.17E+2	1.16E+2	1.14E+2	1.13E+2	1.12E+2	1.11E+2	1.11E+2	1.10E+2
700	1.29E+2	1.29E+2	1.27E+2	1.25E+2	1.24E+2	1.22E+2	1.21E+2	1.21E+2	1.21E+2
700									
1000	1.61E+2	1.60E+2	1.58E+2	1.56E+2	1.53E+2	1.52E+2	1.50E+2	1.50E+2	1.49E+2
1000	1.57e+2								
2000	2.48e+2								
5000	4.75e+2								
10000	8.02e+2								

D on W, Maxwellian velocity distribution, sheath potential 0 kT  
z1= 1, m1= 2.01, z2=74, m2=183.85, sbe=8.68 eV, rho=19.30 g/cm\*\*3  
ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1(KrC)  
program: testvmcx  
ne= 8

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
70	8.28e-5	2.18e-6	3.68e+0	7.44e-1	5.32e-1	1.00e+2	5.09e+1
100	3.54e-4	7.92e-6	4.48e+0	7.26e-1	5.10e-1	1.40e+2	6.16e+1
140	9.57e-4	1.92e-5	5.61e+0	7.09e-1	4.89e-1	1.93e+2	7.42e+1
200	2.13e-3	3.78e-5	7.09e+0	6.91e-1	4.67e-1	2.70e+2	9.06e+1
300	4.42e-3	6.50e-5	8.83e+0	6.69e-1	4.40e-1	3.96e+2	1.15e+2
500	8.58e-3	9.84e-5	1.15e+1	6.39e-1	4.07e-1	6.36e+2	1.57e+2
1000	1.56e-2	1.22e-4	1.57e+1	5.91e-1	3.55e-1	1.20e+3	2.46e+2
2000	2.15e-2	1.11e-4	2.07e+1	5.36e-1	2.98e-1	2.22e+3	3.95e+2

D on W, Maxwellian velocity distribution, sheath potential 3 kT  
ne=13

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
36	2.67e-5	3.02e-7	2.04e+0	6.46e-1	4.31e-1	1.21e+2	5.84e+1
40	5.35e-5		2.54e+0	6.33e-1		1.36e+2	5.87e+1
45	1.06e-4		2.53e+0	6.28e-1		1.49e+2	6.28e+1
50	2.41e-4		2.82e+0	6.21e-1		1.65e+2	6.68e+1
60	4.78e-4		3.52e+0	6.13e-1		1.97e+2	7.41e+1
75	1.06e-3		4.04e+0	6.02e-1		2.43e+2	8.47e+1
100	2.57e-3		5.12e+0	5.86e-1		3.19e+2	1.00e+2
140	4.54e-3		6.84e+0	5.66e-1		4.37e+2	1.24e+2
200	6.67e-3		9.08e+0	5.44e-1		6.11e+2	1.54e+2
300	9.26e-3		1.19e+1	5.13e-1		8.88e+2	2.01e+2
500	1.15e-2		1.58e+1	4.71e-1		1.42e+3	2.83e+2
1000	1.21e-2		2.20e+1	4.03e-1		2.61e+3	4.62e+2
2000	1.23e-2	3.47e-5	2.82e+1	3.24e-1	1.52e-1	4.68e+3	7.74e+2

# T → W

Sputtering yield of W by T  
 z1= 1, m1= 3.02, z2=74, m2=183.85, esb=8.68 eV, rho=19.29 g/cm\*\*3  
 ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trspvmcx  
 ne=17, na=9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
160	9.83E-6	7.83E-6	8.08E-6	1.26E-5	1.26E-5	9.53E-6	2.89E-6		
170	3.77E-5	4.08E-5	4.54E-5	5.05E-5	4.47E-5	3.87E-5	1.62E-5	6.08E-6	
170	3.65E-5								
180	9.81E-5	1.00E-4	1.05E-4	1.16E-4	1.14E-4	8.79E-5	4.71E-5	1.98E-5	1.93E-6
200	3.03E-4	3.07E-4	3.23E-4	3.59E-4	3.55E-4	2.99E-4	1.64E-4	7.18E-5	9.69E-6
250	1.23E-3	1.29E-3	1.28E-3	1.46E-3	1.45E-3	1.34E-3	7.91E-4	4.24E-4	5.49E-5
300	2.41E-3	2.48E-3	2.71E-3	2.85E-3	2.91E-3	2.91E-3	1.91E-3	1.07E-3	1.52E-4
300	2.35E-3					2.87E-3			
400	4.89E-3	4.91E-3	5.17E-3	5.90E-3	6.64E-3	6.73E-3	5.97E-3	3.98E-3	9.08E-4
500	7.22E-3	7.54E-3	8.13E-3	9.01E-3	1.02E-2	1.13E-2	1.17E-2	9.68E-3	2.94E-3
500	7.45E-3					1.12E-2			
700	1.11E-2	1.08E-2	1.25E-2	1.46E-2	1.69E-2	2.04E-2	2.67E-2	2.70E-2	1.25E-2
700						2.04E-2			
1000	1.49E-2	1.50E-2	1.67E-2	1.98E-2	2.41E-2	3.19E-2	4.67E-2	5.34E-2	3.08E-2
1000	1.45E-2					3.17E-2			
2000	1.85E-2					5.28E-2			
5000	2.00E-2					6.52E-2			

Sputtered energy of W by T  
 ne=17, na=9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
160	2.14E-8	1.91E-8	2.14E-8	3.48E-8	3.57E-8	2.86E-8	7.69E-9		
170	1.47E-7	1.68E-7	1.80E-7	2.25E-7	2.02E-7	1.67E-7	6.90E-8	2.49E-8	
170	1.39E-7								
180	4.98E-7	5.24E-7	5.47E-7	6.38E-7	6.45E-7	5.04E-7	2.51E-7	1.02E-7	8.41E-9
200	2.18E-6	2.24E-6	2.39E-6	2.72E-6	2.72E-6	2.30E-6	1.21E-6	5.03E-7	6.64E-8
250	1.26E-5	1.34E-5	1.32E-5	1.59E-5	1.61E-5	1.46E-5	8.50E-6	4.57E-6	5.78E-7
300	2.90E-5	2.98E-5	3.31E-5	3.55E-5	3.70E-5	3.73E-5	2.45E-5	1.36E-5	1.86E-6
300	2.87E-5					3.68E-5			
400	6.61E-5	6.67E-5	6.87E-5	8.21E-5	9.16E-5	9.50E-4	8.34E-5	5.42E-5	1.23E-5
500	9.71E-4	1.03E-4	1.12E-4	1.27E-4	1.44E-4	1.62E-4	1.65E-4	1.39E-4	4.47E-5
500	9.63E-5					1.60E-4			
700	1.47E-4	1.51E-4	1.67E-4	1.97E-4	2.27E-4	2.68E-4	3.53E-4	3.91E-4	2.04E-4
700						2.70E-4			
1000	1.72E-4	1.76E-4	1.96E-4	2.32E-4	2.85E-4	3.80E-4	5.85E-4	7.24E-4	4.93E-4
1000	1.77E-4					3.75E-4			
2000	1.58E-4					4.74E-4			
5000	1.03E-4					3.46E-4			

# T → W

Particle reflection coefficient of T backscattered from W  
 z1= 1, m1= 3.02, z2=74, m2=183.85, esb=8.68 eV, rho=19.29 g/cm\*\*3  
 ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trspvmcx  
 ne=22, na=9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	7.51E-1	7.60E-1	7.89E-1	8.37E-1	8.78E-1	9.19E-1	9.58E-1	9.71E-1	9.79E-1
20	7.15E-1	7.25E-1	7.53E-1	8.03E-1	8.48E-1	9.02E-1	9.57E-1	9.77E-1	9.88E-1
50	6.69E-1	6.79E-1	7.07E-1	7.53E-1	7.98E-1	8.60E-1	9.37E-1	9.73E-1	9.93E-1
100	6.40E-1	6.50E-1	6.75E-1	7.18E-1	7.63E-1	8.20E-1	9.06E-1	9.59E-1	9.93E-1
140	6.25E-1	6.34E-1	6.59E-1	7.04E-1	7.46E-1	8.02E-1	8.88E-1	9.47E-1	9.92E-1
160	6.19E-1	6.28E-1	6.54E-1	6.98E-1	7.39E-1	7.95E-1	8.80E-1	9.42E-1	9.92E-1
170	6.16E-1	6.25E-1	6.51E-1	6.95E-1	7.36E-1	7.91E-1	8.77E-1	9.39E-1	9.91E-1
170	6.16E-1								
180	6.14E-1	6.22E-1	6.48E-1	6.92E-1	7.33E-1	7.89E-1	8.73E-1	9.36E-1	9.91E-1
200	6.09E-1	6.18E-1	6.44E-1	6.88E-1	7.28E-1	7.83E-1	8.67E-1	9.31E-1	9.90E-1
250	5.99E-1	6.07E-1	6.34E-1	6.78E-1	7.18E-1	7.72E-1	8.53E-1	9.19E-1	9.88E-1
300	5.90E-1	5.99E-1	6.26E-1	6.69E-1	7.09E-1	7.63E-1	8.42E-1	9.08E-1	9.85E-1
300	5.90E-1								
400	5.75E-1	5.84E-1	6.11E-1	6.56E-1	6.97E-1	7.49E-1	8.26E-1	8.90E-1	9.80E-1
500	5.63E-1	5.72E-1	5.99E-1	6.45E-1	6.85E-1	7.39E-1	8.13E-1	8.76E-1	9.74E-1
500	5.63E-1								
700	5.43E-1	5.53E-1	5.82E-1	6.30E-1	6.68E-1	7.22E-1	7.96E-1	8.55E-1	9.60E-1
1000	5.20E-1	5.30E-1	5.59E-1	6.07E-1	6.50E-1	7.03E-1	7.76E-1	8.34E-1	9.42E-1
1000	5.18E-1								
2000	4.69E-1								
5000	3.86E-1								

Energy reflection coefficient of T backscattered from W  
 ne=22, na=9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	5.57E-1	5.70E-1	6.11E-1	6.80E-1	7.43E-1	8.12E-1	8.81E-1	9.06E-1	9.22E-1
20	5.12E-1	5.25E-1	5.64E-1	6.35E-1	7.04E-1	7.92E-1	8.87E-1	9.26E-1	9.50E-1
50	4.58E-1	4.76E-1	5.05E-1	5.68E-1	6.32E-1	7.27E-1	8.58E-1	9.25E-1	9.67E-1
100	4.25E-1	4.35E-1	4.67E-1	5.21E-1	5.82E-1	6.67E-1	8.09E-1	9.03E-1	9.71E-1
140	4.09E-1	4.18E-1	4.48E-1	5.03E-1	5.59E-1	6.41E-1	7.81E-1	8.84E-1	9.70E-1
160	4.03E-1	4.12E-1	4.42E-1	4.96E-1	5.50E-1	6.31E-1	7.68E-1	8.74E-1	9.69E-1
170	4.00E-1	4.09E-1	4.39E-1	4.92E-1	5.47E-1	6.27E-1	7.63E-1	8.70E-1	9.69E-1
170	4.00E-1								
180	3.97E-1	4.07E-1	4.36E-1	4.89E-1	5.43E-1	6.22E-1	7.57E-1	8.66E-1	9.68E-1
200	3.92E-1	4.02E-1	4.31E-1	4.84E-1	5.37E-1	6.15E-1	7.47E-1	8.57E-1	9.67E-1
250	3.82E-1	3.91E-1	4.21E-1	4.72E-1	5.24E-1	5.99E-1	7.27E-1	8.37E-1	9.63E-1
300	3.74E-1	3.83E-1	4.12E-1	4.63E-1	5.14E-1	5.88E-1	7.10E-1	8.20E-1	9.59E-1
300	3.74E-1								
300	3.74E-1								
400	3.59E-1	3.69E-1	3.98E-1	4.48E-1	4.99E-1	5.69E-1	6.86E-1	7.92E-1	9.49E-1
500	3.49E-1	3.58E-1	3.86E-1	4.37E-1	4.85E-1	5.56E-1	6.67E-1	7.70E-1	9.38E-1
500	3.49E-1								
500	3.31E-1	3.41E-1	3.69E-1	4.21E-1	4.67E-1	5.36E-1	6.42E-1	7.36E-1	9.16E-1
700	3.11E-1	3.21E-1	3.48E-1	3.98E-1	4.48E-1	5.15E-1	6.16E-1	7.07E-1	8.87E-1
1000	3.10E-1								
2000	2.67E-1								
5000	2.02E-1								

Average depth (mean range) in Å of T implanted in W  
 ne=22, na=9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	1.29E+1	1.28E+1	1.28E+1	1.28E+1	1.26E+1	1.26E+1	1.25E+1	1.24E+1	1.24E+1
20	1.83E+1	1.83E+1	1.82E+1	1.82E+1	1.79E+1	1.79E+1	1.78E+1	1.78E+1	1.77E+1
50	2.95E+1	2.95E+1	2.93E+1	2.91E+1	2.89E+1	2.86E+1	2.86E+1	2.84E+1	2.82E+1
100	4.27E+1	4.28E+1	4.23E+1	4.20E+1	4.15E+1	4.12E+1	4.09E+1	4.08E+1	4.07E+1
140	5.13E+1	5.12E+1	5.08E+1	5.03E+1	5.00E+1	4.96E+1	4.92E+1	4.87E+1	4.93E+1
160	5.53E+1	5.51E+1	5.47E+1	5.41E+1	5.36E+1	5.33E+1	5.29E+1	5.28E+1	5.29E+1
170	5.71E+1	5.70E+1	5.66E+1	5.59E+1	5.55E+1	5.50E+1	5.46E+1	5.45E+1	5.37E+1
170	5.71E+1								
180	5.90E+1	5.88E+1	5.84E+1	5.77E+1	5.73E+1	5.67E+1	5.64E+1	5.62E+1	5.60E+1
200	6.26E+1	6.24E+1	6.19E+1	6.13E+1	6.07E+1	6.02E+1	5.98E+1	5.97E+1	5.95E+1
250	7.10E+1	7.09E+1	7.03E+1	6.95E+1	6.88E+1	6.82E+1	6.76E+1	6.75E+1	6.72E+1
300	7.89E+1	7.86E+1	7.79E+1	7.69E+1	7.62E+1	7.55E+1	7.50E+1	7.48E+1	7.44E+1
300	7.89E+1								
400	9.33E+1	9.31E+1	9.21E+1	9.10E+1	8.99E+1	8.92E+1	8.84E+1	8.84E+1	8.81E+1
500	1.07E+2	1.06E+2	1.05E+2	1.04E+2	1.03E+2	1.02E+2	1.01E+2	1.01E+2	9.96E+1
500	1.07E+2								
700	1.31E+2	1.30E+2	1.29E+2	1.28E+2	1.26E+2	1.24E+2	1.23E+2	1.23E+2	1.24E+2
1000	1.64E+2	1.64E+2	1.62E+2	1.60E+2	1.57E+2	1.55E+2	1.53E+2	1.53E+2	1.54E+2
1000	1.64E+2								
2000	2.59E+2								
5000	5.05E+2								

# $T \rightarrow W$

T on W, Maxwellian velocity distribution, sheath potential 0 kT  
 z1= 1, m1= 3.02, z2=74, m2=183.85, sbe=8.68 eV, rho=19.30 g/cm\*\*3  
 ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1(KrC)  
 program: testvmcx  
 ne=10

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
40	5.90e-5	2.31e-6	3.13e+0	7.65e-1	5.63e-1	5.89e+1	3.73e+1
50	1.64e-4	6.30e-6	3.84e+0	7.55e-1	5.50e-1	7.28e+1	4.20e+1
60	3.22e-4	1.17e-5	4.37e+0	7.47e-1	5.39e-1	8.65e+1	4.63e+1
80	8.55e-4	2.73e-5	5.11e+0	7.34e-1	5.23e-1	1.14e+2	5.41e+1
100	1.63e-3	4.96e-5	6.09e+0	7.22e-1	5.09e-1	1.41e+2	6.14e+1
200	6.54e-3	1.49e-4	9.10e+0	6.89e-1	4.70e-1	2.73e+2	9.13e+1
300	1.16e-2	2.19e-4	1.13e+1	6.68e-1	4.45e-1	4.00e+2	1.17e+2
500	1.93e-2	2.75e-4	1.43e+1	6.41e-1	4.15e-1	6.47e+2	1.61e+2
1000	3.06e-2	2.97e-4	1.94e+1	5.96e-1	3.66e-1	1.23e+3	2.57e+2
2000	3.99e-2	2.48e-4	2.49e+1	5.47e-1	3.14e-1	2.29e+3	4.19e+2

T on W, Maxwellian velocity distribution, sheath potential 3 kT  
 ne=13

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
24	3.64e-5	6.56e-7	2.17e+0	6.59e-1	4.48e-1	8.15e+1	4.64e+1
30	1.77e-4		2.56e+0	6.41e-1		1.02e+2	4.94e+1
36	4.11e-4		2.89e+0	6.33e-1		1.21e+2	5.48e+1
50	1.70e-3		4.24e+0	6.18e-1		1.66e+2	6.67e+1
60	2.57e-3	4.14e-5	4.83e+0	6.16e-1	4.02e-1	1.96e+2	7.75e+1
70	4.22e-3		5.55e+0	6.03e-1		2.29e+2	8.16e+1
100	7.43e-3		7.38e+0	5.85e-1		3.22e+2	1.02e+2
200	1.48e-2		1.21e+1	5.46e-1		6.21e+2	1.59e+2
300	1.91e-2	1.94e-4	1.52e+1	5.24e-1	3.15e-1	9.02e+2	2.11e+2
400	2.03e-2		1.78e+1	4.98e-1		1.18e+3	2.53e+2
600	2.26e-2	1.61e-4	2.14e+1	4.66e-1	2.65e-1	1.71e+3	3.41e+2
1000	2.33e-2	1.21e-4	2.60e+1	4.17e-1	2.25e-1	2.70e+3	4.94e+2
2000	2.04e-2	6.91e-5	3.39e+1	3.41e-1	1.67e-1	4.91e+3	8.37e+2

# He → W

Sputtering yield of W by He  
 z1= 2, m1= 4.00, z2=74, m2=183.85, esb=8.68 eV, rho=19.29 g/cm\*\*3  
 ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trvmc  
 ne=20, na=9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
125	8.26E-6	9.32E-6	1.12E-5	1.11E-5	9.05E-6	4.44E-6	2.00E-6		
130	3.21E-5	3.56E-5	3.51E-5	3.27E-5	2.86E-5	1.57E-5	3.40E-6		
140	1.32E-4	1.36E-4	1.43E-4	1.45E-4	1.16E-4	7.19E-5	1.94E-5	3.74E-6	
150	3.10E-4	3.22E-4	3.19E-4	3.16E-4	2.87E-4	1.95E-4	6.19E-5	1.25E-5	
170	9.50E-4	9.41E-4	1.01E-3	1.01E-3	8.69E-4	6.13E-4	2.32E-4	6.15E-5	
200	2.33E-3	2.44E-3	2.50E-3	2.63E-3	2.27E-3	1.86E-3	7.62E-4	2.31E-4	2.15E-6
250	5.42E-3	5.27E-3	5.76E-3	5.92E-3	6.10E-3	4.86E-3	2.49E-3	9.07E-4	1.58E-5
300	8.61E-3	8.63E-3	9.41E-3	1.02E-2	9.96E-3	9.35E-3	5.74E-3	2.52E-3	7.76E-5
350	1.21E-2	1.17E-2	1.28E-2	1.42E-2	1.49E-2	1.45E-2	1.02E-2	5.80E-3	2.41E-4
400	1.47E-2	1.49E-2	1.63E-2	1.87E-2	1.97E-2	2.09E-2	1.79E-2	9.86E-3	5.58E-4
500	2.03E-2	2.10E-2	2.27E-2	2.63E-2	2.90E-2	3.34E-2	3.32E-2	2.32E-2	2.01E-3
600	2.42E-2	2.57E-2	2.80E-2	3.30E-2	3.79E-2	4.67E-2	5.19E-2	4.08E-2	4.95E-3
700	2.88E-2	3.04E-2	3.31E-2	3.88E-2	4.58E-2	5.82E-2	6.78E-2	5.84E-2	9.14E-3
1000	3.78E-2	3.97E-2	4.32E-2	5.49E-2	6.78E-2	8.93E-2	1.15E-1	1.06E-1	2.63E-2
1400	4.57E-2	4.70E-2	5.31E-2	7.02E-2	8.85E-2	1.18E-1	1.59E-1	1.57E-1	5.54E-2
2000	5.15E-2	5.43E-2	6.31E-2	8.25E-2	1.07E-1	1.47E-1	2.01E-1	2.11E-1	1.01E-1
5000	5.91E-2	6.36E-2	7.64E-2	1.03E-1	1.39E-1	1.89E-1	2.84E-1	3.31E-1	2.67E-1
10000	5.63E-2	6.28E-2	7.47E-2	1.04E-1	1.36E-1	1.96E-1	3.07E-1	3.81E-1	3.93E-1
20000	4.78E-2	5.24E-2	6.44E-2	9.04E-2	1.22E-1	1.77E-1	2.90E-1	3.92E-1	4.79E-1
50000	3.23E-2	3.48E-2	4.49E-2	6.46E-2	8.69E-2	1.27E-1	2.26E-1	3.25E-1	4.94E-1

Sputtered energy of W by He  
 ne=20, na=9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
125	2.08e-8	2.68e-8	3.18e-8	3.61e-8	3.06e-8	1.40e-8	6.54e-9		
130	1.27e-7	1.51e-7	1.51e-7	1.44e-7	1.30e-7	6.83e-8	1.25e-8		
140	8.49e-7	8.78e-7	9.35e-7	9.63e-7	7.76e-7	4.76e-7	1.17e-7	2.09e-8	
150	2.53e-6	2.69e-6	2.71e-6	2.69e-6	2.49e-6	1.69e-6	4.74e-7	9.04e-8	
170	1.03E-5	1.02E-5	1.10E-5	1.14E-5	9.98E-6	6.82E-6	2.45E-6	6.30E-7	
200	3.17E-5	3.35E-5	3.46E-5	3.71E-5	3.17E-5	2.65E-5	1.05E-5	3.05E-6	3.11E-8
250	8.64E-5	8.36E-5	9.33E-5	1.01E-4	9.90E-4	8.17E-5	4.18E-5	1.47B-5	2.45E-7
300	1.46E-4	1.48E-4	1.62E-4	1.81E-4	1.79E-4	1.68E-4	1.02E-4	4.41E-5	1.34E-6
350	2.10E-4	2.03E-4	2.28E-4	2.49E-4	2.68E-4	2.66E-4	1.89E-4	1.07E-4	4.68E-6
400	2.53E-4	2.60E-4	2.83E-4	3.31E-4	3.59E-4	3.80E-4	3.31E-4	1.86B-4	1.18E-5
500	3.46E-4	3.57E-4	3.96E-4	4.49E-4	5.08E-4	5.92E-4	6.19E-4	4.61E-4	4.58E-5
600	3.96E-4	4.24E-4	4.75E-4	5.52E-4	6.34E-4	7.82E-4	9.41E-4	8.11E-4	1.15E-4
700	4.56E-4	4.81E-4	5.28E-4	6.20E-4	7.35E-4	9.48E-4	1.20E-3	1.15E-3	2.15E-4
1000	5.38E-4	5.61E-4	6.15E-4	7.64E-4	9.64E-4	1.29E-3	1.86E-3	1.91E-3	5.80E-4
1400	5.63E-4	5.80E-4	6.50E-4	8.57E-4	1.09E-3	1.52E-3	2.27E-3	2.50E-3	1.10E-3
2000	5.35E-4	5.54E-4	6.44E-4	8.32E-4	1.11E-3	1.60E-3	2.42E-3	2.82E-3	1.70E-3
5000	3.57E-4	3.77E-4	4.47E-4	6.34E-4	8.76E-4	1.25E-3	2.00E-3	2.57E-3	2.55E-3
10000	2.09E-4	2.32E-4	2.88E-4	4.06E-4	5.61E-4	8.55E-4	1.45E-3	1.90E-3	2.34E-3
20000	1.04E-4	1.19E-4	1.56E-4	2.26E-4	3.15E-4	4.89E-4	8.64E-4	1.23E-3	1.73E-3
50000	3.28E-5	3.71E-5	5.19E-5	8.46E-5	1.25E-4	1.86E-4	3.60E-4	5.48E-4	9.08E-4

# He → W

Particle reflection coefficient of He backscattered from W  
 z1= 2, m1= 4.00, z2=74, m2=183.85, esb=8.68 eV, rho=19.29 g/cm\*\*3  
 ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trvmc  
 ne=24, na=9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	8.09E-1	8.21E-1	8.48E-1	8.93E-1	9.30E-1	9.70E-1	9.96E-1	1.00E+0	1.00E+0
20	7.49E-1	7.59E-1	7.93E-1	8.47E-1	8.95E-1	9.48E-1	9.91E-1	9.99E-1	1.00E+0
50	6.80E-1	6.88E-1	7.19E-1	7.75E-1	8.31E-1	8.99E-1	9.74E-1	9.96E-1	1.00E+0
100	6.37E-1	6.47E-1	6.76E-1	7.28E-1	7.79E-1	8.50E-1	9.46E-1	9.88E-1	1.00E+0
125	6.24E-1	6.34E-1	6.63E-1	7.14E-1	7.64E-1	8.34E-1	9.34E-1	9.84E-1	1.00E+0
130	6.22E-1	6.31E-1	6.61E-1	7.12E-1	7.62E-1	8.31E-1	9.32E-1	9.83E-1	1.00E+0
140	6.18E-1	6.27E-1	6.57E-1	7.07E-1	7.57E-1	8.26E-1	9.28E-1	9.80E-1	1.00E+0
150	6.14E-1	6.24E-1	6.52E-1	7.04E-1	7.53E-1	8.21E-1	9.23E-1	9.78E-1	1.00E+0
170	6.07E-1	6.18E-1	6.46E-1	6.96E-1	7.45E-1	8.12E-1	9.15E-1	9.74E-1	1.00E+0
200	5.98E-1	6.07E-1	6.36E-1	6.86E-1	7.35E-1	8.01E-1	9.04E-1	9.68E-1	1.00E+0
250	5.88E-1	5.97E-1	6.26E-1	6.76E-1	7.22E-1	7.87E-1	8.89E-1	9.58E-1	9.99E-1
300	5.78E-1	5.87E-1	6.17E-1	6.65E-1	7.13E-1	7.75E-1	8.74E-1	9.49E-1	9.99E-1
350	5.71E-1	5.82E-1	6.10E-1	6.58E-1	7.03E-1	7.65E-1	8.64E-1	9.39E-1	9.98E-1
400	5.64E-1	5.73E-1	6.01E-1	6.51E-1	6.97E-1	7.57E-1	8.52E-1	9.31E-1	9.97E-1
500	5.51E-1	5.63E-1	5.90E-1	6.38E-1	6.85E-1	7.45E-1	8.37E-1	9.15E-1	9.95E-1
600	5.43E-1	5.54E-1	5.83E-1	6.33E-1	6.75E-1	7.35E-1	8.23E-1	9.02E-1	9.93E-1
700	5.35E-1	5.43E-1	5.75E-1	6.25E-1	6.67E-1	7.25E-1	8.14E-1	8.90E-1	9.90E-1
1000	5.14E-1	5.23E-1	5.55E-1	6.02E-1	6.49E-1	7.07E-1	7.91E-1	8.62E-1	9.80E-1
1400	4.92E-1	5.02E-1	5.35E-1	5.86E-1	6.30E-1	6.89E-1	7.69E-1	8.38E-1	9.64E-1
2000	4.68E-1	4.80E-1	5.09E-1	5.61E-1	6.11E-1	6.71E-1	7.52E-1	8.14E-1	9.41E-1
5000	3.94E-1	4.06E-1	4.42E-1	4.98E-1	5.50E-1	6.18E-1	7.00E-1	7.57E-1	8.66E-1
10000	3.26E-1	3.41E-1	3.76E-1	4.37E-1	4.94E-1	5.67E-1	6.55E-1	7.17E-1	8.16E-1
20000	2.49E-1	2.63E-1	3.02E-1	3.67E-1	4.31E-1	5.08E-1	6.10E-1	6.75E-1	7.69E-1
50000	1.43E-1	1.54E-1	1.92E-1	2.59E-1	3.28E-1	4.20E-1	5.39E-1	6.12E-1	7.18E-1

Energy reflection coefficient of He backscattered from W  
 ne=24, na=9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	5.95E-1	6.14E-1	6.58E-1	7.35E-1	8.03E-1	8.86E-1	9.62E-1	9.84E-1	9.95E-1
20	5.28E-1	5.43E-1	5.90E-1	6.74E-1	7.53E-1	8.51E-1	9.50E-1	9.81E-1	9.94E-1
50	4.52E-1	4.63E-1	5.03E-1	5.81E-1	6.63E-1	7.76E-1	9.17E-1	9.72E-1	9.93E-1
100	4.07E-1	4.19E-1	4.54E-1	5.21E-1	5.94E-1	7.02E-1	8.68E-1	9.53E-1	9.92E-1
125	3.94E-1	4.05E-1	4.39E-1	5.04E-1	5.73E-1	6.78E-1	8.47E-1	9.44E-1	9.91E-1
130	3.92E-1	4.03E-1	4.37E-1	5.01E-1	5.69E-1	6.74E-1	8.44E-1	9.42E-1	9.91E-1
140	3.88E-1	3.99E-1	4.32E-1	4.95E-1	5.63E-1	6.66E-1	8.36E-1	9.38E-1	9.90E-1
150	3.85E-1	3.95E-1	4.28E-1	4.91E-1	5.57E-1	6.59E-1	8.29E-1	9.34E-1	9.90E-1
170	3.78E-1	3.89E-1	4.21E-1	4.82E-1	5.47E-1	6.46E-1	8.16E-1	9.26E-1	9.90E-1
200	3.70E-1	3.80E-1	4.12E-1	4.72E-1	5.34E-1	6.31E-1	7.98E-1	9.15E-1	9.89E-1
250	3.60E-1	3.69E-1	4.00E-1	4.58E-1	5.18E-1	6.10E-1	7.73E-1	8.97E-1	9.87E-1
300	3.51B-1	3.60E-1	3.91E-1	4.47E-1	5.06E-1	5.93E-1	7.51E-1	8.80E-1	9.85E-1
350	3.43E-1	3.54E-1	3.83E-1	4.39E-1	4.95E-1	5.81E-1	7.35E-1	8.65E-1	9.83E-1
400	3.37E-1	3.46E-1	3.76E-1	4.30E-1	4.88E-1	5.70E-1	7.18E-1	8.51E-1	9.81E-1
500	3.27B-1	3.37E-1	3.65E-1	4.18E-1	4.74E-1	5.54E-1	6.94E-1	8.25E-1	9.76E-1
600	3.18E-1	3.29E-1	3.57E-1	4.12E-1	4.62E-1	5.41E-1	6.74E-1	8.03E-1	9.71E-1
700	3.12E-1	3.20E-1	3.50E-1	4.04E-1	4.53E-1	5.30E-1	6.60E-1	7.85E-1	9.65E-1
1000	2.95E-1	3.03E-1	3.33E-1	3.83E-1	4.34E-1	5.07E-1	6.27E-1	7.42E-1	9.45E-1
1400	2.77E-1	2.86E-1	3.14E-1	3.66E-1	4.15E-1	4.86E-1	5.99E-1	7.05E-1	9.17E-1
2000	2.58E-1	2.68E-1	2.94E-1	3.44E-1	3.96E-1	4.66E-1	5.74E-1	6.69E-1	8.79E-1
5000	2.02E-1	2.11E-1	2.39E-1	2.88E-1	3.37E-1	4.08E-1	5.11E-1	5.91E-1	7.63E-1
10000	1.55E-1	1.64E-1	1.88E-1	2.37E-1	2.86E-1	3.57E-1	4.59E-1	5.41E-1	6.85E-1
20000	1.07E-1	1.14E-1	1.38E-1	1.81E-1	2.29E-1	2.98E-1	4.04E-1	4.85E-1	6.19E-1
50000	5.14E-2	5.62E-2	7.27E-2	1.07E-1	1.48E-1	2.13E-1	3.19E-1	4.02E-1	5.38E-1

Average depth (mean range) in Å of He implanted in W  
 ne=24, na=9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	9.20E+0	9.20E+0	9.10E+0	9.10E+0	9.00E+0	9.00E+0	8.70E+0	8.80E+0	8.70E+0
20	1.24E+1	1.24E+1	1.23E+1	1.23E+1	1.21E+1	1.21E+1	1.17B+1	1.22E+1	1.22E+1
50	1.90E+1	1.92E+1	1.90E+1	1.88E+1	1.86E+1	1.85E+1	1.83E+1	1.81E+1	1.62E+1
100	2.69E+1	2.69E+1	2.67E+1	2.65E+1	2.61E+1	2.61E+1	2.60E+1	2.53E+1	2.55E+1
125	3.02E+1	3.02E+1	2.99E+1	2.96E+1	2.93E+1	2.91E+1	2.88E+1	2.85B+1	2.72E+1
130	3.09E+1	3.08E+1	3.05E+1	3.02E+1	2.99E+1	2.96E+1	2.94E+1	2.93B+1	3.06E+1
140	3.21E+1	3.20E+1	3.17E+1	3.13E+1	3.11E+1	3.08E+1	3.05E+1	3.03E+1	3.25E+1
150	3.32E+1	3.31E+1	3.29E+1	3.24E+1	3.22E+1	3.19E+1	3.16E+1	3.14B+1	3.05E+1
170	3.55E+1	3.54E+1	3.51E+1	3.46E+1	3.43E+1	3.40E+1	3.37E+1	3.34E+1	3.65E+1
200	3.85E+1	3.84E+1	3.81E+1	3.75E+1	3.72E+1	3.69E+1	3.66E+1	3.64E+1	3.59E+1
250	4.35B+1	4.34E+1	4.29E+1	4.24E+1	4.18E+1	4.15E+1	4.12E+1	4.10B+1	4.04E+1
300	4.81E+1	4.77E+1	4.74E+1	4.66E+1	4.62E+1	4.58E+1	4.53E+1	4.51E+1	4.45E+1
350	5.22E+1	5.20E+1	5.14E+1	5.09E+1	5.00E+1	4.96E+1	4.94E+1	4.89E+1	4.79E+1
400	5.62B+1	5.58E+1	5.54E+1	5.46E+1	5.39E+1	5.32E+1	5.28E+1	5.28B+1	5.24E+1
500	6.36E+1	6.34E+1	6.26E+1	6.20E+1	6.10E+1	6.05E+1	5.95E+1	5.93E+1	5.89E+1
600	7.06E+1	7.03E+1	6.94E+1	6.84E+1	6.74E+1	6.71E+1	6.59E+1	6.57E+1	6.57E+1
700	7.71E+1	7.69E+1	7.59E+1	7.47E+1	7.39E+1	7.29E+1	7.22E+1	7.19B+1	7.17E+1
1000	9.53E+1	9.47E+1	9.34E+1	9.17E+1	9.07E+1	8.93E+1	8.81E+1	8.76B+1	8.84E+1
1400	1.16E+2	1.16E+2	1.15E+2	1.12E+2	1.11E+2	1.09E+2	1.07E+2	1.08E+2	1.07E+2
2000	1.46E+2	1.46E+2	1.43E+2	1.40E+2	1.37E+2	1.35E+2	1.34E+2	1.33E+2	1.33E+2
5000	2.69E+2	2.67E+2	2.63E+2	2.55E+2	2.49E+2	2.44E+2	2.39E+2	2.37B+2	2.37E+2
10000	4.44E+2	4.40E+2	4.29E+2	4.12E+2	4.02E+2	3.89E+2	3.81E+2	3.79E+2	3.75E+2
20000	7.54E+2	7.45E+2	7.20E+2	6.87E+2	6.59E+2	6.33E+2	6.15E+2	6.06E+2	6.01E+2
50000	1.58E+3	1.55E+3	1.47E+3	1.37E+3	1.28E+3	1.21E+3	1.15E+3	1.12B+3	1.11E+3

# C → W

Sputtering yield of W by C  
 $z1 = 6, m1 = 12.01, z2 = 74, m2 = 183.85, sb = 8.68 \text{ eV}, rho = 19.30 \text{ g/cm}^{**3}$   
 $ef = 3.95 \text{ eV}, esb = 4.00 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1$  (KrC)  
 program : testvmcx  
*only low fluence!*  
 $ne = 11, na = 1$

$E_0(\text{eV})$	$0^\circ$	comment
55	4.77e-5	$ef = 0.95, esb = 1.00 \text{ eV}$
60	2.68e-4	$ef = 0.95, esb = 1.00 \text{ eV}$
70	2.25e-3	
100	1.23e-2	
200	6.24e-2	
500	1.66e-1	
1000	2.67e-1	
2000	3.68E-1	
5000	4.54e-1	
10000	5.02e-1	
40000	4.06e-1	$ef = 1.00, esb = 1.00 \text{ eV}$

Sputtered energy of W by C  
*only low fluence!*  
 $ne = 11, na = 1$

$E_0(\text{eV})$	$0^\circ$	comment
55	5.49e-7	$ef = 0.95, esb = 1.00 \text{ eV}$
60	4.59e-6	$ef = 0.95, esb = 1.00 \text{ eV}$
70	6.75e-5	
100	5.02e-4	
200	2.69e-3	
500	5.36e-3	
1000	6.08e-3	
2000	5.76E-3	
5000	4.16e-3	
10000	2.78e-3	
40000	8.53e-4	$ef = 1.00, esb = 1.00 \text{ eV}$

# C → W

Particle reflection coefficient of C backscattered from W  
 $z1 = 6, m1 = 12.01, z2 = 74, m2 = 183.85, sbe = 8.68 \text{ eV}, rho = 19.30 \text{ g/cm}^{**3}$   
 $ef = 3.95 \text{ eV}, esb = 4.00 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1$  (KrC)  
 program : testvmcx  
*only low fluence!*  
 $ne = 11, na = 1$

$E_0(\text{eV})$	$0^\circ$	comment
55	6.23e-1	$ef = 0.95, esb = 1.00 \text{ eV}$
60	6.16e-1	$ef = 0.95, esb = 1.00 \text{ eV}$
70	5.81e-1	
100	5.61e-1	
200	5.25e-1	
500	4.77e-1	
1000	4.52e-1	
2000	4.22E-1	
5000	3.65e-1	
10000	3.27e-1	
40000	2.16e-1	$ef = 1.00, esb = 1.00 \text{ eV}$

Energy reflection coefficient of C backscattered from W  
*only low fluence!*  
 $ne = 11, na = 1$

$E_0(\text{eV})$	$0^\circ$	comment
55	3.55e-1	$ef = 0.95, esb = 1.00 \text{ eV}$
60	3.50e-1	$ef = 0.95, esb = 1.00 \text{ eV}$
70	3.28e-1	
100	3.10e-1	
200	2.79e-1	
500	2.40e-1	
1000	2.23e-1	
2000	2.02E-1	
5000	1.68e-1	
10000	1.45e-1	
40000	8.68e-2	$ef = 1.00, esb = 1.00 \text{ eV}$

Average depth (mean range) in Å of C implanted in W  
*only low fluence!*  
 $ne = 11, na = 1$

$E_0(\text{eV})$	$0^\circ$	comment
55	9.11e+0	$ef = 0.95, esb = 1.00 \text{ eV}$
60	9.50e+0	$ef = 0.95, esb = 1.00 \text{ eV}$
70	1.01e+1	
100	1.21e+1	
200	1.72e+1	
500	2.82e+1	
1000	4.14e+1	
2000	6.12E+1	
5000	1.10e+2	
10000	1.73e+2	
40000	5.00e+2	$ef = 1.00, esb = 1.00 \text{ eV}$

C on W, Maxwellian velocity distribution, sheath potential 9 kT  
 $z1 = 6, m1 = 12.01, z2 = 74, m2 = 183.85, sbe = 8.68 \text{ eV}, rho = 19.29 \text{ g/cm}^{**3}$   
 $ef = 0.98 \text{ eV}, esb = 1.00 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1$  (KrC)  
 program: trvmc  
*only low fluence!*  
 $ne = 4$

kT(eV)	Y	$Y_E$	$E_{sp}$	$R_N$	$R_E$	$E_b$	range
5	2.45e-4	8.40e-6	1.88e+0	6.50e-1	3.83e-1	3.24e+1	9.23e+0
10	1.59e-2	7.08e-4	4.90e+0	5.92e-1	3.33e-1	6.19e+1	1.29e+1
20	7.19e-2	3.10e-3	9.49e+0	5.45e-1	2.94e-1	1.19e+2	1.82e+1
40	1.61e-1	5.52e-3	1.51e+1	5.07e-1	2.62e-1	2.28e+2	2.61e+1

# N → W

Sputtering yield of W by N  
 z1= 7, m1= 14.01, z2=74, m2=183.85, sbe=8.68 eV, rho=19.29 g/cm\*\*\*  
 ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trvmc  
 ne=22, na=9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
47	9.30e-6	7.00e-6							
48	1.82E-5	1.60E-5	1.20E-5	5.70E-6	2.30E-6				
50	5.70E-5	5.25E-5	3.93E-5	2.11E-5	1.07E-5	2.85E-6			
52	1.35E-4	1.28E-4	9.18E-5	5.06E-5	2.86E-5	9.30E-6			
55	3.60E-4	3.30E-4	2.56E-4	1.52E-4	8.47E-5	2.75E-5	3.08E-6		
60	9.73E-4	9.57E-4	7.55E-4	4.74E-4	2.76E-4	1.08E-4	1.52E-5	2.20E-6	
70	3.26E-3	3.26E-3	2.84E-3	2.02E-3	1.31E-3	5.87E-4	1.08E-4	1.98E-5	1.50E-6
80	7.00E-3	6.70E-3	6.06E-3	4.61E-3	3.18E-3	1.61E-3	3.52E-4	7.13E-5	6.20E-6
90	1.17E-2	1.14E-2	1.06E-2	8.58E-3	6.13E-3	3.36E-3	8.56E-4	2.12E-4	1.76E-5
100	1.72E-2	1.70E-2	1.60E-2	1.30E-2	1.03E-2	6.07E-3	1.78E-3	4.90E-4	4.29E-5
120	2.77E-2	2.79E-2	2.82E-2	2.53E-2	2.17E-2	1.43E-2	5.43E-3	1.70E-3	1.23E-4
140	3.99E-2	4.07E-2	4.14E-2	4.06E-2	3.50E-2	2.65E-2	1.14E-2	3.67E-3	2.47E-4
200	7.57E-2	8.00E-2	8.32E-2	8.70E-2	9.07E-2	7.77E-2	4.11E-2	1.50E-2	8.58E-4
300	1.32E-1	1.35E-1	1.48E-1	1.71E-1	1.85E-1	1.80E-1	1.15E-1	4.56E-2	2.65E-3
500	2.13E-1	2.21E-1	2.52E-1	3.10E-1	3.51E-1	3.68E-1	2.66E-1	1.26E-1	8.67E-3
1000	3.39E-1	3.58E-1	4.22E-1	5.35E-1	6.24E-1	6.89E-1	5.80E-1	3.49E-1	4.00E-2
2000	4.69E-1								
3000	5.40E-1								
5000	6.05E-1								
10000	6.54E-1								
20000	6.18E-1								
50000	5.30E-1								

Sputtered energy of W by N  
 ne=22, na=9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
47	9.95e-8	7.47e-8							
48	2.19e-7	2.10e-7	1.92e-7	8.93e-8	4.20e-8				
50	8.42e-7	8.26e-7	6.77e-7	3.68e-7	1.82e-7	4.76e-8			
52	2.44E-6	2.31E-6	1.75E-6	1.00E-6	5.63E-7	1.87E-7			
55	7.80E-6	7.08E-6	5.73E-6	3.39E-6	1.85E-6	5.84E-7	6.31E-8		
60	2.61E-5	2.56E-5	2.10E-5	1.33E-5	7.59E-6	2.81E-6	3.75E-7	5.17E-8	
70	1.16E-4	1.16E-4	1.03E-4	7.42E-5	4.59E-5	1.97E-5	3.52E-6	6.60E-7	5.65E-8
80	2.85E-4	2.74E-4	2.52E-4	1.93E-4	1.32E-4	6.64E-5	1.39E-5	2.82E-6	3.05E-7
90	5.22E-4	5.06E-4	4.88E-4	3.93E-4	2.86E-4	1.56E-4	3.69E-5	9.32E-6	8.21E-7
100	7.88E-4	7.97E-4	7.61E-4	6.10E-4	5.13E-4	3.05E-4	8.38E-5	2.38E-5	2.27E-6
120	1.35E-3	1.35E-3	1.40E-3	1.30E-3	1.13E-3	7.54E-4	2.93E-4	9.69E-5	7.37E-6
140	1.92E-3	1.98E-3	2.10E-3	2.11E-3	1.89E-3	1.47E-3	6.53E-4	2.27E-4	1.59E-5
200	3.56E-3	3.78E-3	4.01E-3	4.41E-3	4.74E-3	4.30E-3	2.61E-3	1.04E-3	6.16E-5
300	5.49E-3	5.78E-3	6.39E-3	7.63E-3	8.72E-3	9.35E-3	7.08E-3	3.12E-3	1.94E-4
500	7.36E-3	7.71E-3	8.78E-3	1.15E-2	1.38E-2	1.63E-2	1.42E-2	7.70E-3	5.65E-4
1000	8.26E-3	8.76E-3	1.04E-2	1.40E-2	1.77E-2	2.21E-2	2.24E-2	1.55E-2	2.06E-3
2000	7.47E-3								
3000	6.94E-3								
5000	5.74E-3								
10000	3.92E-3								
20000	2.42E-3								
50000	1.06E-3								

# N → W

Particle reflection coefficient of N backscattered from W  
 z1= 7, m1= 14.01, z2=74, m2=183.85, sbe=8.68 eV, rho=19.29 g/cm\*\*3  
 ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trvmc  
 ne=25, na=9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	7.68E-1	7.83E-1	8.14E-1	8.62E-1	9.01E-1	9.43E-1	9.74E-1	9.84E-1	9.88E-1
20	7.17E-1	7.34E-1	7.73E-1	8.36E-1	8.85E-1	9.39E-1	9.80E-1	9.91E-1	9.96E-1
40	6.52E-1	6.68E-1	7.13E-1	7.87E-1	8.50E-1	9.19E-1	9.78E-1	9.93E-1	9.99E-1
47	6.37E-1	6.53E-1							
48	6.35E-1	6.51E-1	6.95E-1	7.72E-1	8.38E-1	9.12E-1	9.76E-1	9.93E-1	9.99E-1
50	6.31E-1	6.47E-1	6.92E-1	7.68E-1	8.35E-1	9.10E-1	9.76E-1	9.93E-1	9.99E-1
52	6.28E-1	6.43E-1	6.88E-1	7.65E-1	8.32E-1	9.08E-1	9.75E-1	9.93E-1	9.99E-1
55	6.22E-1	6.38E-1	6.83E-1	7.60E-1	8.28E-1	9.05E-1	9.74E-1	9.93E-1	9.99E-1
60	6.14E-1	6.30E-1	6.75E-1	7.52E-1	8.21E-1	9.01E-1	9.73E-1	9.93E-1	9.99E-1
70	6.00E-1	6.15E-1	6.61E-1	7.39E-1	8.09E-1	8.92E-1	9.70E-1	9.92E-1	9.99E-1
80	5.90E-1	6.04E-1	6.49E-1	7.27E-1	7.98E-1	8.84E-1	9.67E-1	9.92E-1	9.99E-1
90	5.83E-1	5.96E-1	6.39E-1	7.15E-1	7.88E-1	8.76E-1	9.64E-1	9.91E-1	9.99E-1
100	5.68E-1	5.88E-1	6.31E-1	7.08E-1	7.78E-1	8.70E-1	9.61E-1	9.91E-1	9.99E-1
120	5.58E-1	5.72E-1	6.16E-1	6.89E-1	7.63E-1	8.58E-1	9.56E-1	9.89E-1	9.99E-1
140	5.45E-1	5.61E-1	6.04E-1	6.78E-1	7.48E-1	8.45E-1	9.50E-1	9.88E-1	9.99E-1
200	5.25E-1	5.35E-1	5.77E-1	6.48E-1	7.19E-1	8.15E-1	9.32E-1	9.82E-1	9.99E-1
300	4.99E-1	5.11E-1	5.52E-1	6.19E-1	6.85E-1	7.77E-1	9.09E-1	9.73E-1	9.99E-1
500	4.72E-1	4.82E-1	5.18E-1	5.84E-1	6.48E-1	7.36E-1	8.70E-1	9.54E-1	9.98E-1
1000	4.38E-1	4.51E-1	4.84E-1	5.44E-1	6.09E-1	6.82E-1	8.10E-1	9.10E-1	9.94E-1
2000	4.11E-1								
3000	3.79E-1								
5000	3.55E-1								
10000	3.18E-1								
20000	2.67E-1								
50000	2.03E-1								

Energy reflection coefficient of N backscattered from W  
 ne=25, na=9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	4.40E-1	4.60E-1	5.04E-1	5.78E-1	6.48E-1	7.32E-1	8.13E-1	8.43E-1	8.62E-1
20	4.14E-1	4.35E-1	4.86E-1	5.75E-1	6.55E-1	7.55E-1	8.58E-1	8.97E-1	9.21E-1
40	3.66E-1	3.85E-1	4.38E-1	5.35E-1	6.27E-1	7.43E-1	8.71E-1	9.22E-1	9.52E-1
47	3.55E-1	3.72E-1							
48	3.53E-1	3.71E-1	4.23E-1	5.20E-1	6.15E-1	7.35E-1	8.71E-1	9.26E-1	9.58E-1
50	3.50E-1	3.68E-1	4.19E-1	5.17E-1	6.12E-1	7.33E-1	8.70E-1	9.26E-1	9.59E-1
52	3.47E-1	3.65E-1	4.16E-1	5.13E-1	6.09E-1	7.31E-1	8.70E-1	9.26E-1	9.60E-1
55	3.43E-1	3.60E-1	4.12E-1	5.09E-1	6.04E-1	7.28E-1	8.69E-1	9.28E-1	9.61E-1
60	3.37E-1	3.54E-1	4.04E-1	5.01E-1	5.97E-1	7.23E-1	8.68E-1	9.28E-1	9.63E-1
70	3.26E-1	3.42E-1	3.92E-1	4.87E-1	5.84E-1	7.12E-1	8.65E-1	9.29E-1	9.66E-1
80	3.18E-1	3.33E-1	3.81E-1	4.75E-1	5.72E-1	7.03E-1	8.61E-1	9.29E-1	9.68E-1
90	3.11B-1	3.25E-1	3.72E-1	4.63E-1	5.61E-1	6.93E-1	8.57E-1	9.29E-1	9.70E-1
100	3.03E-1	3.18E-1	3.65E-1	4.55E-1	5.49E-1	6.85E-1	8.53E-1	9.28E-1	9.72E-1
120	2.92E-1	3.07E-1	3.51E-1	4.37E-1	5.32E-1	6.69E-1	8.44E-1	9.26E-1	9.74E-1
140	2.84E-1	2.97E-1	3.41E-1	4.23E-1	5.16E-1	6.54E-1	8.36E-1	9.24E-1	9.75E-1
200	2.68E-1	2.78E-1	3.17E-1	3.95E-1	4.81E-1	6.15E-1	8.10E-1	9.15E-1	9.77E-1
300	2.49E-1	2.59E-1	2.96E-1	3.65E-1	4.43E-1	5.69E-1	7.74E-1	8.98E-1	9.77E-1
500	2.29E-1	2.38E-1	2.69E-1	3.33E-1	4.02E-1	5.17E-1	7.18E-1	8.66E-1	9.75E-1
1000	2.07E-1	2.16E-1	2.45E-1	3.00E-1	3.62E-1	4.53E-1	6.34E-1	7.95E-1	9.64E-1
2000	1.89E-1								
3000	1.72E-1								
5000	1.56E-1								
10000	1.36E-1								
20000	1.10E-1								
50000	7.70E-2								

# N → W

Average depth (mean range) in Å of N implanted in W  
 z1= 7, m1= 14.01, z2=74, m2=183.85, sbe=8.68 eV, rho=19.29 g/cm\*\*3  
 ef=0.98 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trvnc  
 ne=25, na=9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	3.80E+0	3.80E+0	3.80E+0	3.70E+0	3.70E+0	3.60E+0	3.50E+0	3.50E+0	3.40E+0
20	5.30E+0	5.30E+0	5.20E+0	5.20E+0	5.10E+0	5.00E+0	4.90E+0	4.80E+0	4.70E+0
40	7.20E+0	7.20E+0	7.20E+0	7.10E+0	7.00E+0	6.80E+0	6.60E+0	6.50E+0	6.50E+0
47	7.81E+0	7.78E+0							
48	7.90E+0	7.90E+0	7.80E+0	7.70E+0	7.60E+0	7.40E+0	7.20E+0	7.10E+0	7.00E+0
50	8.00E+0	8.00E+0	7.90E+0	7.80E+0	7.70E+0	7.60E+0	7.40E+0	7.20E+0	6.90E+0
52	8.20E+0	8.20E+0	8.10E+0	8.00E+0	7.90E+0	7.70E+0	7.40E+0	7.50E+0	7.30E+0
55	8.40E+0	8.40E+0	8.30E+0	8.20E+0	8.10E+0	7.90E+0	7.70E+0	7.60E+0	7.30E+0
60	8.70E+0	8.70E+0	8.60E+0	8.50E+0	8.40E+0	8.20E+0	8.00E+0	7.90E+0	7.50E+0
70	9.40E+0	9.40E+0	9.30E+0	9.10E+0	9.00E+0	8.90E+0	8.60E+0	8.40E+0	8.30E+0
80	1.00E+1	1.00E+1	9.90E+0	9.70E+0	9.60E+0	9.40E+0	9.20E+0	9.00E+0	8.80E+0
90	1.06E+1	1.06E+1	1.04E+1	1.02E+1	1.01E+1	1.00E+1	9.70E+0	9.40E+0	9.40E+0
100	1.12E+1	1.11E+1	1.10E+1	1.08E+1	1.06E+1	1.04E+1	1.02E+1	1.00E+1	9.70E+0
120	1.22E+1	1.22E+1	1.20E+1	1.18E+1	1.16E+1	1.14E+1	1.11E+1	1.09E+1	1.08E+1
140	1.32E+1	1.31E+1	1.30E+1	1.27E+1	1.24E+1	1.23E+1	1.19E+1	1.18E+1	1.15E+1
200	1.57E+1	1.57E+1	1.55E+1	1.51E+1	1.48E+1	1.45E+1	1.41E+1	1.40E+1	1.37E+1
300	1.92E+1	1.91E+1	1.90E+1	1.84E+1	1.82E+1	1.77E+1	1.74E+1	1.71E+1	1.63E+1
500	2.50E+1	2.50E+1	2.47E+1	2.41E+1	2.34E+1	2.32E+1	2.26E+1	2.24E+1	2.16E+1
1000	3.67E+1	3.65E+1	3.57E+1	3.45E+1	3.38E+1	3.31E+1	3.23E+1	3.23E+1	3.18E+1
2000	5.41E+1								
3000	6.88E+1								
5000	9.41E+1								
10000	1.53E+2								
20000	2.53E+2								
50000	5.15E+2								

# O → W

Sputtering yield of W by O  
 $z_1 = 8$ ,  $m_1 = 16.00$ ,  $z_2 = 74$ ,  $m_2 = 183.85$ ,  $sbe = 8.68$  eV,  $\rho = 19.30$  g/cm<sup>3</sup>  
 $ef = 0.95$  eV,  $esb = 1.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: IPP 9/82  
only low fluence!  
ne = 9, na = 1

E <sub>0</sub> (eV)	0°
50	3.63e-4
100	2.17e-2
200	9.00e-2
300	1.52e-1
500	2.45e-1
1000	3.71e-1
2000	5.33e-1
5000	6.89e-1
6000	7.64e-1

# Ne → W

Sputtering yield of W by Ne  
 $z_1 = 10$ ,  $m_1 = 20.18$ ,  $z_2 = 74$ ,  $m_2 = 183.85$ ,  $sbe = 8.68$  eV,  $\rho = 19.29$  g/cm<sup>3</sup>  
 $ef = 0.20$  eV,  $esb = 0.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: trvnc  
ne = 14, na = 9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
40	9.80E-6	7.70E-6	4.40E-6	1.80E-6	2.00E-6				
45	1.64E-4	1.37E-4	1.01E-4	4.66E-5	2.21E-5	4.88E-6	2.52E-6		
50	7.38E-4	6.43E-4	4.83E-4	2.82E-4	1.44E-4	4.22E-5			
60	3.61E-3	3.30E-3	2.74E-3	1.78E-3	1.09E-3	4.35E-4	5.33E-5	5.00E-6	
70	8.44E-3	8.11E-3	7.47E-3	5.27E-3	3.45E-3	1.69E-3	2.95E-4	4.46E-5	
80	1.58E-2	1.48E-2	1.41E-2	1.05E-2	7.52E-3	4.17E-3	9.51E-4	1.79E-4	
100	3.15E-2	3.13E-2	3.07E-2	2.59E-2	2.11E-2	1.40E-2	4.70E-3	8.37E-4	5.15E-6
140	6.97E-2	6.94E-2	7.15E-2	7.05E-2	6.58E-2	5.08E-2	2.06E-2	4.65E-3	3.58E-5
200	1.23E-1	1.29E-1	1.39E-1	1.50E-1	1.53E-1	1.33E-1	6.38E-2	1.72E-2	1.93E-4
300	2.02E-1	2.14E-1	2.38E-1	2.77E-1	2.91E-1	2.75E-1	1.46E-1	5.07E-2	8.85E-4
400	2.67E-1	2.82E-1	3.22E-1	3.88E-1	4.30E-1	4.11E-1	2.39E-1	9.32E-2	2.23E-3
500	3.24E-1	3.45E-1	4.00E-1	4.88E-1	5.41E-1	5.35E-1	3.37E-1	1.39E-1	4.54E-3
700	4.25E-1	4.44E-1	5.14E-1	6.38E-1	7.16E-1	7.37E-1	5.06E-1	2.38E-1	1.23E-2
1000	5.33E-1	5.62E-1	6.66E-1	8.18E-1	9.43E-1	9.76E-1	7.53E-1	3.99E-1	2.98E-2

Sputtered energy of W by Ne  
ne = 22, na = 9

E <sub>0</sub> (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
40	1.81E-7	1.58E-7	9.73E-8	4.89E-8	1.06E-7				
45	4.44E-6	3.82E-6	3.06E-6	1.41E-6	6.32E-7	1.37E-7			
50	2.59E-5	2.26E-5	1.79E-5	1.07E-5	5.34E-6	1.54E-6	1.21E-7		
60	1.63E-4	1.53E-4	1.29E-4	8.42E-5	5.03E-5	2.14E-5	2.91E-6	3.16E-7	
70	4.42E-4	4.29E-4	4.09E-4	2.92E-4	1.97E-4	9.88E-5	1.85E-5	3.05E-6	
80	8.87E-4	8.80E-4	8.36E-4	6.35E-4	4.66E-4	2.66E-4	6.30E-5	1.30E-5	
100	1.91E-3	1.92E-3	1.95E-3	1.70E-3	1.48E-3	9.78E-4	3.65E-4	7.09E-5	3.81E-7
140	4.12E-3	4.20E-3	4.44E-3	4.68E-3	4.58E-3	3.83E-3	1.77E-3	4.35E-4	2.90E-6
200	6.81E-3	7.39E-3	8.15E-3	9.36E-3	1.02E-2	9.88E-3	5.63E-3	1.64E-3	1.62E-5
300	9.82E-3	1.04E-2	1.18E-2	1.51E-2	1.72E-2	1.84E-2	1.21E-2	4.53E-3	7.32E-5
400	1.15E-2	1.20E-2	1.41E-2	1.87E-2	2.22E-2	2.49E-2	1.74E-2	7.62E-3	1.79E-4
500	1.26E-2	1.35E-2	1.57E-2	2.08E-2	2.57E-2	2.96E-2	2.29E-2	1.06E-2	3.18E-4
700	1.38E-2	1.43E-2	1.72E-2	2.33E-2	2.85E-2	3.42E-2	2.92E-2	1.58E-2	7.77E-4
1000	1.42E-2	1.52E-2	1.79E-2	2.43E-2	3.15E-2	3.70E-2	3.56E-2	2.18E-2	1.61E-3

# Ne → W

Particle reflection coefficient of Ne backscattered from W  
 $z1=10$ ,  $m1=20.18$ ,  $z2=74$ ,  $m2=183.85$ ,  $sbe=8.68$  eV,  $\rho=19.29$  g/cm\*\*3  
 $ef=0.20$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: trvnc  
ne=17, na=9

$E_0$ (eV)	$0^\circ$	$15^\circ$	$30^\circ$	$45^\circ$	$55^\circ$	$65^\circ$	$75^\circ$	$80^\circ$	$85^\circ$
10	8.10E-1	8.24E-1	8.53E-1	8.97E-1	9.36E-1	9.74E-1	9.96E-1	1.00E+0	1.00E+0
20	7.44E-1	7.61E-1	7.98E-1	8.59E-1	9.09E-1	9.62E-1	9.95E-1	9.99E-1	1.00E+0
30	6.97E-1	7.14E-1	7.58E-1	8.28E-1	8.86E-1	9.50E-1	9.93E-1	9.99E-1	1.00E+0
40	6.62E-1	6.80E-1	7.26E-1	8.03E-1	8.67E-1	9.38E-1	9.90E-1	9.99E-1	1.00E+0
45	6.48E-1	6.66E-1	7.13E-1	7.92E-1	8.59E-1	9.32E-1	9.89E-1	9.99E-1	1.00E+0
50	6.36E-1	6.54E-1	7.01E-1	7.82E-1	8.50E-1	9.27E-1	9.88E-1	9.99E-1	1.00E+0
60	6.16E-1	6.32E-1	6.80E-1	7.63E-1	8.36E-1	9.17E-1	9.85E-1	9.98E-1	1.00E+0
70	5.99E-1	6.15E-1	6.62E-1	7.48E-1	8.23E-1	9.08E-1	9.82E-1	9.98E-1	1.00E+0
80	5.85E-1	6.02E-1	6.46E-1	7.34E-1	8.10E-1	8.99E-1	9.79E-1	9.98E-1	1.00E+0
100	5.61E-1	5.79E-1	6.25E-1	7.13E-1	7.88E-1	8.83E-1	9.74E-1	9.97E-1	1.00E+0
140	5.31E-1	5.44E-1	5.93E-1	6.76E-1	7.54E-1	8.58E-1	9.63E-1	9.94E-1	1.00E+0
200	5.02E-1	5.19E-1	5.65E-1	6.42E-1	7.17E-1	8.23E-1	9.46E-1	9.90E-1	1.00E+0
300	4.71E-1	4.87E-1	5.27E-1	6.07E-1	6.82E-1	7.86E-1	9.25E-1	9.82E-1	1.00E+0
400	4.54E-1	4.66E-1	5.15E-1	5.86E-1	6.58E-1	7.57E-1	9.05E-1	9.73E-1	1.00E+0
500	4.39E-1	4.56E-1	4.96E-1	5.60E-1	6.36E-1	7.38E-1	8.80E-1	9.66E-1	1.00E+0
700	4.22E-1	4.35E-1	4.72E-1	5.40E-1	6.05E-1	7.05E-1	8.54E-1	9.48E-1	9.99E-1
1000	4.04E-1	4.15E-1	4.52E-1	5.16E-1	5.83E-1	6.75E-1	8.16E-1	9.23E-1	9.98E-1

Energy reflection coefficient of Ne backscattered from W  
ne=17, na=9

$E_0$ (eV)	$0^\circ$	$15^\circ$	$30^\circ$	$45^\circ$	$55^\circ$	$65^\circ$	$75^\circ$	$80^\circ$	$85^\circ$
10	4.10E-1	4.32E-1	4.80E-1	5.68E-1	6.59E-1	7.76E-1	8.97E-1	9.44E-1	9.77E-1
20	3.77E-1	3.98E-1	4.52E-1	5.48E-1	6.41E-1	7.64E-1	8.97E-1	9.49E-1	9.83E-1
30	3.48E-1	3.69E-1	4.26E-1	5.26E-1	6.23E-1	7.51E-1	8.93E-1	9.50E-1	9.85E-1
40	3.27E-1	3.47E-1	4.03E-1	5.07E-1	6.06E-1	7.37E-1	8.88E-1	9.49E-1	9.86E-1
45	3.19E-1	3.38E-1	3.94E-1	4.97E-1	5.98E-1	7.31E-1	8.86E-1	9.49E-1	9.86E-1
50	3.11E-1	3.30E-1	3.85E-1	4.89E-1	5.90E-1	7.25E-1	8.83E-1	9.48E-1	9.86E-1
60	2.98E-1	3.16E-1	3.69E-1	4.73E-1	5.77E-1	7.13E-1	8.78E-1	9.47E-1	9.87E-1
70	2.87E-1	3.04E-1	3.55E-1	4.59E-1	5.63E-1	7.02E-1	8.73E-1	9.45E-1	9.87E-1
80	2.79E-1	2.95E-1	3.43E-1	4.46E-1	5.51E-1	6.92E-1	8.67E-1	9.43E-1	9.87E-1
100	2.63E-1	2.79E-1	3.27E-1	4.26E-1	5.28E-1	6.74E-1	8.57E-1	9.40E-1	9.87E-1
140	2.45E-1	2.57E-1	3.02E-1	3.94E-1	4.93E-1	6.41E-1	8.39E-1	9.33E-1	9.86E-1
200	2.27E-1	2.39E-1	2.81E-1	3.62E-1	4.54E-1	6.02E-1	8.13E-1	9.22E-1	9.85E-1
300	2.08E-1	2.21E-1	2.56E-1	3.33E-1	4.19E-1	5.55E-1	7.80E-1	9.05E-1	9.84E-1
400	1.97E-1	2.08E-1	2.45E-1	3.12E-1	3.92E-1	5.25E-1	7.48E-1	8.87E-1	9.82E-1
500	1.89E-1	1.99E-1	2.32E-1	2.96E-1	3.75E-1	4.98E-1	7.18E-1	8.74E-1	9.80E-1
700	1.79E-1	1.88E-1	2.18E-1	2.78E-1	3.45E-1	4.65E-1	6.80E-1	8.44E-1	9.77E-1
1000	1.67E-1	1.76E-1	2.06E-1	2.63E-1	3.26E-1	4.30E-1	6.28E-1	8.05E-1	9.71E-1

Average depth (mean range) in Å of Ne implanted in W  
ne=17, na=9

$E_0$ (eV)	$0^\circ$	$15^\circ$	$30^\circ$	$45^\circ$	$55^\circ$	$65^\circ$	$75^\circ$	$80^\circ$	$85^\circ$
10	3.70E+0	3.60E+0	3.60E+0	3.60E+0	3.50E+0	3.40E+0	3.30E+0	3.20E+0	2.90E+0
20	4.70E+0	4.70E+0	4.60E+0	4.60E+0	4.50E+0	4.40E+0	4.20E+0	4.10E+0	4.00E+0
30	5.50E+0	5.40E+0	5.40E+0	5.30E+0	5.20E+0	5.10E+0	4.90E+0	4.80E+0	4.50E+0
40	6.10E+0	6.10E+0	6.10E+0	6.00E+0	5.90E+0	5.70E+0	5.50E+0	5.30E+0	5.10E+0
45	6.40E+0	6.40E+0	6.40E+0	6.30E+0	6.20E+0	6.00E+0	5.80E+0	5.40E+0	5.00E+0
50	6.70E+0	6.70E+0	6.60E+0	6.50E+0	6.40E+0	6.30E+0	6.00E+0	6.00E+0	5.70E+0
60	7.30E+0	7.20E+0	7.20E+0	7.00E+0	6.90E+0	6.80E+0	6.50E+0	6.30E+0	6.20E+0
70	7.80E+0	7.70E+0	7.60E+0	7.50E+0	7.40E+0	7.20E+0	6.90E+0	6.70E+0	5.60E+0
80	8.20E+0	8.20E+0	8.10E+0	8.00E+0	7.80E+0	7.60E+0	7.30E+0	7.10E+0	6.70E+0
100	9.10E+0	9.00E+0	8.90E+0	8.80E+0	8.60E+0	8.40E+0	8.10E+0	7.90E+0	7.70E+0
140	1.06E+1	1.05E+1	1.04E+1	1.02E+1	1.00E+1	9.80E+0	9.30E+0	9.10E+0	8.30E+0
200	1.26E+1	1.25E+1	1.23E+1	1.19E+1	1.16E+1	1.15E+1	1.12E+1	1.08E+1	1.08E+1
300	1.53E+1	1.51E+1	1.49E+1	1.44E+1	1.40E+1	1.38E+1	1.36E+1	1.34E+1	1.22E+1
400	1.76E+1	1.74E+1	1.71E+1	1.68E+1	1.62E+1	1.59E+1	1.54E+1	1.52E+1	1.44E+1
500	1.97E+1	1.96E+1	1.92E+1	1.87E+1	1.82E+1	1.77E+1	1.72E+1	1.70E+1	1.63E+1
700	2.35E+1	2.34E+1	2.30E+1	2.22E+1	2.16E+1	2.10E+1	2.07E+1	1.99E+1	1.90E+1
1000	2.85E+1	2.82E+1	2.74E+1	2.65E+1	2.58E+1	2.53E+1	2.47E+1	2.43E+1	2.30E+1

# $\text{Ar} \rightarrow \text{W}$

Sputtering yield of W by Ar  
 $z1=18$ ,  $m1=39.95$ ,  $z2=74$ ,  $m2=183.85$ ,  $sbe=8.68$  eV,  $\rho=19.29$  g/cm\*\*3  
 $ef=0.20$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: trvmc  
 $ne=18$ ,  $na=9$

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
28	9.03e-7								
29	2.97e-6								
30	1.03e-5	1.54e-5	1.89e-5	1.39e-5	6.10e-6	2.00e-6	4.80e-6		
35	1.17e-4	1.16e-4	1.13e-4	7.32e-5	3.97e-5	2.08e-5	4.80e-6		
40	4.63e-4	4.26e-4	3.63e-4	2.59e-4	1.70e-4	9.82e-5	3.55e-5	8.10e-6	
45	1.26e-3	1.21e-3	1.01e-3	7.35e-4	5.69e-4	3.79e-4	1.47e-4	3.07e-5	
50	2.85e-3	2.74e-3	2.41e-3	1.83e-3	1.48e-3	1.04e-3	4.24e-4	8.66e-5	1.20e-6
55	5.23e-3	5.12e-3	4.44e-3	3.73e-3	3.16e-3	2.39e-3	9.13e-4	1.85e-4	
60	8.40e-3	8.23e-3	7.65e-3	6.36e-3	5.86e-3	4.35e-3	1.72e-3	3.40e-4	2.40e-6
70	1.75e-2	1.75e-2	1.63e-2	1.51e-2	1.41e-2	1.12e-2	4.05e-3	7.82e-4	9.60e-6
80	2.86e-2	2.90e-2	2.93e-2	2.82e-2	2.57e-2	2.10e-2	7.61e-3	1.51e-3	1.39e-5
100	5.60e-2	5.54e-2	5.93e-2	6.20e-2	5.85e-2	4.78e-2	1.82e-2	4.00e-3	4.54e-5
140	1.16e-1	1.19e-1	1.33e-1	1.50e-1	1.49e-1	1.22e-1	5.03e-2	1.22e-2	1.68e-4
200	2.01e-1	2.13e-1	2.50e-1	2.91e-1	2.98e-1	2.50e-1	1.11e-1	3.11e-2	5.67e-4
300	3.36e-1	3.59e-1	4.23e-1	5.08e-1	5.23e-1	4.56e-1	2.27e-1	7.70e-2	2.00e-3
500	5.62e-1	5.91e-1	7.03e-1	8.40e-1	8.99e-1	8.17e-1	4.63e-1	1.82e-1	8.08e-3
700	7.25e-1	7.78e-1	9.26e-1	1.11e-0	1.19e-0	1.13e-0	6.81e-1	3.04e-1	1.84e-2
1000	9.26e-1	9.93e-1	1.19e-0	1.42e-0	1.54e-0	1.52e-0	1.02e-0	4.98e-1	3.94e-2

Sputtered energy of W by Ar  
 $ne=18$ ,  $na=9$

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
28	3.16e-8								
29	1.11e-7								
30	4.34e-7	7.73e-7	1.19e-6	9.26e-7	4.44e-7	1.57e-7			
35	5.98E-6	6.60E-6	7.76E-6	5.60E-6	3.37E-6	2.05E-6	6.27E-7		
40	2.65E-5	2.68E-5	2.58E-5	2.16E-5	1.54E-5	1.01E-5	4.13E-6	9.58E-7	
45	7.98E-5	8.21E-5	7.56E-5	6.21E-5	5.39E-5	3.91E-5	1.65E-5	3.66E-6	
50	1.94E-4	1.97E-4	1.85E-4	1.59E-4	1.46E-4	1.08E-4	4.92E-5	1.06E-5	9.36E-8
55	3.72E-4	3.80E-4	3.63E-4	3.51E-4	3.24E-4	2.64E-4	1.13E-4	2.33E-5	
60	6.12E-4	6.36E-4	6.49E-4	6.19E-4	6.17E-4	4.90E-4	2.24E-4	4.52E-5	2.79E-7
70	1.33E-3	1.40E-3	1.46E-3	1.51E-3	1.50E-3	1.34E-3	5.60E-4	1.11E-4	1.18E-6
80	2.27E-3	2.39E-3	2.64E-3	2.86E-3	2.84E-3	2.64E-3	1.10E-3	2.21E-4	1.56E-6
100	4.45E-3	4.54E-3	5.29E-3	6.30E-3	6.56E-3	6.12E-3	2.75E-3	6.06E-4	5.49E-6
140	8.70E-3	9.24E-3	1.11E-2	1.43E-2	1.61E-2	1.53E-2	7.50E-3	1.88E-3	1.98E-5
200	1.35E-2	1.47E-2	1.83E-2	2.47E-2	2.91E-2	2.91E-2	1.57E-2	4.53E-3	5.90E-5
300	1.88E-2	2.07E-2	2.59E-2	3.65E-2	4.37E-2	4.60E-2	2.79E-2	9.91E-3	1.75E-4
500	2.40E-2	2.59E-2	3.28E-2	4.68E-2	5.82E-2	6.30E-2	4.44E-2	1.92E-2	6.11E-4
700	2.55E-2	2.83E-2	3.66E-2	5.18E-2	6.44E-2	7.35E-2	5.52E-2	2.73E-2	1.21E-3
1000	2.64E-2	2.96E-2	3.80E-2	5.50E-2	6.84E-2	7.99E-2	6.70E-2	3.74E-2	2.32E-3

# Ar → W

Particle reflection coefficient of Ar backscattered from W  
 $z1=18$ ,  $m1=39.95$ ,  $z2=74$ ,  $m2=183.85$ ,  $sbe=8.68$  eV,  $\rho=19.29$  g/cm\*\*3  
 $ef=0.20$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: trvnc  
ne=18, na=9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	7.40E-1	7.60E-1	7.96E-1	8.56E-1	9.09E-1	9.62E-1	9.94E-1	9.99E-1	1.00E+0
20	6.86E-1	7.07E-1	7.54E-1	8.27E-1	8.89E-1	9.53E-1	9.93E-1	9.99E-1	1.00E+0
30	6.41E-1	6.63E-1	7.15E-1	7.99E-1	8.68E-1	9.42E-1	9.92E-1	9.99E-1	1.00E+0
35	6.22E-1	6.44E-1	6.99E-1	7.86E-1	8.59E-1	9.37E-1	9.91E-1	9.99E-1	1.00E+0
40	6.05E-1	6.27E-1	6.83E-1	7.74E-1	8.50E-1	9.31E-1	9.90E-1	9.99E-1	1.00E+0
45	5.90E-1	6.12E-1	6.70E-1	7.64E-1	8.41E-1	9.26E-1	9.89E-1	9.99E-1	1.00E+0
50	5.77E-1	5.99E-1	6.58E-1	7.53E-1	8.33E-1	9.21E-1	9.87E-1	9.99E-1	1.00E+0
55	5.65E-1	5.87E-1	6.45E-1	7.44E-1	8.26E-1	9.16E-1	9.86E-1	9.99E-1	1.00E+0
60	5.56E-1	5.78E-1	6.35E-1	7.34E-1	8.18E-1	9.12E-1	9.85E-1	9.98E-1	1.00E+0
70	5.35E-1	5.56E-1	6.17E-1	7.19E-1	8.05E-1	9.03E-1	9.82E-1	9.98E-1	1.00E+0
80	5.21E-1	5.42E-1	6.02E-1	7.04E-1	7.92E-1	8.94E-1	9.80E-1	9.98E-1	1.00E+0
100	4.97E-1	5.16E-1	5.73E-1	6.76E-1	7.70E-1	8.78E-1	9.74E-1	9.97E-1	1.00E+0
140	4.60E-1	4.80E-1	5.35E-1	6.40E-1	7.35E-1	8.52E-1	9.65E-1	9.95E-1	1.00E+0
200	4.31E-1	4.44E-1	4.97E-1	5.99E-1	6.95E-1	8.19E-1	9.51E-1	9.92E-1	1.00E+0
300	3.93E-1	4.13E-1	4.63E-1	5.57E-1	6.49E-1	7.76E-1	9.27E-1	9.85E-1	1.00E+0
500	3.60E-1	3.71E-1	4.17E-1	5.08E-1	5.97E-1	7.24E-1	8.90E-1	9.71E-1	1.00E+0
700	3.38E-1	3.52E-1	3.98E-1	4.77E-1	5.63E-1	6.79E-1	8.63E-1	9.56E-1	9.99E-1
1000	3.17E-1	3.29E-1	3.81E-1	4.58E-1	5.36E-1	6.45E-1	8.23E-1	9.36E-1	9.99E-1

Energy reflection coefficient of Ar backscattered from W  
ne=18, na=9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	2.34E-1	2.57E-1	3.08E-1	4.07E-1	5.15E-1	6.62E-1	8.27E-1	9.00E-1	9.56E-1
20	2.27E-1	2.50E-1	3.05E-1	4.06E-1	5.11E-1	6.59E-1	8.34E-1	9.11E-1	9.68E-1
30	2.15E-1	2.36E-1	2.92E-1	3.97E-1	5.02E-1	6.50E-1	8.32E-1	9.14E-1	9.72E-1
35	2.09E-1	2.30E-1	2.86E-1	3.92E-1	4.97E-1	6.46E-1	8.30E-1	9.14E-1	9.74E-1
40	2.04E-1	2.24E-1	2.80E-1	3.86E-1	4.93E-1	6.41E-1	8.29E-1	9.15E-1	9.75E-1
45	1.99E-1	2.18E-1	2.74E-1	3.80E-1	4.88E-1	6.37E-1	8.27E-1	9.15E-1	9.75E-1
50	1.94E-1	2.13E-1	2.68E-1	3.75E-1	4.83E-1	6.32E-1	8.25E-1	9.14E-1	9.76E-1
55	1.90E-1	2.08E-1	2.62E-1	3.70E-1	4.78E-1	6.28E-1	8.23E-1	9.14E-1	9.76E-1
60	1.86E-1	2.05E-1	2.58E-1	3.64E-1	4.74E-1	6.25E-1	8.21E-1	9.13E-1	9.77E-1
70	1.79E-1	1.96E-1	2.49E-1	3.54E-1	4.63E-1	6.17E-1	8.16E-1	9.12E-1	9.77E-1
80	1.74E-1	1.90E-1	2.41E-1	3.45E-1	4.54E-1	6.07E-1	8.12E-1	9.11E-1	9.78E-1
100	1.64E-1	1.79E-1	2.28E-1	3.27E-1	4.39E-1	5.94E-1	8.03E-1	9.08E-1	9.78E-1
140	1.49E-1	1.64E-1	2.07E-1	3.03E-1	4.11E-1	5.68E-1	7.87E-1	9.02E-1	9.78E-1
200	1.38E-1	1.48E-1	1.88E-1	2.76E-1	3.76E-1	5.35E-1	7.67E-1	8.92E-1	9.78E-1
300	1.23E-1	1.35E-1	1.70E-1	2.46E-1	3.39E-1	4.93E-1	7.35E-1	8.76E-1	9.76E-1
500	1.09E-1	1.18E-1	1.47E-1	2.15E-1	2.98E-1	4.41E-1	6.85E-1	8.50E-1	9.73E-1
700	1.01E-1	1.10E-1	1.38E-1	1.97E-1	2.73E-1	4.00E-1	6.50E-1	8.25E-1	9.70E-1
1000	9.39E-2	1.00E-1	1.29E-1	1.82E-1	2.52E-1	3.67E-1	6.01E-1	7.92E-1	9.64E-1

Average depth (mean range) in Å of Ar implanted in W  
ne=18, na=9

$E_0$ (eV)	0°	15°	30°	45°	55°	65°	75°	80°	85°
10	2.40E+0	2.40E+0	2.30E+0	2.30E+0	2.20E+0	2.10E+0	1.90E+0	1.70E+0	1.40E+0
20	3.30E+0	3.20E+0	3.10E+0	3.00E+0	2.90E+0	2.60E+0	2.50E+0	2.10E+0	2.70E+0
30	3.90E+0	3.80E+0	3.80E+0	3.70E+0	3.60E+0	3.40E+0	3.20E+0	3.10E+0	3.20E+0
35	4.10E+0	4.10E+0	4.00E+0	3.90E+0	3.80E+0	3.70E+0	3.40E+0	3.20E+0	2.90E+0
40	4.30E+0	4.30E+0	4.30E+0	4.20E+0	4.00E+0	3.90E+0	3.60E+0	3.40E+0	3.10E+0
45	4.60E+0	4.50E+0	4.50E+0	4.40E+0	4.20E+0	4.10E+0	3.80E+0	3.60E+0	3.20E+0
50	4.80E+0	4.70E+0	4.70E+0	4.50E+0	4.40E+0	4.20E+0	4.00E+0	3.70E+0	3.10E+0
55	4.90E+0	4.90E+0	4.80E+0	4.70E+0	4.60E+0	4.40E+0	4.10E+0	3.90E+0	3.60E+0
60	5.10E+0	5.10E+0	5.00E+0	4.90E+0	4.80E+0	4.60E+0	4.20E+0	4.00E+0	3.20E+0
70	5.50E+0	5.40E+0	5.40E+0	5.20E+0	5.10E+0	4.90E+0	4.60E+0	4.30E+0	3.40E+0
80	5.80E+0	5.80E+0	5.70E+0	5.50E+0	5.40E+0	5.20E+0	4.80E+0	4.50E+0	4.10E+0
100	6.40E+0	6.30E+0	6.30E+0	6.10E+0	5.90E+0	5.70E+0	5.30E+0	4.90E+0	4.40E+0
140	7.40E+0	7.40E+0	7.20E+0	7.00E+0	6.80E+0	6.50E+0	6.20E+0	5.80E+0	6.10E+0
200	8.70E+0	8.60E+0	8.40E+0	8.20E+0	7.90E+0	7.60E+0	7.20E+0	6.80E+0	6.00E+0
300	1.05E+1	1.05E+1	1.02E+1	9.80E+0	9.50E+0	9.10E+0	8.60E+0	8.20E+0	9.20E+0
500	1.34E+1	1.33E+1	1.29E+1	1.24E+1	1.19E+1	1.15E+1	1.09E+1	1.06E+1	9.70E+0
700	1.59E+1	1.57E+1	1.52E+1	1.46E+1	1.42E+1	1.35E+1	1.29E+1	1.24E+1	1.14E+1
1000	1.89E+1	1.88E+1	1.81E+1	1.74E+1	1.66E+1	1.59E+1	1.53E+1	1.48E+1	1.38E+1

## Ar → W

Sputtering yield of W by Ar

$z1=18$ ,  $m1=39.95$ ,  $z2=74$ ,  $m2=183.85$ ,  $sbe$  (eV),  $\rho=19.29$  g/cm $^{**3}$   
 $ef=0.20$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: trvmc01  
 $nem=2$ ,  $na=1$ ,  $n(sbe)=5$

$E_0$ (eV)	25	30
$sbe$ (eV)		
4.34	1.01e-3	4.21e-3
5.00	2.91e-4	1.82e-3
6.00	4.24e-5	4.37e-4
7.00	3.56e-6	9.12e-5
8.00		1.36e-5

Sputtered energy of W by Ar  
 $nem=2$ ,  $na=1$ ,  $n(sbe)=5$

$E_0$ (eV)	25	30
$sbe$ (eV)		
4.34	6.81e-5	3.19e-4
5.00	1.76e-5	1.28e-4
6.00	2.13e-6	2.62e-5
7.00	1.51e-7	4.76e-6
8.00		6.21e-7

Particle reflection coefficient of Ar backscattered from W

$z1=18$ ,  $m1=39.95$ ,  $z2=74$ ,  $m2=183.85$ ,  $sbe$  (eV),  $\rho=19.29$  g/cm $^{**3}$   
 $ef=0.20$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: trvmc01  
 $nem=2$ ,  $na=1$ ,  $n(sbe)=5$

$E_0$ (eV)	25	30
$sbe$ (eV)		
4.34	6.55e-1	6.32e-1
5.00	6.55e-1	6.33e-1
6.00	6.55e-1	6.34e-1
7.00	6.55e-1	6.34e-1
8.00		6.33e-1

Energy reflection coefficient of Ar backscattered from W  
 $nem=2$ ,  $na=1$ ,  $n(sbe)=5$

$E_0$ (eV)	25	30
$sbe$ (eV)		
4.34	2.18e-1	2.12e-1
5.00	2.18e-1	2.12e-1
6.00	2.18e-1	2.12e-1
7.00	2.18e-1	2.12e-1
8.00		2.12e-1

Average depth (mean range) in Å of Ar implanted in W  
 $nem=2$ ,  $na=1$ ,  $n(sbe)=5$

$E_0$ (eV)	25	30
$sbe$ (eV)		
4.34	3.50e+0	3.78e+0
5.00	3.50e+0	3.78e+0
6.00	3.50e+0	3.78e+0
7.00	3.50e+0	3.78e+0
8.00		3.78e+0

Sputtering yield of W by Ar

$z1=18$ ,  $m1=39.95$ ,  $z2=74$ ,  $m2=183.85$ ,  $sbe=8.68$  eV,  $\rho=19.29$  g/cm $^{**3}$   
 $ef=0.20$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
 $e0=25$  eV,  $\alpha=0$  deg., Maxwellian target temperature  $tt$  (K) program: trvmc01  
 $nem=1$ ,  $na=1$ ,  $n(tt)=4$

$E_0$ (eV)	25
$tt$ (K)	
9000	1.50e-5
15000	1.00e-4
25000	3.80e-4
50000	1.09e-3

# W → W

Sputtering yield of W by W  
 z1=74, m1=183.85, z2=74, m2=183.85, sbe=8.68 eV, rho=19.30 g/cm\*\*3  
 ef=8.60 eV, esb=8.68 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trvmc, trspvmcx, testvmcx  
 ne=58, na=16

E <sub>0</sub> (eV)	0°	10°	15°	20°	30°	40°	45°	50°	55°	60°	65°	70°
9									4.60e-7		1.25e-6	
10									3.11E-6		6.44E-6	
12					2.98E-6				1.73E-5		2.99E-5	
15							3.44E-5		7.10E-5		1.04E-4	
17				2.50E-6		3.29E-5		1.69E-4		2.61E-4		1.49e-4
20						1.36E-4		4.18E-4		6.28E-4		3.22E-4
20												2.80e-4
25	6.28E-7		1.46E-5								8.73E-4	
23											5.41e-4	
25											8.70e-4	
27	1.40e-6		1.38e-5		9.02e-5		2.96e-4		5.53e-4		1.14e-3	
28											1.79e-3	
30	5.80E-6		4.91E-5		3.11E-4		8.89E-4		1.55E-3		2.63E-3	
30	5.50e-6	1.82e-5		8.59e-5	2.69e-4	5.87e-4		1.10e-3		2.09e-3	2.79e-3	3.43e-3
35	2.13E-5		1.14E-4		6.18E-4		1.93E-3		3.71E-3			
35	2.30e-6											7.93e-3
36	1.10e-5											
37	2.83e-5											
38	5.81e-5											
40	5.60E-5		2.39E-4		1.15E-3		4.02E-3		7.70E-3		1.25E-2	
40	1.43e-4										1.29e-2	
42	2.89e-4											
45	5.69e-4											
50	1.92E-4		7.04E-4		3.64E-3		1.23E-2		2.16E-2		3.08E-2	
50	1.77e-4	3.60e-4		1.20e-3	3.51e-3	8.85e-3		1.78e-2		2.79e-2	3.22e-2	3.54e-2
55	3.13e-4											
60	5.89E-4		1.85E-3		8.48E-3		2.64E-2		4.29E-2		5.59E-2	
60	5.42e-4										5.91e-2	
65	9.32e-4											
70	1.51E-3		4.16E-3		1.70E-2		4.71E-2		7.08E-2		8.55E-2	
70	1.41e-3										8.60e-2	
80	3.15E-3		7.97E-3		2.83E-2		7.25E-2		1.02E-1		1.18E-1	
80	2.99e-3										1.22e-1	
100	9.54E-3		2.04E-2		6.03E-2		1.31E-1		1.71E-1		1.86E-1	
100	9.26e-3	1.42e-2		3.01e-2	5.99e-2	1.06e-1		1.60e-1		1.88e-1	1.90e-1	1.80e-1
120	2.04E-2		3.92E-2		1.00E-1		1.96E-1		2.45E-1		2.54E-1	
140	3.58E-2		6.20E-2		1.43E-1		2.64E-1		3.20E-1		3.27E-1	
140	3.55e-2										3.19e-1	
150	4.26E-2											
200	9.68E-2		1.44E-1		2.80E-1		4.56E-1		5.29E-1		5.20E-1	
200	9.16e-2										5.28e-1	
250	1.53e-1											
300	2.28E-1		2.99E-1		5.01E-1		7.38E-1		8.42E-1		7.94E-1	
300	2.17e-1								8.59e-1			
350	2.92e-1	3.26e-1		4.34e-1	5.98e-1	7.93e-1		9.52e-1	9.84e-1	9.79e-1	9.23e-1	8.15e-1
400	3.59e-1			5.22e-1		8.98e-1		1.07e-0	1.12e-0	1.12e-0	1.06e-0	9.19e-1
450									1.27e-0			
500	4.97E-1		6.04E-1		8.85E-1		1.22E+0		1.36E+0		1.28E+0	
500	4.79e-1								1.37e-0		1.29e-0	
800	8.47e-1	8.97e-1		1.06e-0	1.35e-0	1.66e-0		1.90e-0	1.97e-0	1.97e-0	1.95e-0	1.72e-0
1000	1.07E-0		1.21E+0		1.62E+0		2.14E+0		2.38E+0		2.29E+0	
1000	1.04e-0	1.11e-0		1.31e-0	1.60e-0	1.96e-0		2.29e-0		2.35e-0	2.30e-0	2.02e-0
2000	1.81e-0				2.59e-0					3.89e-0	3.87e-0	
2500	2.10e-0	2.20e-0		2.50e-0	2.98e-0	3.56e-0		4.16e-0	4.41e-0	4.50e-0	4.49e-0	4.09e-0
5000	3.14e-0										6.91e-0	
10000	4.36e-0										1.01e+1	
20000	5.66e-0										1.45e+1	
45000	6.92e-0										2.12e+1	
50000	7.16e-0										2.53e+1	
100000	7.87e-0											

$E_0$ (eV)	75°	80°	85°	87°
9	1.88e-6	2.15e-6	2.31e-6	
10	1.03E-5	1.12E-5	1.14E-5	
12	3.71E-5	4.22E-5	3.98E-5	
15	1.13E-4	1.12e-4	1.11E-4	
20	3.47E-4	3.59E-4	3.52E-4	
25	1.19E-3	1.31E-3	1.39E-3	
27	1.81e-3	2.08e-3	2.27e-3	
30	3.78E-3	4.06E-3	4.21E-3	
30	3.94e-3	4.42e-3	4.39e-3	
35	8.31E-3	9.01E-3	9.26E-3	
40	1.54E-2	1.54E-2	1.65E-2	
50	3.40E-2	3.34E-2	3.23E-2	
50	3.68e-2	3.69e-2	3.32e-2	3.35e-2
60	5.46E-2	5.36E-2	5.04E-2	
70	8.16E-2	7.49E-2	6.95E-2	
80	1.09E-1	9.68E-2	8.85E-2	
100	1.61E-1	1.38E-1	1.19E-1	
100		1.42e-1	1.23e-1	
120	2.09E-1	1.74E-1	1.45E-1	
140	2.53E-1	2.02E-1	1.64E-1	
200	3.73E-1	2.77E-1	2.00E-1	
300	5.52E-1	3.85E-1	2.39E-1	
350		4.44e-1	2.62e-1	
400		4.97e-1		
500	8.81E-1	5.72E-1	2.99E-1	
800	1.35e-0	8.47e-1	3.89e-1	
1000	1.62E+0	1.03E+0	4.30E-1	
1000		1.04e-0	4.41e-1	
2000	2.94e-0			
2500	3.48e-0	2.36e-0	7.89e-1	

# W → W

Sputtered energy of W by W  
 z1=74, m1=183.85, z2=74, m2=183.85, sbe=8.68 eV, rho=19.30 g/cm\*\*3  
 ef=8.60 eV, esb=8.68 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trvmc, trspvmcx, testvmcx  
 ne=58, na=16

E <sub>0</sub> (eV)	0°	10°	15°	20°	30°	40°	45°	50°	55°	60°	65°	70°
9									4.52e-8		1.45e-7	
10									3.08e-7		7.89e-7	
12					2.31E-7				2.06E-6		4.07E-6	
15							5.68e-7		9.18E-6		1.58E-5	
17							3.73E-6				2.28e-5	
20				1.51E-7		2.76E-6		2.03E-5		3.78E-5		5.42E-5
20											4.70e-5	
23											9.94e-5	
25	5.03E-8			1.04E-6		1.23E-5		5.22E-5		9.56E-5		1.56E-4
25											1.59e-4	
27	6.37e-8			9.24e-7		8.40e-6		3.70e-5		8.66e-5		2.13e-4
28											3.33e-4	
30	2.91E-7			3.44E-6		2.91E-5		1.17E-4		2.47E-4		4.96E-4
30	1.29e-6	6.64e-6			6.73e-6	2.55e-5	6.90e-5		1.59e-4		3.66e-4	5.35e-4
35	1.06E-6			7.74E-6		5.97E-5		2.65E-4		6.17E-4		1.25E-3
35	2.30e-6											1.59e-3
36	1.10e-5											
37	2.83e-5											
38	5.81e-5											
40	2.79E-6			1.65E-5		1.16E-4		5.73E-4		1.33E-3		2.57E-3
40	1.43e-4											2.66e-3
42	2.89e-4											
45	5.69e-4											
50	9.96E-6			5.05E-5		3.84E-4		1.83E-3		3.91E-3		6.58E-3
50	9.66e-6	2.36e-5			1.18e-4	3.72e-4	1.17e-3		2.95e-3		5.45e-3	6.89e-3
55	1.93e-5											8.06e-3
60	3.15E-5			1.36E-4		9.31E-4		3.97E-3		7.83E-3		1.22E-2
60	2.90e-5											1.27e-2
65	5.52e-5											
70	8.20E-5			3.08E-4		1.85E-3		7.18E-3		1.31E-2		1.85E-2
70	7.83e-5											1.87e-2
80	1.70E-4			5.84E-4		3.01E-3		1.09E-2		1.85E-2		2.55E-2
80	1.64e-4											2.61e-2
100	5.02E-4			1.42E-3		6.15E-3		1.90E-2		3.02E-2		3.94E-2
100	4.78e-4	8.61e-4			2.40e-3	6.03e-3	1.36E-2		2.56e-2		3.62e-2	3.93e-2
120	1.00E-3			2.58E-3		9.69E-3		2.72E-2		4.18E-2		5.20E-2
140	1.67E-3			3.82E-3		1.32E-2		3.52E-2		5.24E-2		6.39E-2
140	1.65e-3											6.21e-2
150	1.91e-3											
200	4.03E-3			7.73E-3		2.25E-2		5.31E-2		7.62E-2		9.05E-2
200	3.73e-3											8.98e-2
250	6.12e-3											
300	8.09E-3			1.34E-2		3.33E-2		7.16E-2		1.02E-1		1.18E-1
300	7.39e-3									1.03e-1		
350	9.48e-3	1.18e-2			2.00e-2	3.58e-2	6.08e-2		9.28e-2	1.09e-1	1.21e-1	1.22e-1
400	1.10e-2				2.27e-2		6.60e-2		9.83e-2	1.14e-1	1.28e-1	1.35e-1
450										1.22e-1		
500	1.41E-2			2.10E-2		4.47E-2		8.99E-2		1.25E-1		1.46E-1
500	1.32e-2									1.23e-1		1.45e-1
800	1.88e-2	2.17e-2		3.16e-2		5.05e-2	8.02e-2		1.16e-1	1.40e-1	1.55e-1	1.65e-1
1000	2.15E-2			2.92E-2		5.46E-2		1.04E-1		1.44E-1		1.77E-1
1000	2.04e-2	2.39e-2			3.42e-2	5.26e-2	8.29e-2			1.21e-1		1.60e-1
2000	2.47e-2										1.68e-1	1.87e-1
2500	2.52e-2	2.83e-2			3.82e-2	5.64e-2	8.44e-2		1.23e-1	1.46e-1	1.70e-1	1.91e-1
5000	2.56e-2										1.88e-1	
10000	2.41e-2										1.73e-1	
20000	2.05e-2										1.47e-1	
45000	1.68e-2										1.27e-1	
50000	1.66e-2											
100000	1.25e-2											

$E_0$ (eV)	$75^\circ$	$80^\circ$	$85^\circ$	$87^\circ$
9	2.46e-7	2.83e-7	3.09e-7	
10	1.39e-6	1.56e-6	1.62e-6	
12	5.72E-6	6.87E-6	6.58E-6	
15	1.93E-5	1.97E-5	2.01E-5	
20	6.49E-5	7.05E-5	7.25E-5	
25	2.36E-4	2.68E-4	2.90E-4	
27	3.75e-4	4.49e-4	4.96e-4	
30	7.96E-4	8.86E-4	9.38E-4	
30	8.27e-4	9.94e-4	1.00e-3	
35	1.87E-3	2.06E-3	2.16E-3	
40	3.55E-3	3.71E-3	4.05E-3	
50	8.21E-3	8.37E-3	8.26E-3	
50	8.76e-3	9.30e-3	8.65e-3	8.61e-3
60	1.39E-2	1.37E-2	1.30E-2	
70	2.00E-2	1.90E-2	1.80E-2	
80	2.66E-2	2.44E-2	2.27E-2	
100	3.86E-2	3.41E-2	2.98E-2	
100		3.43e-2	3.05e-2	
120	4.81E-2	4.15E-2	3.49E-2	
140	5.61E-2	4.69E-2	3.78E-2	
200	7.48E-2	5.73E-2	4.06E-2	
300	9.48E-2	6.75E-2	3.98E-2	
350		7.21e-2	3.97e-2	
400		7.67e-2		
500	1.19E-1	7.94E-2	3.76E-2	
800	1.35e-1	9.02e-2	3.40e-2	
1000	1.53E-1	1.00E-1	3.40E-2	
1000		9.81e-2	3.49e-2	
2000	1.81e-1			
2500	1.90e-1	1.39e-1	4.19e-2	

# W → W

Particle reflection coefficient of W backscattered from W  
 z1=74, m1=183.85, z2=74, m2=183.85, sbe=8.68 eV, rho=19.30 g/cm\*\*3  
 ef=8.60 eV, esb=8.68 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trvmc, trspvmcx, testvmcx  
 ne=51, na=16

$E_0$ (eV)	0°	10°	15°	20°	30°	40°	45°	50°	55°	60°	65°	70°
15											1.00E-7	
17											2.63e-6	
20											4.73E-5	
23											4.87e-5	
25											3.48e-4	
25											9.39E-4	
27											8.85e-4	
28											2.17e-3	
30											2.95e-3	
30	1.40e-7	2.00e-7									5.14E-3	
35			3.00e-9								5.28e-3	8.45e-3
36											1.47E-2	
40				3.80E-6							1.80e-2	
40											3.03E-2	
50	2.10E-6		5.70E-5								3.06e-2	
50	3.43e-6	1.60e-5		1.68e-4							7.30B-2	
55	1.93e-5										1.23E-1	
60	2.12B-5		2.54E-4								1.24e-1	
60	2.00e-5										4.25E-1	
65	5.10e-5										4.24e-1	
70	8.15B-5		6.55E-4								1.76E-1	
70	7.10e-5										1.72e-1	
80	1.90E-4		1.26E-3								2.27E-1	
80	2.27e-4										2.26e-1	
100	6.89E-4		2.90E-3								3.11E-1	
100	6.51e-4	1.54e-3		5.52e-3							3.17e-1	4.01e-1
120	1.39B-3		4.88E-3								3.78E-1	
140	2.25E-3		7.20E-3								4.25E-1	
140	2.22e-3										4.24e-1	
150	2.75e-3											
200	5.40E-3		1.32E-2								4.95E-1	
200	5.50e-3										4.95e-1	
250	7.88e-3											
300	1.09E-2		2.12E-2								5.17E-1	
300	8.20e-3											
350	1.29E-2	1.74e-2			3.45e-2						5.27e-1	6.42e-1
400	1.44e-2				3.84e-2						5.18e-1	6.35e-1
450												
500	1.76E-2										5.05e-1	
500	1.76E-2		2.97E-2								5.07B-1	
800	2.30E-2	2.83e-2		4.48e-2							4.72e-1	6.10e-1
1000	2.46E-2		3.71E-2								4.58E-1	
1000	2.35E-2	2.97e-2		4.41e-2							3.70e-1	5.87e-1
2000	2.79E-2										3.23e-1	4.18e-1
2500	2.74E-2	3.16e-2			4.46e-2						3.93e-1	5.07e-1
5000	2.61E-2										3.65e-1	
10000	2.10E-2										2.89e-1	
20000	2.14e-2										2.50e-1	
45000	1.94E-2											
50000	1.67E-2										2.54e-1	
100000	1.40E-2										2.37e-1	

$E_0$ (eV)	75°	80°	85°	87°
15	1.48E-6	2.83E-6	4.08E-6	
20	2.18E-4	3.54E-4	4.61E-4	
25	2.83E-3	4.00E-3	4.90E-3	
27	5.86e-3	7.94e-3	9.56e-3	
30	1.23E-2	1.61E-2	1.90E-2	
30	1.23E-2	1.64E-2	1.91e-2	
35	3.07E-2	3.82E-2	4.48E-2	
40	5.67E-2	6.90E-2	8.06E-2	
50	1.25E-1	1.51E-1	1.69E-1	
50	1.25E-1	1.50E-1	1.69e-1	1.76e-1
60	2.05E-1	2.45E-1	2.75E-1	
70	2.86E-1	3.40E-1	3.81E-1	
80	3.62E-1	4.30E-1	4.79E-1	
100	4.91E-1	5.76E-1	6.33E-1	
100		5.79E-1	6.32e-1	
120	5.83E-1	6.71E-1	7.34E-1	
140	6.43E-1	7.36E-1	7.99E-1	
200	7.25E-1	8.26E-1	8.94E-1	
300	7.60E-1	8.68E-1	9.39E-1	
350		8.72E-1	9.49e-1	
400		8.78E-1		
500	7.63E-1	8.85E-1	9.64E-1	
800	7.57E-1	8.83E-1	9.74e-1	
1000	7.27E-1	8.74E-1	9.76E-1	
1000		8.76E-1	9.76e-1	
2000	6.67E-1			
2500	6.34E-1	8.20E-1	9.69E-1	

# W → W

Energy reflection coefficient of W backscattered from W  
 z1=74, m1=183.85, z2=74, m2=183.85, sbe=8.68 eV, rho=19.30 g/cm\*\*3  
 ef=8.60 eV, esb=8.68 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trvmc, trspvmcx, testvmcx  
 ne=51, na=16

$E_0$ (eV)	0°	10°	15°	20°	30°	40°	45°	50°	55°	60°	65°	70°
15							6.18E-8				3.19E-8	
17									7.52E-7		6.80e-7	
20											9.56E-6	
23											9.79e-6	
25											7.13e-5	
25												1.95E-4
27											1.81e-4	
28											4.70e-4	
30											6.47e-4	
30	3.86e-7	3.18e-7									1.17E-3	
35				2.52E-8							1.20e-3	
36											3.62E-3	
40	1.00e-9			3.36E-7							4.48e-3	
40											7.93E-3	
50	1.20E-7			5.19E-6							8.07e-3	
50	1.28e-6	1.90e-6			1.81e-5						2.10E-2	
55	1.93e-5										2.10e-2	
60	1.29E-6			2.33E-5							3.78E-2	
60	1.69e-6										3.81e-2	
65	3.43e-6											
70	5.25E-6			6.30E-5								5.65E-2
70	4.26E-6										5.46E-2	
80	1.18E-5			1.21E-4							7.55E-2	
80	1.41e-5										7.50e-2	
100	4.36E-5			2.64E-4							1.08E-1	
100	4.09e-5	1.22E-4			5.95e-4						1.10e-1	
120	8.31E-5			4.37E-4							1.35E-1	
140	1.31E-4			6.23E-4							1.56E-1	
140	1.29e-4										1.56e-1	
150	1.54e-4											
200	2.85E-4			1.07E-3							1.91E-1	
200	2.93e-4										1.90e-1	
250	3.62E-4											
300	5.36E-4			1.54E-3							2.07E-1	
300	4.26E-4											
350	6.04E-4	1.06e-3			3.02e-3						1.40e-1	
400	6.91e-4				3.16e-3						2.11e-1	
450											2.06e-1	
500	8.09E-4			1.94E-3							3.00e-1	
500	7.90E-4										3.02e-1	
800	9.68E-4	1.48e-3			3.27E-3							
1000	1.03E-3			2.17E-3								
1000	9.97E-4	1.45e-3										
2000	1.06E-3											
2500	1.04E-3	1.37e-3										
5000	1.09E-3											
10000	5.90E-4											
20000	7.20E-4											
45000	6.69E-4											
50000	6.20E-4											
100000	4.91e-4										6.66e-2	
											6.58e-2	

$E_0$ (eV)	75°	80°	85°	87°
15	3.44E-7	6.26E-7	9.31E-7	
20	4.85E-5	8.22E-5	1.09E-4	
25	6.85E-4	1.01E-3	1.28E-3	
27	1.48E-3	2.11E-3	2.63e-3	
30	3.25E-3	4.51E-3	5.50E-3	
30	3.26E-3	4.60E-3	5.56e-3	
35	8.85E-3	1.16E-2	1.42E-2	
40	1.75E-2	2.24E-2	2.74E-2	
50	4.24E-2	5.45E-2	6.36E-2	
50	4.25E-2	5.38E-2	6.32e-2	6.64E-2
60	7.40E-2	9.45E-2	1.10E-1	
70	1.09E-1	1.37E-1	1.61E-1	
80	1.43E-1	1.82E-1	2.11E-1	
100	2.05E-1	2.60E-1	3.02E-1	
100		2.62e-1	3.01e-1	
120	2.56E-1	3.21E-1	3.75E-1	
140	2.96E-1	3.71E-1	4.32E-1	
200	3.63E-1	4.64E-1	5.46E-1	
300	4.07E-1	5.32E-1	6.41E-1	
350		5.49E-1	6.69E-1	
400		5.58E-1		
500	4.26E-1	5.80E-1	7.23E-1	
800	4.23E-1	5.95E-1	7.75E-1	
1000	4.04E-1	5.91E-1	7.90E-1	
1000		5.92E-1	7.91E-1	
2000	3.56E-1			
2500	3.39E-1	5.39E-1	8.19E-1	

# W → W

Average depth (mean range) in Å of W implanted in W  
 z1=74, m1=183.85, z2=74, m2=183.85, sbe=8.68 eV, rho=19.30 g/cm\*\*3  
 ef=8.60 eV, esb=8.68 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trvmc, trspvmcx, testvmcx  
 ne=52, na=16

E <sub>0</sub> (eV)	0°	10°	15°	20°	30°	40°	45°	50°	55°	60°	65°	70°
9												
10	7.00E-1		7.00E-1		6.00E-1		5.00E-1		4.00E-1		4.00E-1	
12	9.00E-1		8.00E-1		7.00E-1		6.00E-1		5.00E-1		5.00E-1	
15	1.10E+0		1.00E+0		9.00E-1		8.00E-1		7.00E-1		6.00E-1	
17											4.08e-1	
20	1.30E+0		1.30E+0		1.10E+0		9.00E-1		8.00E-1		6.00E-1	
20											4.45e-1	
23											4.77e-1	
25	1.60E+0		1.50E+0		1.30E+0		1.10E+0		9.00E-1		7.00E-1	
25											4.98e-1	
27	1.70e+0		1.60e+0		1.40e+0		1.10e+0		9.00e-1		7.00e-1	
28											5.29e-1	
30	1.80E+0		1.70E+0		1.60e+0	1.50E+0	1.20e+0	9.36e-1	9.00E-1	6.71e-1	7.00E-1	
30	1.74e+0	1.70e+0	1.90E+0	1.60e+0	1.43e+0	1.70E+0	1.30E+0	1.00E+0	1.00E+0	1.00E+0	5.51e-1	4.42e-1
35	2.00E+0										8.00E-1	
36											6.13e-1	
40	2.20E+0		2.10E+0		1.80E+0		1.40E+0		1.10E+0		8.00E-1	
40											6.57e-1	
50	2.50E+0		2.40E+0		2.10E+0		1.60E+0		1.30E+0		9.00E-1	
50	2.50e+0	2.45e+0		2.29e+0	2.04e+0	1.70e+0	1.32e+0	9.37e-1	9.37e-1	7.71e-1	6.02e-1	
60	2.80E+0		2.70E+0		2.30E+0		1.80E+0		1.40E+0		1.00E+0	
60	2.82e+0										8.94e-1	
65	2.95e+0											
70	3.10E+0		3.00E+0		2.60E+0		2.00E+0		1.60E+0		1.20E+0	
70	3.09e+0										1.03e+0	
80	3.40E+0		3.20E+0		2.80E+0		2.20E+0		1.70E+0		1.30E+0	
80	3.34e+0										1.17e+0	
100	3.80E+0		3.60E+0		3.50e+0	3.14e+0	2.72e+0	2.26e+0	2.10E+0	1.70e+0	1.60E+0	
100	3.80e+0	3.71e+0									1.46e+0	1.20e+0
120	4.20E+0		4.00E+0		3.60E+0		2.90E+0		2.40E+0		1.90E+0	
140	4.60E+0		4.40E+0		3.90E+0		3.20E+0		2.70E+0		2.20E+0	
140	4.56e+0										2.11e+0	
150	4.72e+0											
200	5.50E+0		5.30E+0		4.80E+0		4.10E+0		3.50E+0		3.00E+0	
200	5.49e+0										2.94e+0	
250	6.10E+0											
300	6.70E+0		6.50E+0		6.00E+0		5.20E+0		4.60E+0		3.90E+0	
300	6.66e+0											
350	7.19e+0	7.12e+0		6.85e+0	6.44e+0	5.95e+0	5.25e+0	5.05e+0	4.65e+0	4.40e+0	3.89e+0	
400	7.71e+0			7.30e+0	6.31e+0		5.82e+0	5.49e+0	5.02e+0	4.69e+0	4.22e+0	
450												
500	8.60E+0		8.40E+0		7.70E+0		6.80E+0		6.10E+0		5.40E+0	
500	8.68e+0										5.33e+0	
800	1.07e+1	1.06e+1		1.02e+1	9.75e+0	8.97e+0	8.16e+0	7.85e+0	7.14e+0	6.86e+0	6.25e+0	
1000	1.19E+1		1.16E+1		1.15e+1	1.08E+1	9.50E+0	9.14e+0	8.60E+0	8.17e+0	7.60E+0	
1000	1.20e+1	1.19e+1				1.08e+1	9.89e+0				1.13e+1	7.27e+0
2000	1.65e+1										1.07e+1	
2500	1.83e+1	1.81e+1		1.75e+1	1.49e+1	1.65e+1	1.53e+1	1.39e+1	1.30e+1	1.24e+1	1.16e+1	1.09e+1
5000	2.56e+1										1.64e+1	
10000	3.62e+1										2.25e+1	
20000	5.24e+1										3.17e+1	
45000	8.28e+1											
50000	8.88e+1										5.25e+1	
100000	1.35e+2										8.14e+1	

E <sub>0</sub> (eV)	75°	80°	85°	87°
9	4.00E-1	4.00E-1	4.00E-1	
10	4.00E-1	4.00E-1	4.00E-1	
12	5.00E-1	4.00E-1	4.00E-1	
15	5.00E-1	5.00E-1	4.00E-1	
20	5.00E-1	5.00E-1	5.00E-1	
25	5.00E-1	5.00E-1	5.00E-1	
27	5.00E-1	5.00E-1	5.00E-1	
30	6.00E-1	5.00E-1	5.00E-1	
30	3.52e-1	2.88e-1	2.45e-1	
35	6.00E-1	5.00E-1	5.00E-1	
40	6.00E-1	5.00E-1	5.00E-1	
50	7.00E-1	6.00E-1	5.00E-1	
50	4.73e-1	3.80e-1	3.19e-1	3.06e-1
60	7.00E-1	6.00E-1	6.00E-1	
70	8.00E-1	7.00E-1	6.00E-1	
80	9.00E-1	7.00E-1	7.00E-1	
100	1.10E+0	9.00E-1	8.00E-1	
100		7.68e-1	6.21e-1	
120	1.30E+0	1.10E+0	9.00E-1	
140	1.60E+0	1.30E+0	1.10E+0	
200	2.20E+0	1.80E+0	1.50E+0	
300	3.10E+0	2.60E+0	2.10E+0	
350		2.82e+0	2.19e+0	
400		3.08e+0		
500	4.40E+0	3.80E+0	3.00E+0	
800	5.84e+0	4.79e+0	4.12e+0	
1000	6.50E+0	5.80E+0	4.60E+0	
1000		5.63e+0	4.28e+0	
2000	9.27e+0	9.21e+0	7.87e+0	

# $W \rightarrow W$

Sputtering yield of W by W  
 $z1=74$ ,  $m1=183.85$ ,  $z2=74$ ,  $m2=183.85$ ,  $sbe=8.68$  eV,  $\rho=19.29$  g/cm $^{**3}$   
 $ef=8.63$  eV,  $esb=8.68$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=3(zbl)$   
program: eck1c (CRAY-T3E)  
 $ne=19$ ,  $na=2$

$E_0$ (eV)	$0^\circ$	$45^\circ$
18		3.25e-7
19		9.11e-7
20		2.45e-6
25		6.66e-5
27	8.03e-7	1.52e-4
30	3.69e-6	4.20e-4
35	1.80e-5	1.43e-3
40	5.18e-5	3.39e-3
50	2.30e-4	1.13e-2
60	7.08e-4	2.41e-2
70	1.80e-3	4.17e-2
80	3.87e-3	6.37e-2
100	1.22e-2	1.16e-1
120	2.70e-2	1.76e-1
140	4.77e-2	2.38e-1
200	1.36e-1	4.32e-1
300	3.19e-1	7.34e-1
500	6.90e-1	1.26e-0
1000	1.45e-0	2.32e-0

Sputtered energy of W by W  
 $ne=19$ ,  $na=2$

$E_0$ (eV)	$0^\circ$	$45^\circ$
18		5.34e-8
19		1.41e-7
20		3.62e-7
25		9.18e-6
27	3.32e-8	2.13e-5
30	1.60e-7	6.03e-5
35	7.99e-7	2.10e-4
40	2.44e-6	5.04e-4
50	1.17e-5	1.71e-3
60	3.85e-5	3.65e-3
70	1.02e-4	6.27e-3
80	2.23e-4	9.46e-3
100	7.04e-4	1.68e-2
120	1.51e-3	2.46e-2
140	2.59e-3	3.24e-2
200	6.52e-3	5.30e-2
300	1.28e-2	7.73e-2
500	2.14e-2	1.03e-1
1000	3.02e-2	1.22e-1

## $W \rightarrow W$

Particle reflection coefficient of W backscattered from W  
 $z1=74$ ,  $m1=183.85$ ,  $z2=74$ ,  $m2=183.85$ ,  $sbe=8.68$  eV,  $\rho=19.29$  g/cm $^{**3}$   
 $ef=8.63$  eV,  $esb=8.68$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=3(zbl)$   
program: ecklc (CRAY-T3E)  
ne=19, na=2

$E_0$ (eV)	$0^\circ$	$45^\circ$
18		2.20e-8
19		1.14e-7
20		4.00e-7
25		4.01e-5
27		1.06e-4
30		3.10e-4
35		1.12e-3
40		2.90e-3
50	2.00e-8	1.07e-2
60	9.40e-7	2.54e-2
70	1.05e-5	4.52e-2
80	5.45e-5	6.71e-2
100	3.64e-4	1.11e-1
120	1.02e-3	1.50e-1
140	1.93e-3	1.80e-1
200	5.55e-3	2.33e-1
300	1.15e-2	2.60e-1
500	1.97e-2	2.58e-1
1000	2.81e-2	2.24e-1

Energy reflection coefficient of W backscattered from W  
ne=19, na=2

$E_0$ (eV)	$0^\circ$	$45^\circ$
18		2.77e-9
19		1.11e-8
20		4.10e-8
25		6.03e-6
27		1.68e-5
30		5.22e-5
35		1.98e-4
40		5.31e-4
50		2.02e-3
60	5.28e-8	4.97e-3
70	6.21e-7	9.18e-3
80	3.28e-6	1.40e-2
100	2.41e-5	2.42e-2
120	7.11e-5	3.34e-2
140	1.32e-4	4.08e-2
200	3.52e-4	5.38e-2
300	6.59e-4	5.93e-2
500	9.69e-4	5.61e-2
1000	1.19e-3	4.41e-2

Average depth (mean range) in Å of W implanted in W  
ne=19, na=2

$E_0$ (eV)	$0^\circ$	$45^\circ$
18		1.81e-1
19		1.89e-1
20		1.97e-1
25		2.48e-1
27	3.82e-1	2.71e-1
30	4.54e-1	3.06e-1
35	5.76e-1	3.65e-1
40	6.84e-1	4.19e-1
50	8.59e-1	5.13e-1
60	1.01e+0	6.00e-1
70	1.15e+0	6.88e-1
80	1.30e+0	7.79e-1
100	1.58e+0	9.69e-1
120	1.83e+0	1.16e+0
140	2.06e+0	1.35e+0
200	2.68e+0	1.89e+0
300	3.54e+0	2.66e+0
500	4.92e+0	3.85e+0
1000	7.44e+0	5.92e+0

# W → W

W on W, Maxwellian velocity distribution, sheath potential 0 kT  
 z1=74, m1=183.85, z2=74, m2=183.85, sbe=8.68 eV, rho=19.30 g/cm\*\*3  
 ef=8.60 eV, esb=8.68 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trspvmcx  
 ne=12

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
7	6.57e-4	3.84e-4	8.19e+0	1.08e-3	1.03e-3	1.33e+1	4.72e-1
12	4.54e-3	2.24e-3	1.18e+1	8.28e-3	6.76e-3	1.96e+1	7.91e-1
20	2.10e-2	8.11e-3	1.55e+1	3.09e-2	2.14e-2	2.77e+1	1.18e+0
30	5.38e-2	1.67e-2	1.84e+1	6.41e-2	3.99e-2	3.74e+1	1.59e+0
50	1.39e-1	3.33e-2	2.39e+1	1.21e-1	6.61e-2	5.48e+1	2.29e+0
70	2.34e-1	4.58e-2	2.74e+1	1.57e-1	8.12e-2	7.23e+1	2.91e+0
100	3.75e-1	5.83e-2	3.16e+1	1.99e-1	9.47e-2	9.67e+1	3.73e+0
200	7.62e-1	7.77e-2	4.06e+1	2.40e-1	9.82e-2	1.63e+2	5.68e+0
500	1.72e-0	9.91e-2	5.87e+1	2.54e-1	9.19e-2	3.70e+2	9.34e+0
1000	2.83e-0	1.07e-1	7.63e+1	2.38e-1	8.21e-2	6.96e+2	1.30e+1
2000	4.29e-0	1.09e-1	1.03e+2	2.23e-1	7.55e-2	1.38e+3	1.78e+1
5000	7.05e-0	9.85e-2	1.43e+2	1.90e-1	5.91e-2	3.20e+3	2.78e+1

W on W, Maxwellian velocity distribution, sheath potential 3 kT  
 ne=21

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
5	5.07e-4	1.22e-4	6.02e+0	2.87e-4	1.17e-4	1.02e+1	1.27e+0
6	1.17e-3	2.74e-4	6.99e+0	7.27e-4	2.74e-4	1.13e+1	1.46e+0
7	2.12e-3	4.90e-4	8.07e+0	1.28e-3	4.55e-4	1.24e+1	1.65e+0
10	8.31e-3	1.62e-3	9.76e+0	4.80e-3	1.58e-3	1.65e+1	2.11e+0
14	2.42e-2	4.07e-3	1.18e+1	1.16e-2	3.31e-3	2.00e+1	2.63e+0
20	6.13e-2	8.71e-3	1.42e+1	2.09e-2	5.09e-3	2.44e+1	3.29e+0
24	9.52e-2	1.20e-2	1.51e+1	2.65e-2	6.13e-3	2.77e+1	3.64e+0
30	1.48e-1	1.60e-2	1.62e+1	3.42e-2	7.15e-3	3.13e+1	4.16e+0
36	2.03e-1	1.96e-2	1.74e+1	3.90e-2	7.93e-3	3.67e+1	4.62e+0
40	2.42e-1	2.24e-2	1.85e+1	4.30e-2	8.37e-3	3.89e+1	4.88e+0
45	2.86e-1	2.44e-2	1.92e+1	4.69e-2	8.99e-3	4.32e+1	5.22e+0
50	3.37e-1	2.68e-2	2.00e+1	4.96e-2	9.27e-3	4.68e+1	5.50e+0
60	4.26e-1	3.04e-2	2.14e+1	5.12e-2	8.67e-3	5.08e+1	6.10e+0
70	5.22e-1	3.37e-2	2.27e+1	5.58e-2	9.22e-3	5.80e+1	6.55e+0
75	5.69e-1	3.54e-2	2.33e+1	5.57e-2	8.66e-3	5.83e+1	6.86e+0
100	7.57e-1	3.82e-2	2.52e+1	6.08e-2	9.02e-3	7.42e+1	7.88e+0
200	1.46e-0	4.79e-2	3.30e+1	6.34e-2	8.11e-3	1.28e+2	1.09e+1
400	2.37e-0	5.13e-2	4.33e+1	6.17e-2	6.46e-3	2.09e+2	1.51e+1
1000	3.89e-0	4.95e-2	6.36e+1	5.50e-2	4.24e-3	3.86e+2	2.36e+1
2000	5.42e-0	4.45e-2	8.24e+1	4.66e-2	4.31e-3	9.27e+2	3.36e+1
5000	7.82e-0	3.78e-2	1.21e+2	4.00e-2	3.25e-3	2.04e+3	5.33e+1

W on W, Maxwellian velocity distribution, sheath potential 9 kT  
 ne=20

kT(eV)	Y	Y <sub>E</sub>	E <sub>sp</sub>	R <sub>N</sub>	R <sub>E</sub>	E <sub>b</sub>	range
3	2.72e-4	3.39e-5	4.12e+0	5.60e-5	1.28e-5	7.53e+0	1.75e+0
4	1.04e-3	1.28e-4	5.41e+0	2.76e-4	5.43e-5	8.65e+0	2.14e+0
5	2.80e-3	3.33e-4	6.55e+0	9.53e-4	1.67e-4	9.61e+0	2.49e+0
7	1.16e-2	1.22e-3	8.05e+0	3.04e-3	4.75e-4	1.20e+1	3.06e+0
10	3.95e-2	3.50e-3	9.74e+0	7.27e-3	1.03e-3	1.55e+1	3.76e+0
20	1.93e-1	1.19e-2	1.36e+1	1.88e-2	2.18e-3	2.56e+1	5.51e+0
24	2.64e-1	1.43e-2	1.43e+1	2.43e-2	2.46e-3	2.67e+1	6.03e+0
30	3.68e-1	1.76e-2	1.58e+1	2.83e-2	2.67e-3	3.11e+1	6.72e+0
36	4.73e-1	2.06e-2	1.73e+1	3.07e-2	2.71e-3	3.50e+1	7.35e+0
40	5.32e-1	2.18e-2	1.80e+1	3.16e-2	2.83e-3	3.94e+1	7.76e+0
45	6.16e-1	2.37e-2	1.90e+1	3.31e-2	2.81e-3	4.20e+1	8.22e+0
50	6.80e-1	2.47e-2	1.99e+1	3.61e-2	2.77e-3	4.23e+1	8.65e+0
60	8.47e-1	2.74e-2	2.14e+1	3.80e-2	3.00e-3	5.20e+1	9.41e+0
70	9.69e-1	2.89e-2	2.29e+1	3.96e-2	2.89e-3	5.61e+1	1.02e+1
75	1.03e-0	2.92e-2	2.33e+1	3.93e-2	2.89e-3	6.05e+1	1.05e+1
100	1.33e-0	3.25e-2	2.69e+1	4.14e-2	3.17e-3	8.43e+1	1.21e+1
200	2.22e-0	3.52e-2	3.49e+1	3.78e-2	2.35e-3	1.37e+2	1.67e+1
500	3.74e-0	3.55e-2	5.23e+1	4.00e-2	2.36e-3	3.25e+2	2.56e+1
1000	5.22e-0	3.31e-2	6.99e+1	3.28e-2	1.65e-3	5.53e+2	3.63e+1
2000	6.29e-0	2.70e-2	9.42e+1	2.75e-2	1.29e-3	1.03e+3	5.25e+1

## He → Pt

Sputtering yield of Pt by He

```

z1= 2, m1= 4.00, z2=78, m2=195.09, sbe=5.86 eV, rho=21.44 g/cm***3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : trvmc95, trspvmcx
nem= 4, na= 2

```

E <sub>0</sub> (eV)	0°	30°
500		4.49e-2
1000		7.35e-2
1500	7.59e-2	9.25e-2
3000	8.77e-2	

Sputtered energy of Pt by He

nem= 4, na= 2

E <sub>0</sub> (eV)	0°	30°
500		7.00e-4
1000		8.54e-4
1500	7.16e-4	8.82e-4
3000	5.50e-4	

Particle reflection coefficient of He backscattered from Pt

```

z1= 2, m1= 4.00, z2=78, m2=195.09, sbe=5.86 eV, rho=21.44 g/cm***3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : trvmc95, trspvmcx
nem= 4, na= 2

```

E <sub>0</sub> (eV)	0°	30°
500		5.99e-1
1000		5.60e-1
1500	4.95e-1	5.36e-1
3000	4.46e-1	

Energy reflection coefficient of He backscattered from Pt

nem= 4, na= 2

E <sub>0</sub> (eV)	0°	30°
500		3.75e-1
1000		3.38e-1
1500	2.80e-1	3.14e-1
3000	2.41e-1	

Average depth (mean range) in Å of He implanted in Pt

nem= 4, na= 2

E <sub>0</sub> (eV)	0°	30°
500		6.02e+1
1000		9.01e+1
1500	1.15e+2	1.14e+2
3000	1.80e+2	

## Ne → Pt

Sputtering yield of Pt by Ne

```

z1=10, m1= 20.18, z2=78, m2=195.09, sbe=5.86 eV, rho=21.44 g/cm**3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : trvnc95
ne= 6, na= 1

```

E <sub>0</sub> (eV)	0°
40	1.63e-3
200	2.61e-1
600	6.75e-1
3000	1.40e-0
5000	1.70e-0
9000	1.76e-0

Sputtered energy of Pt by Ne

ne= 6, na= 2

E <sub>0</sub> (eV)	0°
40	6.75e-5
200	1.30e-2
600	1.90e-2
3000	1.47e-2
5000	1.28e-2
9000	9.52e-3

Particle reflection coefficient of Ne backscattered from Pt

```

z1=10, m1= 20.18, z2=78, m2=195.09, sbe=5.86 eV, rho=21.44 g/cm**3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : trvnc95
ne= 6, na= 1

```

E <sub>0</sub> (eV)	0°
40	6.64e-1
200	5.07e-1
600	4.36e-1
3000	3.82e-1
5000	3.53e-1
9000	3.38e-1

Energy reflection coefficient of Ne backscattered from Pt

ne= 6, na= 1

E <sub>0</sub> (eV)	0°
40	3.40e-1
200	2.34e-1
600	1.90e-1
3000	1.70e-1
5000	1.42e-1
9000	1.48e-1

Average depth (mean range) in Å of Ne implanted in Pt

ne= 6, na= 1

E <sub>0</sub> (eV)	0°
40	5.71e+0
200	1.19e+1
600	2.07e+1
3000	5.37e+1
5000	6.84e+1
9000	1.10e+2

## Xe → Pt

Sputtering yield of Pt by Xe

```

z1=54, m1=131.30, z2=78, m2=195.09, sbe=5.86 eV, rho=21.44 g/cm**3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdeel=kdee2=3, ipot=ipotr=1 (KrC)
program : trvmc95, trspvmcx
ne= 8, na= 2

```

$E_0$ (eV)	0°	30°
40	8.42e-4	
200	3.35e-1	
500		1.47e-0
600	1.33e-0	
1000		2.49e-0
1500		3.24e-0
3000	4.08e-0	
5000	5.25e-0	

Sputtered energy of Pt by Xe  
ne= 8, na= 2

$E_0$ (eV)	0°	30°
40	5.16e-5	
200	1.53e-2	
500		6.13e-2
600	3.33e-2	
1000		6.86e-2
1500		6.87e-2
3000	3.83e-2	
5000	3.62e-2	

Particle reflection coefficient of Xe backscattered from Pt

```

z1=54, m1=131.30, z2=78, m2=195.09, sbe=5.86 eV, rho=21.44 g/cm**3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdeel=kdee2=3, ipot=ipotr=1 (KrC)
program : trvmc95, trspvmcx
ne= 8, na= 2

```

$E_0$ (eV)	0°	30°
40	2.27e-1	
200	1.91e-1	
500		2.31e-1
600	1.54e-1	
1000		2.10e-1
1500		1.90e-1
3000	1.03e-1	
5000	9.15e-2	

Energy reflection coefficient of Xe backscattered from Pt  
ne= 8, na= 2

$E_0$ (eV)	0°	30°
40	1.48e-2	
200	1.39e-2	
500		3.14e-2
600	1.12e-2	
1000	2.61e-2	
1500		2.37e-2
3000	7.38e-3	
5000	6.56e-3	

Average depth (mean range) in Å of Xe implanted in Pt  
ne= 8, na= 2

$E_0$ (eV)	0°	30°
40	2.43e+0	
200	5.60e+0	
500		8.00e+0
600	9.22e+0	
1000		1.08e+1
1500		1.29e+1
3000	1.97e+1	
5000	2.52e+1	

## $\mu \rightarrow \text{Au}$

Particle reflection coefficient of  $\mu$  backscattered from Au  
 z1= 1, m1= 0.11, z2=79, m2=196.97, sbe=3.80 eV, rho=19.31 g/cm\*\*3  
 ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kddee2=3, ipot=ipotr=1 (KrC)  
 10 - 1000 eV : kddee1=3, 1000 - 20000 eV : kddee1=4  
 program: trvrmc  
 ne= 8, na= 1

$E_0$ (eV)	0°
10	6.72e-1
100	4.83e-1
500	3.79e-1
1000	3.15e-1
1000	2.46e-1
5000	1.24e-1
10000	8.52e-2
20000	4.85e-2

Energy reflection coefficient of  $\mu$  backscattered from Au  
 ne= 8, na= 1

$E_0$ (eV)	0°
10	4.27e-1
100	2.43e-1
500	1.69e-1
1000	1.29e-1
1000	9.43e-2
5000	4.13e-2
10000	2.69e-2
20000	1.66e-2

Average depth (mean range) in Å of  $\mu$  implanted in Au  
 ne= 8, na= 1

$E_0$ (eV)	0°
10	8.74e+0
100	2.60e+1
500	6.00e+1
1000	8.80e+1
1000	7.02e+1
5000	2.01e+2
10000	3.40e+2
20000	6.06e+2

# D → Au

Sputtering yield of Au by D  
 z1= 1, m1= 2.01, z2=79, m2=196.97, sbe=3.80, 3.93 eV, rho=19.31 g/cm\*\*3  
 ef=0.98 (0.90) eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx, newtrim (Laszlo), IPP 9/82  
 ne=27, na= 8

$E_0$ (eV)	0°	30°	45°	60°	65°	75°	80°	85°
120	8.40e-5				5.88e-5			
130	2.44e-4	2.68e-4	2.58e-4		1.89e-4	9.63e-5		
135	3.49e-4				2.86e-4			
140	4.92e-4		5.34e-4		4.11e-4	2.10e-4	8.94e-5	
150	7.96e-4	8.35e-4	8.74e-4	7.45e-4	6.86e-4	3.63e-4	1.71e-4	
155	9.27e-4							
160	1.14e-3				1.04e-3	5.78e-4	2.56e-4	
165	1.33e-3							
170		1.73e-3	1.63e-3	1.60e-3		8.27e-4	3.78e-4	
180		2.01e-3				1.09e-3	5.76e-4	
190						1.48e-3	7.85e-4	
200	3.05e-3	3.27e-3	3.41e-3	3.34e-3	3.08e-3	1.89e-3	9.39e-4	
210							1.24e-3	
250	5.45e-3	6.16e-3	6.59e-3	6.96e-3		4.84e-3		
300	7.84e-3	8.68e-3	9.59e-3	1.10e-2	1.00e-2	8.81e-3	6.25e-3	1.47e-3
350				1.46e-2				
400	1.21e-2		1.60e-2			2.02e-2		
500	1.60e-2	1.67e-2	1.96e-2	2.49e-2		3.33e-2	3.25e-2	1.27e-2
700				3.76e-2				
750	2.15e-2	2.35e-2	2.79e-2			6.33e-2		
1000	2.51e-2	2.74e-2	3.43e-2	5.21e-2		8.49e-2	9.55e-2	5.98e-2
2000	2.91e-2				8.45e-2			
3000		3.73e-2	4.91e-2	7.34e-2			1.43e-1	
5000	2.98e-2						1.42e-1	
10000	2.58e-2	3.14e-2	4.59e-2	6.81e-2			1.03e-1	
30000							5.73e-2	
100000								

Sputtered energy of Au by D  
 program: testvmcx, newtrim (Laszlo), IPP 9/82  
 ne=27, na= 8

$E_0$ (eV)	0°	30°	45°	60°	65°	75°	80°	85°
120	2.46e-7				1.81e-7			
130	9.75e-7	1.09e-6	1.11e-6		8.04e-7	3.85e-7		
135	1.52e-6				1.34e-6			
140	2.39e-6		2.67e-6		2.10e-6	9.99e-7	4.17e-7	
150	4.32e-6	4.70e-6	5.17e-6	4.37e-6	3.96e-6	2.05e-6	9.17e-7	
155	5.25e-6							
160	6.81e-6				6.59e-6	3.60e-6	1.54e-6	
165	8.21e-6							
170		1.15e-5	1.10e-5	1.09e-5		5.46e-6	2.50e-6	
180	1.41e-5					7.68e-6	3.95e-6	
190						1.10e-5	5.80e-6	
200	2.27e-5	2.44e-5	2.62e-5	2.57e-5	2.46e-5	1.46e-5	7.18e-6	
210							1.01e-5	
250	4.54e-5	5.13e-5	5.62e-5	5.98e-5		4.16e-5		
300	6.60e-5	7.44e-5	8.31e-5	9.62e-5	9.35e-5	7.91e-5	5.48e-5	1.32e-5
350				1.30e-4				
400	1.02e-4		1.42e-4			1.79e-4		
500	1.28e-4	1.41e-4	1.65e-4	2.06e-4		2.72e-4	2.97e-4	1.34e-4
700				2.82e-4				
750	1.53e-4	1.69e-4	2.05e-4			4.83e-4		
1000	1.64e-4	1.81e-4	2.22e-4	3.33e-4		5.99e-4	7.14e-4	5.42e-4
2000	1.29e-4				3.95e-4			
3000		1.28e-4	1.77e-4	2.56e-4		5.57e-4		
5000	7.43e-5					2.66e-4		
10000	3.75e-5	4.55e-5	7.27e-5	1.21e-4			8.20e-5	
30000							2.40e-5	
100000								

# D → Au

Particle reflection coefficient of D backscattered from Au  
 z1= 1, m1= 2.01, z2=79, m2=196.97, sbe=3.80, 3.93 eV, rho=19.31 g/cm\*\*3  
 ef=0.98 (0.90) eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx, newtrim (Laszlo)  
 ne=28, na= 8

$E_0$ (eV)	0°	30°	45°	60°	65°	75°	80°	85°
100	6.50e-1				8.22e-1			
120	6.43e-1				8.13e-1			
130	6.39e-1	6.72e-1	7.15e-1		8.09e-1	8.90e-1		
135	6.38e-1				8.07e-1			
140	6.36e-1		7.11e-1		8.05e-1	8.86e-1	9.43e-1	
150	6.33e-1	6.66e-1	7.09e-1	7.73e-1	8.01e-1	8.82e-1	9.40e-1	
155	6.32e-1							
160	6.30e-1				7.98e-1	8.78e-1	9.38e-1	
165	6.29e-1							
170		6.61e-1	7.03e-1	7.66e-1		8.75e-1	9.35e-1	
180	6.25e-1					8.71e-1	9.32e-1	
190						8.68e-1	9.30e-1	
200	6.19e-1	6.51e-1	6.95e-1	7.59e-1	7.86e-1	8.66e-1	9.27e-1	
210							9.25e-1	
250	6.08e-1	6.42e-1	6.85e-1	7.48e-1		8.53e-1		
300	5.99e-1	6.36e-1	6.78e-1	7.40e-1	7.68e-1	8.42e-1	9.05e-1	9.82e-1
350				7.33e-1				
400	5.84e-1		6.59e-1			8.27e-1		
500	5.70e-1	6.10e-1	6.51e-1	7.18e-1		8.12e-1	8.73e-1	9.69e-1
700				6.98e-1				
750	5.49e-1	5.80e-1	6.27e-1			7.96e-1		
1000	5.24e-1	5.65e-1	6.11e-1	6.78e-1		7.84e-1	8.35e-1	9.36e-1
2000								
3000	4.69e-1		4.73e-1	5.28e-1	6.06e-1		7.14e-1	
5000	3.75e-1							
10000	2.96e-1	3.43e-1	4.11e-1	5.04e-1			6.35e-1	
30000							5.21e-1	
100000							3.96e-1	

Energy reflection coefficient of D backscattered from Au  
 ne=28, na= 8

$E_0$ (eV)	0°	30°	45°	60°	65°	75°	80°	85°
100	6.50e-1				8.22e-1			
120	6.43e-1				8.13e-1			
130	6.39e-1	6.72e-1	7.15e-1		8.09e-1	8.90e-1		
135	6.38e-1				8.07e-1			
140	6.36e-1		7.11e-1		8.05e-1	8.86e-1	9.43e-1	
150	6.33e-1	6.66e-1	7.09e-1	7.73e-1	8.01e-1	8.82e-1	9.40e-1	
155	6.32e-1							
160	6.30e-1				7.98e-1	8.78e-1	9.38e-1	
165	6.29e-1							
170		6.61e-1	7.03e-1	7.66e-1		8.75e-1	9.35e-1	
180	6.25e-1					8.71e-1	9.32e-1	
190						8.68e-1	9.30e-1	
200	6.19e-1	6.51e-1	6.95e-1	7.59e-1	7.86e-1	8.66e-1	9.27e-1	
210						9.25e-1		
250	6.08e-1	6.42e-1	6.85e-1	7.48e-1		8.53e-1		
300	5.99e-1	6.36e-1	6.78e-1	7.40e-1	7.68e-1	8.42e-1	9.05e-1	9.82e-1
350				7.33e-1				
400	5.84e-1		6.59e-1			8.27e-1		
500	5.70e-1	6.10e-1	6.51e-1	7.18e-1		8.12e-1	8.73e-1	9.69e-1
700				6.98e-1				
750	5.49e-1	5.80e-1	6.27e-1			7.96e-1		
1000	5.24e-1	5.65e-1	6.11e-1	6.78e-1		7.84e-1	8.35e-1	9.36e-1
2000								
3000	4.69e-1		4.73e-1	5.28e-1	6.06e-1		7.14e-1	
5000	3.75e-1							
10000	2.96e-1	3.43e-1	4.11e-1	5.04e-1			6.35e-1	
30000							5.21e-1	
100000							3.96e-1	

# D → Au

Average depth (mean range) in Å of D implanted in Au  
 z1= 1, m1= 2.01, z2=79, m2=196.97, sbe=3.80, 3.93 eV, rho=19.31 g/cm\*\*3  
 ef=0.98 (0.90) eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx, newtrim (Laszlo)  
 ne=28, na= 8

$E_0$ (eV)	0°	30°	45°	60°	65°	75°	80°	85°
100	4.72e+1				4.54e+1			
120	5.17e+1				5.00e+1			
130	5.39e+1	5.34e+1	5.29e+1		5.21e+1	5.18e+1		
135	5.50e+1				5.31e+1			
140	5.60e+1		5.49e+1		5.42e+1	5.39e+1	5.37e+1	
150	5.81e+1	5.76e+1	5.70e+1	5.64e+1	5.62e+1	5.58e+1	5.56e+1	
155	5.91e+1							
160	6.01e+1				5.81e+1	5.77e+1	5.76e+1	
165	6.11e+1							
170		6.14e+1	6.08e+1	6.02e+1		5.96e+1	5.94e+1	
180	6.41e+1					6.15e+1	6.12e+1	
190						6.31e+1	6.31e+1	
200	6.77e+1	6.71e+1	6.64e+1	6.57e+1	6.51e+1	6.50e+1	6.48e+1	
210							6.65e+1	
250	7.67e+1	7.59e+1	7.48e+1	7.41e+1		7.29e+1		
300	8.48e+1	8.36e+1	8.26e+1	8.17e+1	8.08e+1	8.05e+1	8.05e+1	8.07e+1
350				8.89e+1				
400	9.94e+1		9.61e+1			9.46e+1		
500	1.13e+2	1.12e+2	1.10e+2	1.08e+2		1.07e+2	1.06e+2	1.07e+2
700				1.32e+2				
750	1.44e+2	1.42e+2	1.40e+2			1.36e+2		
1000	1.70e+2	1.68e+2	1.66e+2	1.63e+2		1.61e+2	1.60e+2	1.60e+2
2000	2.66e+2				2.49e+2	3.18e+2		
3000		3.42e+2	3.34e+2	3.26e+2				
5000	4.98e+2					7.10e+2		
10000	8.41e+2	8.06e+2	7.70e+2	7.34e+2		1.17e+3		
30000						2.44e+3		
100000								

## He → Au

Sputtering yield of Au by He

$z1 = 2$ ,  $m1 = 4.00$ ,  $z2 = 79$ ,  $m2 = 196.97$ ,  $sbe = 3.80$  eV,  $\rho = 19.30$  g/cm<sup>3</sup>  
 $ef = 3.80$  eV,  $esb = 0.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: trspvmcx, cascopol, casc, IPP 9/82  
nem = 7, na = 2

$E_0$ (eV)	0°	75°	comment
100	5.46e-3		
300	4.98e-2		
500	7.42e-2		
1000	1.06e-1		
2000	1.70e-1	4.64e-1	ca=1.09
4000	1.31e-1		
10000	1.52e-1		

Sputtered energy of Au by He

program: trspvmcx, cascopol, casc  
nem = 7, na = 2

$E_0$ (eV)	0°	75°	comment
100	7.28e-5		
300	7.63e-4		
500	9.42e-4		
1000	9.91e-4		
2000	1.01e-3	3.60e-3	ca=1.09
4000	5.26e-4		
10000	3.02e-4		

Particle reflection coefficient of He backscattered from Au

$z1 = 2$ ,  $m1 = 4.00$ ,  $z2 = 79$ ,  $m2 = 196.97$ ,  $sbe = 3.80$  eV,  $\rho = 19.30$  g/cm<sup>3</sup>  
 $ef = 3.80$  eV,  $esb = 0.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: trspvmcx, cascopol, casc  
nem = 8, na = 2

$E_0$ (eV)	0°	75°	comment
50	6.79e-1		
100	6.41e-1		
300	5.79e-1		
500	5.60e-1		
1000	5.25e-1		
2000	4.93e-1	7.76e-1	ca=1.09
4000	4.35e-1		
10000	3.51e-1		

Energy reflection coefficient of He backscattered from Au  
nem = 8, na = 2

$E_0$ (eV)	0°	75°	comment
50	4.56e-1		
100	4.14e-1		
300	3.56e-1		
500	3.33e-1		
1000	3.02e-1		
2000	2.94e-1	6.25e-1	ca=1.09
4000	2.31e-1		
10000	1.80e-1		

Average depth (mean range) in Å of He implanted in Au  
nem = 8, na = 2

$E_0$ (eV)	0°	75°	comment
50	2.07e+1		
100	2.93e+1		
300	5.15e+1		
500	6.87e+1		
1000	1.02e+2		
2000	1.26e+2	1.18e+2	ca=1.09
4000	2.44e+2		
10000	4.19e+2		

# He → Au

Sputtering yield of Au by He  
 $z1 = 2, m1 = 4.00, z2 = 79, m2 = 196.97, sbe = 3.80 \text{ eV}, rho = 19.31 \text{ g/cm}^{**3}$   
 $ef = 0.50 \text{ eV}, esb = 0.00 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2, ipot = ipotr (\text{KrC})$   
 $\alpha = 0.00 \text{ program: trspvmcx}$   
 $n_{\text{e}} = 4, n_{\text{a}} = 1, n(\text{ipot}) = 3$

$E_0 (\text{eV})$	KrC	Mol	ZBL	comment
4000	1.15e-1			$kdee1 = kdee2 = 1$ (LS)
4000	1.58e-1			$kdee1 = kdee2 = 2$ (OR)
4000	1.61e-1		1.59e-1	$kdee1 = kdee2 = 3$
4000	1.09e-1			$kdee1 = kdee2 = 3, ca = 0.8$

Sputtered energy of Au by He  
 $n_{\text{e}} = 4, n_{\text{a}} = 1, n(\text{ipot}) = 3$

$E_0 (\text{eV})$	KrC	Mol	ZBL	comment
4000	4.34e-4			$kdee1 = kdee2 = 1$ (LS)
4000	5.87e-4			$kdee1 = kdee2 = 2$ (OR)
4000	6.17e-4		5.50e-4	$kdee1 = kdee2 = 3$
4000	4.73e-4			$kdee1 = kdee2 = 3, ca = 0.8$

Particle reflection coefficient of He backscattered from Au  
 $z1 = 2, m1 = 4.00, z2 = 79, m2 = 196.97, sbe = 3.80 \text{ eV}, rho = 19.31 \text{ g/cm}^{**3}$   
 $ef = 0.50 \text{ eV}, esb = 0.00 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2, ipot = ipotr (\text{KrC})$   
 $\alpha = 0.00 \text{ program: trspvmcx}$   
 $n_{\text{e}} = 8, n_{\text{a}} = 1, n(\text{ipot}) = 3$

$E_0 (\text{eV})$	KrC	Mol	ZBL	comment
50	6.45e-1			$kdee1 = kdee2 = 1$ (LS)
50	7.15e-1			$kdee1 = kdee2 = 2$ (OR)
50	7.38e-1		7.06e-1	$kdee1 = kdee2 = 3$
50	6.27e-1			$kdee1 = kdee2 = 3, ca = 0.8$
4000	4.19e-1			$kdee1 = kdee2 = 1$ (LS)
4000	4.28e-1			$kdee1 = kdee2 = 2$ (OR)
4000	4.28e-1		4.39e-1	$kdee1 = kdee2 = 3$
4000	4.00e-1			$kdee1 = kdee2 = 3, ca = 0.8$

Energy reflection coefficient of He backscattered from Au  
 $n_{\text{e}} = 8, n_{\text{a}} = 1, n(\text{ipot}) = 3$

$E_0 (\text{eV})$	KrC	Mol	ZBL	comment
50	4.20e-1			$kdee1 = kdee2 = 1$ (LS)
50	4.96e-1			$kdee1 = kdee2 = 2$ (OR)
50	5.32e-1		4.96e-1	$kdee1 = kdee2 = 3$
50	3.92e-1			$kdee1 = kdee2 = 3, ca = 0.8$
4000	2.21e-1			$kdee1 = kdee2 = 1$ (LS)
4000	2.25e-1			$kdee1 = kdee2 = 2$ (OR)
4000	2.36e-1		2.43e-1	$kdee1 = kdee2 = 3$
4000	2.00e-1			$kdee1 = kdee2 = 3, ca = 0.8$

Average depth (mean range) in Å of He implanted in Au  
 $n_{\text{e}} = 8, n_{\text{a}} = 1, n(\text{ipot}) = 3$

$E_0 (\text{eV})$	KrC	Mol	ZBL	comment
50	1.84e+1			$kdee1 = kdee2 = 1$ (LS)
50	2.41e+1			$kdee1 = kdee2 = 2$ (OR)
50	1.59e+1		1.53e+1	$kdee1 = kdee2 = 3$
50	2.79e+1			$kdee1 = kdee2 = 3, ca = 0.8$
4000	2.40e+2			$kdee1 = kdee2 = 1$ (LS)
4000	2.54e+2		2.23e+2	$kdee1 = kdee2 = 2$ (OR)
4000	2.90e+2			$kdee1 = kdee2 = 3$
4000				$kdee1 = kdee2 = 3, ca = 0.8$

## Ne → Au

Sputtering yield of Au by Ne

$z1=10$ ,  $m1= 20.18$ ,  $z2=79$ ,  $m2=196.97$ ,  $sbe=3.80$  eV,  $\rho=19.30$  g/cm $^{**3}$   
 $ef=3.80$  eV,  $esb=0.00$  eV,  $ca=1.09$ ,  $kk0=kk0r=1$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: cascopol, casc  
 $n_{\text{e}} = 2$ ,  $n_{\text{a}} = 2$

$E_0$ (eV)	$0^\circ$	$75^\circ$
2000	2.73e-0	2.46e-0
10000		6.53e-0

Sputtered energy of Au by Ne  
 $n_{\text{e}} = 2$ ,  $n_{\text{a}} = 2$

$E_0$ (eV)	$0^\circ$	$75^\circ$
2000	2.72e-2	4.90e-2
10000		3.93e-2

Particle reflection coefficient of Ne backscattered from Au

$z1=10$ ,  $m1= 20.18$ ,  $z2=79$ ,  $m2=196.97$ ,  $sbe=3.80$  eV,  $\rho=19.30$  g/cm $^{**3}$   
 $ef=3.80$  eV,  $esb=0.00$  eV,  $ca=1.09$ ,  $kk0=kk0r=1$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: cascopol, casc  
 $n_{\text{e}} = 2$ ,  $n_{\text{a}} = 2$

$E_0$ (eV)	$0^\circ$	$75^\circ$
2000	4.02e-1	8.08e-1
10000		6.67e-1

Energy reflection coefficient of Ne backscattered from Au  
 $n_{\text{e}} = 2$ ,  $n_{\text{a}} = 2$

$E_0$ (eV)	$0^\circ$	$75^\circ$
2000	1.83e-1	6.33e-1
10000		4.71e-1

## Na → Au

Sputtering yield of Au by Na  
 $z1=11$ ,  $m1=22.99$ ,  $z2=79$ ,  $m2=196.97$ ,  $sbe=3.80$  eV,  $\rho=19.30$  g/cm\*\*3  
 $ef=eV$ ,  $esb=eV$ ,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
only low fluence!  
IPP9/82  
 $n_e = 1$ ,  $n_a = 8$

$E_0$ (eV)	0°	15°	30°	40°	50°	60°	70°	80°
30000	2.20e-0	2.45e-0	3.03e-0	3.45e-0	4.42e-0	5.62e-0	7.42e-0	8.27e-0

Sputtered energy of Au by Na  
 $n_e = 1$ ,  $n_a = 8$

$E_0$ (eV)	0°	15°	30°	40°	50°	60°	70°	80°
30000	4.12e-3	4.73e-3	6.50e-3	8.03e-3	1.13e-2	1.60e-2	2.38e-2	3.11e-2

Particle reflection coefficient of Na backscattered from Au  
 $z1=11$ ,  $m1=22.99$ ,  $z2=79$ ,  $m2=196.97$ ,  $sbe=3.80$  eV,  $\rho=19.30$  g/cm\*\*3  
 $ef=eV$ ,  $esb=eV$ ,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
only low fluence!  
 $n_e = 1$ ,  $n_a = 8$

$E_0$ (eV)	0°	15°	30°	40°	50°	60°	70°	80°
30000	2.29e-1	2.33e-1	2.74e-1	3.06e-1	3.61e-1	4.32e-1	5.32e-1	6.71e-1

Energy reflection coefficient of Na backscattered from Au  
 $n_e = 1$ ,  $n_a = 8$

$E_0$ (eV)	0°	15°	30°	40°	50°	60°	70°	80°
30000	8.13e-2	8.78e-2	1.08e-1	1.27e-1	1.65e-1	2.21e-1	3.08e-1	4.65e-1

Average depth (mean range) in Å of Na implanted in Au  
 $n_e = 1$ ,  $n_a = 8$

$E_0$ (eV)	0°	15°	30°	40°	50°	60°	70°	80°
30000	2.39e+2	2.36e+2	2.26e+2	2.17e+2	2.07e+2	1.99e+2	1.89e+2	1.84e+2

## Ar → Au

Sputtering yield of Au by Ar

$z1=18$ ,  $m1=39.95$ ,  $z2=79$ ,  $m2=196.97$ ,  $sbe=3.80$  eV,  $\rho=19.31$  g/cm $^{**3}$   
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: trspvmcx, trspv1cs, IPP 9/82  
ne= 9, na= 1

$E_0$ (eV)	$0^\circ$
50	7.43e-2
100	2.86e-1
300	9.30e-1
500	1.38e-0
1000	2.10e-0
2000	3.03e-0
3000	3.72e-0
4000	3.68e-0
100000	4.03e-0

Sputtered energy of Au by Ar  
program: trspvmcx, trspv1cs  
ne= 8, na= 1

$E_0$ (eV)	$0^\circ$
50	5.84e-3
100	1.86e-2
300	3.31e-2
500	3.62e-2
1000	3.57e-2
2000	3.45e-2
3000	3.41e-2
4000	2.60e-2

Particle reflection coefficient of Ar backscattered from Au  
 $z1=18$ ,  $m1=39.95$ ,  $z2=79$ ,  $m2=196.97$ ,  $sbe=3.80$  eV,  $\rho=19.31$  g/cm $^{**3}$   
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: trspvmcx, trspv1cs  
ne= 8, na= 1

$E_0$ (eV)	$0^\circ$
50	5.67e-1
100	4.89e-1
300	3.99e-1
500	3.66e-1
1000	3.35e-1
2000	3.01e-1
3000	2.84e-1
4000	2.74e-1

Energy reflection coefficient of Ar backscattered from Au  
ne= 8, na= 1

$E_0$ (eV)	$0^\circ$
50	2.04e-1
100	1.71e-1
300	1.31e-1
500	1.16e-1
1000	1.03e-1
2000	9.50e-2
3000	8.88e-2
4000	8.12e-2

Average depth (mean range) in Å of Ar implanted in Au  
ne= 8, na= 1

$E_0$ (eV)	$0^\circ$
50	5.16e+0
100	6.96e+0
300	1.15e+1
500	1.46e+1
1000	2.06e+1
2000	3.07e+1
3000	3.78e+1
4000	4.38e+1

# K → Au

Sputtering yield of Au by K  
 $z1=19$ ,  $m1=42.00$ ,  $z2=79$ ,  $m2=196.97$ ,  $sbe=3.80$  eV,  $\rho=19.30$  g/cm\*\*3  
 $ef=eV$ ,  $esb=2.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
 IPP9/82  
 only low fluence!  
 $ne=1$ ,  $na=8$

$E_0$ (eV)	0°	15°	30°	40°	50°	60°	70°	80°
30000	4.72e-0	5.11e-0	5.99e-0	7.31e-0	8.90e-0	1.11e+1	1.33e+1	1.30e+1

Sputtered energy of Au by K  
 $ne=1$ ,  $na=8$

$E_0$ (eV)	0°	15°	30°	40°	50°	60°	70°	80°
30000	1.03e-2	1.15e-2	1.52e-2	2.06e-2	2.82e-2	3.88e-2	5.51e-2	6.62e-2

Particle reflection coefficient of K backscattered from Au  
 $z1=19$ ,  $m1=42.00$ ,  $z2=79$ ,  $m2=196.97$ ,  $sbe=3.80$  eV,  $\rho=19.30$  g/cm\*\*3  
 $ef=eV$ ,  $esb=2.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
 only low fluence!  
 $ne=1$ ,  $na=8$

$E_0$ (eV)	0°	15°	30°	40°	50°	60°	70°	80°
30000	1.79e-1	1.94e-1	2.18e-1	2.60e-1	3.21e-1	3.86e-1	4.87e-1	6.41e-1

Energy reflection coefficient of K backscattered from Au  
 $ne=1$ ,  $na=8$

$E_0$ (eV)	0°	15°	30°	40°	50°	60°	70°	80°
30000	4.94e-2	5.55e-2	6.83e-2	9.13e-2	1.27e-1	1.75e-1	2.56e-1	4.24e-1

Average depth (mean range) in Å of K implanted in Au  
 $ne=1$ ,  $na=8$

$E_0$ (eV)	0°	15°	30°	40°	50°	60°	70°	80°
30000	1.50e+2	1.48e+2	1.43e+2	1.36e+2	1.29e+2	1.20e+2	1.16e+2	1.08e+2

## Xe → Au

Sputtering yield of Au by Xe  
 $z1=54$ ,  $m1=131.00$ ,  $z2=79$ ,  $m2=196.97$ ,  $sbe=3.80$  eV,  $\rho=19.30$  g/cm<sup>3</sup>  
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: trspvmcx, cascpol, trspst, IPP 9/82  
ne= 9, na= 2

$E_0$ (eV)	0°	75°	comment
50	2.70e-2		
100	2.16e-1		
300	1.07e-0		
500	1.71e-0		
1000	2.87e-0		
2000	4.49e-0		
2000	6.54e-0	4.29e-0	ca=1.09
3000	5.54e-0		
4000	5.95e-0		

Sputtered energy of Au by Xe  
program: trspvmcx, cascpol, trspst  
ne= 9, na= 2

$E_0$ (eV)	0°	75°	comment
50	1.73e-3		
100	1.07e-2		
300	3.11e-2		
500	3.77e-2		
1000	4.14e-2		
2000	4.42e-2		
2000	6.89e-2	1.67e-1	ca=1.09
3000	4.34e-2		
4000	3.75e-2		

Particle reflection coefficient of Xe backscattered from Au  
 $z1=54$ ,  $m1=131.00$ ,  $z2=79$ ,  $m2=196.97$ ,  $sbe=3.80$  eV,  $\rho=19.30$  g/cm<sup>3</sup>  
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: trspvmcx, cascpol, trspst  
ne= 9, na= 2

$E_0$ (eV)	0°	75°	comment
50	2.36e-1		
100	2.23e-1		
300	1.79e-1		
500	1.64e-1		
1000	1.38e-1		
2000	1.27e-1		
2000	1.49e-1	7.99e-1	ca=1.09
3000	1.07e-1		
4000	9.52e-2		

Energy reflection coefficient of Xe backscattered from Au  
ne= 9, na= 2

$E_0$ (eV)	0°	75°	comment
50	1.73e-2		
100	1.66e-2		
300	1.33e-2		
500	1.21e-2		
1000	1.02e-2		
2000	9.71e-3		
2000	1.18e-2	4.72e-1	ca=1.09
3000	8.04e-3		
4000	6.69e-3		

Average depth (mean range) in Å of Xe implanted in Au  
ne= 9, na= 2

$E_0$ (eV)	0°	75°	comment
50	3.34e+0		
100	4.75e+0		
300	7.76e+0		
500	9.73e+0		
1000	1.32e+1		
2000	1.83e+1		
2000	1.12e+1	7.29e+0	ca=1.09
3000	2.18e+1		
4000	2.56e+1		

## Au → Au

Sputtering yield of Au by Au  
 $z1=79$ ,  $m1=196.97$ ,  $z2=79$ ,  $m2=196.97$ ,  $sbe=3.93$  eV,  $\rho=19.30$  g/cm\*\*3  
 $ef=3.43$  eV,  $esb=3.93$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: newtrim (Laszlo)  
ne=24, na= 2

$E_0$ (eV)	$0^\circ$	$65^\circ$
10		5.28e-5
12		5.31e-4
13		1.10e-3
14		1.98e-3
15		3.11e-3
20		1.61e-2
30	5.97e-4	6.51e-2
33	1.20e-3	
37	2.65e-3	
40	4.49e-3	1.28e-1
50	1.34e-2	
60	3.03e-2	
80	8.38e-2	
100	1.50e-1	
120	2.11e-1	
140	2.80e-1	
150	3.11e-1	
170	3.91e-1	
200	5.09e-1	
250	6.74e-1	
300	8.36e-1	
400	1.22e-0	
500	1.40e-0	
600	1.60e-0	2.74e-0

Sputtered energy of Au by Au  
ne=24, na= 2

$E_0$ (eV)	$0^\circ$	$65^\circ$
10		1.09e-5
12		1.03e-4
13		2.07e-4
14		3.74e-4
15		6.07e-4
20		3.33e-3
30	3.46e-5	1.37e-2
33	7.01e-5	
37	1.51e-4	
40	2.52e-4	2.65e-2
50	7.12e-4	
60	1.50e-3	
80	3.59e-3	
100	6.15e-3	
120	7.93e-3	
140	1.02e-2	
150	1.06e-2	
170	1.30e-2	
200	1.52e-2	
250	1.86e-2	
300	2.13e-2	
400	2.63e-2	
500	2.78e-2	
600	2.87e-2	1.89e-1

## Au → Au

Particle reflection coefficient of Au backscattered from Au  
 $z_1=79$ ,  $m_1=196.97$ ,  $z_2=79$ ,  $m_2=196.97$ ,  $sbe=3.93$  eV,  $\rho=19.30$  g/cm\*\*3  
 $ef=3.43$  eV,  $esb=3.93$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: newtrim (Laszlo)  
ne=24, na= 2

$E_0$ (eV)	0°	65°
10		2.21e-4
12		1.47e-3
13		2.94e-3
14		5.23e-3
15		8.92e-3
20		4.19e-2
30	1.44e-5	1.55e-1
33	2.86e-5	
37	1.09e-4	
40	1.89e-4	2.74e-1
50	7.22e-4	
60	1.68e-3	
80	4.09e-3	
100	7.34e-3	
120	9.22e-3	
140	1.05e-2	
150	1.33e-2	
170	1.57e-2	
200	1.90e-2	
250	2.18e-2	
300	2.59e-2	
400	2.45e-2	
500	2.48e-2	
600	2.86e-2	4.96e-1

Energy reflection coefficient of Au backscattered from Au  
ne=24, na= 2

$E_0$ (eV)	0°	65°
10		5.30e-5
12		3.57e-4
13		7.09e-4
14		1.29e-3
15		2.22e-3
20		1.13e-2
30	7.91e-7	4.73e-2
33	1.92e-6	
37	6.14e-6	
40	1.09e-5	9.06e-2
50	4.28e-5	
60	1.04e-4	
80	2.55e-4	
100	4.48e-4	
120	4.47e-4	
140	5.23e-4	
150	6.71e-4	
170	8.79e-4	
200	9.23e-4	
250	9.22e-4	
300	9.99e-4	
400	8.09e-4	
500	9.82e-4	
600	1.44e-3	1.95e-1

Average depth (mean range) in Å of Au implanted in Au  
ne=24, na= 2

$E_0$ (eV)	0°	65°
10		1.97e-1
12		2.23e-1
13		2.41e-1
14		2.63e-1
15		2.78e-1
20		3.62e-1
30	1.80e+0	5.63e-1
33	1.93e+0	
37	2.25e+0	
40	2.55e+0	7.84e-1
50	2.93e+0	
60	3.27e+0	
80	3.85e+0	
100	4.31e+0	
120	4.74e+0	
140	5.13e+0	
150	5.31e+0	
170	5.65e+0	
200	6.10e+0	
250	6.82e+0	
300	7.53e+0	
400	8.65e+0	
500	9.42e+0	
600	1.00e+1	6.81e+0

## Au → Au

Backward sputtering, forward sputtering, transmission, backscattering  
 $z1=79$ ,  $m1=196.97$ ,  $z2=79$ ,  $m2=196.97$ ,  $sbe=3.80$  eV,  $\rho=19.31$  g/cm\*\*3  
 $ef=3.75$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
 $e0=2.3e+8$  eV,  $dx=1000$  Å  
program: trvrmc95  
na= 3

$\alpha$ (degree)	Y	$Y_E$	YT	$YT_E$	$T_N$	$T_E$	$R_N$	$R_E$
0	1.52e+0	1.26e-5	1.61e+0	9.28e-5	1.00e-0	9.90e-1		
45	1.89e+0	6.69e-5	2.00e+0	1.41e-4	1.00e-0	9.86e-1	9.99e-6	3.86e-6
70	3.93e+0	2.12e-4	4.09e+0	2.77e-4	1.00e-0	9.71e+0	2.60e-4	1.59e-4

## Kr → Hg

Sputtering yield of Hg by Kr  
 $z1=36$ ,  $m1=83.80$ ,  $z2=80$ ,  $m2=200.59$ ,  $sbe=6.36$  eV,  $\rho=13.60$  g/cm\*\*3  
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program : IPP 9/82  
ne=13, na=12

$E_0$ (eV)	0°	10°	20°	30°	40°	45°	50°	60°	70°	75°	80°	85°
50	8.75e-3											
100	9.07e-2											
200	2.85e-1											
500	7.62e-1											
762	1.06e-0	1.10e-0	1.23e-0	1.43e-0	1.66e-0	1.77e-0	1.88e-0	1.99e-0	1.77e-0	1.42e-0	8.30e-1	1.45e-1
1000	1.27e-0											
2000	1.92e-0											
5000	2.88e-0											
10000	3.65e-0											
20000	4.33e-0											
50000	4.95e-0											
100000	4.92e-0											
200000	4.69e-0											

Sputtered energy of Hg by Kr  
program :  
ne=13, na=12

$E_0$ (eV)	0°	10°	20°	30°	40°	45°	50°	60°	70°	75°	80°	85°
50	6.92e-4											
100	6.52e-3											
200	1.56e-2											
500	2.59e-2											
762	2.87e-2	3.02e-2	3.72e-2	4.89e-2	6.68e-2	7.86e-2	9.10e-2	1.15e-1	1.28e-1	1.15e-1	7.53e-2	1.11e-2
1000	2.93e-2											
2000	2.97e-2											
5000	2.68e-2											
10000	2.31e-2											
20000	1.88e-2											
50000	1.31e-2											
100000	8.76e-3											
200000	5.83e-3											

# Kr → Hg

Particle reflection coefficient of Kr backscattered from Hg  
 z1=36, m1= 83.80, z2=80, m2=200.59, sbe=6.36 eV, rho=13.60 g/cm\*\*3  
 ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program :  
 ne=13, na=12

$E_0$ (eV)	0°	10°	20°	30°	40°	45°	50°	60°	70°	75°	80°	85°
50	3.49e-1											
100	3.09e-1											
200	2.65e-1											
500	2.22e-1											
762	2.02e-1	2.14e-1	2.29e-1	2.60e-1	3.13e-1	3.48e-1	3.85e-1	4.91e-1	6.50e-1	7.60e-1	8.90e-1	9.94e-1
1000	1.99e-1											
2000	1.74e-1											
5000	1.50e-1											
10000	1.33e-1											
20000	1.19e-1											
50000	9.58e-2											
100000	7.67e-2											
200000	5.52e-2											

Energy reflection coefficient of Kr backscattered from Hg  
 ne=13, na=12

$E_0$ (eV)	0°	10°	20°	30°	40°	45°	50°	60°	70°	75°	80°	85°
50	5.76e-2											
100	5.17e-2											
200	4.41e-2											
500	3.60e-2											
762	3.15e-2	3.49e-2	4.14e-2	5.38e-2	7.82e-2	9.71e-2	1.19e-1	1.96e-1	3.43e-1	4.74e-1	6.73e-1	9.15e-1
1000	3.14e-2											
2000	2.66e-2											
5000	2.28e-2											
10000	2.03e-2											
20000	1.83e-2											
50000	1.49e-2											
100000	1.17e-2											
200000	8.72e-3											

Average depth (mean range) in Å of Kr implanted in Hg  
 ne=13, na=12

$E_0$ (eV)	0°	10°	20°	30°	40°	45°	50°	60°	70°	75°	80°	85°
50	8.31e+0											
100	1.02e+1											
200	1.27e+1											
500	1.75e+1											
762	2.09e+1	2.07e+1	2.04e+1	1.97e+1	1.91e+1	1.86e+1	1.82e+1	1.73e+1	1.65e+1	1.60e+1	1.54e+1	1.43e+1
1000	2.35e+1											
2000	3.17e+1											
5000	4.94e+1											
10000	7.18e+1											
20000	1.09e+2											
50000	1.92e+2											
100000	3.18e+2											
200000	5.43e+2											

## H → U

Sputtering yield of U by H

```

z1= 1, m1= 1.01, z2=92, m2=238.03, sbe=5.42 eV, rho=19.07 g/cm***3
ef=0.95 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : testvmcx, IPP 9/82
ne= 1, na= 8

```

E <sub>0</sub> (eV)	0°	30°	45°	60°	70°	80°	85°	87°
2000	4.13e-3	5.01e-3	5.78e-3	8.53e-3	1.24e-2	2.20e-2	2.38e-2	1.35e-2

Sputtered energy of U by H

```

program : testvmcx
ne= 1, na= 8

```

E <sub>0</sub> (eV)	0°	30°	45°	60°	70°	80°	85°	87°
2000	1.29e-5	1.62e-5	1.85e-5	2.71e-5	3.99e-5	7.36e-5	9.37e-5	5.75e-5

Particle reflection coefficient of H backscattered from U

```

z1= 1, m1= 1.01, z2=92, m2=238.03, sbe=5.42 eV, rho=19.07 g/cm***3
ef=0.95 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : testvmcx
ne= 1, na= 8

```

E <sub>0</sub> (eV)	0°	30°	45°	60°	70°	80°	85°	87°
2000	4.55e-1	4.96e-1	5.49e-1	6.26e-1	6.91e-1	7.79e-1	8.72e-1	9.50e-1

Energy reflection coefficient of H backscattered from U

```

ne= 1, na= 8

```

E <sub>0</sub> (eV)	0°	30°	45°	60°	70°	80°	85°	87°
2000	2.44e-1	2.79e-1	3.28e-1	4.08e-1	4.86e-1	6.13e-1	7.63e-1	8.95e-1

Average depth (mean range) in Å of H implanted in U

```

ne= 1, na= 8

```

E <sub>0</sub> (eV)	0°	30°	45°	60°	70°	80°	85°	87°
2000	2.81e+2	2.75e+2	2.68e+2	2.61e+2	2.56e+2	2.54e+2	2.53e+2	2.53e+2

## He → U

Sputtering yield of U by He  
 $z_1 = 2, m_1 = 4.00, z_2 = 92, m_2 = 238.03, sbe = 5.42 \text{ eV}, \rho = 19.07 \text{ g/cm}^{**3}$   
 $ef = 0.50 \text{ eV}, esb = 0.00 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1 \text{ (KrC)}$   
 program : IPP 9/82  
 $ne = 12, na = 1$

$E_0(\text{eV})$	$0^\circ$
200	5.40e-3
300	1.63e-2
500	2.27e-2
1000	4.45e-2
3000	6.40e-2
5000	6.54e-2
10000	5.94e-2
30000	4.57e-2
50000	3.12e-2
75000	2.59e-2
100000	2.09e-2
200000	1.26e-2

## Ne → U

Sputtering yield of U by Ne  
 $z_1 = 10, m_1 = 20.18, z_2 = 92, m_2 = 238.03, sbe = 5.42 \text{ eV}, \rho = 19.07 \text{ g/cm}^{**3}$   
 $ef = 0.50 \text{ eV}, esb = 0.00 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1 \text{ (KrC)}$   
 program : IPP 9/82  
 $ne = 13, na = 1$

$E_0(\text{eV})$	$0^\circ$
50	7.30e-3
100	7.56e-2
300	2.96e-1
500	4.26e-1
1000	6.46e-1
2000	8.72e-1
3000	9.97e-1
5000	1.17e-0
10000	1.28e-0
30000	1.34e-0
100000	9.68e-1
300000	5.84e-1
500000	5.12e-1

## Ar → U

Sputtering yield of U by Ar  
 $z_1 = 10, m_1 = 20.18, z_2 = 92, m_2 = 238.03, sbe = 5.42 \text{ eV}, \rho = 19.07 \text{ g/cm}^{**3}$   
 $ef = 0.50 \text{ eV}, esb = 0.00 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1 \text{ (KrC)}$   
 program : IPP 9/82  
 $ne = 11, na = 1$

$E_0(\text{eV})$	$0^\circ$
50	2.22e-2
100	1.37e-1
300	5.07e-1
1000	1.19e-0
3000	2.00e-0
10000	2.77e-0
30000	3.08e-0
34300	3.05e-0
100000	2.77e-0
300000	2.10e-0
500000	1.54e-0

# Kr → U

Sputtering yield of U by Kr

$z1=36$ ,  $m1=83.80$ ,  $z2=92$ ,  $m2=238.03$ ,  $sbe=5.42$  eV,  $\rho=19.07$  g/cm<sup>3</sup>  
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program : IPP 9/82  
ne=12, na=15

$E_0$ (eV)	0°	15°	20°	30°	45°	50°	55°	60°	65°	70°	75°	80°
50	1.93e-2											
100	1.48e-1											
300	6.78e-1											
1000	1.70e-0											
3000	3.09e-0											
10000	4.67e-0											
17900	5.76e-0	5.88e-0	6.26e-0	6.97e-0	9.15e-0	1.01e+1	1.04e+1	1.11e+1	1.21e+1	1.23e+1	1.20e+1	1.05e+1
17930	5.47e-0											
30000	6.12e-0											
100000	6.37e-0											
300000	5.80e-0											
500000	4.93e-0											

$E_0$ (eV)	82.5°	85°	87.5°
17900	8.78e+0	5.96e+0	1.26e-0

Sputtered energy of U by Kr

program :  
ne= 1, na=15

$E_0$ (eV)	0°	15°	20°	30°	45°	50°	55°	60°	65°	70°	75°	80°
17900	2.25e-2	2.48e-2	2.83e-2	3.61e-2	5.73e-2	6.64e-2	8.00e-2	8.98e-2	1.03e-1	1.13e-1	1.25e-1	1.27e-1

$E_0$ (eV)	82.5°	85°	87.5°
17900	1.11e-1	7.55e-2	1.41e-2

Particle reflection coefficient of Kr backscattered from U

$z1=36$ ,  $m1=83.80$ ,  $z2=92$ ,  $m2=238.03$ ,  $sbe=5.42$  eV,  $\rho=19.07$  g/cm<sup>3</sup>  
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program :  
ne= 1, na=15

$E_0$ (eV)	0°	15°	20°	30°	45°	50°	55°	60°	65°	70°	75°	80°
17900	1.60e-1	1.71e-1	1.63e-1	1.93e-1	2.51e-1	2.94e-1	3.18e-1	3.87e-1	4.28e-1	4.97e-1	5.61e-1	6.57e-1

$E_0$ (eV)	82.5°	85°	87.5°
17900	7.32e-1	8.47e-1	9.86e-1

Energy reflection coefficient of Kr backscattered from U

ne= 1, na=15

$E_0$ (eV)	0°	15°	20°	30°	45°	50°	55°	60°	65°	70°	75°	80°
17900	3.09e-2	3.13e-2	3.25e-2	4.23e-2	7.14e-2	8.80e-2	1.07e-1	1.42e-1	1.79e-1	2.27e-1	2.96e-1	4.07e-1

$E_0$ (eV)	82.5°	85°	87.5°
17900	6.99e-1	8.05e-1	9.34e-1

Average depth (mean range) in Å of Kr implanted in U

ne= 1, na=15

$E_0$ (eV)	0°	15°	20°	30°	45°	50°	55°	60°	65°	70°	75°	80°
17900	8.13e+1	8.29e+1	8.09e+1	7.81e+1	7.14e+1	6.90e+1	6.72e+1	6.58e+1	6.19e+1	6.03e+1	5.91e+1	5.87e+1

$E_0$ (eV)	82.5°	85°	87.5°
17900	5.70e+1	5.51e+1	4.83e+1

## Xe → U

Sputtering yield of U by Xe  
 $z_1=54$ ,  $m_1=131.30$ ,  $z_2=92$ ,  $m_2=238.03$ ,  $sbe=5.42$  eV,  $\rho=19.07$  g/cm\*\*3  
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program : IPP 9/82  
ne=12, na= 1

$E_0$ (eV)	0°
50	6.30e-3
70	3.26e-2
100	1.01e-1
200	3.72e-1
300	6.33e-1
1000	1.80e-0
3000	3.41e-0
10000	5.35e-0
30000	7.58e-0
100000	8.62e-0
300000	8.98e-0
500000	8.13e-0

## Rn → U

Sputtering yield of U by Rn  
 $z_1=86$ ,  $m_1=222.00$ ,  $z_2=92$ ,  $m_2=238.03$ ,  $sbe=5.42$  eV,  $\rho=19.07$  g/cm\*\*3  
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program : IPP 9/82  
ne=12, na= 1

$E_0$ (eV)	0°
50	9.00e-4
70	9.70e-3
100	4.05e-2
150	1.37e-1
200	2.47e-1
300	4.69e-1
1000	1.62e-0
3000	3.30e-0
10000	5.85e-0
30000	8.55e-0
100000	1.12e+1
300000	1.25e+1

# U → U

Sputtering yield of U by U

```

z1=92, m1=238.03, z2=92, m2=238.03, sbe=5.42 eV, rho=19.07 g/cm**3
ef=5.37 eV, esb=5.42 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : IPP 9/82
ne=11, na= 1

```

$E_0$ (eV)	$0^\circ$
70	1.32e-2
100	4.84e-2
150	1.38e-1
200	2.58e-1
300	4.60e-1
500	8.84e-1
1000	1.64e-0
3000	3.35e-0
10000	6.06e-0
30000	8.50e-0
100000	1.14e+1

Sputtered energy of U by U

```

program : trspvmc
ne= 7, na= 1

```

$E_0$ (eV)	$ca=1.00$	$ca=1.15$
	$0^\circ$	$0^\circ$
70	7.78e-4	1.02e-3
100	2.28e-3	3.59e-3
200	9.19e-3	1.26e-2
500	1.95e-2	2.68e-2
1000	2.56e-2	3.40e-2
3000	2.84e-2	3.59e-2
10000	2.63e-2	2.90e-2

Particle reflection coefficient of U backscattered from U

```

z1=92, m1=238.03, z2=92, m2=238.03, sbe=5.42 eV, rho=19.07 g/cm**3
ef=5.37 eV, esb=5.42 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program : trspvmc
ne= 7, na= 1

```

$E_0$ (eV)	$ca=1.00$	$ca=1.15$
	$0^\circ$	$0^\circ$
70	6.60e-4	1.42e-3
100	2.90e-3	5.40e-3
200	1.26e-2	1.54e-2
500	2.15e-2	2.62e-2
1000	2.66e-2	3.17e-2
3000	2.74e-2	3.30e-2
10000	2.23e-2	2.29e-2

Energy reflection coefficient of U backscattered from U

```

ne= 7, na= 1

```

$E_0$ (eV)	$ca=1.00$	$ca=1.15$
	$0^\circ$	$0^\circ$
70	3.46e-5	1.18e-4
100	1.38e-4	3.09e-4
200	5.83e-4	8.48e-4
500	8.93e-4	1.19e-3
1000	1.15e-3	1.30e-3
3000	1.09e-3	1.25e-3
10000	7.81e-4	9.25e-4

Average depth (mean range) in Å of U implanted in U  
ne= 7, na= 1

$E_0$ (eV)	$ca=1.00$	$ca=1.15$
	$0^\circ$	$0^\circ$
70	3.83e+0	2.35e+0
100	4.61e+0	2.95e+0
200	6.46e+0	4.38e+0
500	9.93e+0	7.18e+0
1000	1.38e+1	1.02e+1
3000	2.30e+1	1.73e+1
10000	4.11e+1	3.28e+1

## Compound targets

# O → BeO

Sputtering yield of BeO by O

$z1 = 8, m1 = 16.00$

$z2 = 4 (0.50), 8 (0.50), m2 = 9.01, 16.00, sbe = 6.33 \text{ eV}, rho = 3.01 \text{ g/cm}^{**3}$

$ef = 6.30 \text{ eV}, esb = 6.33 \text{ eV}, ca = 1.00, kk0 = kk0r = 2, kddee1 = kddee2 = 3, ipot = ipotr = 1$  (KrC)

program: trspvmcx, IPP 9/82

only low fluence!

$ne = 10, na = 17$

Be

$E_0$ (eV)	0°	10°	20°	30°	40°	50°	55°	60°	62.5°	65°	67.5°	70°
100	1.23e-2											
140	2.66e-2											
200	5.03e-2	6.00e-2	1.01e-1	1.62e-1	2.52e-1	3.58e-1	3.95e-1	4.22e-1	5.87e-1	3.96e-1	3.37e-1	
300	8.18e-2	9.59e-2	1.39e-1	2.19e-1	3.35e-1	4.75e-1	5.34e-1	5.82e-1		5.78e-1	5.02e-1	
500	1.31e-1	1.44e-1	1.99e-1	2.87e-1	4.23e-1	6.24e-1		7.94e-1		8.36e-1	7.95e-1	
1000	1.92e-1	2.11e-1	2.66e-1	3.71e-1	5.38e-1	7.78e-1			1.07e-0	1.18e-0	1.24e-0	1.26e-0
2000	2.40e-1											
3000	2.54e-1	2.84e-1	3.36e-1	4.33e-1	6.12e-1	8.96e-1			1.29e-0		1.56e-0	
5000	2.64e-1											1.81e-0
10000	2.35e-1											

Be

$E_0$ (eV)	72.5°	75°	77.5°	80°	85°
200		2.40e-1		1.27e-1	6.18e-2
300		3.66e-1		1.82e-1	6.02e-2
500		5.90e-1		2.99e-1	6.81e-2
1000	1.20e-0	1.11e-0	9.21e-1	6.52e-1	1.05e-1
3000		1.98e-0		1.76e-0	4.68e-1

O

$E_0$ (eV)	0°	10°	20°	30°	40°	50°	55°	60°	62.5°	65°	67.5°	70°
100	5.77e-3											
140	1.46e-2											
200	2.89e-2	3.45e-2	6.70e-2	1.20e-1	2.05e-1	3.11e-1	3.55e-1	3.75e-1		3.61e-1	3.05e-1	
300	5.05e-2	6.61e-2	1.01e-1	1.70e-1	2.80e-1	4.23e-1	5.03e-1	5.22e-1	5.35e-1	5.30e-1	4.64e-1	
500	8.35e-2	9.99e-2	1.41e-1	2.35e-1	3.63e-1	5.48e-1		7.31e-1		7.77e-1	7.56e-1	
1000	1.35e-1	1.51e-1	1.96e-1	2.93e-1	4.52e-1	6.88e-1		9.70e-1		1.09e-0	1.14e-0	1.19e-0
2000	1.81e-1											
3000	1.96e-1	2.01e-1	2.57e-1	3.54e-1	5.09e-1	7.55e-1		1.16e-0		1.43e-0		1.70e-0
5000	2.08e-1											
10000	1.88e-1											

O

$E_0$ (eV)	72.5°	75°	77.5°	80°	85°
200		2.11e-1		1.15e-1	4.86e-2
300		3.29e-1		1.62e-1	5.45e-2
500		5.70e-1		2.72e-1	5.75e-2
1000	1.16e-0	1.06e-0	8.84e-1	6.28e-1	9.22e-2
3000		1.88e-0		1.70e-0	4.46e-1

# O → BeO

Sputtered energy of BeO by O

```

z1= 8, m1= 16.00
z2= 4 (0.50), 8 (0.50), m2= 9.01, 16.00, sbe=6.33 eV, rho=3.01 g/cm**3
ef=6.30 eV, esb=6.33 eV, ca=1.00, kk0=kk0r=2, kddee1=kddee2=3, ipot=ipotr=1 (KrC)
program: trspvmcx
only low fluence!
ne=10, na=17
Be

```

$E_0$ (eV)	0°	10°	20°	30°	40°	50°	55°	60°	62.5°	65°	67.5°	70°
100	2.42e-4											
140	5.17e-4											
200	8.67e-4	1.20e-3	3.08e-3	7.32e-3	1.63e-2	3.20e-2	4.22e-2	4.91e-2	6.01e-2	5.39e-2	5.15e-2	
300	1.25e-3	1.84e-3	3.76e-3	8.19e-3	1.84e-2	3.50e-2	4.64e-2	5.46e-2		6.44e-2	6.32e-2	
500	1.73e-3	2.27e-3	3.96e-3	8.84e-3	1.80e-2	3.27e-2				5.61e-2	6.71e-2	7.34e-2
1000	1.94e-3	2.44e-3	4.13e-3	8.12e-3	1.53e-2	2.88e-2				5.00e-2		
2000	1.83e-3										6.23e-2	
3000	1.62e-3	1.75e-3	3.14e-3	5.54e-3	1.02e-2	1.94e-2				3.56e-2		
5000	1.38e-3										4.68e-2	
10000	9.05e-4											6.10e-2

Be

$E_0$ (eV)	72.5°	75°	77.5°	80°	85°
200		4.03e-2		2.12e-2	9.60e-3
300		4.79e-2		2.59e-2	7.87e-3
500		5.81e-2		3.29e-2	7.49e-3
1000	7.29e-2	7.19e-2	6.25e-2	4.62e-2	7.34e-3
3000		6.57e-2		6.28e-2	1.96e-2

O

$E_0$ (eV)	0°	10°	20°	30°	40°	50°	55°	60°	62.5°	65°	67.5°	70°
100	2.42e-4											
140	5.17e-4											
200	8.67e-4	1.20e-3	3.08e-3	7.32e-3	1.63e-2	3.20e-2	4.22e-2	4.91e-2	6.01e-2	5.39e-2	5.15e-2	
300	1.25e-3	1.84e-3	3.76e-3	8.19e-3	1.84e-2	3.50e-2	4.64e-2	5.46e-2		6.44e-2	6.32e-2	
500	1.73e-3	2.27e-3	3.96e-3	8.84e-3	1.80e-2	3.27e-2				5.61e-2	6.71e-2	7.34e-2
1000	1.94e-3	2.44e-3	4.13e-3	8.12e-3	1.53e-2	2.88e-2				5.00e-2		
2000	1.83e-3										6.23e-2	
3000	1.62e-3	1.75e-3	3.14e-3	5.54e-3	1.02e-2	1.94e-2				3.56e-2		
5000	1.38e-3									4.68e-2		
10000	9.05e-4										6.10e-2	

O

$E_0$ (eV)	72.5°	75°	77.5°	80°	85°
200		3.97e-2		2.28e-2	9.63e-3
300		5.07e-2		2.63e-2	8.03e-3
500		6.52e-1		3.54e-2	7.93e-3
1000	7.97e-2	7.67e-2	6.97e-2	5.43e-2	8.87e-3
3000		7.15e-2		7.21e-2	2.43e-2

# $O \rightarrow BeO$

Particle reflection coefficient of O backscattered from  
 $z1 = 8$ ,  $m1 = 16.00$   
 $z2 = 4$  (0.50), 8 (0.50),  $m2 = 9.01$ , 16.00,  $sbe = 6.33$  eV,  $\rho = 3.01$  g/cm\*\*3  
 $ef = 6.30$  eV,  $esb = 6.33$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: trspvmcx, IPP 9/82  
*only low fluence!*  
 $ne = 10$ ,  $na = 17$

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$55^\circ$	$60^\circ$	$62.5^\circ$	$65^\circ$	$67.5^\circ$	$70^\circ$
100	4.70e-4											
140	1.04e-3											
200	1.33e-3	2.78e-3	7.98e-3	2.40e-2	5.98e-2	1.50e-1	2.28e-1	3.33e-1	3.52e-1	4.64e-1	4.18e-1	6.26e-1
300	2.17e-3	3.60e-3	8.90e-3	2.43e-2	5.76e-2	1.29e-1	1.92e-1	2.85e-1		3.42e-1	3.42e-1	5.79e-1
500	3.35e-3	4.10e-3	8.80e-3	2.04e-2	4.68e-2	1.03e-1		2.29e-1		2.46e-1		4.82e-1
1000	3.05e-3	2.80e-3	5.70e-3	1.54e-2	3.45e-2	7.77e-2		1.75e-1		3.02e-1		3.66e-1
2000	1.60e-3											
3000	1.30e-3	2.40e-3	4.60e-3	9.20e-3	2.19e-2	5.05e-2		1.13e-1		1.76e-1		2.59e-1
5000	1.50e-3											
10000	6.00e-4											

$E_0$ (eV)	$72.5^\circ$	$75^\circ$	$77.5^\circ$	$80^\circ$	$85^\circ$
200		7.84e-1		9.08e-1	9.70e-1
300		7.60e-1		9.12e-1	9.82e-1
500		6.89e-1		8.87e-1	9.86e-1
1000	4.52e-1	5.48e-1	6.68e-1	7.95e-1	9.84e-1
3000		3.72e-1		5.77e-1	9.22e-1

Energy reflection coefficient of O backscattered from  
*only low fluence!*  
 $ne = 10$ ,  $na = 17$

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$55^\circ$	$60^\circ$	$62.5^\circ$	$65^\circ$	$67.5^\circ$	$70^\circ$
100	3.04e-5											
140	6.79e-5											
200	6.65e-5	2.05e-4	7.18e-4	2.97e-3	1.06e-2	3.74e-2	6.76e-2	1.19e-1	1.32e-1	1.98e-1	1.76e-1	3.21e-1
300	1.06e-4	1.98e-4	7.34e-4	2.58e-3	9.50e-3	2.96e-2	5.37e-2	9.73e-2		1.30e-1	1.30e-1	2.95e-1
500	1.10e-4	2.20e-4	6.41e-4	1.98e-3	6.80e-3	2.15e-2		7.12e-2	4.72e-2	8.73e-2	1.18e-1	2.33e-1
1000	1.00e-4	1.43e-4	3.83e-4	1.66e-3	4.77e-3	1.43e-2						1.55e-1
2000	1.35e-4											
3000	4.39e-5	8.83e-5	2.54e-4	6.55e-4	2.48e-3	8.56e-3		2.81e-2		5.27e-2		9.43e-2
5000	7.74e-5											
10000	2.07e-5											

$E_0$ (eV)	$72.5^\circ$	$75^\circ$	$77.5^\circ$	$80^\circ$	$85^\circ$
200		4.67e-1		6.27e-1	7.33e-1
300		4.68e-1		6.66e-1	8.05e-1
500		4.21e-1		6.62e-1	8.57e-1
1000	2.20e-1	3.04e-1	4.32e-1	5.82e-1	8.88e-1
3000		1.75e-1		3.64e-1	8.13e-1

Average depth (mean range) in Å of O implanted in  
*only low fluence!*  
 $ne = 10$ ,  $na = 17$

$E_0$ (eV)	$0^\circ$	$10^\circ$	$20^\circ$	$30^\circ$	$40^\circ$	$50^\circ$	$55^\circ$	$60^\circ$	$62.5^\circ$	$65^\circ$	$67.5^\circ$	$70^\circ$
100	4.28e+0											
140	5.51e+0											
200	7.18e+0	7.08e+0	6.70e+0	6.14e+0	5.44e+0	4.69e+0	4.29e+0	3.88e+0	3.48e+0	4.87e+0	7.29e+0	3.12e+0
300	9.66e+0	9.50e+0	9.08e+0	8.29e+0	7.35e+0	6.42e+0	5.87e+0	5.37e+0	5.15e+0	6.02e+0	7.66e+0	4.47e+0
500	1.40e+1	1.38e+1	1.32e+1	1.22e+1	1.08e+1	9.39e+0			1.35e+1	1.26e+1	1.19e+1	6.66e+0
1000	2.38e+1	2.33e+1	2.23e+1	2.06e+1	1.85e+1	1.60e+1			3.30e+1	2.98e+1		1.13e+1
2000	4.14e+1											
3000	5.89e+1	5.79e+1	5.51e+1	5.13e+1	4.61e+1	3.94e+1						2.70e+1
5000	9.25e+1											
10000	1.79e+2											

$E_0$ (eV)	$72.5^\circ$	$75^\circ$	$77.5^\circ$	$80^\circ$	$85^\circ$
200		2.67e+0		2.09e+0	1.60e+0
300		3.91e+0		3.15e+0	2.61e+0
500		6.15e+0		5.21e+0	4.03e+0
1000	1.07e+1	1.03e+1	9.70e+0	9.08e+0	7.28e+0
3000		2.44e+1		2.27e+1	1.88e+1

# H → B<sub>4</sub>C

Sputtering yield of B<sub>4</sub>C by H  
 z1= 1, m1= 1.01, z2= 5 (0.8), 6 (0.2), m2= 10.81, 12.01, alpha=0.00  
 testvmcx: sbe=5.73, 7.42 eV, rho=2.51 g/cm\*\*3, ef=1.00 eV  
 trspvmc: sbe=5.90, 7.40 eV, rho=2.28 g/cm\*\*3, ef=0.90 eV  
 esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx, IPP 9/82, trspvmc  
*only low fluence!*  
 ne=12, na= 1

E <sub>0</sub> (eV)	B	C	B + C	comment
40	3.61e-4	5.35e-5	4.15e-4	
50	1.23e-3	2.19e-4	1.45e-3	
70	2.99e-3	6.41e-4	3.63e-3	
100	5.17e-3	1.32e-3	6.49e-3	
100	5.49e-3	1.09e-3	6.58e-3	trspvmc
200	7.61e-3	1.72e-3	9.33e-3	
300	7.70e-3	1.93e-3	9.63e-3	trspvmc
333	7.93e-3	2.03e-3	9.96e-3	trspvmc
500	7.57e-3	1.83e-3	9.39e-3	
1000	6.40e-3	1.40e-3	7.80e-3	
1000	5.67e-3	1.47e-3	7.14e-3	trspvmc
2000	4.40e-3	1.06e-3	5.46e-3	trspvmc

Sputtered energy of B<sub>4</sub>C by H  
 program: testvmcx, trspvmc  
*only low fluence!*  
 ne=12, na= 1

E <sub>0</sub> (eV)	B	C	B + C	comment
40	1.17e-5	1.37e-6	1.31e-5	
50	5.10e-5	7.62e-6	5.86e-5	
70	1.43e-4	2.80e-5	1.71e-4	
100	2.45e-4	5.89e-5	3.04e-4	
100	2.68e-4	4.60e-5	3.14e-4	trspvmc
200	3.10e-4	5.81e-5	3.68e-4	
300	2.56e-4	6.13e-5	3.17e-4	trspvmc
333	2.45e-4	6.24e-5	3.17e-4	trspvmc
500	1.85e-4	4.22e-5	2.27e-4	
1000	1.01e-4	2.05e-5	1.22e-4	
1000	8.82e-5	2.05e-5	1.09e-4	trspvmc
2000	4.33e-5	1.05e-5	5.38e-5	trspvmc

## H → B<sub>4</sub>C

Particle reflection coefficient of H backscattered from B<sub>4</sub>C  
 z1= 1, m1= 1.01, z2= 5 (0.8), 6 (0.2), m2= 10.81, 12.01, alpha=0.00  
 testvmcx: sbe=5.73, 7.42 eV, rho=2.51 g/cm\*\*3, ef=1.00 eV  
 trspvmc: sbe=5.90, 7.40 eV, rho=2.28 g/cm\*\*3, ef=0.90 eV  
 esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx, trspvmc  
*only low fluence!*  
 ne=12, na= 1

E <sub>0</sub> (eV)	0°	comment
40	3.43e-1	
50	3.22e-1	
70	2.93e-1	
100	2.65e-1	
100	2.63e-1	trspvmc
200	2.09e-1	
300	1.76e-1	trspvmc
333	1.70e-1	trspvmc
500	1.38e-1	
1000	8.57e-2	
1000	8.43e-2	trspvmc
2000	4.35e-2	trspvmc

Energy reflection coefficient of H backscattered from B<sub>4</sub>C  
*only low fluence!*  
 ne=12, na= 1

E <sub>0</sub> (eV)	0°	comment
40	1.57e-1	
50	1.44e-1	
70	1.28e-1	
100	1.12e-1	
100	1.11e-1	trspvmc
200	8.26e-2	
300	6.56e-2	trspvmc
333	6.25e-2	trspvmc
500	4.82e-2	
1000	2.68e-2	
1000	2.62e-2	trspvmc
2000	1.19e-2	trspvmc

Average depth (mean range) in Å of H implanted in B<sub>4</sub>C  
*only low fluence!*  
 ne=12, na= 1

E <sub>0</sub> (eV)	0°	comment
40	1.18e+1	
50	1.40e+1	
70	1.82e+1	
100	2.43e+1	
100	2.67e+1	trspvmc
200	4.31e+1	
300	6.73e+1	trspvmc
333	7.34e+1	trspvmc
500	9.53e+1	
1000	1.76e+2	
1000	1.94e+2	trspvmc
2000	3.58e+2	trspvmc

# D → B<sub>4</sub>C

Sputtering yield of B<sub>4</sub>C by D  
 z1= 1, m1= 2.01, z2= 5 (0.8), 6 (0.2), m2= 10.81, 12.01, sbe=5.73, 7.42 eV, rho=2.51 g/cm\*\*3  
 ef=1.00 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx, IPP 9/82  
*only low fluence!*  
 ne=11, na= 2

E <sub>0</sub> (eV)	B 0°	B 85°	C 0°	C 85°	B + C 0°	B + C 85°
25	1.47e-4		1.90e-5		1.66e-4	
30	7.54e-4		1.02e-4		8.56e-4	
40	2.75e-3		5.28e-4		3.27e-3	
50	4.75e-3		9.73e-4		5.72e-3	
70	8.26e-3		2.07e-3		1.03e-2	
100	1.15e-2		2.71e-3		1.42e-2	
200	1.51e-2		3.50e-3		1.86e-2	
500	1.49e-2		3.67e-3		1.86e-2	
1000	1.34e-2		2.98e-3		1.63e-2	
8000	4.10e-3		1.20e-3		5.30e-3	
100000		3.06e-2		7.54e-3		3.81e-2

Sputtered energy of B<sub>4</sub>C by D  
 program: testvmcx  
*only low fluence!*  
 ne=11, na= 2

E <sub>0</sub> (eV)	B 0°	B 85°	C 0°	C 85°	B + C 0°	B + C 85°
25	6.95e-6		6.72e-7		7.62e-6	
30	4.22e-5		5.13e-6		4.73e-5	
40	1.77e-4		3.04e-5		2.07e-4	
50	3.21e-4		5.82e-5		3.79e-4	
70	5.72e-4		1.39e-4		7.11e-4	
100	7.32e-4		1.50e-4		8.82e-4	
200	7.42e-4		1.55e-4		8.97e-4	
500	4.45e-4		1.04e-4		5.49e-4	
1000	2.46e-4		5.20e-5		2.98e-4	
8000	1.91e-5		2.96e-6		2.21e-5	
100000		5.26e-5		1.04e-5		6.30e-5

# D → B<sub>4</sub>C

Particle reflection coefficient of D backscattered from B<sub>4</sub>C  
 z1= 1, m1= 2.01, z2= 5 (0.8), 6 (0.2), m2= 10.81, 12.01, sbe=5.73, 7.42 eV, rho=2.51 g/cm\*\*3  
 ef=1.00 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx  
*only low fluence!*  
 ne=11, na= 2

E <sub>0</sub> (eV)	0°	85°
25	2.95e-1	
30	2.78e-1	
40	2.54e-1	
50	2.35e-1	
70	2.12e-1	
100	1.92e-1	
200	1.52e-1	
500	1.03e-1	
1000	6.68e-2	
8000	6.40e-3	
100000		2.91e-1

Energy reflection coefficient of D backscattered from B<sub>4</sub>C  
*only low fluence!*  
 ne=11, na= 2

E <sub>0</sub> (eV)	0°	85°
25	1.09e-1	
30	1.02e-1	
40	9.17e-2	
50	8.39e-2	
70	7.42e-2	
100	6.59e-2	
200	5.03e-2	
500	3.20e-2	
1000	1.90e-2	
8000	1.28e-3	
100000		4.05e-2

Average depth (mean range) in Å of D implanted in B<sub>4</sub>C  
*only low fluence!*  
 ne=11, na= 2

E <sub>0</sub> (eV)	0°	85°
25	7.04e+0	
30	8.10e+0	
40	1.02e+1	
50	1.22e+1	
70	1.61e+1	
100	2.17e+1	
200	4.02e+1	
500	9.45e+1	
1000	1.85e+2	
8000	1.29e+3	
100000		9.82e+2

## D → B<sub>4</sub>C

Sputtering yield of B<sub>4</sub>C by D  
z1= 1, m1= 2.01, z2= 5 (0.8), 6 (0.2), m2= 10.81, 12.01, sbe=5.98, 5.98 eV, rho=2.52 g/cm\*\*\*3  
ef=0.90 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdell=kdeel=2=3, ipot=ipotr=1 (KrC)

program: trspvmc  
*only low fluence!*

ne= 3, na= 6

B

E <sub>0</sub> (eV)	0°	30°	45°	60°	75°	85°
100	1.14e-2	1.74e-2	3.19e-2	5.79e-2	6.04e-2	2.50e-3
300	1.46e-2					
500	1.60e-2	2.83e-2	5.35e-2	1.05e-1	2.02e-1	4.03e-2

C

E <sub>0</sub> (eV)	0°	30°	45°	60°	75°	85°
100	2.59e-3	3.84e-3	7.24e-3	1.27e-2	1.43e-2	6.15e-4
300	3.60e-3					
500	3.66e-3	7.95e-3	1.27e-2	2.55e-2	5.39e-2	1.07e-2

B + C

E <sub>0</sub> (eV)	0°	30°	45°	60°	75°	85°
100	1.40e-2	2.12e-2	3.91e-2	7.06e-2	7.47e-2	3.12e-3
300	1.82e-2					
500	1.97e-2	3.63e-2	6.62e-2	1.31e-1	2.56e-1	5.10e-2

Sputtered energy of B<sub>4</sub>C by D

*only low fluence!*

ne= 3, na= 6

B

E <sub>0</sub> (eV)	0°	30°	45°	60°	75°	85°
100	7.56e-4	1.20e-3	2.37e-3	5.00e-3	7.00e-3	3.89e-4
300	5.66e-4					
500	4.57e-4	8.15e-4	1.81e-3	4.42e-3	9.76e-3	3.06e-3

C

E <sub>0</sub> (eV)	0°	30°	45°	60°	75°	85°
100	1.63e-4	2.49e-4	4.95e-4	1.04e-3	1.59e-3	8.50e-5
300	1.37e-4					
500	1.04e-4	2.41e-4	4.43e-4	1.15e-3	2.80e-3	7.48e-4

B + C

E <sub>0</sub> (eV)	0°	30°	45°	60°	75°	85°
100	9.19e-4	1.45e-3	2.87e-3	6.04e-3	8.59e-3	3.12e-3
300	7.03e-4					
500	5.61e-4	1.06e-3	2.25e-3	5.57e-3	1.26e-2	3.81e-3

Particle reflection coefficient of D backscattered from B<sub>4</sub>C

z1= 1, m1= 2.01, z2= 5 (0.8), 6 (0.2), m2= 10.81, 12.01, sbe=5.98, 5.98 eV, rho=2.52 g/cm\*\*\*3  
ef=0.90 eV, esb=1.00 eV, ca=1.00, kk0=kk0r=2, kdell=kdeel=2=3, ipot=ipotr=1 (KrC)

program: trspvmc

*only low fluence!*

ne= 3, na= 6

B

E <sub>0</sub> (eV)	0°	30°	45°	60°	75°	85°
100	1.92e-1	2.49e-1	3.40e-1	4.96e-1	8.18e-1	9.97e-1
300	1.28e-1					
500	1.04e-1	1.51e-1	2.14e-1	3.36e-1	5.55e-1	9.66e-1

Energy reflection coefficient of D backscattered from B<sub>4</sub>C

*only low fluence!*

ne= 3, na= 6

C

E <sub>0</sub> (eV)	0°	30°	45°	60°	75°	85°
100	6.56e-2	9.85e-2	1.56e-1	2.85e-1	6.66e-1	9.58e-1
300	4.14e-2					
500	3.22e-2	5.27e-2	8.58e-2	1.61e-1	3.65e-1	9.17e-1

Average depth (mean range) in Å of D implanted in B<sub>4</sub>C

*only low fluence!*

ne= 3, na= 6

B

E <sub>0</sub> (eV)	0°	30°	45°	60°	75°	85°
100	2.16e+1	2.03e+1	1.88e+1	1.74e+1	1.61e+1	1.46e+1
300	6.43e+1					
500	9.38e+1	8.73e+1	7.90e+1	6.95e+1	6.26e+1	5.89e+1

# He → B<sub>4</sub>C

Sputtering yield of B<sub>4</sub>C by He  
 z1= 2, m1= 4.00, z2= 5 (0.8), 6 (0.2), m2= 10.81, 12.01, sbe=5.73, 7.42 eV, rho=2.51 g/cm\*\*3  
 ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kddee1=kddee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx, IPP 9/82, trspvmc  
*only low fluence!*  
 ne=10, na= 5

B

E <sub>0</sub> (eV)	0°	30°	60°	75°	85°	comment
30	8.92e-4					
40	3.61e-3					
50	8.27e-3					
70	1.65e-2					
100	2.51e-2					
200	4.14e-2					
500	5.70e-2					
800	5.89e-2	1.09e-1	3.77e-1	6.38e-1	3.79e-2	sbe=5.98, 5.98 eV
1000	5.76e-2					
2000	4.72e-2					

C

E <sub>0</sub> (eV)	0°	30°	60°	75°	85°	comment
30	1.45e-4					
40	7.64e-4					
50	1.77e-3					
70	3.57e-3					
100	6.09e-3					
200	9.53e-3					
500	1.26e-2					
800	1.55e-2	2.63e-2	9.33e-2	1.60e-1	8.13e-3	sbe=5.98, 5.98 eV
1000	1.30e-2					
2000	1.21e-2					

B + C

E <sub>0</sub> (eV)	0°	30°	60°	75°	85°	comment
30	1.04e-3					
40	4.37e-3					
50	1.00e-2					
70	2.01e-2					
100	3.12e-2					
200	5.09e-2					
500	6.96e-2					
800	7.44e-2	1.35e-1	4.70e-1	7.98e-1	4.60e-2	sbe=5.98, 5.98 eV
1000	7.06e-2					
2000	5.93e-2					

# $\text{He} \rightarrow \text{B}_4\text{C}$

Sputtered energy of  $\text{B}_4\text{C}$  by He  
 program: testvnmcx, trspvnmc  
*only low fluence!*  
 ne=10, na= 5

B

$E_0$ (eV)	0°	30°	60°	75°	85°	comment
30	6.29e-5					
40	2.73e-4					
50	6.24e-4					
70	1.20e-3					
100	1.66e-3					
200	2.03e-3					
500	1.63e-3					
800	1.35e-3	3.10e-3	1.58e-2	3.24e-2	2.63e-3	sbe=5.98, 5.98 eV
1000	1.18e-3					
2000	6.03e-4					

C

$E_0$ (eV)	0°	30°	60°	75°	85°	comment
30	1.09e-5					
40	5.64e-5					
50	1.20e-4					
70	2.36e-4					
100	4.00e-4					
200	4.78e-4					
500	3.69e-4					
800	3.98e-4	7.38e-4	3.85e-3	7.82e-3	5.22e-4	sbe=5.98, 5.98 eV
1000	2.51e-4					
2000	1.59e-4					

B + C

$E_0$ (eV)	0°	30°	60°	75°	85°	comment
30	7.38e-5					
40	3.29e-4					
50	7.44e-4					
70	1.44e-3					
100	2.06e-3					
200	2.51e-3					
500	2.00e-3					
800	1.75e-3	3.84e-3	1.97e-2	4.02e-2	3.15e-3	sbe=5.98, 5.98 eV
1000	1.43e-3					
2000	7.62e-4					

# He → B<sub>4</sub>C

Particle reflection coefficient of He backscattered from B<sub>4</sub>C  
 z1= 2, m1= 4.00, z2= 5 (0.8), 6 (0.2), m2= 10.81, 12.01, sbe=5.73, 7.42 eV, rho=2.51 g/cm\*\*3  
 ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: testvmcx, trspvmc  
*only low fluence!*  
 ne=10, na= 5

E <sub>0</sub> (eV)	0°	30°	60°	75°	85°
30	2.47e-1				
40	2.12e-1				
50	1.88e-1				
70	1.59e-1				
100	1.33e-1				
200	9.90e-2				
500	6.88e-2				
800	5.18e-2	8.40e-2	2.71e-1	5.16e-1	9.84e-1
1000	4.85e-2				
2000	2.88e-2				

Energy reflection coefficient of He backscattered from B<sub>4</sub>C  
*only low fluence!*  
 ne=10, na= 5

E <sub>0</sub> (eV)	0°	30°	60°	75°	85°
30	5.45e-2				
40	4.64e-2				
50	4.11e-2				
70	3.42e-2				
100	2.86e-2				
200	2.07e-2				
500	1.40e-2				
800	1.07e-2	2.11e-2	1.13e-1	3.19e-1	9.45e-1
1000	9.93e-3				
2000	5.33e-3				

Average depth (mean range) in Å of He implanted in B<sub>4</sub>C  
*only low fluence!*  
 ne=10, na= 5

E <sub>0</sub> (eV)	0°	30°	60°	75°	85°
30	4.41e+0				
40	5.48e+0				
50	6.48e+0				
70	8.43e+0				
100	1.12e+1				
200	1.99e+1				
500	4.52e+1				
800	7.04e+1	6.27e+1	4.76e+1	4.02e+1	2.64e+1
1000	8.73e+1				
2000	1.74e+2				

# C → B<sub>4</sub>C

Sputtering yield of B<sub>4</sub>C by C  
 z1= 6, m1= 12.01, z2= 5 (0.8), 6 (0.2), m2= 10.81, 12.01, sbe=5.98, 5.98 eV, rho=2.52 g/cm\*\*3  
 ef=2.00 eV, esb=2.50 eV, ca=1.00, kk0=kk0r=2, kd0el=kd0e2=3, ipot=ipotr=1 (KrC)  
 program: trspvmc  
*only low fluence!*  
 ne= 4, na= 4

B

E <sub>0</sub> (eV)	0°	60°	70°	80°	comment
150			3.83e-1		sbe=5.90, 7.40 eV, esb=2.60 eV
300			8.30e-1		sbe=5.90, 7.40 eV, esb=2.60 eV
1000	2.10e-1	1.34e-0	1.77e-0	1.07e-0	
3000			2.24e-0		

C

E <sub>0</sub> (eV)	0°	60°	70°	80°	comment
150			8.92e-2		sbe=5.90, 7.40 eV, esb=2.60 eV
300			2.11e-1		sbe=5.90, 7.40 eV, esb=2.60 eV
1000	4.34e-2	3.36e-1	4.47e-1	2.64e-1	
3000			5.36e-	1	

B + C

E <sub>0</sub> (eV)	0°	60°	70°	80°	comment
150			4.72e-1		sbe=5.90, 7.40 eV, esb=2.60 eV
300			1.04e-0		sbe=5.90, 7.40 eV, esb=2.60 eV
1000	2.53e-2	1.68e-0	2.22e-0	1.33e-0	
2000			2.78e-0		

Sputtered energy of B<sub>4</sub>C by C

*only low fluence!*  
 ne= 4, na= 4

B

E <sub>0</sub> (eV)	0°	60°	70°	80°	comment
150			7.00e-2		sbe=5.90, 7.40 eV, esb=2.60 eV
300			9.73e-2		sbe=5.90, 7.40 eV, esb=2.60 eV
1000	3.43e-3	6.47e-2	9.79e-2	7.45e-2	
3000			7.13e-	2	

C

E <sub>0</sub> (eV)	0°	60°	70°	80°	comment
150			1.51e-2		sbe=5.90, 7.40 eV, esb=2.60 eV
300			2.50e-2		sbe=5.90, 7.40 eV, esb=2.60 eV
1000	7.06e-4	1.70e-2	2.55e-2	1.95e-2	
3000			1.94e-2		

B + C

E <sub>0</sub> (eV)	0°	60°	70°	80°	comment
150			8.51e-2		sbe=5.90, 7.40 eV, esb=2.60 eV
300			1.08e-1		sbe=5.90, 7.40 eV, esb=2.60 eV
1000	4.14e-3	8.17e-2	1.23e-1	9.40e-2	
2000			9.07e-2		

# C → B<sub>4</sub>C

Particle reflection coefficient of C backscattered from B<sub>4</sub>C  
 z1= 6, m1= 12.01, z2= 5 (0.8), 6 (0.2), m2= 10.81, 12.01, sbe=5.98, 5.98 eV, rho=2.52 g/cm\*\*3  
 ef=2.00 eV, esb=2.50 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trspvmc  
*only low fluence!*  
 ne= 4, na= 4

E <sub>0</sub> (eV)	0°	60°	70°	80°	comment
150			6.87e-1		esb=2.60 eV
300			5.37e-1		esb=2.60 eV
1000	4.90e-3	1.68e-1	3.36e-1	7.58e-1	
3000			2.38e-1		

Energy reflection coefficient of C backscattered from B<sub>4</sub>C  
*only low fluence!*  
 ne= 4, na= 4

E <sub>0</sub> (eV)	0°	60°	70°	80°	comment
150			3.82e-1		esb=2.60 eV
300			2.75e-1		esb=2.60 eV
1000	1.98e-4	4.76e-2	1.42e-1	5.57e-1	
3000			8.65e-2		

Average depth (mean range) in Å of C implanted in B<sub>4</sub>C  
*only low fluence!*  
 ne= 4, na= 4

E <sub>0</sub> (eV)	0°	60°	70°	80°	comment
150			3.83e+0		esb=2.60 eV
300			6.93e+0		esb=2.60 eV
1000	3.11e+1	1.79e+1	1.49e+1	1.24e+1	
3000			4.10e+1		

# $O \rightarrow B_4C$

Sputtering yield of  $B_4C$  by O  
 $z1 = 8, m1 = 16.00, z2 = 5 (0.8), 6 (0.2), m2 = 10.81, 12.01, sbe = 5.90, 7.40$  eV  
 $\rho_{\text{O}} = 0.85, 1.62, 2.28, 2.52$  g/cm\*\*\*3,  $sbe(\text{average}) = 1.17, 1.28, 2.21, 5.98, 6.05$  eV,  $\alpha = 0.00$   
 $e_f = 2.10$  eV,  $e_{\text{sb}} = 2.60$  eV,  $c_a = 1.00, kk0 = kk0r = 2, kdeel = kdeel2 = 3, ipot = ipotr = 1$  (KrC)  
program: trspvmc  
only low fluence!  
nem = 5, na = 1, n(rho) = 4

B

$\rho(g/cm^{**3})$	0.85	0.85	1.62	2.28	2.28	2.28	2.52
$sbe(eV)$	1.17	2.21	1.28	1.17	2.21	6.05	5.98
$E_0(eV) 0^\circ$	0°	0°	0°	0°	0°	0°	
100							1.03e-2
150	4.12e-1	1.41e-1	5.90e-1	8.32e-1	3.03e-1	2.88e-2	
300	6.19e-1	2.51e-1	8.48e-1	1.29e-0	8.98e-2	5.32e-1	1.02e-1
1000	8.63e-1	4.48e-1	1.17e-0	1.68e-0	2.34e-1	8.48e-1	2.52e-1
3000	9.86e-1	5.52e-1	1.18e-0	1.79e-0	3.13e-1	9.60e-1	3.18e-1

C

$\rho(g/cm^{**3})$	0.85	0.85	1.62	2.28	2.28	2.28	2.52
$sbe(eV)$	1.17	2.21	1.28	1.17	2.21	6.05	5.98
$E_0(eV) 0^\circ$	0°	0°	0°	0°	0°	0°	
100							2.31e-3
150	1.04e-1	3.37e-2	1.38e-1	1.94e-1	7.06e-2	6.12e-3	
300	1.39e-1	5.81e-2	2.26e-1	3.17e-1	2.14e-2	1.20e-1	2.46e-2
1000	1.98e-1	1.10e-1	2.93e-1	4.60e-1	5.02e-2	2.09e-1	5.61e-2
3000	2.76e-1	1.23e-1	3.02e-1	4.39e-1	6.55e-2	2.30e-1	7.04e-2

B + C

$\rho(g/cm^{**3})$	0.85	0.85	1.62	2.28	2.28	2.28	2.52
$sbe(eV)$	1.17	2.21	1.28	1.17	2.21	6.05	5.98
$E_0(eV) 0^\circ$	0°	0°	0°	0°	0°	0°	
100							1.26e-2
150	5.16e-1	1.73e-1	7.28e-1	1.03e-0	3.73e-1	3.48e-2	
300	7.58e-1	3.09e-1	1.07e-0	1.61e-0	1.11e-1	6.51e-1	1.27e-1
1000	1.06e-0	5.58e-1	1.46e-0	2.14e-0	2.84e-1	1.06e-0	3.08e-1
3000	1.26e-0	6.45e-1	1.48e-0	2.23e-0	3.78e-1	1.19e-0	3.88e-1

Sputtered energy of  $B_4C$  by O

only low fluence!

nem = 5, na = 1, n(rho) = 4

B

$\rho(g/cm^{**3})$	0.85	0.85	1.62	2.28	2.28	2.28	2.52
$sbe(eV)$	1.17	2.21	1.28	1.17	2.21	6.05	5.98
$E_0(eV) 0^\circ$	0°	0°	0°	0°	0°	0°	
100							3.96e-4
150	7.37e-3	3.42e-3	1.01e-2	1.36e-2	5.88e-3	9.71e-4	
300	7.85e-3	4.46e-3	9.38e-3	1.32e-2	8.49e-3	2.50e-3	2.69e-3
1000	5.72e-3	4.74e-3	6.52e-3	8.32e-3	6.63e-3	3.90e-3	4.14e-3
3000	5.13e-3	3.71e-3	4.16e-3	5.36e-3	4.36e-3	2.60e-3	2.70e-3

C

$\rho(g/cm^{**3})$	0.85	0.85	1.62	2.28	2.28	2.28	2.52
$sbe(eV)$	1.17	2.21	1.28	1.17	2.21	6.05	5.98
$E_0(eV) 0^\circ$	0°	0°	0°	0°	0°	0°	
100							8.62e-5
150	1.79e-3	8.20e-4	2.07e-3	2.89e-3	1.36e-3	2.04e-4	
300	1.53e-3	9.69e-4	2.48e-3	3.10e-3	1.82e-3	5.17e-4	6.04e-4
1000	1.27e-3	1.25e-3	1.58e-3	1.96e-3	1.66e-3	8.12e-4	8.59e-4
3000	9.54e-4	4.64e-4	8.75e-4	1.51e-3	1.09e-3	6.58e-4	6.01e-4

B + C

$\rho(g/cm^{**3})$	0.85	0.85	1.62	2.28	2.28	2.28	2.52
$sbe(eV)$	1.17	2.21	1.28	1.17	2.21	6.05	5.98
$E_0(eV) 0^\circ$	0°	0°	0°	0°	0°	0°	
100							4.78e-4
150	9.16e-3	4.24e-3	1.22e-2	1.65e-2	7.25e-3	1.18e-3	
300	9.38e-3	5.43e-3	1.19e-2	1.63e-2	1.03e-2	3.02e-3	3.29e-3
1000	6.98e-3	5.99e-3	8.09e-3	1.03e-2	8.30e-3	4.17e-3	4.99e-3
3000	6.08e-3	4.17e-3	5.03e-3	6.87e-3	5.45e-3	3.26e-3	3.30e-3

## O → B<sub>4</sub>C

Average depth (mean range) in Å of O implanted in B<sub>4</sub>C  
z1= 8, m1= 16.00, z2= 5 (0.8), 6 (0.2), m2= 10.81, 12.01, sbe=5.90, 7.40 eV  
rho=0.85, 1.62, 2.28, 2.52 g/cm\*\*3, sbe(average)=1.17, 1.28, 2.21, 5.98, 6.05 eV, alpha=0.00  
ef=2.10 eV, esb=2.60 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
program: trspvmc  
*only low fluence!*  
ne= 5, na= 1, n(rho)= 4

rho(g/cm**3)	0.85	0.85	1.62	2.28	2.28	2.28	2.52
sbe(eV)	1.17	2.21	1.28	1.17	2.21	6.05	5.98
E <sub>0</sub> (eV) 0°	0°	0°	0°	0°	0°	0°	
100							4.89e+0
150	2.23e+1	2.19e+1	1.08e+1	7.51e+0	7.48e+0	7.57e+0	
300	3.59e+1	3.45e+1	1.75e+1	1.24e+1	1.22e+1	1.24e+1	1.08e+1
1000	8.45e+1	8.21e+1	4.18e+1	3.09e+1	2.97e+1	3.07e+1	2.71e+1
3000	2.12e+1	1.95e+2	1.05e+2	7.62e+1	7.36e+1	7.83e+1	6.68e+1

## Ne → B<sub>4</sub>C

Sputtering yield of B<sub>4</sub>C by Ne  
z1=10, m1= 20.18, z2= 5, 6, m2= 10.81, 12.01, sbe=6.06 eV, rho=2.51 g/cm\*\*3  
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
program: IPP 9/82; total yield only!  
*only low fluence!*  
ne= 7, na= 1

B + C

E <sub>0</sub> (eV)	0°
100	8.10e-3
300	1.09e-1
500	1.98e-1
1000	3.34e-1
2000	4.46e-1
5000	5.40e-1
10000	5.41e-1

## $O \rightarrow B_2O_3$

Sputtering yield of  $B_2O_3$  by O  
 $z1 = 8, m1 = 16.00, z2 = 5 (0.4), 8 (0.6), m2 = 10.81, 16.00, sbe = 5.90, 2.50$  eV  
 $\rho = 1.62$  g/cm<sup>3</sup>,  $sbe(\text{average}) = 1.28$  eV,  $\alpha = 0.00$   
 $e_f = 2.10$  eV,  $e_{sb} = 2.60$  eV,  $c_a = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1$  (KrC)  
 program: trspvmc  
*only low fluence!*  
 $n_e = 4, n_a = 1$

$E_0$ (eV)	B	O	B + O
150	3.26e-1	4.27e-1	7.52e-1
300	4.51e-1	6.21e-1	1.07e-0
1000	6.72e-1	8.54e-1	1.53e-0
3000	6.29e-1	9.17e-1	1.55e-0

Sputtered energy of  $B_2O_3$  by O  
*only low fluence!*  
 $n_e = 4, n_a = 1$

$E_0$ (eV)	B	O	B + O
150	5.97e-3	7.21e-3	1.32e-2
300	5.54e-3	7.09e-3	1.26e-2
1000	4.71e-3	4.62e-3	9.33e-3
3000	2.22e-3	2.74e-3	4.95e-3

Average depth (mean range) in Å of O implanted in  $B_2O_3$   
*only low fluence!*  
 $n_e = 4, n_a = 1$

$E_0$ (eV)	$O^{circ}$
150	1.22e+1
300	1.94e+1
1000	4.60e+1
3000	1.13e+2

## O → B(OH)<sub>3</sub>

Sputtering yield of B(OH)<sub>3</sub> by O  
 z1= 8, m1= 16.00, z2= 5 (0.14), 8 (0.43), 1 (0.43), m2= 10.81, 16.00, 1.01  
 sbe=5.90, 2.50, 2.19 eV, sbe(average)=1.22 eV, rho=0.85 g/cm\*\*3, alpha=0.00  
 ef=2.10 eV, esb=2.60 eV, ca=1.00, kk0=kk0r=2, kddee1=kddee2=3, ipot=ipotr=1 (KrC)  
 program: trspvmc  
*only low fluence!*  
 ne= 4, na= 1

E <sub>0</sub> (eV)	B	O	H	B + O + H
150	5.95e-2	1.52e-1	1.89e-1	4.01e-1
300	9.29e-2	2.29e-1	3.62e-1	6.84e-1
1000	1.44e-1	4.07e-1	6.47e-1	1.20e-0
3000	1.32e-1	3.71e-1	7.74e-1	1.28e-0

Sputtered energy of B(OH)<sub>3</sub> by O  
*only low fluence!*  
 ne= 4, na= 1

E <sub>0</sub> (eV)	B	O	H	B + O + H
150	1.40e-3	2.88e-3	3.63e-3	7.91e-3
300	1.46e-3	2.89e-3	4.92e-3	9.27e-3
1000	1.06e-3	2.82e-3	5.67e-3	9.55e-3
3000	1.10e-3	1.20e-3	5.02e-3	7.32e-3

Average depth (mean range) in Å of O implanted in B(OH)<sub>3</sub>  
*only low fluence!*  
 ne= 4, na= 1

E <sub>0</sub> (eV)	O <sup>circ</sup>
150	2.26e+1
300	3.61e+1
1000	8.05e+1
3000	1.97e+2

## $\mu \rightarrow \text{SiO}_2$

Particle reflection coefficient of  $\mu$  backscattered from  $\text{SiO}_2$   
 $z1 = 1$ ,  $m1 = 0.11$ ,  $z2 = 14$ ,  $8$ ,  $m2 = 28.09$ ,  $16.00$ ,  $sbe = 4.70$  eV,  $\rho = 2.20$  g/cm\*\*3  
 $ef = 0.50$  eV,  $esb = 0.00$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
 $10 - 1000$  eV :  $kdee1 = 3$ ,  $1000 - 20000$  eV :  $kdee1 = 4$   
program: trvrmc  
*only low fluence!*  
ne = 8, na = 1

$E_0$ (eV)	$0^{circ}$
10	5.64e-1
100	3.02e-1
500	1.48e-1
1000	8.83e-2
1000	7.88e-2
5000	1.28e-2
10000	5.10e-3
20000	1.70e-3

Energy reflection coefficient of  $\mu$  backscattered from  $\text{SiO}_2$   
*only low fluence!*  
ne = 8, na = 1

$E_0$ (eV)	$0^{circ}$
10	3.16e-1
100	1.25e-1
500	4.79e-2
1000	2.79e-2
1000	2.32e-2
5000	3.58e-3
10000	1.40e-3
20000	5.71e-4

Average depth (mean range) in Å of  $\mu$  implanted in  $\text{SiO}_2$   
*only low fluence!*  
ne = 8, na = 1

$E_0$ (eV)	$0^{circ}$
10	8.03e+0
100	3.11e+1
500	9.03e+1
1000	1.48e+2
1000	1.33e+2
5000	4.50e+2
10000	7.93e+2
20000	1.56e+3

# $H \rightarrow Ti_x C_y$

Sputtering yield of  $Ti_x C_y$  by H  
 $z1 = 1, m1 = 1.01, z2=22 (0.72, 0.6), 6 (0.28,0.4), m2 = 47.90, 12.01, sbe=4.89, 7.40$  eV,  $\rho = 4.93$  g/cm\*\*3  
 $ef=0.98$  eV,  $esb=1.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: trspvnmcx  
*only low fluence!*  
ne= 2, na= 2  
Ti

$E_0$ (eV)	0°	30°	comment
500	6.79e-3		x=0.72, y=0.28
2000		6.06e-3	x=0.60, y=0.40

C

$E_0$ (eV)	0°	30°	comment
500	7.37e-3		x=0.72, y=0.28
2000		6.63e-3	x=0.60, y=0.40

Ti + C

$E_0$ (eV)	0°	30°	comment
500	1.42e-2		x=0.72, y=0.28
2000		1.27e-2	x=0.60, y=0.40

Sputtered energy of  $Ti_x C_y$  by H  
*only low fluence!*  
ne= 2, na= 2  
Ti

$E_0$ (eV)	0°	30°	comment
500	9.28e-5		x=0.72, y=0.28
2000		4.10e-5	x=0.60, y=0.40

C

$E_0$ (eV)	0°	30°	comment
500	2.23e-4		x=0.72, y=0.28
2000		9.23e-5	x=0.60, y=0.40

Ti + C

$E_0$ (eV)	0°	30°	comment
500	3.16e-4		x=0.72, y=0.28
2000		1.33e-4	x=0.60, y=0.40

Particle reflection coefficient of H backscattered from  $Ti_x C_y$   
 $z1 = 1, m1 = 1.01, z2=22 (0.72, 0.6), 6 (0.28,0.4), m2 = 47.90, 12.01, sbe=4.89, 7.40$  eV,  $\rho = 4.93$  g/cm\*\*3  
 $ef=0.98$  eV,  $esb=1.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: trspvnmcx  
*only low fluence!*  
ne= 2, na= 2

$E_0$ (eV)	0°	30°	comment
500	3.79e-1		x=0.72, y=0.28
2000		2.25e-1	x=0.60, y=0.40

Energy reflection coefficient of H backscattered from  $Ti_x C_y$   
*only low fluence!*  
ne= 2, na= 2

$E_0$ (eV)	0°	30°	comment
500	1.92e-1		x=0.72, y=0.28
2000		9.11e-2	x=0.60, y=0.40

Average depth (mean range) in Å of H implanted in  $Ti_x C_y$   
*only low fluence!*  
ne= 2, na= 2

$E_0$ (eV)	0°	30°	comment
500	9.84e+1		x=0.72, y=0.28
2000		2.62e+2	x=0.60, y=0.40

# O → WO<sub>3</sub>

Sputtering yield of WO<sub>3</sub> by O  
 z1= 8, m1= 16.00, z2=74 (0.25), 8 (0.75), m2=183.85, 16.00, sbe=6.28, 6.28 eV, rho=6.47 g/cm\*\*3  
 ef=2.50 eV, esb=2.60 eV, ca=1.00, kk0=kk0r=2, kddee1=kddee2=3, ipot=ipotr=1 (KrC)  
 program: trspvmc  
*only low fluence!*  
 ne=11, na= 4

W

E <sub>0</sub> (eV)	0°	30°	60°	85°	comment
50	7.71e-5				sbe=6.28, 6.28 eV
100	1.68e-3				sbe=6.28, 6.28 eV
200	7.79e-3				sbe=6.28, 6.28 eV
300	1.30e-2				sbe=6.28, 6.28 eV
500	2.29e-2				sbe=6.28, 6.28 eV
500	4.46e-2				sbe=8.68, 2.60 eV
1000	4.61e-2	8.06e-2	1.71e-1	2.38e-2	sbe=6.28, 6.28 eV
1000	6.32e-2	8.75e-2	2.61e-1	3.58e-2	sbe=8.68, 2.60 eV
2000	6.88e-2				sbe=6.28, 6.28 eV
6000	8.87e-2	1.33e-1	3.26e-1	3.63e-1	sbe=6.28, 6.28 eV
6000	1.17e-1	2.04e-1	4.87e-1	4.39e-1	sbe=8.68, 2.60 eV

O

E <sub>0</sub> (eV)	0°	30°	60°	85°	comment
50	3.99e-2				sbe=6.28, 6.28 eV
100	1.18e-1				sbe=6.28, 6.28 eV
200	2.33e-1				sbe=6.28, 6.28 eV
300	3.03e-1				sbe=6.28, 6.28 eV
500	4.05e-1				sbe=6.28, 6.28 eV
500	5.79e-1				sbe=8.68, 2.60 eV
1000	5.43e-1	7.50e-1	1.32e-0	1.88e-1	sbe=6.28, 6.28 eV
1000	7.65e-1	9.86e-1	1.78e-0	2.44e-1	sbe=8.68, 2.60 eV
2000	6.21e-1				sbe=6.28, 6.28 eV
6000	6.70e-1	8.97e-1	1.74e-0	1.67e-0	sbe=6.28, 6.28 eV
6000	8.98e-1	1.24e-0	2.27e-0	1.88e-0	sbe=8.68, 2.60 eV

W + O

E <sub>0</sub> (eV)	0°	30°	60°	85°	comment
50	4.00e-2				
100	1.20e-1				
200	2.41e-1				
300	3.16e-1				
500	4.28e-1				
500	6.24e-1				sbe=8.68, 2.60 eV
1000	5.89e-1	8.31e-1	1.49e-0	2.12e-1	
1000	8.28e-1	1.07e-0	2.04e-0	2.80e-1	sbe=8.68, 2.60 eV
2000	6.90e-1				
6000	7.59e-1	1.03e-0	2.07e-0	2.30e-0	
6000	1.02e-0	1.44e-0	2.76e-0	2.32e-0	sbe=8.68, 2.60 eV

# O → WO<sub>3</sub>

Sputtered energy of WO<sub>3</sub> by O  
only low fluence!

ne=11, na= 4

W

E <sub>0</sub> (eV)	0°	30°	60°	85°	comment
50	2.75e-6				sbe=6.28, 6.28 eV
100	8.06e-5				sbe=6.28, 6.28 eV
200	3.59e-4				sbe=6.28, 6.28 eV
300	4.52e-4				sbe=6.28, 6.28 eV
500	5.74e-4				sbe=6.28, 6.28 eV
500	9.92e-4				sbe=8.68, 2.60 eV
1000	8.91e-4	1.46e-3	4.78e-3	1.43e-3	sbe=6.28, 6.28 eV
1000	1.08e-3	1.61e-3	5.34e-3	1.77e-3	sbe=8.68, 2.60 eV
2000	1.00e-3				sbe=6.28, 6.28 eV
6000	6.27e-4	1.14e-3	3.16e-3	7.22e-3	sbe=6.28, 6.28 eV
6000	5.00e-4	1.98e-3	4.03e-3	8.53e-3	sbe=8.68, 2.60 eV

O

E <sub>0</sub> (eV)	0°	30°	60°	85°	comment
50	6.29e-3				sbe=6.28, 6.28 eV
100	1.33e-2				sbe=6.28, 6.28 eV
200	1.89e-2				sbe=6.28, 6.28 eV
300	2.05e-2				sbe=6.28, 6.28 eV
500	2.21e-2				sbe=6.28, 6.28 eV
500	2.54e-2				sbe=8.68, 2.60 eV
1000	2.01e-2	3.22e-2	8.04e-2	1.60e-2	sbe=6.28, 6.28 eV
1000	2.20e-2	3.48e-2	8.68e-2	1.52e-2	sbe=8.68, 2.60 eV
2000	1.80e-2				sbe=6.28, 6.28 eV
6000	1.34e-2	1.89e-2	4.72e-2	5.44e-2	sbe=6.28, 6.28 eV
6000	1.26e-2	2.10e-2	4.93e-2	4.41e-2	sbe=8.68, 2.60 eV

W + O

E <sub>0</sub> (eV)	0°	30°	60°	85°	comment
50	6.29e-3				
100	1.34e-2				
200	1.93e-2				
300	2.10e-2				
500	2.27e-2				
500	2.64e-2				sbe=8.68, 2.60 eV
1000	2.10e-2	3.37e-2	8.52e-2	1.74e-2	
1000	2.31e-2	3.64e-2	9.21e-2	1.70e-2	sbe=8.68, 2.60 eV
2000	1.90e-2				
6000	1.40e-2	2.00e-2	5.04e-2	6.16e-2	
6000	1.31e-2	2.30e-2	5.33e-2	5.26e-2	sbe=8.68, 2.60 eV

# O → WO<sub>3</sub>

Particle reflection coefficient of O backscattered from WO<sub>3</sub>  
z1= 8, m1= 16.00, z2=74 (0.25), 8 (0.75), m2=183.85, 16.00, sbe=6.28, 6.28 eV, rho=6.47 g/cm\*\*3  
ef=2.50 eV, esb=2.60 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
program: trspvmc  
*only low fluence!*  
ne=11, na= 4

E <sub>0</sub> (eV)	0°	30°	60°	85°	comment
50	1.33e-1				
100	1.30e-1				
200	1.24e-1				
300	1.25e-1				
500	1.18e-1				
500	1.26e-1				
1000	1.10e-1	1.61e-1	3.24e-1	9.72e-1	sbe=8.68, 2.60 eV
1000	1.06e-1	1.51e-1	3.51e-1	9.69e-1	sbe=8.68, 2.60 eV
2000	1.11e-1				
6000	1.01e-1	1.29e-1	2.87e-1	7.73e-1	
6000	9.32e-2	1.22e-1	2.85e-1	7.69e-1	sbe=8.68, 2.60 eV

Energy reflection coefficient of O backscattered from WO<sub>3</sub>  
*only low fluence!*  
ne=11, na= 4

E <sub>0</sub> (eV)	0°	30°	60°	85°	comment
50	5.30e-2				
100	4.87e-2				
200	4.34e-2				
300	4.37e-2				
500	3.97e-2				
500	4.49e-2				
1000	3.77e-2	5.72e-2	1.49e-1	8.97e-1	sbe=8.68, 2.60 eV
1000	3.68e-2	5.49e-2	1.52e-1	8.97e-1	sbe=8.68, 2.60 eV
2000	4.03e-2				
6000	3.53e-2	4.77e-2	1.27e-1	6.43e-1	
6000	3.11e-2	4.99e-2	1.37e-1	6.49e-1	sbe=8.68, 2.60 eV

Average depth (mean range) in Å of O implanted in WO<sub>3</sub>  
*only low fluence!*  
ne=11, na= 4

E <sub>0</sub> (eV)	0°	30°	60°	85°	comment
50	5.30e+0				
100	8.21e+0				
200	1.25e+1				
300	1.63e+1				
500	2.24e+1				
500	2.20e+1				
1000	3.49e+1	3.12e+1	2.38e+1	1.61e+1	sbe=8.68, 2.60 eV
1000	3.39e+1	3.13e+1	2.28e+1	1.59e+1	sbe=8.68, 2.60 eV
2000	5.61e+1				
6000	1.36e+2	1.15e+2	8.40e+1	5.62e+1	
6000	1.26e+2	1.12e+2	8.07e+1	5.43e+1	sbe=8.68, 2.60 eV

## Ne → WO<sub>3</sub>

Sputtering yield of WO<sub>3</sub> by Ne  
 z1=10, m1= 20.18, z2=74 (0.25), 8 (0.75), m2=183.85, 16.00, sbe=6.28, 6.28 eV, rho=6.47 g/cm\*\*3, alpha=0.00  
 ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trspvmc  
*only low fluence!*  
 ne= 5, na= 1

E <sub>0</sub> (eV)	W	O	W + O
100	1.98e-3	1.15e-1	1.17e-1
200	8.51e-3	2.35e-1	2.44e-1
500	2.53e-2	4.58e-1	4.83e-1
1000	4.72e-2	5.89e-1	6.36e-1
5000	1.12e-1	8.36e-1	9.48e-1

Sputtered energy of WO<sub>3</sub> by Ne  
*only low fluence!*  
 ne= 5, na= 1

E <sub>0</sub> (eV)	W	O	W + O
100	1.09e-4	1.25e-2	1.26e-2
200	3.88e-4	1.88e-2	1.92e-2
500	8.86e-4	2.50e-2	2.59e-2
1000	1.04e-3	2.18e-2	2.28e-2
5000	1.04e-3	1.78e-2	1.88e-2

Particle reflection coefficient of Ne backscattered from WO<sub>3</sub>  
 z1=10, m1= 20.18, z2=74 (0.25), 8 (0.75), m2=183.85, 16.00, sbe=6.28, 6.28 eV, rho=6.47 g/cm\*\*3, alpha=0.00  
 ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trspvmc  
*only low fluence!*  
 ne= 5, na= 1

E <sub>0</sub> (eV)	0°
100	1.44e-1
200	1.27e-1
500	1.13e-1
1000	1.06e-1
5000	9.46e-2

Energy reflection coefficient of Ne backscattered from WO<sub>3</sub>  
*only low fluence!*  
 ne= 5, na= 1

E <sub>0</sub> (eV)	0°
100	4.54e-2
200	3.91e-2
500	3.34e-2
1000	3.27e-2
5000	3.16e-2

Average depth (mean range) in Å of Ne implanted in WO<sub>3</sub>  
*only low fluence!*  
 ne= 5, na= 1

E <sub>0</sub> (eV)	0°
100	7.91e+0
200	1.18e+1
500	2.01e+1
1000	3.15e+1
5000	9.92e+1

# Kr → WO<sub>3</sub>

Sputtering yield of WO<sub>3</sub> by Kr  
 z1=36, m1= 83.80, z2=74 (0.25), 8 (0.75), m2=183.85, 16.00, sbe=3.01, 3.01 eV, rho=6.47 g/cm\*\*3, alpha=0.00  
 ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trspvmc  
*only low fluence!*  
 ne= 3, na= 1

E <sub>0</sub> (eV)	W	O	W + O	comment
6000	4.81e-1	2.82e-0	3.30e-0	
10000	5.82e-1	3.26e-0	3.84e-0	
10000	3.38e-1	1.86e-0	2.20e-0	sbe=6.28, 6.28 eV

Sputtered energy of WO<sub>3</sub> by Kr  
*only low fluence!*  
 ne= 3, na= 1

E <sub>0</sub> (eV)	W	O	W + O	comment
6000	1.96e-3	1.82e-2	2.02e-2	
10000	2.21e-3	1.62e-2	1.84e-2	
10000	2.05e-3	1.58e-2	1.79e-2	sbe=6.28, 6.28 eV

Particle reflection coefficient of Kr backscattered from WO<sub>3</sub>  
 z1=36, m1= 83.80, z2=74 (0.25), 8 (0.75), m2=183.85, 16.00, sbe=3.01, 3.01 eV, rho=6.47 g/cm\*\*3, alpha=0.00  
 ef=0.20 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: trspvmc  
*only low fluence!*  
 ne= 3, na= 1

E <sub>0</sub> (eV)	0°	comment
6000	3.50e-2	
10000	4.94e-2	
10000	4.24e-2	sbe=6.28, 6.28 eV

Energy reflection coefficient of Kr backscattered from WO<sub>3</sub>  
*only low fluence!*  
 ne= 3, na= 1

E <sub>0</sub> (eV)	0°	comment
6000	3.02e-3	
10000	3.33e-3	
10000	3.35e-3	sbe=6.28, 6.28 eV

Average depth (mean range) in Å of Kr implanted in WO<sub>3</sub>  
*only low fluence!*  
 ne= 3, na= 1

E <sub>0</sub> (eV)	0°	comment
6000	6.29e+1	
10000	7.68e+1	
10000	8.46e+1	sbe=6.28, 6.28 eV

## $O \rightarrow WO_4$

Sputtering yield of  $WO_4$  by O  
 $z1 = 8, m1 = 16.00, z2 = 74$  (0.20), 8 (0.80),  $m2 = 183.85, 16.00, sbe = 8.68, 2.60$  eV,  $\rho = 6.47$  g/cm\*\*3, alpha=0.00  
 $ef = 2.50$  eV,  $esb = 2.60$  eV, ca=1.00, kk0=kk0r=2, kdell=kdee2=3, ipot=ipotr=1 (KrC)  
program: trspvmc  
*only low fluence!*  
ne= 3, na= 1

$E_0$ (eV)	W	O	W + O
500	3.12e-2	6.69e-1	7.00e-2
1000	5.75e-2	8.71e-1	9.29e-2
6000	8.70e-2	9.22e-1	1.01e-3

Sputtered energy of  $WO_4$  by O  
*only low fluence!*  
ne= 3, na= 1

$E_0$ (eV)	W	O	W + O
500	5.53e-4	2.45e-2	2.51e-2
1000	7.09e-4	2.30e-2	2.37e-2
6000	5.21e-4	1.16e-2	1.21e-2

Particle reflection coefficient of O backscattered from  $WO_4$   
 $z1 = 8, m1 = 16.00, z2 = 74$  (0.20), 8 (0.80),  $m2 = 183.85, 16.00, sbe = 8.68, 2.60$  eV,  $\rho = 6.47$  g/cm\*\*3, alpha=0.00  
 $ef = 2.50$  eV,  $esb = 2.60$  eV, ca=1.00, kk0=kk0r=2, kdell=kdee2=3, ipot=ipotr=1 (KrC)  
program: trspvmc  
*only low fluence!*  
ne= 3, na= 1

$E_0$ (eV)	$0^\circ$
500	1.05e-1
1000	1.03e-1
6000	7.29e-2

Energy reflection coefficient of O backscattered from  $WO_4$   
*only low fluence!*  
ne= 3, na= 1

$E_0$ (eV)	$0^\circ$
500	3.32e-2
1000	3.13e-2
6000	2.37e-2

Average depth (mean range) in Å of O implanted in  $WO_4$   
*only low fluence!*  
ne= 3, na= 1

$E_0$ (eV)	$0^\circ$
500	1.89e+1
1000	2.93e+1
6000	1.16e+2

# $O \rightarrow W_x O_y$

Sputtering yield of  $W_x O_y$  by  $O$   
 $z1 = 8, m1 = 16.00, z2=74$  (x), 8 (y),  $m2=183.85, 16.00, sbe=6.28, 6.28$  eV,  $\rho_{O}=6.47$  g/cm\*\*3, alpha=0.00  
 $ef=2.50$  eV,  $esb=2.60$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: trspvnc  
*only low fluence!*  
ne= 5, na= 1, n(x)=10

W

	x	0.90	0.80	0.75	0.70	0.65	0.60	0.55	0.50	0.40	0.35
E <sub>0</sub> (eV)											
100		2.31e-2	1.76e-2	1.60e-2							
200				5.38e-2	5.25e-2	4.22e-2					
500			1.69e-1		1.15e-1	1.00e-1					
1000							8.81e-2	1.33e-1	8.92e-2		
5000										1.43e-1	

O

	x	0.90	0.80	0.75	0.70	0.65	0.60	0.55	0.50	0.40	0.35
E <sub>0</sub> (eV)											
100		2.89e-2	5.43e-2	6.76e-2							
200				1.35e-1	1.63e-1	1.83e-1					
500			2.00e-1			3.06e-1	3.35e-1	3.67e-1			
1000							4.35e-1	4.55e-1	4.90e-1	5.01e-1	
5000										6.29e-1	

W + O

	x	0.90	0.80	0.75	0.70	0.65	0.60	0.55	0.50	0.40	0.35
E <sub>0</sub> (eV)											
100		5.20e-2	7.19e-2	8.36e-2							
200			3.69e-1	1.89e-1	2.16e-1	2.25e-1					
500					4.21e-1	4.35e-1	4.55e-1				
1000							6.23e-1	5.90e-1			
5000									7.72e-1		

Sputtered energy of  $W_x O_y$  by  $O$   
*only low fluence!*

ne= 5, na= 1, n(x)=10

W

	x	0.90	0.80	0.75	0.70	0.65	0.60	0.55	0.50	0.40	0.35
E <sub>0</sub> (eV)											
100		1.33e-3	9.79e-4	8.69e-4							
200				2.40e-3	2.38e-3	1.91e-3					
500			5.50e-3			3.38e-3	3.06e-3	2.63e-3			
1000							2.90e-3	1.78e-3			
5000									1.23e-3		

O

	x	0.90	0.80	0.75	0.70	0.65	0.60	0.55	0.50	0.40	0.35
E <sub>0</sub> (eV)											
100		4.66e-3	8.69e-3	1.07e-2							
200			1.65e-2	1.61e-2	1.93e-2	2.02e-2					
500					2.40e-2	2.60e-2	2.62e-2				
1000						2.61e-2	2.37e-2				
5000								1.53e-2			

W + O

	x	0.90	0.80	0.75	0.70	0.65	0.60	0.55	0.50	0.40	0.35
E <sub>0</sub> (eV)											
100		5.99e-3	9.67e-3	1.16e-2							
200			2.20e-2	1.85e-2	2.17e-2	2.21e-2					
500					2.74e-2	2.91e-2	2.88e-2				
1000						2.90e-2	2.55e-2				
5000								1.65e-2			

# $O \rightarrow W_x O_y$

Particle reflection coefficient of  $O$  backscattered from  $W_x O_y$   
 $z1=8$ ,  $m1=16.00$ ,  $z2=74$  (x), 8 (y),  $m2=183.85$ , 16.00,  $sbe=6.28$ , 6.28 eV,  $\rho=6.47$  g/cm\*\*3,  $\alpha=0.00$   
 $ef=2.50$  eV,  $esb=2.60$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: trspvnc  
*only low fluence!*  
 $ne=5$ ,  $na=1$ ,  $n(x)=10$

x	0.90	0.80	0.75	0.70	0.65	0.60	0.55	0.50	0.40	0.35
$E_0$ (eV)										
100	4.16e-1	3.66e-1	3.42e-1							
200			3.36e-1	3.08e-1	2.91e-1	2.77e-1	2.56e-1	2.33e-1		
500		3.44e-1							2.16e-1	1.80e-1
1000										1.35e-1
5000										

Energy reflection coefficient of  $O$  backscattered from  $W_x O_y$   
*only low fluence!*  
 $ne=5$ ,  $na=1$ ,  $n(x)=10$

x	0.90	0.80	0.75	0.70	0.65	0.60	0.55	0.50	0.40	0.35
$E_0$ (eV)										
100	1.93e-1	1.64e-1	1.51e-1							
200			1.45e-1	1.31e-1	1.22e-1	1.14e-1	1.03e-1	9.13e-2		
500		1.46e-1							8.24e-2	6.49e-2
1000										5.05e-2
5000										

Average depth (mean range) in Å of  $O$  implanted in  $W_x O_y$   
*only low fluence!*  
 $ne=5$ ,  $na=1$ ,  $n(x)=10$

x	0.90	0.80	0.75	0.70	0.65	0.60	0.55	0.50	0.40	0.35
$E_0$ (eV)										
100	2.78e+1	2.38e+1	2.19e+1							
200			3.15e+1	2.92e+1	2.73e+1	4.53e+1	4.24e+1	3.91e+1		
500		5.38e+1							5.45e+1	4.81e+1
1000										1.35e+2
5000										

## Layered targets

## Ar → Li on Cu

Sputtering yield of Li on Cu by Ar  
 $z_1=18$ ,  $m_1=39.95$

```
layer 1: z2= 3, m2= 6.94, sbe=1.68 eV, rho=0.53 g/cm**3
layer 2: z2=29, m2= 63.54, sbe=3.52 eV, rho=8.95 g/cm**3
ef=0.50 eV, esb=0.00 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program: testvmcx
e0=6000 eV, alpha=0.00, dx(1)=thickness (in Å) of layer 1
only low fluence !
ne=11, n(m2)= 2
```

dx (Å)	Li	Cu
0		3.77e-0
1	2.16e-1	4.74e-0
2	3.49e-1	4.31e-0
4	1.13e-0	2.99e-0
6	1.49e-0	1.44e-0
8	1.58e-0	8.50e-1
10	1.52e-0	4.76e-1
12	1.60e-0	3.77e-1
14	1.57e-0	2.55e-1
20	1.53e-0	1.20e-1
30	1.54e-0	4.73e-2

Sputtered energy of Li on Cu by Ar  
*only low fluence !*  
 $ne=11$ ,  $n(m2)= 2$

dx (Å)	Li	Cu
0		1.62e-2
1	1.95e-3	9.82e-3
2	3.09e-3	8.73e-3
4	4.12e-3	6.05e-3
6	5.43e-3	4.02e-3
8	6.42e-3	3.42e-3
10	6.97e-3	2.42e-3
12	7.79e-3	2.05e-3
14	8.19e-3	1.68e-3
20	8.85e-3	1.05e-3
30	8.91e-3	4.34e-4

## Ar → Li on Cu

Particle reflection coefficient of Ar backscattered from Li on Cu  
 $z_1=18$ ,  $m_1=39.95$   
layer 1:  $z_2=3$ ,  $m_2=6.94$ ,  $sbe=1.68$  eV,  $\rho=0.53$  g/cm $^{**3}$   
layer 2:  $z_2=29$ ,  $m_2=63.54$ ,  $sbe=3.52$  eV,  $\rho=8.95$  g/cm $^{**3}$   
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: testvmcx  
 $e0=6000$  eV,  $\alpha=0.00$ ,  $dx(1)=$ thickness (in Å) of layer 1  
*only low fluence!*  
 $ne=11$ ,  $n(m2)=2$

$dx$ (Å)	$0^\circ$
0	5.80e-2
1	3.72e-2
2	3.35e-2
4	3.83e-2
6	2.80e-2
8	2.68e-2
10	2.83e-2
12	2.92e-2
14	2.97e-2
20	2.42e-2
30	2.09e-2

Energy reflection coefficient of Ar backscattered from Li on Cu  
*only low fluence!*  
 $ne=11$ ,  $n(m2)=2$

$dx$ (Å)	$0^\circ$
0	5.08e-3
1	2.79e-3
2	2.52e-3
4	2.68e-3
6	1.85e-3
8	2.16e-3
10	1.80e-3
12	1.51e-3
14	1.92e-3
20	9.27e-4
30	7.49e-4

Average depth (mean range) in Å of Ar implanted in Li on Cu  
*only low fluence!*  
 $ne=11$ ,  $n(m2)=2$

$dx$ (Å)	$0^\circ$
0	4.50e+1
1	4.65e+1
2	4.62e+1
4	4.86e+1
6	5.06e+1
8	5.14e+1
10	5.50e+1
12	5.57e+1
14	5.75e+1
20	6.33e+1
30	7.24e+1

## Ar → Li on Cu

Sputtering yield of Li on Cu by Ar  
 $z1=18$ ,  $m1=39.95$

layer 1:  $z2=3$ ,  $m2=6.94$ ,  $sbe=1.67$  eV,  $ef=1.65$  eV,  $\rho=4.60e-2$  atoms/ $\text{Å}^{**3}$   
 layer 2:  $z2=29$ ,  $m2=63.54$ ,  $sbe=3.52$  eV,  $ef=3.50$  eV,  $\rho=8.48e-2$  atoms/ $\text{Å}^{**3}$   
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
 program: tridyn (version 3.3), idrel=1 (static)  
 $e0=6000$  eV,  $\alpha=0.00$ ,  $dx(1)=$ thickness (in Å) of layer 1  
*only low fluence!*  
 $ne=15$ ,  $n(m2)=2$

$dx (\text{Å})$	Li	Cu
0		4.01e-0
1.5	1.03e-0	2.89e-0
2	1.36e-0	2.64e-0
3	1.83e-0	2.29e-0
4	2.13e-0	1.98e-0
5	2.46e-0	1.82e-0
5	2.12e-0	1.64e-0
6	2.51e-0	1.51e-0
7.5	2.54e-0	1.19e-0
10	2.43e-0	8.30e-1
12.5	2.27e-0	5.68e-1
15	2.15e-0	4.31e-1
20	2.09e-0	2.54e-1
25	2.09e-0	1.71e-1
30	1.93e-0	1.14e-1

Sputtered energy of Li on Cu by Ar  
*only low fluence!*  
 $ne=15$ ,  $n(m2)=2$

$dx (\text{Å})$	Li	Cu
0		1.77e-2
1.5	2.15e-3	1.27e-2
2	2.95e-3	1.07e-2
3	3.80e-3	1.13e-2
4	5.78e-3	9.55e-3
5	6.57e-3	8.85e-3
5	5.61e-3	8.66e-3
6	6.79e-3	8.28e-3
7.5	7.92e-3	6.75e-3
10	9.21e-3	5.27e-3
12.5	1.10e-2	4.18e-3
15	1.00e-2	2.72e-3
20	1.08e-2	2.38e-3
25	1.20e-2	1.82e-3
30	1.35e-2	9.79e-4

## Ar → Li on Cu

Particle reflection coefficient of Ar backscattered from Li on Cu  
 $z_1=18$ ,  $m_1=39.95$   
layer 1:  $z_2=3$ ,  $m_2=6.94$ ,  $sbe=1.67$  eV,  $ef=1.65$  eV,  $\rho=4.60e-2$  atoms/ $\text{\AA}^{**3}$   
layer 2:  $z_2=29$ ,  $m_2=63.54$ ,  $sbe=3.52$  eV,  $ef=3.50$  eV,  $\rho=8.48e-2$  atoms/ $\text{\AA}^{**3}$   
 $ef=0.50$  eV,  $esb=0.00$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: tridyn (version 3.3), idrel=1 (static)  
 $e0=6000$  eV,  $\alpha=0.00$ ,  $dx(1)=\text{thickness (in \AA) of layer 1}$   
*only low fluence!*  
 $ne=15$ ,  $n(m2)=2$

$dx (\text{\AA})$	$0^\circ$
0	5.60e-3
1.5	4.00e-3
2	3.52e-3
3	3.34e-3
4	4.28e-3
5	3.99e-3
5	3.82e-3
6	3.74e-3
7.5	4.50e-3
10	3.35e-3
12.5	1.89e-3
15	2.15e-3
20	2.09e-3
25	1.93e-3
30	1.03e-3

Energy reflection coefficient of Ar backscattered from Li on Cu  
*only low fluence!*  
 $ne=15$ ,  $n(m2)=2$

$dx (\text{\AA})$	$0^\circ$
0	5.30e-2
1.5	5.20e-2
2	4.20e-2
3	5.20e-2
4	5.50e-2
5	5.70e-2
5	4.90e-2
6	5.70e-2
7.5	4.90e-2
10	4.70e-2
12.5	4.20e-2
15	4.10e-2
20	3.90e-2
25	5.10e-2
30	2.40e-2

Average depth (mean range) in  $\text{\AA}$  of Ar implanted in Li on Cu  
*only low fluence!*  
 $ne=15$ ,  $n(m2)=2$

$dx (\text{\AA})$	$0^\circ$
0	4.40e+1
1.5	4.71e+1
2	4.69e+1
3	4.69e+1
4	4.98e+1
5	4.79e+1
5	4.93e+1
6	4.95e+1
7.5	5.31e+1
10	5.41e+1
12.5	5.62e+1
15	5.94e+1
20	6.25e+1
25	6.66e+1
30	7.09e+1

# D → Li on LiCu

Sputtering yield of Li on LiCu by D  
 $z1 = 1$ ,  $m1 = 2.01$ ,  $ef = 0.20$  eV,  $dns0 = 1.00e-1$  atoms/ $\text{A}^{**3}$   
layer 1:  $z2 = 3$ ,  $m2 = 6.94$ ,  $sbe = 1.67$  eV,  $ef = 1.65$  eV,  $\rho = 4.60e-2$  atoms/ $\text{A}^{**3}$   
layer 2:  $z2 = 3$  (0.24), 29 (0.76),  $m2 = 6.94$ , 63.54,  $sbe = 1.67$ , 3.52 eV,  
 $ef = 1.65$ , 3.50 eV,  $\rho = 4.60e-2$ , 8.48e-2 atoms/ $\text{A}^{**3}$   
 $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: tridyn (version 3.3), idrel=1 (static)  
alpha=0.00, dx(1)=thickness (in A) of layer 1  
*only low fluence!*  
nem = 4, na = 1, n(dx(1))=15, n(m2)= 2

$E_0$	30 eV		100 eV		300 eV		1000 eV	
dx (A)	Li	Cu	Li	Cu	Li	Cu	Li	Cu
0	4.62e-2	6.00e-5	5.66e-2	8.43e-3	4.63e-2	2.55e-2	3.18e-2	2.73e-2
1	6.29e-2	2.00e-5						
1.5			8.16e-2	4.00e-3	6.94e-2	1.93e-2	4.35e-2	2.18e-2
2	8.19e-2				8.16e-2	1.45e-2	4.75e-2	1.88e-2
3	8.94e-2		1.10e-1	1.77e-3	8.41e-2	1.11e-2	5.66e-2	1.45e-2
4	9.70e-2							
5			1.30e-1	1.67e-4	1.05e-1	5.00e-3	7.00e-2	1.16e-2
6	9.16e-2							
7.5					1.22e-1	3.27e-3	8.45e-2	5.75e-3
8	8.39e-2							
10	7.36e-2		1.43e-1		1.33e-1	6.00e-4	8.35e-2	3.88e-3
15	4.85e-2		1.41e-1		1.44e-1		8.78e-2	1.50e-3
20	3.48e-2		1.25e-1		1.50e-1		8.68e-2	7.50e-4
25	2.79e-2		1.17e-1		1.46e-1		8.56e-2	2.50e-4
30	2.36e-2		1.02e-1		1.41e-1		1.01e-1	

Sputtered energy of Li on LiCu by D  
*only low fluence!*  
nem = 4, na = 1, n(dx(1))=15, n(m2)= 2

$E_0$	30 eV		100 eV		300 eV		1000 eV	
dx (A)	Li	Cu	Li	Cu	Li	Cu	Li	Cu
0	5.05e-3	2.01e-6	3.94e-3	2.00e-4	1.97e-3	4.68e-4	6.61e-4	3.38e-4
1	7.51e-3	5.16e-7						
1.5			6.10e-3	8.67e-5	2.95e-3	3.36e-4	8.30e-4	2.04e-4
2	9.61e-3				3.23e-3	2.54e-4	1.08e-3	1.91e-4
3	1.01e-2		7.94e-3	2.79e-5	3.40e-3	1.70e-4	1.06e-3	1.50e-4
4	1.04e-2							
5			8.82e-3	2.21e-5	4.21e-3	7.97e-5	1.24e-3	1.06e-4
6	8.91e-3							
7.5					5.08e-3	3.30e-5	1.54e-3	4.28e-5
8	7.72e-3							
10	6.48e-3		9.01e-3		5.33e-3	3.93e-6	1.40e-3	3.07e-5
15	3.82e-3		8.21e-3		5.67e-3		1.85e-3	8.35e-6
20	2.33e-3		6.88e-3		5.64e-3		1.54e-3	3.57e-6
25	1.84e-3		6.51e-3		5.69e-3		1.90e-3	1.90e-6
30	1.56e-3		5.23e-3		5.41e-3		2.20e-3	

## D → Li on LiCu

Particle reflection coefficient of D backscattered from Li on LiCu  
 z1= 1, m1= 2.01, ef=0.20 eV, dns0=1.00e-1 atoms/Å\*\*3  
 layer 1: z2= 3, m2= 6.94, sbe=1.67 eV, ef=1.65 eV, rho=4.60e-2 atoms/Å\*\*3  
 layer 2: z2=3 (0.24), 29 (0.76), m2=6.94, 63.54, sbe=1.67, 3.52 eV,  
 ef=1.65, 3.50 eV, rho=4.60e-2, 8.48e-2 atoms/Å\*\*3  
 ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 program: tridyn (version 3.3), idrel=1 (static)  
 alpha=0.00, dx(1)=thickness (in Å) of layer 1  
*only low fluence!*  
 ne= 4, na= 1, n(dx(1))=15, n(m2)= 2

E <sub>0</sub>	30 eV	100 eV	300 eV	1000 eV
dx (Å)	0°	0°	0°	0°
0	5.19e-1	4.53e-1	4.10e-1	3.24e-1
1	4.92e-1			
1.5		4.43e-1	3.93e-1	3.35e-1
2	4.79e-1		4.03e-1	3.27e-1
3	4.65e-1	4.38e-1	4.00e-1	3.30e-1
4	4.56e-1			
5		4.32e-1	3.99e-1	3.25e-1
6	4.25e-1			
7.5			3.91e-1	3.35e-1
8	3.96e-1			
10	3.62e-1	4.11e-1	3.90e-1	3.28e-1
15	2.77e-1	3.83e-1	3.76e-1	3.24e-1
20	2.19e-1	3.48e-1	3.82e-1	3.22e-1
25	1.80e-1	3.18e-1	3.64e-1	3.20e-1
30	1.60e-1	2.84e-1	3.53e-1	3.13e-1

Energy reflection coefficient of D backscattered from Li on LiCu  
*only low fluence!*  
 ne= 4, na= 1, n(dx(1))=15, n(m2)= 2

E <sub>0</sub>	30 eV	100 eV	300 eV	1000 eV
dx (Å)	0°	0°	0°	0°
0	3.04e-1	2.57e-1	2.24e-1	1.61e-1
1	2.67e-1			
1.5		2.41e-1	2.13e-1	1.66e-1
2	2.45e-1		2.11e-1	1.64e-1
3	2.26e-1	2.31e-1	2.11e-1	1.62e-1
4	2.11e-1			
5		2.22e-1	2.09e-1	1.62e-1
6	1.77e-1			
7.5			2.01e-1	1.64e-1
8	1.52e-1			
10	1.27e-1	1.92e-1	1.96e-1	1.60e-1
15	8.15e-2	1.63e-1	1.83e-1	1.56e-1
20	5.75e-2	1.36e-1	1.80e-1	1.52e-1
25	4.56e-2	1.15e-1	1.65e-1	1.53e-1
30	4.09e-2	9.65e-2	1.56e-1	1.45e-1

Average depth (mean range) in Å of D implanted in Li on LiCu  
*only low fluence!*  
 ne= 4, na= 1, n(dx(1))=15, n(m2)= 2

E <sub>0</sub>	30 eV	100 eV	300 eV	1000 eV
dx (Å)	0°	0°	0°	0°
0	1.61e+1	3.64e+1	8.04e+1	2.00e+2
1	1.64e+1			
1.5		3.71e+1	7.95e+1	2.00e+2
2	1.68e+1		8.01e+1	2.01e+2
3	1.72e+1	3.78e+1	8.09e+1	1.98e+2
4	1.74e+1			
5		3.94e+1	8.28e+1	2.04e+2
6	1.79e+1			
7.5			8.43e+1	2.05e+2
8	1.83e+1			
10	1.84e+1	4.12e+1	8.59e+1	2.04e+2
15	1.94e+1	4.24e+1	8.89e+1	2.10e+2
20	2.07e+1	4.40e+1	9.18e+1	2.10e+2
25	2.24e+1	4.57e+1	9.32e+1	2.13e+2
30	2.41e+1	4.72e+1	9.57e+1	2.20e+2

## D → Li on LiCu

Sputtering yield of Li on LiCu by D  
 $z1 = 1, m1 = 2.01, ef = 0.20 \text{ eV}, dns0 = 1.00e-1 \text{ atoms}/\text{A}^{**3}$   
 layer 1:  $z2 = 3, m2 = 6.94, sbe = 1.67 \text{ eV}, ef = 1.65 \text{ eV}, rho = 4.60e-2 \text{ atoms}/\text{A}^{**3}$   
 layer 2:  $z2 = 3 (0.06), 29 (0.94), m2 = 6.94, 63.54, sbe = 1.67, 3.52 \text{ eV},$   
 $ef = 1.65, 3.50 \text{ eV}, rho = 4.60e-2, 8.48e-2 \text{ atoms}/\text{A}^{**3}$   
 $ca = 1.00, kk0 = kk0r = 2, kdee1 = kdee2 = 3, ipot = ipotr = 1 (\text{KrC})$   
 program: tridyn (version 3.3), idrel = 1 (static)  
 $\alpha = 0.00, dx(1) = \text{thickness (in A) of layer 1}$   
*only low fluence!*  
 $n_{\text{e}} = 4, n_{\text{a}} = 1, n(dx(1)) = 16, n(m2) = 2$

$E_0$	30 eV	100 eV	300 eV	1000 eV
$dx (\text{\AA})$	Li	Cu	Li	Cu
0	1.33e-2		1.32e-2	1.23e-2
1	4.55e-2		5.66e-2	7.57e-3
1.5			5.20e-3	4.65e-2
2	7.49e-2		9.15e-2	5.57e-2
2.5			2.47e-3	6.45e-2
3	9.17e-2			7.54e-2
4	1.01e-1			1.90e-2
5				5.11e-2
6	1.05e-1		1.19e-1	5.00e-4
7.5				9.89e-2
8	9.49e-2			1.12e-1
10	8.54e-2		1.52e-1	4.30e-3
15	5.64e-2		1.57e-1	1.31e-1
20	3.86e-2		1.43e-1	1.40e-1
25	2.83e-2		1.27e-1	1.46e-1
30	2.64e-2		1.14e-1	1.64e-1

Sputtered energy of Li on LiCu by D  
*only low fluence!*  
 $n_{\text{e}} = 4, n_{\text{a}} = 1, n(dx(1)) = 16, n(m2) = 2$

$E_0$	30 eV	100 eV	300 eV	1000 eV
$dx (\text{\AA})$	Li	Cu	Li	Cu
0	1.47e-3		9.94e-4	3.05e-4
1	6.14e-3			5.47e-4
1.5			4.90e-3	1.56e-4
2	9.43e-3		5.85e-3	8.65e-5
2.5				2.23e-3
3	1.08e-2		6.98e-3	3.54e-5
4	1.14e-2			2.68e-3
5			9.05e-3	3.67e-3
6	1.09e-2			1.49e-4
7.5				4.32e-3
8	9.19e-3			5.25e-5
10	7.67e-3		9.96e-3	5.41e-3
15	4.47e-3		9.80e-3	5.18e-3
20	2.83e-3		8.80e-3	5.73e-3
25	1.87e-3		7.00e-3	5.88e-3
30	1.77e-3		6.12e-3	6.26e-3

## D → Li on LiCu

Particle reflection coefficient of D backscattered from Li on LiCu  
 $z1 = 1$ ,  $m1 = 2.01$ ,  $ef = 0.20$  eV,  $dns0 = 1.00e-1$  atoms/ $\text{Å}^{**3}$   
layer 1:  $z2 = 3$ ,  $m2 = 6.94$ ,  $sbe = 1.67$  eV,  $ef = 1.65$  eV,  $\rho = 4.60e-2$  atoms/ $\text{Å}^{**3}$   
layer 2:  $z2 = 3$  (0.06), 29 (0.94),  $m2 = 6.94$ , 63.54,  $sbe = 1.67$ , 3.52 eV,  
 $ef = 1.65$ , 3.50 eV,  $\rho = 4.60e-2$ , 8.48e-2 atoms/ $\text{Å}^{**3}$   
 $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
program: tridyn (version 3.3), idrel = 1 (static)  
alpha = 0.00, dx(1) = thickness (in Å) of layer 1  
*only low fluence!*  
ne = 4, na = 1, n(dx(1)) = 16, n(m2) = 2

E <sub>0</sub>	30 eV	100 eV	300 eV	1000 eV
dx (Å)	0°	0°	0°	0°
0	6.01e-1	5.16e-1	4.49e-1	3.61e-1
1	5.58e-1			
1.5		4.96e-1	4.41e-1	3.64e-1
2	5.49e-1	4.94e-1	4.46e-1	3.59e-1
2.5			4.43e-1	
3	5.34e-1	4.99e-1	4.44e-1	3.57e-1
4	5.26e-1			
5			4.35e-1	
6	4.93e-1			
7.5			4.32e-1	3.63e-1
8	4.57e-1			
10	4.11e-1	4.60e-1	4.34e-1	3.56e-1
15	3.12e-1	4.31e-1	4.27e-1	3.49e-1
20	2.34e-1	3.99e-1	4.16e-1	3.50e-1
25	1.89e-1	3.57e-1	4.02e-1	3.54e-1
30	1.64e-1	3.24e-1	3.96e-1	3.56e-1

Energy reflection coefficient of D backscattered from Li on LiCu  
*only low fluence!*

ne = 4, na = 1, n(dx(1)) = 16, n(m2) = 2

E <sub>0</sub>	30 eV	100 eV	300 eV	1000 eV
dx (Å)	0°	0°	0°	0°
0	3.74e-1	3.06e-1	2.50e-1	1.87e-1
1	3.20e-1			
1.5		2.81e-1	2.42e-1	1.84e-1
2	2.98e-1	2.76e-1	2.45e-1	1.85e-1
2.5			2.42e-1	
3	2.74e-1	2.75e-1	2.41e-1	1.79e-1
4	2.55e-1			
5		2.57e-1	2.35e-1	1.78e-1
6	2.14e-1			
7.5			2.27e-1	1.82e-1
8	1.81e-1			
10	1.49e-1	2.22e-1	2.25e-1	1.76e-1
15	9.45e-2	1.92e-1	2.13e-1	1.73e-1
20	6.21e-2	1.61e-1	2.02e-1	1.72e-1
25	4.85e-2	1.32e-1	1.87e-1	1.69e-1
30	4.17e-2	1.11e-1	1.77e-1	1.69e-1

Average depth (mean range) in Å of D implanted in Li on LiCu  
*only low fluence!*

ne = 4, na = 1, n(dx(1)) = 16, n(m2) = 2

E <sub>0</sub>	30 eV	100 eV	300 eV	1000 eV
dx (Å)	0°	0°	0°	0°
0	1.43e+1	3.09e+1	6.46e+1	1.54e+2
1	1.46e+1			
1.5		3.18e+1	6.55e+1	1.57e+2
2	1.52e+1	3.22e+1	6.62e+1	1.58e+2
2.5			6.63e+1	
3	1.55e+1	3.29e+1	6.63e+1	1.59e+2
4	1.59e+1			
5		3.38e+1	6.83e+1	1.61e+2
6	1.63e+1			
7.5			6.98e+1	1.60e+2
8	1.65e+1			
10	1.67e+1	3.61e+1	7.06e+1	1.64e+2
15	1.77e+1	3.80e+1	7.42e+1	1.66e+2
20	1.92e+1	3.96e+1	7.79e+1	1.72e+2
25	2.10e+1	4.14e+1	8.05e+1	1.76e+2
30	2.30e+1	4.26e+1	8.31e+1	1.79e+2

## Ar → Li on LiCu

Sputtering yield of Li on LiCu by Ar  
 $z_1=18$ ,  $m_1=39.95$

layer 1:  $z_2=3$ ,  $m_2=6.94$ ,  $sbe=1.67$  eV,  $ef=1.65$  eV,  $\rho=4.60e-2$  atoms/ $\text{A}^{**3}$   
 layer 2:  $z_2=3$  (0.24), 29 (0.76),  $m_2=6.94$ , 63.54,  $sbe=1.67$ , 3.52 eV,  
 $ef=1.65$ , 3.50 eV,  $\rho=4.60e-2$ , 8.48e-2 atoms/ $\text{A}^{**3}$   
 $ef=0.20$ ,  $sbe=0.00$ ,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdeel=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
 program: tridyn (version 3.3), idrel=1 (static)  
 $e_0=6000$  eV,  $\alpha=0.00$ ,  $dx(1)=$ thickness (in Å) of layer 1  
*only low fluence!*  
 $ne=11$ ,  $n(m2)=2$

$dx$ (Å)	Li	Cu
0	1.48e-0	2.16e-0
1.5	1.83e-0	1.74e-0
2	2.04e-0	1.51e-0
3	2.38e-0	1.36e-0
5	2.36e-0	9.55e-1
10	2.67e-0	4.71e-1
12.5	2.40e-0	3.71e-1
15	2.39e-0	2.88e-1
20	2.45e-0	2.06e-1
25	2.13e-0	1.27e-1
30	2.19e-0	7.20e-2

Sputtered energy of Li on LiCu by Ar  
*only low fluence!*  
 $ne=15$ ,  $n(m2)=2$

$dx$ (Å)	Li	Cu
0	9.27e-3	1.06e-2
1.5	1.03e-2	7.99e-3
2	9.59e-3	7.31e-3
3	1.07e-2	6.99e-3
5	1.15e-2	5.53e-3
10	1.37e-2	3.31e-3
12.5	1.46e-2	2.46e-3
15	1.45e-2	2.34e-3
20	1.50e-2	2.29e-3
25	1.68e-2	8.19e-4
30	1.81e-2	4.60e-4

## Ar → Li on LiCu

Particle reflection coefficient of Ar backscattered from Li on LiCu  
 $z_1=18$ ,  $m_1=39.95$   
layer 1:  $z_2=3$ ,  $m_2=6.94$ ,  $sbe=1.67$  eV,  $ef=1.65$  eV,  $\rho=4.60e-2$  atoms/ $\text{Å}^{**3}$   
layer 2:  $z_2=3$  (0.24), 29 (0.76),  $m_2=6.94$ , 63.54,  $sbe=1.67$ , 3.52 eV,  
 $ef=1.65$ , 3.50 eV,  $\rho=4.60e-2$ , 8.48e-2 atoms/ $\text{Å}^{**3}$   
 $ef=0.20$ ,  $sbe=0.00$ ,  $ca=1.00$ ,  $kk_0=kk_0r=2$ ,  $kdeel=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
program: tridyn (version 3.3), idrel=1 (static)  
 $e_0=6000$  eV,  $\alpha=0.00$ ,  $dx(1)=$ thickness (in Å) of layer 1  
*only low fluence!*  
 $ne=11$ ,  $n(m2)=2$

$dx$ (Å)	$0^\circ$
0	4.60e-2
1.5	5.20e-2
2	4.10e-2
3	4.50e-2
5	4.00e-2
10	4.80e-2
12.5	4.00e-2
15	3.10e-2
20	3.20e-2
25	3.30e-2
30	2.50e-2

Energy reflection coefficient of Ar backscattered from Li on LiCu  
*only low fluence!*  
 $ne=11$ ,  $n(m2)=2$

$dx$ (Å)	$0^\circ$
0	3.42e-3
1.5	4.55e-3
2	2.95e-3
3	4.25e-3
5	2.71e-3
10	2.15e-3
12.5	2.18e-3
15	1.67e-3
20	1.36e-3
25	1.06e-3
30	9.20e-4

Average depth (mean range) in Å of Ar implanted in Li on LiCu  
*only low fluence!*  
 $ne=11$ ,  $n(m2)=2$

$dx$ (Å)	$0^\circ$
0	6.56e+1
1.5	6.69e+1
2	6.79e+1
3	6.81e+1
5	6.97e+1
10	7.47e+1
12.5	7.68e+1
15	7.91e+1
20	8.27e+1
25	8.50e+1
30	8.83e+1

# O → B<sub>2</sub>O<sub>3</sub> on B

Sputtering yield of B<sub>2</sub>O<sub>3</sub> on B by O

```

z1= 8, m1= 16.00
1.layer: z2= 5 (0.40), 8 (0.60), m2= 10.81, 16.00, sbe=5.90, 2.50 eV, rho=1.62 g/cm**3
2.layer: z2= 5, m2= 10.81, sbe=5.90 eV, rho= 2.35 g/cm**3
ef=2.10 eV, esb=2.60 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
alpha=0.00, dx(1)=thickness of 1.layer
program: trspvmc
only low fluence !
nes= 4, na= 1, n(dx(1))= 2
B (1.layer)
```

	dx (Å)	5	10
E <sub>0</sub> (eV)			
100	2.39e-1	2.53e-1	
300	4.68e-1	4.72e-1	
1000	5.87e-1	6.07e-1	
3000	6.03e-1		

	dx (Å)	5	10
E <sub>0</sub> (eV)			
100	2.86e-1	2.83e-1	
300	5.56e-1	6.16e-1	
1000	8.37e-1	8.07e-1	
3000	7.99e-1		

	dx (Å)	5	10
E <sub>0</sub> (eV)			
100	5.10e-3	5.13e-4	
300	4.43e-2	1.43e-2	
1000	1.01e-1	3.28e-2	
3000			

Sputtered energy of B<sub>2</sub>O<sub>3</sub> on B by O

only low fluence !

nes= 4, na= 1, n(dx(1))= 2

	dx (Å)	5	10
E <sub>0</sub> (eV)			
100	5.90e-3	5.99e-3	
300	5.06e-3	6.44e-3	
1000	3.05e-3	4.19e-3	
3000	2.05e-3		

	dx (Å)	5	10
E <sub>0</sub> (eV)			
100	5.89e-3	6.06e-3	
300	5.75e-3	6.64e-3	
1000	4.42e-3	4.81e-3	
3000	2.32e-3		

	dx (Å)	5	10
E <sub>0</sub> (eV)			
100	1.69e-4		
300	7.62e-4	6.83e-6	
1000	1.21e-3	4.22e-4	
3000		4.79e-4	

## O → B<sub>2</sub>O<sub>3</sub> on B

Particle reflection coefficient of O backscattered from B<sub>2</sub>O<sub>3</sub> on B  
z1 = 8, m1 = 16.00  
1.layer: z2 = 5 (0.40), 8 (0.60), m2 = 10.81, 16.00, sbe = 5.90, 2.50 eV, rho = 1.62 g/cm\*\*3  
2.layer: z2 = 5, m2 = 10.81, sbe = 5.90 eV, rho = 2.35 g/cm\*\*3  
ef = 2.10 eV, esb = 2.60 eV, ca = 1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
alpha=0.00, dx(1)=thickness of 1.layer  
program: trspvmc  
*only low fluence!*  
ne = 4, na = 1, n(dx(1)) = 2

dx (Å)	5	10
E <sub>0</sub> (eV)		
100	4.37e-3	5.46e-3
300	6.58e-3	6.15e-3
1000	4.68e-3	3.96e-3
3000	1.75e-3	

Energy reflection coefficient of O backscattered from B<sub>2</sub>O<sub>3</sub> on B  
*only low fluence!*  
ne = 4, na = 1, n(dx(1)) = 2

dx (Å)	5	10
E <sub>0</sub> (eV)		
100	1.84e-4	1.94e-4
300	3.12e-4	2.83e-4
1000	2.89e-4	7.97e-5
3000		4.88e-5

Average depth (mean range) in Å of O implanted in B<sub>2</sub>O<sub>3</sub> on B  
*only low fluence!*  
ne = 4, na = 1, n(dx(1)) = 2

dx (Å)	5	10
E <sub>0</sub> (eV)		
100	7.60e+0	8.94e+0
300	1.42e+1	1.59e+1
1000	3.22e+1	3.38e+1
3000		8.05e+1

# $O \rightarrow B_2O_3$ on $B_4C$

Sputtering yield of  $B_2O_3$  on  $B_4C$  by O

```

z1= 8, m1= 16.00
1.layer: z2= 5 (0.40), 8 (0.60), m2= 10.81, 16.00,
sbe=5.90, 2.50 eV, sbe(mean)=1.28 eV, rho=1.62 g/cm***3
2.layer: z2= 5 (0.80), 6 (0.20), m2= 10.81, 12.01
sbe=5.90, 7.40 eV, sbe(mean)=6.05 eV, rho= 2.28 g/cm***3
ef=2.10 eV, esb=2.60 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
alpha=0.00, dx(B2O3)=2,...10 Å, dx(b4c)=10000 Å
program: trspvnc
only low fluence!
ne= 4, na= 1, n(dx(1))= 4

```

B (1.layer)

dx (Å)	2	4	5	10
E <sub>0</sub> (eV)				
150				3.25e-1
300				4.51e-1
1000				6.17e-1
3000	1.54e-1	5.26e-1	6.46e-1	5.74e-1

O (1.layer)

dx (Å)	2	4	5	10
E <sub>0</sub> (eV)				
150				4.13e-1
300				5.83e-1
1000				8.45e-1
3000	1.81e-1	6.73e-1	8.45e-1	8.23e-1

B (2.layer)

dx (Å)	2	4	5	10
E <sub>0</sub> (eV)				
300				7.12e-4
1000				1.05e-2
3000	1.22e-0	2.69e-1	1.71e-1	1.69e-2

C (2.layer)

dx (Å)	2	4	5	10
E <sub>0</sub> (eV)				
300				3.56e-4
1000				2.09e-3
3000	2.85e-1	5.75e-2	2.81e-2	2.11e-3

Sputtered energy of  $B_2O_3$  on  $B_4C$  by O

only low fluence!

```

ne= 4, na= 1, n(dx(1))= 4

```

B (1.layer)

dx (Å)	2	4	5	10
E <sub>0</sub> (eV)				
150				5.82e-3
300				6.01e-3
1000				3.91e-3
3000	6.13e-4	1.37e-3	1.43e-3	2.45e-3

O (1.layer)

dx (Å)	2	4	5	10
E <sub>0</sub> (eV)				
150				6.90e-3
300				6.66e-3
1000				5.05e-3
3000	8.13e-4	1.55e-3	2.02e-3	2.73e-3

B (2.layer)

dx (Å)	2	4	5	10
E <sub>0</sub> (eV)				
300				2.85e-5
1000				3.08e-4
3000	2.86e-3	1.68e-3	1.79e-3	6.18e-4

C (2.layer)

dx (Å)	2	4	5	10
E <sub>0</sub> (eV)				
300				2.28e-5
1000				4.86e-5
3000	6.19e-4	2.60e-4	2.75e-4	2.78e-5

## O → B<sub>2</sub>O<sub>3</sub> on B<sub>4</sub>C

Particle reflection coefficient of O backscattered from B<sub>2</sub>O<sub>3</sub> on B<sub>4</sub>C  
z1= 8, m1= 16.00  
1.layer: z2= 5 (0.40), 8 (0.60), m2= 10.81, 16.00,  
sbe=5.90, 2.50 eV, sbe(mean)=1.28 eV, rho=1.62 g/cm\*\*3  
2.layer: z2= 5 (0.80), 6 (0.20), m2= 10.81, 12.01  
sbe=5.90, 7.40 eV, sbe(mean)=6.05 eV, rho= 2.28 g/cm\*\*3  
ef=2.10 eV, esb=2.60 eV, ca=1.00, kk0=kk0r=2, kddee1=kddee2=3, ipot=ipotr=1 (KrC)  
alpha=0.00, dx(B2O3)=2,...10 Å, dx(b4c)=10000 Å  
program: trspvnc  
*only low fluence!*  
ne= 4, na= 1, n(dx(1))= 2

dx (Å)	2	10
E <sub>0</sub> (eV)		
150	4.65e-3	
300	5.70e-3	
1000	5.58e-3	
3000	9.74e-4	4.22e-3

Energy reflection coefficient of O backscattered from B<sub>2</sub>O<sub>3</sub> on B<sub>4</sub>C  
*only low fluence!*  
ne= 4, na= 1, n(dx(1))= 2

dx (Å)	2	10
E <sub>0</sub> (eV)		
150	1.81e-4	
300	1.77e-4	
1000	3.88e-4	
3000	5.03e-5	3.22e-4

Average depth (mean energy) in Å of O implanted in B<sub>2</sub>O<sub>3</sub> on B<sub>4</sub>C  
*only low fluence!*  
ne= 4, na= 1, n(dx(1))= 4

dx (Å)	2	4	5	10
E <sub>0</sub> (eV)				
150				1.08e+1
300				1.59e+1
1000				3.32e+1
3000	7.38e+1	7.55e+1	7.70e+1	7.91e+1

# O → B(OH)<sub>3</sub> on B

Sputtering yield of B(OH)<sub>3</sub> on B by O

```

z1= 8, m1= 16.00
1.layer: z2= 5 (0.14), 8 (0.43), 1 (0.43), m2= 10.81, 16.00, 1.01,
sbe=5.90, 2.50, 2.19 eV, rho=0.85 g/cm**3
2.layer: z2= 5, m2= 10.81, sbe=5.90 eV, rho= 2.35 g/cm**3
ef=2.10 eV, esb=2.60 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
alpha=0.00, dx(b03h3)=10 Å
program: trspvmc
only low fluence!
nem= 4, na= 1, n(dx(1))= 2
B (1.layer)
```

E <sub>0</sub> (eV)	0°
100	3.61e-2
300	7.30e-2
1000	1.30e-1
3000	1.20e-1

O (1.layer)

E <sub>0</sub> (eV)	0°
100	9.94e-2
300	2.17e-1
1000	3.15e-1
3000	3.63e-1

H (1.layer)

E <sub>0</sub> (eV)	0°
100	1.12e-1
300	3.39e-1
1000	4.38e-1
3000	4.14e-1

B (2.layer)

E <sub>0</sub> (eV)	0°
300	6.23e-3
1000	3.44e-2
3000	6.03e-2

Sputtered energy of B(OH)<sub>3</sub> on B by O

```

z1= 8, m1= 16.00
1.layer: z2= 5 (0.14), 8 (0.43), 1 (0.43), m2= 10.81, 16.00, 1.01,
sbe=5.90, 2.50, 2.19 eV, rho=0.85 g/cm**3
2.layer: z2= 5, m2= 10.81, sbe=5.90 eV, rho= 2.35 g/cm**3
ef=2.10 eV, esb=2.60 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
alpha=0.00, dx(b03h3)=10 Å
program: trspvmc
only low fluence!
nem= 4, na= 1, n(dx(1))= 2
B (1.layer)
```

E <sub>0</sub> (eV)	0°
100	9.75e-4
300	1.03e-3
1000	9.49e-4
3000	3.63e-4

O (1.layer)

E <sub>0</sub> (eV)	0°
100	2.41e-3
300	2.86e-3
1000	1.97e-3
3000	1.45e-3

H (1.layer)

E <sub>0</sub> (eV)	0°
100	2.32e-3
300	4.98e-3
1000	3.88e-3
3000	1.57e-3

B (2.layer)

E <sub>0</sub> (eV)	0°
300	1.35e-4
1000	5.24e-4
3000	5.83e-4

## O → B(OH)<sub>3</sub> on B

Particle reflection coefficient of O backscattered from B(OH)<sub>3</sub> on B  
 $z1 = 8, m1 = 16.00$   
 1.layer:  $z2 = 5$  (0.14), 8 (0.43), 1 (0.43),  $m2 = 10.81, 16.00, 1.01$ ,  
 $sbe = 5.90, 2.50, 2.19$  eV,  $\rho = 0.85$  g/cm<sup>\*\*3</sup>  
 2.layer:  $z2 = 5, m2 = 10.81, sbe = 5.90$  eV,  $\rho = 2.35$  g/cm<sup>\*\*3</sup>  
 $ef = 2.10$  eV,  $esb = 2.60$  eV,  $ca = 1.00$ ,  $kk0 = kk0r = 2$ ,  $kdee1 = kdee2 = 3$ ,  $ipot = ipotr = 1$  (KrC)  
 $\alpha = 0.00$ ,  $dx(b03h3) = 10$  Å  
 program: trspvmc  
*only low fluence!*  
 $ne = 4, na = 1, n(dx(1)) = 2$

E <sub>0</sub> (eV)	0°
100	2.98e-3
300	4.89e-3
1000	1.64e-3
3000	2.44e-3

Energy reflection coefficient of O backscattered from B(OH)<sub>3</sub> on B  
*only low fluence!*  
 $ne = 4, na = 1, n(dx(1)) = 2$

E <sub>0</sub> (eV)	0°
100	2.05e-4
300	1.90e-4
1000	9.73e-5
3000	2.47e-5

Average depth (mean range) in Å of O implanted in B(OH)<sub>3</sub> on B  
*only low fluence!*  
 $ne = 4, na = 1, n(dx(1)) = 2$

E <sub>0</sub> (eV)	0°
100	1.24e+1
300	1.93e+1
1000	3.72e+1
3000	8.41e+1

# O → B(OH)<sub>3</sub> on B<sub>4</sub>C

Sputtering yield of B(OH)<sub>3</sub> on B<sub>4</sub>C by O

```

z1= 8, m1= 16.00
1.layer: z2= 5 (0.14), 8 (0.43), 1 (0.43), m2= 10.81, 16.00, 1.01,
sbe=5.90, 2.50, 2.19 eV, sbe(mean)=1.22 eV, rho=0.85 g/cm***3
2.layer: z2= 5 (0.80), 6 (0.20), m2= 10.81, 12.01
sbe=5.90, 7.40 eV, sbe(mean)=6.05 eV, rho= 2.28 g/cm***3
ef=2.10 eV, esb=2.60 eV, ca=1.00, kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
alpha=0.00, dx(B(OH)3)=2,...20 Å, dx(b4c)=10000 Å
program: trspvmc
only low fluence!
ne= 4, na= 1, n(dx(1))= 7

```

B (1.layer)

dx (Å)	2	3	4	5	7	10	20
E <sub>0</sub> (eV)							
150	1.77e-2	3.96e-2	5.60e-2	5.22e-2	6.69e-2	5.97e-2	
300	2.43e-2	5.45e-2	8.59e-2	9.47e-2	8.11e-2	9.56e-2	
1000	3.02e-2	7.44e-2	1.12e-1	1.20e-1	1.34e-1	1.23e-1	
3000		6.87e-2	1.06e-1	1.34e-1			

O (1.layer)

dx (Å)	2	3	4	5	7	10	20
E <sub>0</sub> (eV)							
150	4.20e-2	1.04e-1	1.51e-1	1.55e-1	1.74e-1	1.51e-1	
300	5.91e-2	1.41e-1	2.43e-1	2.43e-1	2.24e-1	2.53e-1	
1000	9.46e-2	1.99e-1	3.28e-1	3.96e-1	3.79e-1	3.20e-1	
3000		2.04e-1	2.97e-1	3.98e-1			

H (1.layer)

dx (Å)	2	3	4	5	7	10	20
E <sub>0</sub> (eV)							
150	7.50e-2	1.07e-1	1.34e-1	1.48e-1	1.98e-1	1.85e-1	
300	9.25e-2	1.42e-1	1.88e-1	2.03e-1	2.77e-1	3.35e-1	
1000	1.30e-1	1.75e-1	2.45e-1	2.88e-1	3.74e-1	4.04e-1	
3000		2.02e-1	2.54e-1	2.89e-1			

B (2.layer)

dx (Å)	2	3	4	5	7	10	20
E <sub>0</sub> (eV)							
150	4.25e-1	2.62e-1	1.12e-1	3.15e-2	6.55e-3	2.60e-4	
300	6.67e-1	4.45e-1	1.87e-1	7.50e-2	2.21e-2	3.25e-3	
1000	1.00e-0	6.82e-1	3.39e-1	1.75e-1	8.22e-2	2.71e-2	
3000		6.97e-1	3.15e-1	1.86e-1			

C (2.layer)

dx (Å)	2	3	4	5	7	10	20
E <sub>0</sub> (eV)							
150	1.10e-1	5.99e-2	2.73e-2	9.58e-3			
300	1.69e-1	1.07e-1	4.28e-2	1.38e-2	5.64e-3		
1000	2.39e-1	1.92e-1	7.56e-2	2.93e-2	1.61e-2	2.85e-3	
3000		1.72e-1	8.03e-2	4.25e-2			

# O → B(OH)<sub>3</sub> on B<sub>4</sub>C

Sputtered energy of B(OH)<sub>3</sub> on B<sub>4</sub>C by O

```

z1= 8, m1= 16.00
1.layer: z2= 5 (0.14), 8 (0.43), 1 (0.43), m2= 10.81, 16.00, 1.01,
sbe=5.90, 2.50, 2.19 eV, sbe(mean)=1.22 eV, rho=0.85 g/cm**3
2.layer: z2= 5 (0.80), 6 (0.20), m2= 10.81, 12.01
sbe=5.90, 7.40 eV, sbe(mean)=6.05 eV, rho= 2.28 g/cm***3
ef=2.10 eV, esb=2.60 eV, ca=1.00, kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
alpha=0.00, dx(B(OH)3)=2,...20 Å, dx(b4c)=10000 Å
program: trspvmc
only low fluence!
ne= 4, na= 1, n(dx(1))= 7

```

B (1.layer)

dx (Å)	2	3	4	5	7	10	20
E <sub>0</sub> (eV)							
150	3.88e-4	7.36e-4	9.02e-4	7.81e-4	1.26e-3	1.22e-3	
300	3.49e-4	6.59e-4	1.02e-3	1.10e-3	9.92e-4	1.28e-3	
1000	2.33e-4	4.75e-4	4.33e-4	6.64e-4	6.69e-4	8.80e-4	
3000	1.60e-4	1.90e-4	2.24e-4				9.68e-4

O (1.layer)

dx (Å)	2	3	4	5	7	10	20
E <sub>0</sub> (eV)							
150	9.14e-4	1.98e-3	2.57e-3	2.72e-3	3.10e-3	2.74e-3	
300	9.37e-4	1.73e-3	2.52e-3	2.30e-3	2.54e-3	3.34e-3	
1000	7.48e-4	1.19e-3	1.42e-3	1.75e-3	2.18e-3	1.95e-3	
3000	4.04e-4	8.04e-4	7.25e-4				2.80e-3

H (1.layer)

dx (Å)	2	3	4	5	7	10	20
E <sub>0</sub> (eV)							
150	1.60e-3	2.20e-3	2.62e-3	2.84e-3	3.72e-3	3.28e-3	
300	1.64e-3	2.15e-3	2.82e-3	3.10e-3	3.85e-3	5.33e-3	
1000	1.30e-3	1.62e-3	1.89e-3	2.29e-3	2.44e-3	3.52e-3	
3000	1.16e-3	1.02e-3	9.40e-4				5.15e-3

B (2.layer)

dx (Å)	2	3	4	5	7	10	20
E <sub>0</sub> (eV)							
150	5.27e-3	3.07e-3	1.22e-3	4.12e-4	1.42e-4	4.65e-6	
300	4.90e-3	3.28e-3	1.52e-3	7.48e-4	3.54e-4	4.00e-5	
1000	3.79e-3	2.31e-3	1.67e-3	1.26e-3	1.17e-3	2.87e-4	
3000	1.35e-3	8.06e-4	1.43e-3				9.37e-5

C (2.layer)

dx (Å)	2	3	4	5	7	10	20
E <sub>0</sub> (eV)							
100	1.25e-3	6.85e-4	3.05e-4	1.23e-4			
300	1.17e-3	6.81e-4	2.51e-4	1.18e-4	6.86e-5		
1000	7.81e-4	6.70e-4	3.01e-4	3.08e-4	2.14e-4	8.77e-5	
3000	2.51e-4	1.74e-4	1.56e-4				6.54e-5

# O → B(OH)<sub>3</sub> on B<sub>4</sub>C

Particle reflection coefficient of O backscattered from B(OH)<sub>3</sub> on B<sub>4</sub>C  
 $z1 = 8$ ,  $m1 = 16.00$   
1.layer:  $z2 = 5$  (0.14), 8 (0.43), 1 (0.43),  $m2 = 10.81, 16.00, 1.01$ ,  
 $sbe=5.90, 2.50, 2.19$  eV,  $sbe(\text{mean})=1.22$  eV,  $\rho=0.85$  g/cm\*\*3  
2.layer:  $z2 = 5$  (0.80), 6 (0.20),  $m2 = 10.81, 12.01$   
 $sbe=5.90, 7.40$  eV,  $sbe(\text{mean})=6.05$  eV,  $\rho=2.28$  g/cm\*\*3  
 $ef=2.10$  eV,  $esb=2.60$  eV,  $ca=1.00$ ,  $kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
 $\alpha=0.00$ ,  $dx(B(OH)_3)=2, \dots, 20$  Å,  $dx(b4c)=10000$  Å  
program: trspvpmc  
*only low fluence!*  
 $ne = 3$ ,  $na = 1$ ,  $n(dx(1)) = 7$

$dx$ (Å)	2	3	4	5	7	10	20
$E_0$ (eV)							
150	7.97e-4	1.40e-3	1.62e-3	1.85e-3	2.07e-3	3.11e-3	
300	1.30e-3	1.63e-3	1.70e-3	3.73e-3	3.08e-3	5.10e-3	3.95e-3
1000				1.61e-3		2.14e-3	1.48e-3

Energy reflection coefficient of O backscattered from B(OH)<sub>3</sub> on B<sub>4</sub>C  
*only low fluence!*  
 $ne = 3$ ,  $na = 1$ ,  $n(dx(1)) = 7$

$dx$ (Å)	2	3	4	5	7	10	20
$E_0$ (eV)							
150	4.63e-5	5.57e-5	8.40e-5	5.51e-5	8.93e-5	1.43e-4	
300	5.85e-5	8.70e-5	4.52e-5	1.66e-4	1.93e-4	2.40e-4	1.91e-4
1000				3.41e-5		3.28e-5	4.23e-5

Average depth (mean range) in Å of O implanted in B(OH)<sub>3</sub> on B<sub>4</sub>C  
*only low fluence!*  
 $ne = 4$ ,  $na = 1$ ,  $n(dx(1)) = 7$

$dx$ (Å)	2	3	4	5	7	10	20
$E_0$ (eV)							
150	9.48e+0	9.91e+0	1.06e+1	1.15e+1	1.28e+1	1.45e+1	
300	1.44e+1	1.48e+1	1.55e+1	1.64e+1	1.76e+1	1.94e+1	2.53e+1
1000	3.36e+1	3.28e+1	3.27e+1	3.45e+1	3.59e+1	3.77e+1	4.36e+1
3000		7.56e+1	7.72e+1	7.86e+1			

# O → O on WO<sub>3</sub>

Sputtering yield of O on WO<sub>3</sub> by O

```

z1= 8, m1= 16.00
layer 1: z2= 8, m2= 16.00, sbe=2.60 eV, rho=1.14 g/cm**3
layer 2: z2=74 (0.25), 8 (0.75), m2=183.85, 16.00, dx=10000 Å, sbe=6.28, 6.28 eV, rho=6.47 g/cm**3
ef=2.50 eV, esb=2.60 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)
program: trspvnc
only low fluence!
ne= 3, na= 1, n(dx(1)= 2
O (1.layer) 

| dx (Å)              | 1       | 5       |
|---------------------|---------|---------|
| E <sub>0</sub> (eV) |         |         |
| 1000                | 8.71e-2 | 6.85e-1 |


```

W (2.layer)

dx (Å)	1	5
E <sub>0</sub> (eV)		
1000	8.29e-2	4.30e-2

O (2.layer)

dx (Å)	1	5
E <sub>0</sub> (eV)		
1000	8.72e-1	2.98e-1

Sputtered energy of O on WO<sub>3</sub> by O

only low fluence!

ne= 3, na= 1, n(dx(1)= 2

O (1.layer)

dx (Å)	1	5
E <sub>0</sub> (eV)		
1000	2.72e-3	9.07e-3

W (2.layer)

dx (Å)	1	5
E <sub>0</sub> (eV)		
1000	7.57e-4	4.28e-4

O (2.layer)

dx (Å)	1	5
E <sub>0</sub> (eV)		
1000	2.06e-2	1.00e-2

Particle reflection coefficient of O backscattered from O on WO<sub>3</sub>

only low fluence!

ne= 3, na= 1, n(dx(1)= 2

O (1.layer)

dx (Å)	1	5
E <sub>0</sub> (eV)		
1000	7.87e-2	7.51e-2

Energy reflection coefficient of O backscattered from O on WO<sub>3</sub>

only low fluence!

ne= 3, na= 1, n(dx(1)= 2

O (1.layer)

dx (Å)	1	5
E <sub>0</sub> (eV)		
1000	2.27e-2	1.74e-2

Average depth (mean range) in Å of O implanted in O on WO<sub>3</sub>

only low fluence!

ne= 3, na= 1, n(dx(1)= 2

O (1.layer)

dx (Å)	1	5
E <sub>0</sub> (eV)		
1000	3.44e+1	3.47e+1

# O → WO<sub>3</sub> on W

Sputtering yield of WO<sub>3</sub> on W by O  
 $z1 = 8, m1 = 16.00$

1.layer:  $z2=74$  (0.25), 8 (0.75),  $m2=183.85$ , 16.00,  $sbe=6.28$ , 6.28 eV,  $\rho=6.47$  g/cm\*\*3  
 2.layer:  $z1 = 74$ ,  $m2=183.85$ ,  $sbe=8.68$  eV,  $\rho=19.30$  g/cm\*\*3  
 $ef=2.50$  eV,  $esb=2.60$  eV,  $ca=1.00$ ,  $kk0=kk0r=2$ ,  $kdee1=kdee2=3$ ,  $ipot=ipotr=1$  (KrC)  
 $\alpha=0.00$ ,  $dx(1)=$ thickness of 1.layer  
 program: trspvmc  
*only low fluence!*  
 $ne = 9, na = 1, n(dx) = 3$

W (1.layer)

$dx$ (Å)	10	15	25
$E_0$ (eV)			
50			$7.71e-5$
100		$1.74e-3$	$1.66e-3$
200	$8.86e-3$		
300	$1.88e-2$		
500	$4.09e-2$	$2.93e-2$	$2.00e-2$
1000	$8.79e-2$	$6.40e-2$	$6.01e-2$
2000	$1.36e-1$		
5000	$1.38e-1$	$1.46e-2$	
6000	$1.80e-1$		

O (1.layer)

$dx$ (Å)	10	15	25
$E_0$ (eV)			
50			$3.99e-2$
100		$1.19e-1$	$1.19e-1$
200	$2.67e-1$		
300	$3.85e-1$		
500	$5.57e-1$	$4.87e-1$	$4.02e-1$
1000	$7.14e-1$	$6.78e-1$	$6.25e-1$
2000	$7.94e-1$		
5000	$7.04e-1$	$9.04e-1$	
6000	$7.09e-1$		

W (2.layer)

$dx$ (Å)	10
$E_0$ (eV)	
200	$6.19e-6$
300	$3.09e-4$
500	$1.63e-3$
1000	$8.24e-3$
2000	$2.54e-2$
5000	$5.53e-2$
6000	$6.77e-2$

Sputtered energy of WO<sub>3</sub> on W by O

*only low fluence!*  
 $ne = 9, na = 1, n(dx) = 3$

W (1.layer)

$dx$ (Å)	10	15	25
$E_0$ (eV)			
50			$2.75e-6$
100		$7.97e-5$	$9.25e-5$
200	$3.52e-4$		
300	$6.02e-4$		
500	$1.11e-3$	$8.38e-4$	$5.71e-4$
1000	$1.76e-3$	$1.03e-3$	$1.22e-3$
2000	$1.99e-3$		
5000	$1.28e-3$	$1.50e-3$	
6000	$1.56e-3$		

O (1.layer)

$dx$ (Å)	10	15	25
$E_0$ (eV)			
50			$6.29e-3$
100			$1.36e-2$
200	$2.14e-2$	$1.37e-2$	
300	$2.69e-2$		
500	$3.25e-2$	$2.57e-2$	$2.24e-2$
1000	$3.54e-2$	$2.71e-2$	$2.37e-2$
2000	$2.71e-2$		
5000	$1.59e-2$	$1.92e-2$	
6000	$1.25e-2$		

W (2.layer)

$dx$ (Å)	10
$E_0$ (eV)	
200	$7.37e-8$
300	$4.94e-6$
500	$2.70e-5$
1000	$7.52e-5$
2000	$3.90e-4$
5000	$8.52e-4$
6000	$8.79e-4$

# O → WO<sub>3</sub> on W

Particle reflection coefficient of O backscattered from WO<sub>3</sub> on W  
 z1 = 8, m1 = 16.00  
 1.layer: z2=74 (0.25), 8 (0.75), m2=183.85, 16.00, sbe=6.28, 6.28 eV, rho=6.47 g/cm\*\*3  
 2.layer: z1 = 74, m2=183.85, sbe=8.68 eV, rho=19.30 g/cm\*\*3  
 ef=2.50 eV, esb=2.60 eV, ca=1.00, kk0=kk0r=2, kdee1=kdee2=3, ipot=ipotr=1 (KrC)  
 alpha=0.00, dx(1)=thickness of 1.layer  
 program: trspvmc  
*only low fluence!*  
 ne= 9, na= 1, n(dx)= 3

dx (Å)	10	15	25
E <sub>0</sub> (eV)			
50			1.33e-1
100		1.31e-1	1.31e-1
200	1.47e-1		
300	1.71e-1		
500	2.15e-1	1.47e-1	1.19e-1
1000	2.67e-1	1.95e-1	1.27e-1
2000	3.14e-1		
5000	3.12e-1	3.03e-1	
6000	3.01e-1		

Energy reflection coefficient of O backscattered from WO<sub>3</sub> on W  
*only low fluence!*  
 ne= 9, na= 1, n(dx)= 3

dx (Å)	10	15	25
E <sub>0</sub> (eV)			
50			5.30e-2
100		4.84e-2	4.90e-2
200	4.71e-2		
300	5.07e-2		
500	5.95e-2	4.16e-2	4.01e-2
1000	8.66e-2	5.62e-2	3.80e-2
2000	1.08e-1		
5000	1.14e-1	1.09e-1	
6000	1.13e-1		

Average depth (mean range) in Å of O implanted in WO<sub>3</sub> on W  
*only low fluence!*  
 ne= 9, na= 1, n(dx)= 3

dx (Å)	10	15	25
E <sub>0</sub> (eV)			
50			5.30e+0
100		8.10e+0	8.17e+0
200	1.11e+1		
300	1.41e+1		
500	1.92e+1	1.86e+1	2.01e+1
1000	2.86e+1	2.82e+1	2.96e+1
2000	4.75e+1		
5000	8.05e+1	7.63e+1	
6000	9.80e+1		